

ARMY RESEARCH LABORATORY



Lithium Ion Aqueous Cells

Edward J. Plichta and Wishvender K. Behl

ARL-TR-422

February 1995



19950503 052

DTIC QUALITY INSPECTED 1

APPROVED FOR PUBLIC RELEASE; DISTRIBUTION IS UNLIMITED.

NOTICES

Disclaimers

The findings in this report are not to be construed as an official Department of the Army position, unless so designated by other authorized documents.

The citation of trade names and names of manufacturers in this report is not to be construed as official Government endorsement or approval of commercial products or services referenced herein.

REPORT DOCUMENTATION PAGE

Form Approved
OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

1. AGENCY USE ONLY (Leave blank)	2. REPORT DATE February 1995	3. REPORT TYPE AND DATES COVERED Technical Report: Jul to Dec 94
---	--	--

4. TITLE AND SUBTITLE LITHIUM ION AQUEOUS CELLS	5. FUNDING NUMBERS PR: 62705 PE: H94
6. AUTHOR(S) Edward J. Plichta and Wishvender K. Bell	

7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) US Army Research Laboratory (ARL) Electronics and Power Sources Directorate (EPSD) ATTN: AMSRL-EP-PB Fort Monmouth, NJ 07703-5601	8. PERFORMING ORGANIZATION REPORT NUMBER ARL-TR-422
---	---

9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)	10. SPONSORING/MONITORING AGENCY REPORT NUMBER
--	---

11. SUPPLEMENTARY NOTES

12a. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution is unlimited.	12b. DISTRIBUTION CODE
--	-------------------------------

13. ABSTRACT (Maximum 200 words)

Lithium ion aqueous cells were investigated using lithium intercalating compounds as anodes and cathodes. The aqueous electrolyte consisted of 4 to 5 molar solutions of either lithium perchlorate or lithium nitrate which contained lithium hydroxide in millimolar amounts to make the solutions slightly basic with a pH of about 8.5. Several electrode combinations were evaluated using lithium intercalating compounds such as lithium cobalt oxide and lithium manganese oxide as cathodes and lithium vanadium oxide, lithium manganese oxide, titanium disulfide, and molybdenum dioxide as the anodes. The cell employing manganese oxide as both the anode and cathode exhibited good charge-discharge characteristics with an open circuit potential of about one volt.

14. SUBJECT TERMS Lithium ion aqueous cells; lithium intercalation; rechargeable cells	15. NUMBER OF PAGES 19
	16. PRICE CODE

17. SECURITY CLASSIFICATION OF REPORT Unclassified	18. SECURITY CLASSIFICATION OF THIS PAGE Unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT Unclassified	20. LIMITATION OF ABSTRACT UL
--	---	--	---

CONTENTS

	Page
INTRODUCTION	1
EXPERIMENTAL	2
RESULTS AND DISCUSSION	2
CONCLUSIONS	11
REFERENCES	11

TABLES

TABLE 1. Aqueous ion cells studied.	3
TABLE 2. LiMn ₂ O ₄ X-ray diffraction results.	3

FIGURES

FIGURE 1. Cyclic voltammogram of aqueous electrolytes at a smooth Platinum electrode.	5
FIGURE 2. Observed potential ranges in 5M lithium nitrate, 1mM LiOH (pH=8.2).	6
FIGURE 3. Initial cycle of manganese oxide cell.	7
FIGURE 4. Initial cycle of reversed manganese oxide cell.	8
FIGURE 5. Initial cycle of vanadium oxide/cobalt oxide cell.	9
FIGURE 6. Initial cycle of cupric oxide/manganese oxide cell.	10


Accession For	
NTIS CRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution /	
Availability Codes	
Dist	Avail and/or Special
A-1	

INTRODUCTION


Lithium ion or "rocking chair" cells have been extensively explored recently using organic solvent based electrolytes (1-5). The advantage of the lithium ion cell is that the safety problem associated with the cycling of metallic lithium, namely dendritic shorting, is eliminated. Lithium ion cell voltages and energy densities are comparable to lead-acid and nickel-cadmium cells with the additional advantage that their cell components are considered less hazardous to the environment. The primary drawback to the lithium ion cell development has been with the use of organic solvents in the electrolyte which are flammable. In addition, organic solvents offer no means for electrochemical protection of cells during overcharging operations (i.e., recombination in aqueous electrolytes), resulting in the need for costly electrical control circuits in multi-cell batteries.

Recently, it was discovered that lithium aqueous electrolytes could be successfully used in rechargeable cells containing lithium ion intercalating compounds as the anode and cathode (6,7). As reported, the aqueous lithium ion cell may offer the development of a safe, environmentally favorable rechargeable battery. The use of an aqueous electrolyte also allows for electrochemical overcharge protection of cells thereby making it a potentially lower cost cell for development into batteries. In view of these advantages, several electrode combinations were explored for lithium ion aqueous cells, and results are summarized in this report.

A lithium ion aqueous cell contains transition metal oxide electrodes which are chemically stable in the aqueous electrolyte provided the electrolyte pH is slightly basic ($\sim \text{pH} > 8$). Additionally, the electrochemical potential of many of these oxides are between that of the hydrogen and oxygen evolution potentials, making them suitable for use in an aqueous cell. Lithiated metal oxides such as LiCoO_2 , LiMn_2O_4 , and LiNiO_2 can be used as positive electrodes which act as a source of lithium ions. Negative electrodes can use metal oxides such as VO_2 , V_6O_{13} , and LiMn_2O_4 which then intercalate the lithium. The aqueous electrolyte typically consists of neutral pH lithium salts such as LiNO_3 and LiClO_4 in high concentrations (i.e., up to 5M). Lithium hydroxide is added to the electrolyte in millimolar concentrations in order to adjust the electrolyte pH to be slightly basic ($\text{pH} \sim 8$). By keeping the pH slightly basic the hydrogen and oxygen evolution potentials are shifted, thereby allowing cell potentials up to about 2 V. Cells are prepared cathode limited so that hydrogen evolution is minimized at the anode, thereby avoiding excessive irreversible reduction of the oxide anode material. At the end of charge, oxygen evolution occurs at the cathode and is considered controllable through gas recombination back into the electrolyte. A typical aqueous lithium ion cell that was studied, may be represented as:



The cells are assembled in the discharged state, where, during charge, lithium ions are deintercalated from the LiCoO_2 cathode electrode and intercalated into the vanadium oxide electrode. The electrode processes are reversed during discharge. The cell reactions may be represented as:



The charged cell potential is 1.6 V resulting in a theoretical energy density of 234 Wh/kg, which is comparable to lead-acid and nickel-cadmium cells.

EXPERIMENTAL

Aqueous lithium ion cell electrodes were prepared by roll pressing composite pastes having compositions of 80 wt% active material, 10 wt% graphite powder, and 10 wt% Teflon powder binder onto platinum screen. Distilled water was used to prepare the electrode pastes for roll pressing. Electrodes having geometric areas of 1 to 1.5 cm² were air dried at 110°C and assembled as cells using a single layer of Celgard 2402 polypropylene separator. Carbon black (Black Pearls 2000) was attempted as a substitute for graphite in order to gain increased electrode porosity; however, the cathodes when oxidized evolved gas and leached a brown color into the electrolyte solution. The brown color and gas are probably due to humic acid formation and carbon dioxide evolution (8). Cells were immersed in argon gas deaerated aqueous electrolytes of 5M LiNO₃ -1mM LiOH (pH~8.5) and cycled under constant current conditions at ambient temperatures. Cells were charged at a current density of 1 mA/cm² and electrode potentials measured versus a reference electrode. A hydrogen reference was used in the LiMn₂O₄/LiMn₂O₄ cell. Other cells used a LiCoO₂ pseudo-reference electrode which was found to have an equivalent potential to a saturated calomel electrode in the 5M LiNO₃ -1mM LiOH at 25°C. Table 1 lists the aqueous ion cells that were studied; included are the theoretical cell potentials and energy densities based on 100% utilization of the active materials. All cells were prepared cathode limited to avoid hydrogen evolution during charging.

The aqueous electrolytes 5M LiNO₃ -1mM LiOH (pH=8.2) and 4M LiClO₄ -1mM LiOH (pH=9.0) were studied by cyclic voltammetry using a smooth platinum working electrode versus a LiCoO₂ pseudo-reference electrode. Solutions were deaerated using argon gas prior to performing scans.

X-ray powder diffraction results were obtained using a Phillips PW 1729 X-ray generator. Diffraction patterns were verified versus JCPD standards. Electrolyte conductivities were measured using a Wayne Kerr model 6425 precision bridge at 1 KHz using Jones type conductivity cells calibrated using standard KCl solution. Cell cycling was performed using an AMEL model 545 galvanostat-electrometer and data collected using a Nicolet 310 oscilloscope.

RESULTS AND DISCUSSION

Figure 1 shows cyclic voltammograms obtained in 5M LiNO₃ -1mM LiOH (pH=8.2) and 4M LiClO₄ -1mM LiOH (pH=9.0) solutions at smooth platinum working electrodes using a

TABLE 1. Aqueous Ion Cells Studied.

Electrode (-)	Active Materials (+)	Theoretical Cell Potentials, V	Theoretical Energy Density, Wh/kg	Observed Avg. Cell Potential at 1 mA/cm ² Load
LiMn ₂ O ₄	LiMn ₂ O ₄	1.0	74	1.00
LiMn ₂ O ₄	LiCoO ₂	0.9	86	0.79
TiS ₂	LiCoO ₂	1.8	230	0.94
V ₆ O ₁₃	LiCoO ₂	1.6	234	1.19
MoO ₂	LiCoO ₂	2.4	285	0.80
CuO	LiMn ₂ O ₄	1.8	323	0.50*

* at 0.5 mA/cm²**TABLE 2.** LiMn₂O₄ X-ray Diffraction Results.

(h,k,l)	LiMn ₂ O ₄ , [ASTM]		"LiMn ₂ O ₄ " Foote Mineral as Received	"LiMn ₂ O ₄ " Electrode Mix Processed With H ₂ O	"LiMn ₂ O ₄ " Cycled Electrode From Aqueous Cell
	d	I	d-observed	d-observed	d-observed
111	4.72	100	4.69	4.62	4.59
311	2.47	90	2.47	2.451	2.42
222	2.37	5	2.37	2.34	-----
400	2.05	100	2.046	2.033	2.009
331	1.88	10	1.88	1.87	1.85
333,511	1.58	50	1.58	1.574	1.55
440	1.45	90	1.45	1.446	1.42
531	1.39	30	1.39	1.38	-----
533	1.25	10	-----	-----	-----
622	1.24	5	-----	-----	-----

Structure Determined From Shift in d-spacing:

[Li _{0.8} Mn ₂ O ₄]	[Li _{0.75} Mn ₂ O ₄]	[alpha-MnO ₂]
---	--	---------------------------

LiCoO₂ pseudo-reference electrode. Scans were performed between the hydrogen and oxygen evolution potentials at a scan rate of 50 mV/sec. Observed oxidation and reduction peaks corresponded to those typically observed at smooth platinum electrodes in aqueous electrolytes. Lithium perchlorate solutions were oxidized at about 0.9 V versus the LiCoO₂ reference. The lithium nitrate solution was found to possess a higher oxidation potential to about 1.2 V versus the reference and was the preferred electrolyte for use in the cell studies. The specific conductivity of the 5M LiNO₃ - 1mM LiOH solution was measured to be 0.145 S/cm at 25°C.

Figure 2 presents the observed potential ranges of the lithium intercalation electrodes versus a LiCoO₂ pseudo-reference electrode. Table 1 depicts the average discharge potentials observed for 1 mA/cm² constant current discharges to a zero volt cell cutoff. Cells observed to have average discharge potentials lower than those expected from the theoretical cell potentials were not found to be stable in the aqueous electrolyte. The cell which used MoO₂ as the anode could not be cycled since the potential for lithium intercalation in MoO₂ was found to be below that of hydrogen evolution. Titanium disulfide was capable of intercalating lithium on charging; however, it rapidly decomposed in the electrolyte during discharge.

Figure 3 depicts the initial cycle of the LiMn₂O₄/LiMn₂O₄ cell at 1 mA/cm². The cell was charged to a cell cutoff voltage of 1.3 V to give a charge capacity of 0.5 F/mole of LiMn₂O₄. The cathode potential was measured versus a hydrogen reference and was found to remain below the oxygen evolution potential during charging. The observed capacity for the initial discharge to 0 V was 0.34 F/mole of LiMn₂O₄ with an average cell potential of 1.0 V. Subsequent cycles between a cell voltage of 1.3 V and 0 V resulted in discharge capacities of only 0.2 F/mole of LiMn₂O₄. The average cell potential during discharge remained at 1.0 V over ten cycles. The cell leads were then reversed and constant current cycling resumed between the cell voltage limits of 1.3 V and 0 V. Figure 4 shows the initial cycle for the reversed LiMn₂O₄/LiMn₂O₄ cell. The observed cell capacity and average discharge cell potential of the reversed cell was the same as for the original configuration. No capacity recovery over the 0.2 F/mole of LiMn₂O₄ observed for the initial cell configuration was obtained. The loss of expected capacity was believed to be due to a reaction between the lithium in the electrodes and the electrolyte to form LiOH. However, the electrolyte pH before and after cycling was found to be unchanged, suggesting that possibly the electrode preparation may have caused the lithium loss. To determine this, X-ray powder diffraction was performed on the pure LiMn₂O₄ and both the freshly prepared and the cycled LiMn₂O₄ electrodes. From table 2, the diffraction results show that the initial LiMn₂O₄ used was not fully lithiated as expected. A composition of only about Li_{0.8}Mn₂O₄ was determined from the observed diffraction peak shifts. The composition of the fresh manganese oxide electrode was Li_{0.7}Mn₂O₄, confirming a reactivity with water. A Li_{0.7}Mn₂O₄ electrode was used as the cathode in a cell and, after twenty cycles, disassembled in the reduced state. The X-ray pattern showed that the active material was completely converted to alpha-MnO₂. This corresponds to the phase changes observed by Thackeray (5), where excessive lithium removal during oxidation results in the conversion of the LiMn₂O₄ phase to alpha-MnO₂. As a result of the electrodes being lithium poor, only about 0.2 - 0.3 F/mole of LiMn₂O₄ could be reversibly obtained at a current density of 1 mA/cm². Since excessive lithium removal can occur before oxygen evolution, cells of this type will require electrical overcharge




Figure 1. Cyclic voltammogram of aqueous electrolytes at a smooth Platinum electrode.




Figure 2. Observed potential ranges in 5M lithium nitrate, 1mM LiOH (pH=8.2).




Figure 3. Initial cycle of manganese oxide cell.

REVERSED $\text{Li}_{1+x}\text{Mn}_2\text{O}_4/5\text{M LiNO}_3-1\text{mM LiOH in H}_2\text{O}/\text{Li}_{1-x}\text{Mn}_2\text{O}_4$




Figure 4. Initial cycle of reversed manganese oxide cell.
(dotted line: anode versus lithium cobalt oxide reference)
(solid line: cell)

$\text{Li}_x\text{V}_6\text{O}_{13}/5\text{M LiNO}_3-1\text{mM LiOH in H}_2\text{O}/\text{Li}_{1-x}\text{CoO}_2$




Figure 5. Initial cycle of vanadium oxide/cobalt oxide cell.

CuO/5M LiNO₃-1mM LiOH in H₂O/LiMn₂O₄




Figure 6. Initial cycle of cupric oxide/manganese oxide cell.

protection and may not be able to rely on the chemical gas recombination mechanism used in other aqueous cells.

Figure 5 shows the initial cycling of the $V_6O_{13}/LiCoO_2$ cell at 1 mA/cm^2 . The initial cell open circuit potential was -0.15 V . The cell was charged to a cell voltage limit of 1.9 V to give a charge capacity of $0.35\text{ F/mole of }LiCoO_2$. The observed discharge capacity was only $0.19\text{ F/mole of }LiCoO_2$ with an average discharge potential of 1.19 V . V_6O_{13} was found to undergo lithium ion intercalation; however, it was slightly soluble in the electrolyte and the electrode capacity faded rapidly over five cycles. Excessive oxidation of the $LiCoO_2$ cathode resulted in rapid capacity loss with cycling, similar to that observed with $LiMn_2O_4$.

Figure 6 shows the initial cycle of the $CuO/LiMn_2O_4$ cell at 0.5 mA/cm^2 . The initial cell open circuit potential was 0.10 V . Cupric oxide did not cycle as an anode and was not found to undergo lithium ion intercalation. Instead, the cupric oxide was converted to a soluble copper compound as noted by a blue color which was observed at the anode during the initial cycle. During the early stages of charging, a potential spike was observed as shown in figure 6; however, though it occurred at the anode, the reaction could not be identified. The observed discharge capacity, after charging to 1.6 V to a capacity limit of $0.4\text{ F/mole of }LiMn_2O_4$, was $0.05\text{ F/mole of }LiMn_2O_4$. The average cell potential during discharge was 0.69 V .

CONCLUSIONS

Li et al. (7) reported good cycling results with the use of an anode of VO_2 (B) and the $LiMn_2O_4$ cathode. These cycling results were not observed with the cells chosen in this study. Of the cells studied, only $LiCoO_2/LiMn_2O_4$ and $LiMn_2O_4/LiMn_2O_4$ were found to be suitable for use in the $5M\text{ LiNO}_3$, $-1mM\text{ LiOH}$ electrolyte. Their cell potentials however, are only about one volt, with less than practical energy densities. In addition, the lithiated manganese oxide was found to undergo lithium loss in water, however it was stable in the slightly basic electrolyte. The lithiated transition metal oxide cathodes decompose during excessive oxidation which occurs before oxygen evolution. This would eliminate the use of the oxygen-hydrogen recombination reaction which is beneficial in other aqueous cells for overcharge protection. Improvements in electrode processing to limit loss of lithium or in situ enrichment of the electrodes with lithium is needed to demonstrate higher cell capacities. Further work is needed to evaluate other electrode combinations to improve on the energy density of the aqueous lithium ion cell.

REFERENCES

1. H. Huang and P.G. Bruce, *J. Electrochem. Soc.*, **141**, L106 (1994).
2. S. Megahed and B. Scrosati, *J. Power Sources*, **51**, 79 (1994).
3. E.J. Plichta and W.K. Behl, *J. Electrochem. Soc.*, **140**, 46 (1993).

4. M.M. Thackeray, W.I.F. David, P.G. Bruce, and J.B. Goodenough, *Mat. Res. Bull.*, 18, 461 (1983).
5. M.M. Thackeray, P.J. Johnson, and L.A. de Picciotto, *Mat. Res. Bull.*, 19, 179 (1984).
6. W. Li, W.R. McKinnon, and J.R. Dahn, *J. Electrochem. Soc.*, 141, 2310 (1994).
7. W. Li, J.R. Dahn, and D.S. Wainwright, *Science*, 264, 1115 (1994).

ARMY RESEARCH LABORATORY
ELECTRONICS AND POWER SOURCES DIRECTORATE
CONTRACT OR IN-HOUSE TECHNICAL REPORTS
MANDATORY DISTRIBUTION LIST

February 1995
Page 1 of 3

Defense Technical Information Center*
ATTN: DTIC-OCC
Cameron Station (Bldg 5)
Alexandria, VA 22304-6145
(*Note: Two copies will be sent from
STINFO office, Fort Monmouth, NJ)

Commander, CECOM
R&D Technical Library
Fort Monmouth, NJ 07703-5703
(1) AMSEL-IM-BM-I-L-R (Tech Library)
(3) AMSEL-IM-BM-I-L-R (STINFO ofc)

Director
US Army Material Systems Analysis Actv
ATTN: DRXSY-MP
(1) Aberdeen Proving Ground, MD 21005

Director, Army Research Laboratory
2800 Powder Mill Road
Adelphi, MD 20783-1145
(1) AMSRL-OP-SD-TP (Debbie Lehtinen)

Commander, AMC
ATTN: AMCDE-SC
5001 Eisenhower Ave.
(1) Alexandria, VA 22333-0001

Director
Army Research Laboratory
ATTN: AMSRL-D (John W. Lyons)
2800 Powder Mill Road
(1) Adelphi, MD 20783-1145

Director
Army Research Laboratory
ATTN: AMSRL-DD (COL Thomas A. Dunn)
2800 Powder Mill Road
(1) Adelphi, MD 20783-1145

Director
Army Research Laboratory
2800 Powder Mill Road
Adelphi, MD 20783-1145
(1) AMSRL-OP-SD-TA (ARL-ALC Records Mgt)
(1) AMSRL-OP-SD-TL (ARL-ALC Tech Libr)
(1) AMSRL-OP-SD-TP (ARL-ALC Tech Publ Br)

Directorate Executive
Army Research Laboratory
Electronics and Power Sources Directorate
Fort Monmouth, NJ 07703-5601
(1) AMSRL-EP
(1) AMSRL-EP-T (M. Hayes)
(1) AMSRL-OP-RM-FM
(22) Originating Office

Advisory Group on Electron Devices
ATTN: Documents
2011 Crystal Drive, Suite 307
(2) Arlington, VA 22202

ARMY RESEARCH LABORATORY
ELECTRONICS AND POWER SOURCES DIRECTORATE
SUPPLEMENTAL DISTRIBUTION LIST
(ELECTIVE)

February 1995
Page 2 of 3

- (1) Deputy for Science & Technology
Office, Asst Sec Army (R&D)
Washington, DC 20310
- (1) HQDA (DAMA-ARZ-D/
Dr. F.D. Verderame)
Washington, DC 20310
- (1) Director
Naval Research Laboratory
ATTN: Code 2627
Washington, DC 20375-5000
- (1) USAF Rome Laboratory
Technical Library, FL2810
ATTN: Documents Library
Corridor W, STE 262, RL/SUL
26 Electronics Parkway, Bldg 106
Griffiss Air Force Base
NY 13441-4514
- (1) Dir, ARL Battlefield
Environment Directorate
ATTN: AMSRL-BE
White Sands Missile Range
NM 88002-5501
- (1) Dir, ARL Sensors, Signatures,
Signal & Information Processing
Directorate (S3I)
ATTN: AMSRL-SS
2800 Powder Mill Road
Adelphi, MD 20783-1145
- (1) Dir, CECOM Night Vision/
Electronic Sensors Directorate
ATTN: AMSEL-RD-NV-D
Fort Belvoir, VA 22060-5677
- (1) Dir, CECOM Intelligence and
Electronic Warfare Directorate
ATTN: AMSEL-RD-IEW-D
Vint Hill Farms Station
Warrenton, VA 22186-5100
- (1) Cdr, Marine Corps Liaison Office
ATTN: AMSEL-LN-MC
Fort Monmouth, NJ 07703-5033
- (1) Naval Surface Weapons Center
Code R-23
ATTN: Patricia Smith
Silver Spring, MD 20903-5000
- (1) DARPA/TTO
ATTN: Dr. Peter Kemmey
1400 Wilson Blvd
Arlington, VA 22209
- (1) US Army Armament Research,
Development & Engineering Ctr
ATTN: SMCAR-FSE
(1) Dr. A. Graf
(1) Dr. K.C. Pan
(1) Ms. Laura Krzastek
(1) Ms. Pam Stevens
Picatinny Arsenal, NJ 07806-5000
- (1) US Army Armament Research,
Development & Engineering Ctr
ATTN: SMCAR-FSC
(1) Mr. G. Ferdinand
(1) Ms. H. Naber-Libby
Picatinny Arsenal, NJ 07806-5000
- (1) US Army Armament Research,
Development & Engineering Ctr
ATTN: SMCAR-TD
(1) Dr. T. Davidson
Picatinny Arsenal, NJ 07806-5000
- (1) US Army Armament Research,
Development & Engineering Ctr
ATTN: SMCAR-CCL-FA
(1) Mr. H. Moore
Picatinny Arsenal, NJ 07806-5000
- (1) US Army Armament Research,
Development & Engineering Ctr
ATTN: SMCAR-AEE-B
(1) Dr. D. Downs
Picatinny Arsenal, NJ 07806-5000

- US Army Ballistic Research Lab
ATTN: SLCBR-IB-B
(1) Mr. W. Oberle
(1) Dr. K. White
Aberdeen Proving Ground, MD
21005-0566
- US Army Ballistic Research Lab
ATTN: SLCBR-TB-EP
(1) Mr. A. Zielinski
Aberdeen Proving Ground, MD
21005-0566
- Dr. John Transue
1901 North Beauregard St
Suite 380
(1) Alexandria, VA 22311
- Westinghouse
Naval Systems Division
ATTN: Mr. Steven Specht
476 Center Street
(1) Chardon, OH 44024
- University of Texas at Austin
ATTN: Mr. John H. Gully
10100 Burnet Road
EME, Bldg 133
(1) Austin, TX 70758-4497
- University of Texas at Austin
Institute for Advanced Technology
ATTN: Dr. Harry D. Fair, Jr.
10100 Burnet Road
(1) Austin, TX 70758-4497
- FMC Corporation
Advanced Systems Center
ATTN: Mr. Michael Seale
4800 E. River Road
(1) Minneapolis, MN 55459-0043
- General Dynamics Land Systems Div
ATTN: Dr. Bruce VanDeusen
P.O. Box 2074
(1) Warren, MI 48090-2074
- State University of NY at Buffalo
Electrical and Computer Engrg Dept
ATTN: Dr. Walter J. Sarjeant
Bonner Hall, Room 312
(1) Buffalo, NY 14260