

OFFICE OF NAVAL RESEARCH

GRANT : N00014-89-J-3062

R&T Code 3132084

Technical Report No. 44

Approaches to Bridged Planar Polypyridine, Polypyrazine, and Polythiophene Derivatives for
Maximization of Extended pi-Conjugation.

by


Y. Zhang, Q. Zhang, J. J. S. Lamba, and J. M. Tour

Accepted for Publication in

Polym. Prepr. (Am. Chem. Soc., Div. Polym. Chem.) 1994, 35(2), 691.

Department of Chemistry and Biochemistry
University of South Carolina
Columbia, SC 29208

June 7, 1995



Reproduction in whole, or in part, is permitted for any purpose of the United States Government

This document has been approved for public release and sale; its distribution is unlimited.

19950705 055

DTIC QUALITY INSPECTED 8

REPORT DOCUMENTATION PAGE

Form Approved
OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE 6-7-95	3. REPORT TYPE AND DATES COVERED Technical Report	
4. TITLE AND SUBTITLE Approaches to Bridged Planar Polypyridine, Polypyrazine, Derivatives for Maximization of Extended pi-Conjugation.			5. FUNDING NUMBERS G- N00014-89-J3062 R&T 3132084 K. Wynne	
6. AUTHOR(S) Y. Zhang, Q. Zhang, J. J. S. Lamba, and J. M. Tour			8. PERFORMING ORGANIZATION REPORT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Department of Chemistry and Biochemistry University of South Carolina Columbia, SC 29208			10. SPONSORING/MONITORING AGENCY REPORT NUMBER 44	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) Department of the Navy Office of Naval Research 800 North Quincy Street Arlington, VA 22217-5000			11. SUPPLEMENTARY NOTES Polym. Prepr. (Am. Chem. Soc., Div. Polym. Chem.) 1994, 35(2), 691.	
12a. DISTRIBUTION/AVAILABILITY STATEMENT Reproduction in whole or in part is permitted for any purpose of the United States Government. This document has been approved for public release and sale; its distribution is unlimited.			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) <p style="text-align: center;">Our approaches to the following three planar conjugated polymers will be described.</p>				
14. SUBJECT TERMS			15. NUMBER OF PAGES	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT Unclassified	18. SECURITY CLASSIFICATION OF THIS PAGE Unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT Unclassified	20. LIMITATION OF ABSTRACT UL	




Approaches to Bridged Planar Polypyridine, Polypyrazine, and Polythiophene Derivatives for Maximization of Extended π -Conjugation

Yonghui Zhang, Qing Zhang, Jaydeep J. S. Lamba
and James M. Tour*







Department of Chemistry and Biochemistry
University of South Carolina
Columbia, South Carolina 29208

We have been directing synthetic efforts toward the construction of conjugated macromolecules that are fixed in a planar conformation.¹ The planar conformations should maximize the extended π -conjugation. Additionally, the bridging units, if sp^2 -hybridized, should further increase the extended π -conjugation of the macromolecular systems.^{1,2} We previously described a synthetic route to planar poly(*p*-phenylene) derivatives by the retrosynthetic approach outlined in eq 1 (M = metal).³ The actual synthetic components are shown in eq 2.

Accession For	
NTIS	CRA&I <input checked="" type="checkbox"/>
DTIC	TAB <input type="checkbox"/>
Unannounced <input type="checkbox"/>	
Justification _____	
By _____	
Distribution / _____	
Availability Codes	
Dist	Avail and/or Special
A-1	




Here we describe our approach to the analogous planar polypyridine, polypyrazine, and polythiophene derivatives. The retrosynthetic approaches are shown in eqs 3-5, respectively (M = metal). The key features of these



retrosynthetic approaches are, first, imine cleavage to the ketone and amine functionalized polyaromatics, and second, bond cleavage to the AB-type polymerization monomers (eqs 1, 3, and 4) or the difunctional monomer (eq 5).


The desired monomers for the planar polypyrazine are being synthesized in the following manner. According to



standard protocol, ethyl acetoacetate was saponified, nitrosolated, and decarboxylated to form the α -ketooxime. Reduction and condensation afforded the dihydrodimethylpyrazine that was oxidized to dimethylpyrazine with air.⁴ Selenium dioxide-promoted diacid formation⁵ followed by treatment with oxalyl chloride afforded the pyrazine diacid chloride **1**. This common intermediate could be used to synthesize both of the required monomers. First, conversion to the bis(acyl azide) under phase transfer conditions followed by a thermal bis-Curtius rearrangement and *t*-butanol capture afforded the bis(BOC)-protected diaminopyrazine **2**.⁶ Remarkably, tetralithiation with LDA or LTMP followed by treatment with methyl pinacol borate afforded the required dimetalated diamine **3**. The lithiation proceeded in very high yield since the tetralithio derivative could be quenched with TMSCl to afford the bis(trimethylsilyl)arene in 91% yield after aqueous work-up and purification. Further purification of the bis(boronic


ester) is required. **1** could also be dibutylated with the dialkylcuprate to afford the required diketo functionality of the second monomeric intermediate (**4**). Methods for the selective bromination of **4** for the preparation of the required diketodibromide **5** are currently being developed. The superb efficiency of this divergent (common intermediate **1**) approach is indeed apparent.

The required monomer for the planar polythiophene is being prepared in the following manner. Standard protocol



was used for thiol conjugate addition, ester enolate formation, cyclization, oxime formation, and dehydration to afford the thiophene skeleton (**6**) with the amine and carbonyl moieties in place.⁷ Imide formation, saponification, and acid chloride formation afforded **7** which could be converted to the ketone (**8**) with butylzinc chloride and Pd(0) catalysis.⁸ We are presently working on methods to permit 2-position bromination and 5-position metalation to afford the required monomer **9** for the step growth polymerization.

Our approach to the planar polypyridine monomers is less well-developed, however, our progress is as outlined below. Dimethylpyridine was brominated under forcing



conditions to yield 10.⁹ A two step oxidation procedure afforded the desired dibrombis(acid) 11.¹⁰ We hope to utilize a divergent approach as outlined for 1 to convert 11 into the two monomers needed for the planar polypyridine material.

Acknowledgments. We are grateful for support from the Office of Naval Research, and the National Science Foundation (EHR-91-08772, DMR-9158315), and generous industrial contributors to the NSF Presidential Young Investigator Award (1991-96): Hercules, IBM, Ethyl, Shell, Exxon, Farchan, Molecular Design Ltd., and Eli Lilly Corporations.

References and Notes

(1) For some discussions of aromatic ladder polymers, see: (a) Overberger, C. G.; Moore, J. A. *Adv. Polym. Sci.* **1970**, *7*, 113. (b) Schlüter, A.-D. *Adv. Mater.* **1991**, *3*, 282. (c) Yu, L.; Chen, M. Dalton, L. R. *Chem. Mater.* **1990**, *2*, 649. (d) Hong, S. Y.; Kertesz, M.; Lee, Y. S.; Kim, O.-K. *Chem. Mater.* **1992**, *4*, 378. (e) Godt, A.; Schlüter, A.-D. *Adv. Mater.* **1991**, *3*, 497. (f) Yu, L.; Dalton, L. R. *Macromolecules* **1990**, *23*, 3439. (g) Scherf, U.; Müllen, K. *Macromolecules* **1992**, *25*, 3546. (h) Goldfinger, M. B.; Swager, T. M. *Polym. Prepr. (Am. Chem. Soc., Div. Polym. Chem.)* **1994**, *35*(1), 273.

(2) For a discussion of twist angle versus degree of extended conjugation, see: (a) Brédas, J. L. In *Handbook of Conducting Polymers*; Skotheim, T. A., Ed.; Dekker: New York, 1986. (b) Ferraris, J. P.; Andrus, R. G.; Hrcir, D. C. *J. Chem. Soc., Chem. Commun.* **1989**, 1318. (c) Gorman, C. B.; Ginsburg, E. J.; Moore, J. S.; Grubbs, R. H. *Polym. Prepr. (Am. Chem. Soc., Div. Polym. Chem.)* **1991**, *32*(3), 714.

(3) Tour, J. M.; Lamba, J. J. S. *J. Am. Chem. Soc.* **1993**, *115*, 4935.

(4) Beech, W. F. *J. Chem. Soc.* **1955**, 3094.

(5) Schut, W. J.; Mager, H. I. X.; Bereends, W. *Recueil* **1961**, *80*, 391.

(6) We developed these rearrangements conditions at the same time that Swager described an analogous procedure without BOC protection. See: Zhou, Q.; Swager, T. M. *Polym. Prepr. (Am. Chem. Soc., Div. Polym. Chem.)* 1994, 35(1), 277. Our development was based on work by Pfister. See: Pfister, J. R.; Wymann, W. E. *Synthesis* 1983, 38.

(7) (a) Woodward, R. B.; Eastham, R. H. *J. Am. Chem. Soc.* 1946, 68, 2229. (b) Baker, B. R.; Joseph, J. P.; Schaub, R. E. *J. Org. Chem.* 1953, 81, 138.

(8) Negishi, E.; Bagheri, V.; Chatterjee, S.; Luo, F.-T.; Miller, J. A.; Stoll, A. T. *Tetrahedron Lett.* 1983, 24, 5181.

(9) Abblard, J.; Decoret, C.; Cronenberger, L.; Pacheco, H. *Bull. Soc. Chim. Fr.* 1972, 2466.

(10) A similar two step oxidation procedure was suggested by Swager, T. M., personal communication.