


LEHIGH UNIVERSITY




SUDDEN STRETCHING OF A FOUR LAYERED-COMPOSITE PLATE

BY

G. C. SIH AND E. P. CHEN

MARCH 1980

NASA CR 259870



19951214 113


MATERIALS AND STRUCTURES DIVISION
NASA-LEWIS RESEARCH CENTER
CLEVELAND, OHIO 44135

DEPARTMENT OF DEFENSE
PLASTICS TECHNICAL EVALUATION CENTER
ARADCOM, DOWER, N. J. 07801

PLASTEC

27390

NO ETC-1-102-
D-FOU OZA EDC-10ADT
NO-2AION3



1. Report No. NASA CR159870	2. Government Accession No.	3. Recipient's Catalog No.	
4. Title and Subtitle Sudden Stretching of a Four-Layered Composite Plate		5. Report Date March 1980	
		6. Performing Organization Code	
7. Author(s) G. C. Sih and E. P. Chen		8. Performing Organization Report No.	
9. Performing Organization Name and Address Lehigh University Institute of Fracture and Solid Mechanics Bethlehem, PA 18015		10. Work Unit No.	
		11. Contract or Grant No. NSG3179	
12. Sponsoring Agency Name and Address National Aeronautics and Space Administration Washington DC 20546		13. Type of Report and Period Covered Interim Report	
		14. Sponsoring Agency Code	
15. Supplementary Notes Project Manager: C. C. Chamis Structures and Mechanical Technologies Division NASA-Lewis Research Center 21000 Brookpark Road, Mail Stop 49-3 Cleveland, OH 44135			
16. Abstract An approximate theory of laminated plates is developed by assuming that the extensional and thickness mode of vibration are coupled. The mixed boundary value crack problem of a four-layered composite plate is solved. Dynamic stress intensity factors for a crack subjected to suddenly applied stress are found to vary as a function of time and depend on the material properties of the laminate. Stress intensification in the region near the crack front can be reduced by having the shear modulus of the inner layers to be larger than that of the outer layers.			
17. Key Words (Suggested by Author(s)) Elastodynamics, stress intensity, layered plates, stress analysis, cracks, computer program		18. Distribution Statement Unclassified, unlimited	
19. Security Classif. (of this report) Unclassified	20. Security Classif. (of this page) Unclassified	21. No. of Pages 35	22. Price* A03

DTIC QUALITY INSPECTED 3

* For sale by the National Technical Information Service, Springfield, Virginia 22161

FOREWORD

The results in this report on the sudden stretching of a four-layered composite plate were obtained during the course of research supported by the NASA-Lewis Research Center in Cleveland, Ohio, for the period February 13, 1979 through February 12, 1980 under Grant NSG 3179 with the Institute of Fracture and Solid Mechanics at Lehigh University. The Principal Investigator of the Project is Professor George C. Sih who wishes to acknowledge Dr. Christos C. Chamis, the NASA Project Manager, for the encouragement he provided during this Project.

TABLE OF CONTENTS

FOREWORD	iv
TABLE OF CONTENTS	v
LIST OF FIGURES	vi
LIST OF SYMBOLS	vii
ABSTRACT	1
INTRODUCTION	2
BASIC FORMULATION	4
METHOD OF SOLUTION	10
DUAL COUPLED INTEGRAL EQUATIONS	13
DYNAMIC STRESS INTENSITY FACTORS	16
CONCLUDING REMARKS	20
REFERENCES	21
COMPUTER PROGRAM: DYNAMIC LAMINATE PLATE THEORY WITH A CRACK	22

Accession For	
NTIS CRA&I	☒
DTIC TAB	☐
Unannounced	☐
Justification _____	
By _____	
Distribution /	
Availability Codes	
Dist	Avail and/or Special
A-1	

LIST OF FIGURES

Figure 1 - A four-layered composite plate with a crack

Figure 2 - Numerical values of $\phi^*(1,p)$ as a function of c_{21}/pa for $a/h = 1.0$

Figure 3 - Normalized resultant stress intensity factor versus $c_{21}t/a$ for $a/h = 1.0$

LIST OF SYMBOLS

a	- half crack length
$A, B, \dots, D$	- unknowns in integrals, functions of (s, p)
Br	- Bromwich contour in complex p -plane
c_{21}	- shear wave speed for material 1
F, G	- known functions of (s, p)
h	- laminate thickness
H	- potential function
H^*	- Laplace transform of H
$H(t)$	- Heaviside unit step function
J_0	- Bessel function of order zero
$k_I(t)$	- dynamic stress intensity factor
$k_I^*(p)$	- Laplace transform of $k_I(t)$
$L(\xi, n, p)$	- kernel in Fredholm integral equation
N_0	- constant stress resultant
$N_x, N_y, \dots, N_{xy}$	- stress resultants
p	- Laplace transform variable
R_x, R_y	- transverse shear forces
r, θ	- crack tip polar coordinates
s	- variable of integration
s_j	- parameter defined in equation (26) with $j = 1, 2$
t	- time
u_x, v_y, w_z	- displacement components in the (x, y, z) coordinate system
v_x, v_y, v_z	- displacement functions of x and y
x, y, z	- rectangular coordinates

$\alpha_0, \gamma_0, \delta_0, \rho_0, \omega_0$	- material parameters
β, γ, δ	- material constants
Δ_j	- defined in equation (28) with $j = 1, 2$
$\epsilon_x, \epsilon_y, \dots, \gamma_{yz}$	- strain components
κ	- correction factor $\pi/\sqrt{12}$ in plate theory
μ_j	- shear moduli with $j = 1, 2$
ν_j	- Poisson's ratio with $j = 1, 2$
ξ, η	- variables of integration
ρ_j	- mass density for material j
λ_j, μ_j	- Lamé coefficients with $j = 1, 2$
$(\Lambda_x)_j, (\Lambda_y)_j, \dots, (\Lambda_{xy})_j$	- strain resultants
$\sigma_x, \sigma_y, \dots, \tau_{yz}$	- stress components
ϕ^*	- potential function in Laplace transform plane
$\Phi^*(\xi, p)$	- unknown in Fredholm integral equation

SUDDEN STRETCHING OF A FOUR-LAYERED COMPOSITE PLATE

by

G. C. Sih
Institute of Fracture and Solid Mechanics
Lehigh University
Bethlehem, Pennsylvania 18015

and

E. P. Chen
Sandia Laboratories
Albuquerque, New Mexico 87115

ABSTRACT

A research effort primarily concerned with the understanding of laminated composite plates with cracks subjected to time-dependent extensional loads is reported here. When loads are applied suddenly to a laminate, waves are reflected and refracted through the laminae and give rise to stresses and strains throughout the composite system. The process is three-dimensional in character and presents a formidable problem in the theory of elastodynamics, particularly in the presence of crack-like imperfections.

An approximate theory of laminated plates is developed by assuming that the extensional and thickness mode of vibration are coupled. The mixed boundary value crack problem of a four-layered composite plate is solved. Dynamic stress intensity factors for a crack subjected to suddenly applied stress are found to vary as a function of time and depend on the material properties of the laminate. Stress intensification in the region near the crack front can be reduced by having the shear modulus of the inner layers to be larger than that of the outer layers.

INTRODUCTION

The current interest in laminates for structural application is associated with the high strength-to-weight ratio which can be developed in laminates. These laminates are generally composed of layers which have been reinforced by embedding unidirectional fibers. The layers are adhered to each other such that the fiber direction varies from one layer to the next in a previously determined manner. The freedom of choice for fiber orientation in the layers of the composite system enables the development of laminates with special preferential directional properties for particular applications. Because of this characteristic of fibrous composites, the employment of these systems rather than equivalent homogeneous members will be clearly advantageous in many applications.

Because of the complicated internal structure of composite systems, stress analysis is much more difficult than for equivalent single-phase material. One fact which emerges very clearly from laminate studies is that the stress field in composite systems is truly three-dimensional in character. Thus, even the stress field in a symmetric laminate subjected to in-plane loading cannot be accurately modeled by standard two-dimensional methods of analysis. The previous work in this area further indicates that relatively little effort has been made to formulate laminate plate theories that can effectively solve for the redistribution of stresses and strains due to the presence of mechanical imperfections such as cracks.

One possible means of simplifying the three-dimensional equations of elasticity is to invoke the concept adopted in the formulation of plate theory. Approximate stress and strain dependence on the plate thickness coordinate are assumed such that the governing differential equations possess only two independent

space variables. In addition, special attention must be given to the state of affairs near the crack when formulating plate theories for analyzing crack problems. With this in mind, Hartranft and Sih [1] developed an approximate three-dimensional theory for a single material plate containing a through crack. The condition of plane strain was preserved ahead of the crack as suggested by Sih [2]. This theory was later extended to laminates by Badaliance, Sih and Chen [3] to solve the problem of a through crack in a laminar plate subjected to in-plane loading. The through crack configuration represents a preliminary effort to model the damage of composite plates. Additional complications arise when the load is time dependent. These considerations will be taken into account in the development of a new dynamic theory of laminated composite plates subjected to extensional loads.

This work is concerned with the formulation of a dynamic theory of laminated plates and reduces to that of Kane and Mindlin [4] for the single material plate. The idealized condition of stress and displacement continuity across the interface is replaced by assigning certain conditions of material nonhomogeneity in the thickness direction of the laminated plate as if it were a single layered nonhomogeneous plate. The nonhomogeneity is made equivalent to a symmetric laminate balanced with reference to its mid-plane. A through crack is assumed to exist in a four-layered laminate. Dynamic stress intensity factors are obtained for the case of a suddenly applied uniform in-plane loading and shown to vary as a function of time. Discussed are also the influence of material properties of the layers on the local stresses.

BASIC FORMULATION

The elastodynamic equations of generalized plane stress are adequate only if the frequency of vibration is lower than that of the first thickness mode and the wave length is large in comparison with the plate thickness. In other words, the coupling between extensional and thickness mode of vibration can be neglected. When laminated composite plates are stressed dynamically, loads are transmitted through the laminae by the reflection of thickness refraction of stress waves. The mode of vibration cannot be ignored, particularly in the vicinity of a crack-like imperfection where the stress state acquires a three-dimensional character.

A dynamic laminate plate theory will be developed to solve the problem of a four-layered composite plate with a through crack subjected to a suddenly applied uniform extensional load. The theory is a generalization to that given by Kane and Mindlin [4] for a single layer plate in which the extensional and thickness mode of vibration are assumed to be coupled. Accounted for is the lowest thickness-stretch mode such that the displacement is normal to the plate surface. Mindlin and Medick [5] have also considered a formulation in which the thickness-shear mode of vibration with displacement parallel to the plate surface is also included. The mid-plane of the plate is taken as the nodal plane of vibration.

Consider a four-layered composite plate of thickness h as shown in Figure 1 where each layer has the same thickness $h/4$. The two outer layers have material properties (μ_2, ν_2) or (λ_2, μ_2) while the two inner layers have material properties (μ_1, ν_1) or (λ_1, μ_1) . The Lamé coefficients are denoted by λ_j and μ_j ($j = 1, 2$). The layers are stacked such that symmetry prevails across the mid-plane of the laminate composite. The crack of width $2a$ cuts through the entire thickness of the laminate.




Figure 1 - A four-layered composite plate with a crack

The time-dependent displacement field is assumed to be

$$\begin{aligned}
 u_x &= v_x(x, y, t) \\
 v_y &= v_y(x, y, t) \\
 w_z &= \frac{2z}{h} v_z(x, y, t)
 \end{aligned}
 \tag{1}$$

It follows that the strain components can be written as

$$\begin{aligned}
 \epsilon_x(x, y, t) &= \frac{\partial v_x}{\partial x} \\
 \epsilon_y(x, y, t) &= \frac{\partial v_y}{\partial y} \\
 \epsilon_z(x, y, t) &= \frac{2}{h} v_z \\
 \gamma_{xy}(x, y, t) &= \frac{\partial v_x}{\partial y} + \frac{\partial v_y}{\partial x} \\
 \gamma_{yz}(x, y, t) &= \frac{2z}{h} \frac{\partial v_z}{\partial y} \\
 \gamma_{zx}(x, y, t) &= \frac{2z}{h} \frac{\partial v_z}{\partial x}
 \end{aligned}
 \tag{2}$$

in which the transverse normal and shear strains are assumed to be linear in the thickness coordinate z . If each layer of the laminated composite plate is isotropic, then the following stress-strain relationships may be used:

$$\begin{aligned}
 \sigma_x &= (\lambda + 2\mu)\epsilon_x + \lambda(\epsilon_y + \kappa\epsilon_z) \\
 \sigma_y &= (\lambda + 2\mu)\epsilon_y + \lambda(\epsilon_x + \kappa\epsilon_z) \\
 \sigma_z &= (\lambda + 2\mu)\kappa^2\epsilon_z + \lambda\kappa(\epsilon_x + \epsilon_y)
 \end{aligned}$$

$$\tau_{yz} = \mu \gamma_{yz}$$

$$\tau_{zx} = \mu \gamma_{zx}$$

$$\tau_{xy} = \mu \gamma_{xy} \quad (3)$$

The constant

$$\kappa = \pi/\sqrt{12} \quad (4)$$

accounts for the coupling between the extensional and thickness mode of vibration.

It is determined from the three-dimensional equations of elasticity. As in the development of plate theories, the resultant strain quantities $(\Lambda_x)_j$, $(\Lambda_y)_j$, ..., $(\Lambda_{xy})_j$ ($j = 1, 2$) will be defined:

$$\begin{aligned} [(\Lambda_x)_1, (\Lambda_y)_1, (\Lambda_z)_1, (\Lambda_{xy})_1] &= \frac{2}{h} \int_{-h/4}^{h/4} [\epsilon_x, \epsilon_y, \epsilon_z, \gamma_{xy}] dz \\ [(\Lambda_x)_2, (\Lambda_y)_2, (\Lambda_z)_2, (\Lambda_{xy})_2] &= \frac{2}{h} \left\{ \int_{h/4}^{h/2} [\epsilon_x, \epsilon_y, \epsilon_z, \gamma_{xy}] dz \right. \\ &\quad \left. + \int_{-h/2}^{-h/4} [\epsilon_x, \epsilon_y, \epsilon_z, \gamma_{xy}] dz \right\} \end{aligned} \quad (5)$$

$$\begin{aligned} [(\Lambda_{xz})_1, (\Lambda_{yz})_1] &= \frac{96}{h^3} \int_{-h/4}^{h/4} [\gamma_{xz}, \gamma_{yz}] z dz \\ [(\Lambda_{xz})_2, (\Lambda_{yz})_2] &= \frac{96}{7h^3} \int_{-h/2}^{-h/4} [\gamma_{xz}, \gamma_{yz}] z dz + \frac{h/2}{h/4} \int_{h/4}^{h/2} [\gamma_{xz}, \gamma_{yz}] z dz \end{aligned}$$

Substituting equations (2) into (5), it is found that

$$(\Lambda_x)_1 = (\Lambda_x)_2 = \frac{\partial v_x}{\partial x}$$

$$\begin{aligned}
(\Lambda_y)_1 &= (\Lambda_y)_2 = \frac{\partial v_x}{\partial y} \\
(\Lambda_z)_1 &= (\Lambda_z)_2 = \frac{2}{h} v_z \\
(\Lambda_{xy})_1 &= (\Lambda_{xy})_2 = \frac{\partial v_x}{\partial y} + \frac{\partial v_y}{\partial x} \\
(\Lambda_{xz})_1 &= (\Lambda_{xz})_2 = \frac{2}{h} \frac{\partial v_z}{\partial x} \\
(\Lambda_{yz})_1 &= (\Lambda_{yz})_2 = \frac{2}{h} \frac{\partial v_z}{\partial y}
\end{aligned} \tag{6}$$

The laminate plate theory can be most conveniently formulated in terms of the stress resultants

$$(N_x, N_y, N_z, N_{xy}) = \int_{-h/2}^{h/2} (\sigma_x, \sigma_y, \sigma_z, \tau_{xy}) dz \tag{7}$$

and the transverse shears

$$(R_x, R_y) = \int_{-h/2}^{h/2} (\tau_{xz}, \tau_{yz}) z dz \tag{8}$$

The stress-strain relations in equations (3) when enforced yield

$$\begin{aligned}
N_x(x, y, t) &= \frac{h}{2} [(\beta+2\gamma) \frac{\partial v_x}{\partial x} + \beta \frac{\partial v_y}{\partial y}] + \beta \kappa v_z \\
N_y(x, y, t) &= \frac{h}{2} [(\beta+2\gamma) \frac{\partial v_y}{\partial y} + \beta \frac{\partial v_x}{\partial x}] + \beta \kappa v_z \\
N_z(x, y, t) &= (\beta+2\gamma) \kappa^2 v_z + \frac{1}{2} \beta \kappa h \left(\frac{\partial v_x}{\partial x} + \frac{\partial v_y}{\partial y} \right) \\
N_{xy}(x, y, t) &= \frac{1}{2} \gamma h \left(\frac{\partial v_x}{\partial y} + \frac{\partial v_y}{\partial x} \right)
\end{aligned} \tag{9}$$

and

$$R_x(x,y,t) = \frac{1}{48} \delta h^2 \frac{\partial v_z}{\partial x}$$

$$R_y(x,y,t) = \frac{1}{48} \delta h^2 \frac{\partial v_z}{\partial y}$$
(10)

In equations (9) and (10), β , γ and δ stand for

$$\beta = \lambda_1 + \lambda_2, \quad \gamma = \mu_1 + \mu_2, \quad \delta = \mu_1 + 7\mu_2$$
(11)

Denoting ρ_1 and ρ_2 as the mass density of the inner and outer layers of the laminate, the three equations of motion governing N_x , N_y , ..., R_y become

$$\frac{\partial N_x}{\partial x} + \frac{\partial N_{xy}}{\partial y} = \frac{1}{2} h(\rho_1 + \rho_2) \frac{\partial^2 v_x}{\partial t^2}$$

$$\frac{\partial N_{xy}}{\partial x} + \frac{\partial N_y}{\partial y} = \frac{1}{2} h(\rho_1 + \rho_2) \frac{\partial^2 v_y}{\partial t^2}$$

$$\frac{\partial R_x}{\partial x} + \frac{\partial R_y}{\partial y} - N_z = \frac{1}{48} h^2(\rho_1 + 7\rho_2) \frac{\partial^2 v_z}{\partial t^2}$$
(12)

The result of substituting equations (9) and (10) into (12) renders

$$\gamma \nabla^2 v_x + (\beta + \gamma) \frac{\partial}{\partial x} \left(\frac{\partial v_x}{\partial x} + \frac{\partial v_y}{\partial y} \right) + \frac{2\beta\kappa}{h} \frac{\partial v_z}{\partial x} = (\rho_1 + \rho_2) \frac{\partial^2 v_x}{\partial t^2}$$

$$\gamma \nabla^2 v_y + (\beta + \gamma) \frac{\partial}{\partial y} \left(\frac{\partial v_x}{\partial x} + \frac{\partial v_y}{\partial y} \right) + \frac{2\beta\kappa}{h} \frac{\partial v_z}{\partial y} = (\rho_1 + \rho_2) \frac{\partial^2 v_y}{\partial t^2}$$

$$\delta \nabla^2 v_z - \frac{48}{h^2} (\beta + 2\gamma) \kappa^2 v_z - \frac{24\beta\kappa}{h} \left(\frac{\partial v_x}{\partial x} + \frac{\partial v_y}{\partial y} \right) = (\rho_1 + 7\rho_2) \frac{\partial^2 v_z}{\partial t^2}$$
(13)

where $\nabla^2 = \partial^2/\partial x^2 + \partial^2/\partial y^2$ is the Laplacian operator in two dimensions.

METHOD OF SOLUTION

Equations (13) will be solved by introducing two potential functions $\phi(x,y,t)$ and $H(x,y,t)$ as

$$\begin{aligned} v_x(x,y,t) &= \frac{\partial \phi}{\partial x} + \frac{\partial H}{\partial y} \\ v_y(x,y,t) &= \frac{\partial \phi}{\partial y} - \frac{\partial H}{\partial x} \end{aligned} \quad (14)$$

Making the appropriate algebraic manipulations, the governing equations for the potential functions can be derived by enforcing equations (13):

$$\begin{aligned} \gamma \nabla^2 H &= (\rho_1 + \rho_2) \frac{\partial^2 H}{\partial t^2} - \delta(\beta + 2\gamma) \nabla^4 \phi + \frac{192 \kappa^2 \gamma (\beta + 2\gamma)}{h^2} \nabla^2 \phi \\ &= \{(\rho_1 + \rho_2) [(\rho_1 + 7\rho_2) \frac{\partial^4 \phi}{\partial t^4} + \frac{48}{h^2} (\beta + 2\gamma) \frac{\partial^2 \phi}{\partial t^2}] \\ &\quad - [\delta(\rho_1 + \rho_2) + (\beta + 2\gamma)(\rho_1 + 7\rho_2) \frac{\partial^2}{\partial t^2} (\nabla^2 \phi)]\} \end{aligned} \quad (15)$$

Once $\phi(x,y,t)$ and $H(x,y,t)$ are known, v_x and v_y can be obtained from equations (14) and

$$v_z(x,y,t) = \frac{h}{2\beta\kappa} [(\rho_1 + \rho_2) \frac{\partial^2 \phi}{\partial t^2} - (\beta + 2\kappa) \nabla^2 \phi] \quad (16)$$

Suppose that a uniform stress resultant N_0 is applied suddenly to the crack surfaces and the resulting deformation is symmetrical with respect to the x-axis, then the following conditions are to be specified:

$$N_y(x,0,t) = -N_0 H(t), \quad x < a \quad (17)$$

$$v_y(x,0,t) = 0, \quad x \geq a$$

where $H(t)$ is the Heaviside unit step function. The condition of symmetry further requires that

$$N_{xy}(x,0,t) = R_y(x,0,t) = 0, \quad \text{for all } x \quad (18)$$

Use will now be made of the Laplace transform. Let $\phi^*(x,y,p)$, $H^*(x,y,p)$, etc., denote the Laplace transforms of the functions $\phi(x,y,t)$, $H(x,y,t)$, etc. Equation (15) when expressed in the Laplace transform domain become

$$(\nabla^2 - \omega_1^2) \phi_1^*(x,y,p) = 0$$

$$(\nabla^2 - \omega_2^2) \phi_2^*(x,y,p) = 0 \quad (19)$$

$$(\nabla^2 - \omega_3^2) H^*(x,y,p) = 0$$

where the potential $\phi(x,y,t)$ has been separated into two parts:

$$\phi(x,y,t) = \phi_1(x,y,t) + \phi_2(x,y,t) \quad (20)$$

in terms of time t or

$$\phi^*(x,y,p) = \phi_1^*(x,y,p) + \phi_2^*(x,y,p) \quad (21)$$

in terms of the Laplace transform variable p . The parameters ω_j ($j = 1,2,3$) in equations (19) are defined as

$$\omega_{1,2}^2 = \frac{6\kappa^2}{h\delta_0} [(\alpha_0 + \delta_0) \left(\frac{p}{\omega_0}\right)^2 + \rho_0 \pm \{[(\alpha_0 + \delta_0) \left(\frac{p}{\omega_0}\right)^2 + \rho_0]^2 - 4\alpha_0\delta_0 \left(\frac{p}{\omega_0}\right)^2 [(\frac{p}{\omega_0})^2 + \rho_0]\}^{1/2}] \quad (22)$$

$$\omega_3^2 = (\rho_1 + \rho_2) p^2 \gamma^{-1}$$

in which the newly defined quantities are

$$\alpha_0 = \frac{\beta + 2\gamma}{(\rho_1 + \rho_2)\gamma_0^2}, \quad \delta_0 = \frac{\delta}{(\rho_1 + 7\rho_2)\gamma_0^2} \quad (23)$$

$$\rho_0 = \frac{4(\rho_1 + \rho_2)}{\rho_1 + 7\rho_2}, \quad \omega_0^2 = \frac{12\kappa^2(\beta + 2\gamma)}{h^2(\rho_1 + \rho_2)}$$

and γ_0 takes the form

$$\gamma_0^2 = \frac{4\gamma(\beta + \gamma)}{(\rho_1 + \rho_2)(\beta + 2\gamma)} \quad (24)$$

Equations (19) then give

$$\phi_1^*(x, y, p) = \frac{2}{\pi} \int_0^\infty A(s, p) \cos(sx) \exp(-s_1 y) ds$$

$$\phi_2^*(x, y, p) = \frac{2}{\pi} \int_0^\infty B(s, p) \cos(sx) \exp(-s_2 y) ds \quad (25)$$

$$H^*(x, y, p) = \frac{2}{\pi} \int_0^\infty C(s, p) \sin(sx) \exp(-s_3 y) ds$$

with s_j being given by

$$s_j = \sqrt{s^2 + \omega_j^2}, \quad j = 1, 2, 3 \quad (26)$$

The dynamic problem has now been reduced to finding the three unknown functions $A(s,p)$, $B(s,p)$ and $C(s,p)$.

DUAL COUPLED INTEGRAL EQUATIONS

Before the boundary and symmetry conditions can be enforced, it is necessary to obtain $v_x^*(s,y,p)$, $v_y^*(x,y,p)$, etc., in terms of the unknowns in equations (25). With the help of equations (14) and (16), it can be shown that

$$v_x^*(x,y,p) = -\frac{2}{\pi} \int_0^\infty [sA(s,p) \exp(-s_1 y) + sB(s,p) \exp(-s_2 y) + s_3 C(s,p) \exp(-s_3 y)] \sin(sx) ds$$

$$v_y^*(x,y,p) = -\frac{2}{\pi} \int_0^\infty [s_1 A(s,p) \exp(-s_1 y) + s_2 B(s,p) \exp(-s_2 y) + sC(s,p) \exp(-s_3 y)] \cos(sx) ds \quad (27)$$

$$v_z^*(x,y,p) = \frac{2}{\pi} \int_0^\infty [\Delta_1 A(s,p) \exp(-s_1 y) + \Delta_2 B(s,p) \exp(-s_2 y)] \cos(sx) ds$$

The quantities Δ_j ($j = 1,2$) are given by

$$\Delta_j = \frac{h(\beta+2\gamma)}{2\beta\kappa} \left[\frac{(\rho_1+\rho_2)p^2}{\beta+2\gamma} - \omega_j^2 \right], \quad j = 1,2 \quad (28)$$

Similarly, the Laplace transform of $N_x^*(x,y,p)$, $N_y^*(x,y,p)$ become

$$N_x^*(x,y,p) = \frac{2}{\pi} \gamma h \int_0^\infty \left\{ \left[\frac{(\rho_1+\rho_2)p^2}{2\gamma} - s_1^2 \right] A(s,p) \exp(-s_1 y) + \left[\frac{(\rho_1+\rho_2)p^2}{2\gamma} - s_2^2 \right] B(s,p) \exp(-s_2 y) - s s_3 C(s,p) \exp(-s_3 y) \right\} \cos(sx) ds$$

$$N_y^*(x,y,p) = \frac{2}{\pi} \gamma h \int_0^\infty \left\{ [s^2 + \frac{(\rho_1 + \rho_2)p^2}{2\gamma}] [A(s,p) \exp(-s_1 y) + B(s,p) \exp(-s_2 y)] \right. \\ \left. + s s_3 C(s,p) \exp(-s_3 y) \right\} \cos(sx) ds \quad (29)$$

$$N_{xy}^*(x,y,p) = \frac{2}{\pi} \gamma h \int_0^\infty \{ s s_1 A(s,p) \exp(-s_1 y) + s s_2 B(s,p) \exp(-s_2 y) \\ + \frac{1}{2} (s^2 + s_3^2) C(s,p) \exp(-s_3 y) \} \sin(sx) ds$$

while $R_x^*(x,y,p)$ and $R_y^*(x,y,p)$ take the forms

$$R_x^*(x,y,p) = - \frac{\delta h^2}{24\pi} \int_0^\infty s [\Delta_1 A(s,p) \exp(-s_1 y) + \Delta_2 B(s,p) \exp(-s_2 y)] \sin(sx) ds \quad (30)$$

$$R_y^*(x,y,p) = - \frac{\delta h^2}{24\pi} \int_0^\infty [s_1 \Delta_1 A(s,p) \exp(-s_1 y) + s_2 \Delta_2 B(s,p) \exp(-s_2 y)] \cos(sx) ds$$

The symmetry conditions in equations (18) when applied show that $A(s,p)$, $B(s,p)$ and $C(s,p)$ can be expressed in terms of a single unknown $D(s,p)$:

$$A(s,p) = \frac{s^2 + s_3^2}{s_1} D(s,p) \\ B(s,p) = -s_1 \left[\frac{(\rho_1 + \rho_2)p^2}{\beta + 2\gamma} - \omega_1^2 \right] / \{ s_2 \left[\frac{(\rho_1 + \rho_2)p^2}{\beta + 2\gamma} - \omega_2^2 \right] \} A(s,p) \quad (31) \\ C(s,p) = - \frac{2s s_1 (\omega_1^2 - \omega_2^2)}{(s^2 + s_3^2) \left[\frac{(\rho_1 + \rho_2)p^2}{\beta + 2\gamma} - \omega_2^2 \right]} A(s,p)$$

Application of the mixed boundary conditions in equations (17) leads to a system of dual integral equations

$$\int_0^{\infty} D(s,p) \cos(sx) ds = 0, \quad x \geq a \quad (32)$$

$$\int_0^{\infty} sF(s,p) D(s,p) \cos(sx) ds = -\frac{\pi N_0}{2\gamma hp}, \quad x < a$$

The function $F(s,p)$ is known:

$$F(s,p) = \frac{s^2 + s_3^2}{ss_1} \left[\left[s^2 + \frac{(\rho_1 + \rho_2)p^2}{2\gamma} \right] \left\{ 1 - \frac{s_1 \left[\frac{(\rho_1 + \rho_2)p^2}{\beta + 2\gamma} - \omega_2^2 \right]}{s_2 \left[\frac{(\rho_1 + \rho_2)p^2}{\beta + 2\gamma} - \omega_2^2 \right]} \right\} - \frac{2s^2 s_1 s_3}{s^2 + s_3^2} \left[\frac{\omega_1^2 - \omega_2^2}{(\rho_1 + \rho_2)p^2 / (\beta + 2\gamma) - \omega_2^2} \right] \right] \quad (33)$$

The standard procedure by Copson [6] may be applied to solve equations (32) and the result is

$$D(s,p) = -\frac{\pi N_0 a^2}{2\gamma hp} \left\{ \frac{[(\rho_1 + \rho_2)p^2 / (\beta + 2\gamma)] - \omega_2^2}{\frac{(\rho_1 + \rho_2)p^2}{\gamma} \left(1 - \frac{\gamma}{\beta + 2\gamma} \right) (\omega_1^2 - \omega_2^2)} \right\} \times \int_0^1 \sqrt{\xi} \Phi^*(\xi, p) J_0(sa\xi) d\xi \quad (34)$$

in which $\Phi^*(\xi, p)$ can be computed from a Fredholm integral equation of the second kind:

$$\Phi^*(\xi, p) + \int_0^1 \Phi^*(\eta, p) L(\xi, \eta, p) d\eta = \sqrt{\xi} \quad (35)$$

The kernel $L(\xi, \eta, p)$ is

$$L(\xi, \eta, p) = \sqrt{\xi\eta} \int_0^{\infty} s \left[G\left(\frac{s}{a}, p\right) - 1 \right] J_0(s\xi) J_0(s\eta) ds \quad (36)$$

while the function $G(s,p)$ is related to $F(s,p)$ in equation (33):

$$G(s,p) = \frac{\{[(\rho_1 + \rho_2)p^2/(\beta + 2\gamma)] - \omega_2^2\}^\gamma}{p^2[1 - \gamma/(\beta + 2\gamma)](\omega_1^2 - \omega_2^2)} F(s,p) \quad (37)$$

DYNAMIC STRESS INTENSITY FACTORS

Of interest is the intensification of the dynamic stresses ahead of the crack. Hence, the integrals in equations (29) and (30) must be evaluated for large values of s which corresponds to distances near the crack edge $x = \pm a$ and $y=0$. In terms of the polar coordinates r and θ in Figure 1, the Laplace transform of the stress resultants for small r are found:

$$\begin{aligned} N_x^*(r, \theta, p) &= \frac{k_1^*(p)}{\sqrt{2r}} \cos \frac{\theta}{2} (1 - \sin \frac{\theta}{2} \sin \frac{3\theta}{2}) + O(r^0) \\ N_y^*(r, \theta, p) &= \frac{k_1^*(p)}{\sqrt{2r}} \cos \frac{\theta}{2} (1 + \sin \frac{\theta}{2} \sin \frac{3\theta}{2}) + O(r^0) \\ N_{xy}^*(r, \theta, p) &= \frac{k_1^*(p)}{\sqrt{2r}} \sin \frac{\theta}{2} \cos \frac{\theta}{2} \cos \frac{3\theta}{2} + O(r^0) \\ R_x^*(r, \theta, p) &= R_y^*(r, \theta, p) = O(r^0) \end{aligned} \quad (38)$$

in which $k_1^*(p)$ is the Laplace transform of $k_1(t)$:

$$k^*(p) = \frac{\Phi^*(1, p)}{p} N_0 \sqrt{a} \quad (39)$$

The Laplace inversion theorem may now be applied to give

$$N_x(r, \theta, t) = \frac{k_1(t)}{\sqrt{2r}} \cos \frac{\theta}{2} (1 - \sin \frac{\theta}{2} \sin \frac{3\theta}{2}) + O(r^0)$$

$$N_y(r, \theta, t) = \frac{k_1(t)}{\sqrt{2r}} \cos \frac{\theta}{2} (1 + \sin \frac{\theta}{2} \sin \frac{3\theta}{2}) + O(r^0)$$

(40)

$$N_{xy}(r, \theta, t) = \frac{k_1(t)}{\sqrt{2r}} \sin \frac{\theta}{2} \cos \frac{\theta}{2} \cos \frac{3\theta}{2} + O(r^0)$$

$$R_x(r, \theta, t) = R_y(r, \theta, t) = O(r^0)$$

Equations (40) reveal that dynamic loading does not affect the functional relationship of r and θ . The stress intensity factor, however, is a function of time:

$$k_1(t) = \frac{N_0 \sqrt{a}}{2\pi i} \int_{Br} \frac{\Phi^*(1, p)}{p} \exp(pt) dp \quad (41)$$

where Br denotes the Bromwich path of integration. Once $\Phi^*(\xi, p)$ is calculated from equation (35) and evaluated at $\xi=1$, equation (41) may be solved numerically.

Figure 2 gives a plot of $\Phi^*(1, p)$ as a function of c_{21}/pa where $c_{21} = (\mu_1/\rho_1)^{1/2}$ is the shear wave velocity referred to the material in the inner layers. For $\rho_1 = \rho_2$, $\nu_1 = \nu_2 = 0.3$ and $\rho_1 = \rho_2$, $\Phi^*(1, p)$ is seen to increase monotonically with c_{21}/pa . Three different ratios of $\mu_2/\mu_1 = 0.2, 1.0$ and 5.0 are considered. Making use of the results in Figure 2, $k_1(t)$ in equation (41) may be computed. Refer to Figure 3 for a display of $k_1(t)/N_0 \sqrt{a}$ versus $c_{21}t/a$. The resultant stress intensity factors are observed to vary as a function of time. Their amplitude rise quickly reaching a peak and then declines. The solution for a homogeneous plate corresponds to $\mu_2/\mu_1 = 1.0$ as the Poisson's ratio and mass density




Figure 2 - Numerical values of $\phi^*(1, p)$ as a function of c_{21}/pa for $a/h = 1.0$




Figure 3 - Normalized resultant stress intensity factor versus $c_{21}t/a$ for $a/h = 1.0$

for the inner and outer layers are assumed to be equal. The peak value of $k_1(t)$ is greater than that of the homogeneous plate solution for $\mu_2 > \mu_1$ while the opposite is found for $\mu_2 < \mu_1$. Hence, the intensity of the crack border stress field can be reduced by having the shear modulus of the outer layers to be smaller than that of the inner layers.

CONCLUDING REMARKS

A dynamic laminate plate theory has been developed for solving crack boundary value problems. The complexity of the problem owing to material nonhomogeneity and dynamic stress analysis necessitates certain simplifying assumptions so that effective analytical solutions can be obtained. It is shown that the dynamic stresses near a mechanical imperfection such as a crack are intensified depending on the stacking sequence of the laminae. In general, this intensity tends to increase quickly for small time reaching a peak and then decreases to the static solution for sufficiently long time. When the modulus of the outer layers are smaller than that of the inner layers, the crack border stress intensity reaches a maximum quicker than the homogeneous solution but with a smaller magnitude. The opposite holds for the case when the outer layers are stiffer than the inner layers. Information of this type is useful for evaluating the resistance of laminate plates to impact loadings.

REFERENCES

- [1] Hartranft, R. J. and Sih, G. C., An approximate three-dimensional theory of plate with application to crack problems, Int. J. Engng. Sci., Vol. 8, pp. 711-729 (1970).
- [2] Sih, G. C., A review of the three-dimensional stress problem for a cracked plate, International Journal of Fracture Mechanics, Vol. 7, pp. 39-61 (1971).
- [3] Badaliance, R., Sih, G. C. and Chen, E. P., Through cracks in multilayered plates, Mechanics of Fracture III, edited by G. C. Sih, Noordhoff International Publishing, Leyden, pp. 85-115 (1977).
- [4] Kane, T. R. and Mindlin, R. D., High-frequency extensional vibrations of plates, Journal of Applied Mechanics, 23, pp. 277-283 (1956).
- [5] Mindlin, R. D. and Medick, M. A., Extensional vibrations of elastic plates, Journal of Applied Mechanics, 26, pp. 561-569 (1959).
- [6] Copson, E. T., On certain dual integral equations, Proceedings Glasgow Mathematical Association, 5, pp. 19-24 (1961).

COMPUTER PROGRAM: DYNAMIC LAMINATE PLATE THEORY WITH A CRACK

```

1      PROGRAM FLAP(INPUT,OUTPUT)
      REAL NON(4),F(4,4,2),G(4,4),D(4),PT(4)
      REAL B(4),C(4)
      REAL LP(19),DTA(19)
5      EQUIVALENCE (NON,R)
      COMMON K1,K2,K3,K4
      COMMON/AUX/H,P,PK1,PK2,BMU,X,Y
      LP(1)=0.0
      DTA(1)=0.0
10     READ 2,K1,K2,K3,K4
      2  FORMAT(I2)
      * K1 = ORDER OF SYSTEM OF EQUATIONS
      * K2 = NO. OF DISTINCT KERNELS
      * K3 = NO. OF DATA POINTS
15     * K4 = NO. OF DATA SETS TO BE EVALUATED
      * SET UP DATA POINTS
      AK=K3
      DO 5 N=1,K3
      AN=N
20     5  PT(N)=AN/AK
      * SET UP INTEGRATION MATRIX
      M=K3-2
      N=K3-1
      A=K3
25     A=1./(3.*A)
      DO 10 K=2,M,2
10     D(K)=2.*A
      DO 15 K=1,N,2
15     D(K)=4.*A
30     D(K3)=A
      * CALCULATE NONHOMOGENEOUS TERMS
      RHS=1.0
      DO 22 I=1,K2
      PRINT 9
35     9  FORMAT(1H1)
      DO 999 II=1,K4
      DO 35 N=1,K3
35     NON(N)=RHS*SQRT(PT(N))
      CALL CONST(I)
40     * CALCULATE KERNEL MATRICES
      DO 20 N=1,K3
      DO 20 M=1,K3
      F(M,N,I)=FU(I,PT(M),PT(N))
20     CONTINUE
45     CALL CHANGE(F,G,D,I)
      CALL LINEQ(G,B,C, K3)
      DO 40 L=1,K3
      PRINT 6,PT(L),NON(L)
50     6  FORMAT(5X,F8.4,F15.6)
      40  CONTINUE
      LP(II+1)=NON(K3)
      DTA(II+1)=P
999    CONTINUE
      CALL LAPINV(DTA,LP)
55     22 CONTINUE
      END

```

```

1      FUNCTION SIMP(I,A,B)
      COMMON/AUX/H,P,PK1,PK2,BMU,X,Y
      MXYZ=2**15
      DEL=0.25*(B-A)
5      IF(DEL)40,45,50
      45 SIMP=0.0
      RETURN
      50 CONTINUE
      SA=Z(I,A)+Z(I,B)
10     SB=Z(I,A+2.*DEL)
      SC=Z(I,A+DEL)+Z(I,A+3.*DEL)
      S1=(DEL/3.)*(SA+2.*SB+4.*SC)
      IF(S1.EQ.0.0) GO TO 45
      K=8
15     35 SB=SB+SC
      DEL=0.5*DEL
      SC=Z(I,A+DEL)
      J=K-1
      DO 5 N=3,J,2
20     AN=N
      5 SC=SC+Z(I,A+AN*DEL)
      S2=(DEL/3.)*(SA+2.*SB+4.*SC)
      DIF=ABS((S2-S1)/S1)
      ER=0.01
25     IF(DIF-ER)30,25,25
      30 SIMP=S2
      RETURN
      25 K=2*K
      S1=S2
30     IF(K-MXYZ)35,35,40
      40 PRINT 42,I,A,B
      42 FORMAT(5X,* INT. DOES NOT CONVERGE *,I3,2F9.4)
      PRINT 60,X,Y
      60 FORMAT(2F10.5)
35     DO 70 J=1,10
      DIP=J
      DIP=DIP/10.
      W=Z(I,DIP)
      PRINT 60,W
40     70 CONTINUE
      CALL EXIT
      END

```

SYMBOLIC REFERENCE MAP (R=1)

ENTRY POINTS
4 SIMP

VARIABLES	SN	TYPE	RELOCATION		
0 A		REAL	F.P.	260	AN REAL
0 B		REAL	F.P.	4	BMU REAL
250 DEL		REAL		262	DIF REAL
264 DIP		REAL		263	ER REAL

```

1          SUBROUTINE CHANGE(F,G,D,I)
          COMMON K1,K2,K3,K4
          REAL F(4,4,2),G(4,4),D(4)
          DO 10 N=1,K3
5           DO 10 M=1,K3
              G(M,N) =F(M,N,I)*D(N)
          10  CONTINUE
              DO 20 N=1,K3
          20  G(N,N)=G(N,N)+1.0
          RETURN
          END
10

```

SYMBOLIC REFERENCE MAP (R=1)

ENTRY POINTS
3 CHANGE

VARIABLES	SN	TYPE	RELOCATION			
0 D		REAL	ARRAY	F.P.	0 F	REAL
0 G		REAL	ARRAY	F.P.	0 I	INTEGER
0 K1		INTEGER		//	1 K2	INTEGER
2 K3		INTEGER		//	3 K4	INTEGER
53 M		INTEGER			52 N	INTEGER

STATEMENT LABELS

0 10

0 20

LOOPS	LABEL	INDEX	FROM-TO	LENGTH	PROPERTIES
17	10	* N	4 7	17B	NOT INNER
30	10	M	5 7	2B	INSTACK
43	20	N	8 9	4B	INSTACK

COMMON BLOCKS LENGTH
/ / 4

STATISTICS

PROGRAM LENGTH	65B	53
SCM BLANK COMMON LENGTH	4B	4
47000B SCM USED		

```

1          SUBROUTINE LINEQ(A,B,T,N)
          REAL A(N,N),B(N),T(N)
          DO 5 I=2,N
5           A(I,1)=A(I,1)/A(1,1)
          DO 10 K=2,N
            M=K-1
            DO 15 I=1,N
15             T(I)=A(I,K)
            DO 20 J=1,M
10              A(J,K)=T(J)
              J1=J+1
              DO 20 I=J1,N
                T(I)=T(I)-A(I,J)*A(J,K)
20             CONTINUE
            A(K,K)=T(K)
            IF(K.EQ.N) GO TO 10
            M=K+1
            DO 25 I=M,N
25             A(I,K)=T(I)/A(K,K)
10          CONTINUE
          * BACK SUBSTITUTE
            DO 31 I=1,N
              T(I)=B(I)
              M=I+1
25             IF(M.GT.N) GO TO 31
              DO 30 J=M,N
                B(J)=B(J)-A(J,I)*T(I)
30             CONTINUE
31          CONTINUE
            DO 35 I=1,N
30              K=N+1-I
              B(K)=T(K)/A(K,K)
              K1=K-1
              IF(K1.EQ.0) GO TO 35
35              DO 36 J1=1,K1
                J=K-J1
                T(J)=T(J)-A(J,K)*B(K)
36             CONTINUE
35          CONTINUE
            RETURN
40         END

```

SYMBOLIC REFERENCE MAP (R=1)

ENTRY POINTS
3 LINEQ

VARIABLES	SN	TYPE	RELOCATION			
0 A		REAL	ARRAY	F.P.	0 B	REAL
172 I		INTEGER			175 J	INTEGER
176 J1		INTEGER			173 K	INTEGER
177 K1		INTEGER			174 M	INTEGER
0 N		INTEGER		F.P.	0 T	REAL

```

1      FUNCTION FU(I,A,B)
      COMMON/AUX/H,P,PK1,PK2,BMU,X,Y
      X=A
      Y=B
5      IF(A*B)5,10,5
      10  FU=0.0
      RETURN
      5   SUM=SIMP(I,0.0,5.0)
      ER=0.01
10     DEL =5.0
      20  UP=DEL+5.0
      ADDL=SIMP(I,DEL,UP)
      DEL =UP
      TEST=ABS(ADDL/SUM)
      SUM=SUM+ADDL
15     IF(TEST-ER)15,20,20
      15  FU=SQRT(X*Y)*SUM
      RETURN
      END

```

SYMBOLIC REFERENCE MAP (R=1)

ENTRY POINTS

4 FU

VARIABLES	SN	TYPE	RELOCATION			
0 A		REAL	F.P.	62	ADDL	REAL
0 B		REAL	F.P.	4	BMU	REAL
60 DEL		REAL		57	ER	REAL
55 FU		REAL		0	H	REAL
0 I		INTEGER	F.P.	1	P	REAL
2 PK1		REAL	AUX	3	PK2	REAL
56 SUM		REAL		63	TEST	REAL
61 UP		REAL		5	X	REAL
6 Y		REAL	AUX			

EXTERNALS	TYPE	ARGS			
SIMP	REAL	3		SQRT	REAL

INLINE FUNCTIONS	TYPE	ARGS	
ABS	REAL	1	INTRIN

STATEMENT LABELS

14 5	0	10	INACTIVE
22 20			

COMMON BLOCKS	LENGTH
AUX	7

STATISTICS

PROGRAM LENGTH	648	52
SCM LABELED COMMON LENGTH	78	7
47000B SCM USED		

```

1      FUNCTION BESJO(A)
      IF (A-3.)5,5,10
5      B=A*A/9.
      W=1.-2.2499997*B
15     Z=B*B
      W=W+1.2656208*Z
      Z=Z*B
      W=W-.3163866*Z
      Z=Z*B
10     W=W+.0444479*Z
      Z=Z*B
      W=W-.0039444*Z
      Z=Z*B
      BESJO=W+.00021*Z
15     RETURN
      10  B=3./A
      W=.79788456-.00000077*B
      V=A-.78539816-.04166397*B
      Z=B*B
20     W=W-.0055274*Z
      V=V-.00003954*Z
      Z=Z*B
      W=W-.00009512*Z
      V=V+.00262573*Z
25     Z=Z*B
      W=W+.00137237*Z
      V=V-.00054125*Z
      Z=Z*B
      W=W-.00072805*Z
30     V=V-.00029333*Z
      Z=Z*B
      W=W+.00014476*Z
      V=V+.00013558*Z
      BESJO=W/SQRT(A)*COS(V)
35     RETURN
      END

```

SYMBOLIC REFERENCE MAP (R=1)

ENTRY POINTS
4 BESJO

VARIABLES	SN	TYPE	RELOCATION		
0 A		REAL	F.P.	114 B	REAL
113 BESJO		REAL		117 V	REAL
115 W		REAL		116 Z	REAL

EXTERNALS	TYPE	ARGS		
COS	REAL	1 LIBRARY	SQRT	REAL

STATEMENT LABELS			
0 5	INACTIVE	26	10

```

1      SUBROUTINE CONST(I)
      COMMON/AUX/H,P,PK1,PK2,BMU,X,Y
      PK1=0.3
      PK2=0.3
5      BMU=50.0
      H=1.0
      READ 2,P
      2 FORMAT(F10.5)
      HH=1./H
10     PRINT 1,BMU,PK1,PK2,HH,P
      1 FORMAT(/////5X,* MU2/MU1 =*F6.2,* NU1 =*F4.2,* NU2 =
      1A/H =*F4.2,* C21/PA =*F4.2//)
      RETURN
      END

```

SYMBOLIC REFERENCE MAP (R=1)

ENTRY POINTS

3 CONST

VARIABLES	SN	TYPE	RELOCATION			
4 BMU		REAL	AUX	0	H	REAL
55 HH		REAL		0	I	INTEGER
1 P		REAL	AUX	2	PK1	REAL
3 PK2		REAL	AUX	5	X	REAL
6 Y		REAL	AUX			

FILE NAMES	MODE			
INPUT	FMT	OUTPUT	FMT	

STATEMENT LABELS

37 1	FMT	25	2	FMT
------	-----	----	---	-----

COMMON BLOCKS LENGTH

AUX	7
-----	---

STATISTICS

PROGRAM LENGTH	568	46
SCM LABELED COMMON LENGTH	78	7
47000B SCM USED		

```

1      FUNCTION Z(I,S)
COMMON/AUX/H,P,PK1,PK2,BMU,X,Y
COMPLEX DA,DL1,DL2,SA,SB,SC,SD
COMPLEX GA,GB,CA,CR,CC,F,G
5      PI=3.1415926
      PP=P*P
      PG=2./PP/(1.+BMU)
      AA=2.*(1.-PK1)/(1.-2.*PK1)
      AB=2.*(1.-PK2)/(1.-2.*PK2)
10     PA=2./PP/(AA+BMU*AR)
      PO=2.*H*H/PI/PI/(AA+BMU*AB)/PP
      RA=(1.+BMU)/(AA+BMU*AB)
      BB=1.-BA
      BC=(1.+7.*BMU)/4./(1.+BMU)
15     BD=PI*PI/2./H/H
      ALP=1./4./BA/BB
      DLP=BC/4./BB
      DD=((ALP+DLP)*PO+1.)*2-4.*ALP*DLP*PO*(PO+1.)
      G=CMPLX(DD,0.0)
20     DA=CSQRT(G)
      DL1=BD/DLP*((ALP+DLP)*PO+1.+DA)
      DL2=BD/DLP*((ALP+DLP)*PO+1.-DA)
      SC=S*S+DL1
      SD=S*S+DL2
25     GA=CSQRT(SC)
      GB=CSQRT(SD)
      GC=SQRT(S*S+PG)
      SA=(PA-DL2)/(DL1-DL2)
      SB=(PA-DL1)/(PA-DL2)
30     CA=SA/PG/BB
      CB=2.*(S*S+PG/2.)*2/GA*(1.-GA/GB*SB)
      CC=2.*S*S*GC/SA
      F=CA*(CB-CC)
      Q=REAL(F)
35     QA=AIMAG(F)
      IF(QA-0.0)5,10,5
10     Z=(Q-S)*BESJO(S*X)*BESJO(S*Y)
      RETURN
5      PRINT 9,P,S,F
40     9 FORMAT(4F10.5)
      CALL EXIT
      END

```

SYMBOLIC REFERENCE MAP (R=1)

ENTRY POINTS

4 Z

VARIABLES	SN	TYPE	RELOCATION		
276 AA		REAL		277 AB	REAL
306 ALP		REAL		302 BA	REAL
303 BB		REAL		304 BC	REAL
305 BD		REAL		4 BMU	REAL

```

1      SUBROUTINE LAPINV(GLAM,PHI)
C      THIS PROGRAM EVALUATES THE COEFFICIENTS FOR SERIES
C      OF JACOBI POLYNOMIALS WHICH REPRESENTS A LAPLACE
C      INVERSION INTEGRAL
5      REAL MUL
      DIMENSION A(50),GLAM(50),PHI(50),C(4,50)
      DIMENSION BK(101),TT(101)
      COMMON/2/TI,TF,DT,MN,BK,TT
      READ 1,NN,MN,MM
10     1 FORMAT(3I2)
      READ 2,TI,TF,DT
      2 FORMAT(3F10.5)
      PRINT 99
      99 FORMAT(1H1)
15     CALL SPLICE(GLAM,PHI,MM,C)
      PRINT 101
      101 FORMAT(/////5X,*   GLAM           PHI   *)
      PRINT 102,(GLAM(I),PHI(I),I=1,MM)
      102 FORMAT(5X,F10.5,5X,F10.5)
20     M11=MM-1
      PRINT 99
      DO 10 I=1,NN
      READ 3,BET,DEL
      3 FORMAT(2F10.5)
      PRINT 98,BET,DEL
25     98 FORMAT(/////5X,*BETA =*F5.3,* DELTA =*F5.3)
      DO 11 L=1,MN
      AL=L
      S=1./(AL+BET)/DEL
      CALL SPLINE(GLAM,PHI,MM,C,S,G)
      F=G*S
      IF(AL-2.)81,82,83
30     81 A(1)=(1.+BET)*DEL*F
      GO TO 11
      82 A(2)=((2.+BET)*DEL*F-A(1))*(3.+BET)
      GO TO 11
      83 CONTINUE
      TOP=1.
      L1=L-1
      AL1=L1
40     DO 12 J=1,L1
      AJ=J
      TOP=AJ*TOP
      12 CONTINUE
      L2=2*L-1
      BOT=1.
      DO 13 J=L,L2
      AJ=J
      BOT=(AJ+BET)*BOT
45     13 CONTINUE
      MUL=BOT/TOP
      SUM=0.0
      DO 14 N=1,L1
      AN=N
50     IF(AN-2.)85,86,87
      85 TOD=1.
      GO TO 88

```

```

      86 TOD=AL1
      GO TO 88
60      87 CONTINUE
      TOD=1.
      ICH=L1-(N-2)
      DO 15 J=ICH,L1
      AJ=J
      65      TOD=AJ*TOD
      15 CONTINUE
      88 CONTINUE
      BOD=1.
      JA=L1+N
      70      DO 16 J=L,JA
      AJ=J
      BOD=BOD*(AJ+BET)
      16 CONTINUE
      CO=TOD/BOD
      75      SUM=SUM+CO*A(N)
      14 CONTINUE
      A(L)=MUL*(DEL*F-SUM)
      11 CONTINUE
      CALL JACSER(DEL,A,PET)
      80      10 CONTINUE
      999 CONTINUE
      RETURN
      END

```

SYMBOLIC REFERENCE MAP (R=1)

ENTRY POINTS
3 LAPINV

VARIABLES	SN	TYPE	RELOCATION			
377 A		REAL	ARRAY		364 AJ	REAL
354 AL		REAL			362 AL1	REAL
371 AN		REAL			351 BET	REAL
4 BK		REAL	ARRAY	2	374 BOD	REAL
366 BOT		REAL			461 C	REAL
376 CO		REAL			352 DEL	REAL
2 DT		REAL		2	357 F	REAL
356 G		REAL			0 GLAM	REAL
347 I		INTEGER			373 ICH	INTEGER
363 J		INTEGER			375 JA	INTEGER
353 L		INTEGER			361 L1	INTEGER
365 L2		INTEGER			346 MM	INTEGER
3 MN		INTEGER		2	344 MUL	REAL
350 M11		INTEGER			370 N	INTEGER
345 NN		INTEGER			0 PHI	REAL
355 S		REAL			367 SUM	REAL
1 TF		REAL		2	0 TI	REAL
372 TOD		REAL			360 TOP	REAL
151 TT		REAL	ARRAY	2		

```

1          SUBROUTINE JACSER(D,C,R)
            DIMENSION C(50),SF(50),P(50)
            DIMENSION BK(101),TT(101)
            COMMON/2/TI,TF,DT,MN,BK,TT
5          TT(1)=0.0
            BK(1)=0.0
            LM=1
            T=TI
12         T=T+DT
10         X=2.*EXP(-D*T)-1.
            CALL JACOBI(MN,X,R,P)
            SF(1)=C(1)*P(1)
            DO 10 L=2,MN
            L1=L-1
15         AL=L
            SF(L)=SF(L1)+C(L)*D(L)
10        CONTINUE
            LM=LM+1
            BK(LM)=SF(5)
20         TT(LM)=T
            IF(T.LE.TF) GO TO 12
            PRINT 97
97        FORMAT(/////5X,* T K T K
1          T K *)
25         DO 31 MY=1.25
            MA=MY+1
            MB=MA+25
            MC=MB+25
            MD=MC+25
30         PRINT 96,TT(MA),BK(MA),TT(MB),BK(MB),TT(MC),BK(MC),T
96        FORMAT(5X,F5.2,3X,F7.5,3X,F5.2,3X,F7.5,3X,F5.2,3X,F7
1F7.5)
31        CONTINUE
            RETURN
35         END

```

SYMBOLIC REFERENCE MAP (R=1)

ENTRY POINTS
3 JACSER

VARIABLES	SN	TYPE	RELOCATION			
151 AL		REAL		0	B	REAL
4 BK		REAL	ARRAY	2	0	C
0 D		REAL			2	DT
147 L		INTEGER			144	LM
150 L1		INTEGER			153	MA
154 MB		INTEGER			155	MC
156 MD		INTEGER			3	MN
152 MY		INTEGER			241	P
157 SF		REAL	ARRAY		145	T
1 TF		REAL		2	0	TI
151 TT		REAL	ARRAY	2	146	X
						REAL

```

1      SUBROUTINE JACOBI(N,X,B,PB)
C      THIS PROGRAM CALCULATES JACOBI POLYNOMIALS OF ORDER
C      K-1 WITH ARG X AND PARAMETER B GT -1
      DIMENSION PB(N)
5      AN=N
      IF (AN-2.)1,2,3
1      PB(1)=1.
      RETURN
10     2 PB(1)=1.
      PB(2)=X-B*(1.-X)/2.
      RETURN
      3 BSQ=B*B
      BONE=B+1.
      PB(1)=1.
15     PB(2)=X-B*(1.-X)/2.
      DO 4 K=3,N
      AK=K
      AK1=AK-1.
      AK2=AK-2.
20     K1=K-1
      K2=K-2
      C01=((2.*AK1)+B)*X
      C01=((2.*AK2)+B)*C01
      C01=((2.*AK2)+BONE)*(C01-BSQ)
25     C02=2.*AK2*(AK2+B)*((2.*AK1)+B)
      C0=2.*AK1*(AK1+B)*((2.*AK2)+B)
      4 PB(K)=(C01*PB(K1)-C02*PB(K2))/C0
      RETURN
      END

```

SYMBOLIC REFERENCE MAP (R=1)

ENTRY POINTS
3 JACORI

VARIABLES	SN	TYPE	RELOCATION			
106 AK		REAL		107 AK1		REAL
110 AK2		REAL		102 AN		REAL
0 B		REAL	F.P.	104 BONE		REAL
103 BSQ		REAL		115 C0		REAL
113 C01		REAL		114 C02		REAL
105 K		INTEGER		111 K1		INTEGER
112 K2		INTEGER		0 N		INTEGER
0 PB		REAL	ARRAY F.P.	0 X		REAL

STATEMENT LABELS

0 1	INACTIVE	24 2
0 4		

LOOPS	LABEL	INDEX	FROM-TO	LENGTH	PROPERTIES
47	4	K	16 27	25B	OPT

```

1      SUBROUTINE SPLINE(X,Y,M,C,XINT,YINT)
      DIMENSION X(50),Y(50),C(4,50)
      IF(XINT-X(1))1,10,11
5      10 YINT=Y(1)
      RETURN
      11 CONTINUE
      IF(X(M)-XINT)1,12,13
      12 YINT=Y(M)
      RETURN
10     13 CONTINUE
      K=M/2
      N=M
      2 CONTINUE
      IF(X(K)-XINT)3,14,5
15     14 YINT=Y(K)
      RETURN
      3 CONTINUE
      IF(XINT-X(K+1))4,15,7
      15 YINT=Y(K+1)
20     RETURN
      4 CONTINUE
      YINT=(X(K+1)-XINT)*(C(1,K)*(X(K+1)-XINT)**2+C(3,K))
      YINT=YINT+(XINT-X(K))*(C(2,K)*(XINT-X(K))**2+C(4,K))
      RETURN
25     5 CONTINUE
      IF(X(K-1)-XINT)6,16,17
      6 K=K-1
      GO TO 4
      16 YINT=Y(K-1)
30     RETURN
      17 N=K
      K=K/2
      GO TO 2
      7 LL=K
35     K=(N+K)/2
      8 CONTINUE
      IF(X(K)-XINT)3,14,18
      18 CONTINUE
      IF(X(K-1)-XINT)6,16,19
40     19 N=K
      K=(LL+K)/2
      GO TO 8
      1 PRINT 101
45     101 FORMAT(* OUT OF RANGE FOR INTERPOLATION *)
      STOP
      END

```

SYMBOLIC REFERENCE MAP (R=1)

ENTRY POINTS
3 SPLINE

```

1      SUBROUTINE SPLICE(X,Y,M,C)
      DIMENSION X(50),Y(50),D(50),P(50),E(50),C(4,50)
      DIMENSION A(50,3),B(50),Z(50)
      MM=M-1
5      DO 2 K=1,MM
      D(K)=X(K+1)-X(K)
      P(K)=D(K)/6.
      2 E(K)=(Y(K+1)-Y(K))/D(K)
      DO 3 K=2,MM
10     3 B(K)=E(K)-E(K-1)
      A(1,2)=-1.-D(1)/D(2)
      A(1,3)=D(1)/D(2)
      A(2,3)=P(2)-P(1)*A(1,3)
      A(2,2)=2.*(P(1)+P(2))-P(1)*A(1,2)
15     A(2,3)=A(2,3)/A(2,2)
      B(2)=B(2)/A(2,2)
      DO 4 K=3,MM
      A(K,2)=2.*(P(K-1)+P(K))-P(K-1)*A(K-1,3)
      B(K)=B(K)-P(K-1)*B(K-1)
20     A(K,3)=P(K)/A(K,2)
      4 B(K)=B(K)/A(K,2)
      Q=D(M-2)/D(M-1)
      A(M,1)=1.+Q*A(M-2,3)
      A(M,2)=-Q-A(M,1)*A(M-1,3)
25     B(M)=B(M-2)-A(M,1)*B(M-1)
      Z(M)=B(M)/A(M,2)
      MN=M-2
      DO 6 I=1,MN
      K=M-I
30     6 Z(K)=B(K)-A(K,3)*Z(K+1)
      Z(1)=-A(1,2)*Z(2)-A(1,3)*Z(3)
      DO 7 K=1,MM
      Q=1./(6.*D(K))
      C(1,K)=Z(K)*Q
35     C(2,K)=Z(K+1)*Q
      C(3,K)=Y(K)/D(K)-Z(K)*P(K)
      7 C(4,K)=Y(K+1)/D(K)-Z(K+1)*P(K)
      RETURN
      END

```

SYMBOLIC REFERENCE MAP (R=1)

ENTRY POINTS
3 SPLICE

VARIABLES	SN	TYPE	RELOCATION			
373 A		REAL	ARRAY	621	R	REAL
0 C		REAL	ARRAY	145	D	REAL
311 E		REAL	ARRAY	144	I	INTEGER
141 K		INTEGER		0	M	INTEGER
140 MM		INTEGER		143	MN	INTEGER
227 P		REAL	ARRAY	142	Q	REAL
0 X		REAL	ARRAY	0	Y	REAL

INTERIM REPORT DISTRIBUTION LIST

NSG 3179

SUDDEN STRETCHING OF A FOUR-LAYERED
COMPOSITE PLATE

Advanced Research Projects Agency
Washington DC 20525
Attn: Library

Advanced Technology Center, Inc.
LTV Aerospace Corporation
P.O. Box 6144
Dallas, TX 75222
Attn: D. H. Petersen
W. J. Renton

Air Force Flight Dynamics Laboratory
Wright-Patterson Air Force Base, OH 45433
Attn: E. E. Bailly
G. P. Sendeckyj (FBC)
R. S. Sandhu

Air Force Materials Laboratory
Wright-Patterson Air Force Base, OH 45433
Attn: H. S. Schwartz (LN)
T. J. Reinhart (MBC)
G. P. Peterson (LC)
E. J. Morrissey (LAE)
S. W. Tsai (MBM)
N. J. Pagano
J. M. Whitney (MBM)

Air Force Office of Scientific Research
Washington DC 20333
Attn: J. F. Masi (SREP)

Air Force Office of Scientific Research
1400 Wilson Blvd.
Arlington, VA 22209

AFOSR/NA
Bolling AFB, DC 20332
Attn: J. Morgan

Air Force Rocket Propulsion Laboratory
Edwards, CA 93523
Attn: Library

Babcock & Wilcox Company
Advanced Composites Department
P.O. Box 419
Alliance, Ohio 44601
Attn: P. M. Leopold

Bell Helicopter Company
P.O. Box 482
Ft. Worth, TX 76101
Attn: H. Zinberg

The Boeing Company
P. O. Box 3999
Seattle, WA 98124
Attn: J. T. Hoggatt, MS. 88-33
T. R. Porter

The Boeing Company
Vertol Division
Morton, PA 19070
Attn: E. C. Durchlaub

Battelle Memorial Institute
Columbus Laboratories
505 King Avenue
Columbus, OH 43201
Attn: L. E. Hulbert

Brunswick Corporation
Defense Products Division
P. O. Box 4594
43000 Industrial Avenue
Lincoln, NE 68504
Attn: R. Morse

Celanese Research Company
86 Morris Ave.
Summit, NJ 07901
Attn: H. S. Kliger

Chemical Propulsion Information Agency
Applied Physics Laboratory
8621 Georgia Avenue
Silver Spring, MD 20910
Attn: Library

Commander
Natick Laboratories
U. S. Army
Natick, MA 01762
Attn: Library

Commander
Naval Air Systems Command
U. S. Navy Department
Washington DC 20360
Attn: M. Stander, AIR-43032D

Commander
Naval Ordnance Systems Command
U.S. Navy Department
Washington DC 20360
Attn: B. Drimmer, ORD-033
M. Kinna, ORD-033A

Cornell University
Dept. Theoretical & Applied Mech.
Thurston Hall
Ithaca, NY 14853
Attn: S. L. Phoenix

Defense Metals Information Center
Battelle Memorial Institute
Columbus Laboratories
505 King Avenue
Columbus, OH 43201

Department of the Army
U.S. Army Aviation Materials Laboratory
Ft. Eustis, VA 23604
Attn: I. E. Figge, Sr.
Library

Department of the Army
U.S. Army Aviation Systems Command
P.O. Box 209
St. Louis, MO 63166
Attn: R. Vollmer, AMSAV-A-UE

Department of the Army
Plastics Technical Evaluation Center
Picatinny Arsenal
Dover, NJ 07801
Attn: H. E. Pebly, Jr.

Department of the Army
Watervliet Arsenal
Watervliet, NY 12189
Attn: G. D'Andrea

Department of the Army
Watertown Arsenal
Watertown, MA 02172
Attn: A. Thomas

Department of the Army
Redstone Arsenal
Huntsville, AL 35809
Attn: R. J. Thompson, AMSMI-RSS

Department of the Navy
Naval Ordnance Laboratory
White Oak
Silver Spring, MD 20910
Attn: R. Simon

Department of the Navy
U.S. Naval Ship R&D Laboratory
Annapolis, MD 21402
Attn: C. Hersner, Code 2724

Director
Deep Submergence Systems Project
6900 Wisconsin Avenue
Washington DC 20015
Attn: H. Bernstein, DSSP-221

Director
Naval Research Laboratory
Washington DC 20390
Attn: Code 8430
I. Wolock, Code 8433

Drexel University
32nd and Chestnut Streets
Philadelphia, PA 19104
Attn: P. C. Chou

E. I. DuPont DeNemours & Co.
DuPont Experimental Station
Wilmington, DE 19898
Attn: D. L. G. Sturgeon

Fiber Science, Inc.
245 East 157 Street
Gardena, CA 90248
Attn: E. Dunahoo

General Dynamics
P.O. Box 748
Ft. Worth, TX 76100
Attn: D. J. Wilkins
Library

General Dynamics/Convair
P.O. Box 1128
San Diego, CA 92112
Attn: J. L. Christian

General Electric Co.
Evendale, OH 45215
Attn: C. Stotler
R. Ravenhall
R. Stabrylla

General Motors Corporation
Detroit Diesel-Allison Division
Indianapolis, IN 46244
Attn: M. Herman

Georgia Institute of Technology
School of Aerospace Engineering
Atlanta, GA 30332
Attn: L. W. Rehfield

Grumman Aerospace Corporation
Bethpage, Long Island, NY 11714
Attn: S. Dastin
J. B. Whiteside

Hamilton Standard Division
United Aircraft Corporation
Windsor Locks, CT 06096
Attn: W. A. Percival

Hercules, Inc.
Allegheny Ballistics Laboratory
P. O. Box 210
Cumberland, MD 21053
Attn: A. A. Vicario

Hughes Aircraft Company
Culver City, CA 90230
Attn: A. Knoell

Illinois Institute of Technology
10 West 32 Street
Chicago, IL 60616
Attn: L. J. Broutman

IIT Research Institute
10 West 35 Street
Chicago, IL 60616
Attn: I. M. Daniel

Jet Propulsion Laboratory
4800 Oak Grove Drive
Pasadena, CA 91103
Attn: Library

Lawrence Livermore Laboratory
P.O. Box 808, L-421
Livermore, CA 94550
Attn: T. T. Chiao
E. M. Wu

Lehigh University
Institute of Fracture &
Solid Mechanics
Bethlehem, PA 18015
Attn: G. C. Sih

Lockheed-Georgia Co.
Advanced Composites Information Center
Dept. 72-14, Zone 402
Marietta, GA 30060
Attn: T. M. Hsu

Lockheed Missiles and Space Co.
P.O. Box 504
Sunnyvale, CA 94087
Attn: R. W. Fenn

Lockheed-California
Burbank, CA 91503
Attn: J. T. Ryder
K. N. Lauraitis
J. C. Ekvall

McDonnell Douglas Aircraft Corporation
P.O. Box 516
Lambert Field, MS 63166
Attn: J. C. Watson

McDonnell Douglas Aircraft Corporation
3855 Lakewood Blvd.
Long Beach, CA 90810
Attn: L. B. Greszczuk

Material Sciences Corporation
1777 Walton Road
Blue Bell, PA 19422
Attn: B. W. Rosen

Massachusetts Institute of Technology
Cambridge, MA 02139
Attn: F. J. McGarry
J. F. Mandell
J. W. Mar

NASA-Ames Research Center
Moffett Field, CA 94035
Attn: Dr. J. Parker
Library

NASA-Flight Research Center
P.O. Box 273
Edwards, CA 93523
Attn: Library

NASA-George C. Marshall Space Flight Center
Huntsville, AL 35812
Attn: C. E. Cataldo, S&E-ASTN-MX
Library

NASA-Goddard Space Flight Center
Greenbelt, MD 20771
Attn: Library

NASA-Langley Research Center
Hampton, VA 23365
Attn: J. H. Starnes
R. A. Pride, MS 188a
M. C. Card
J. R. Davidson

NASA-Lewis Research Center
21000 Brookpark Road
Cleveland, Ohio 44135
Attn: Administration & Technical Service Section
Tech. Report Control, MS. 5-5
Tech. Utilization, MS 3-19
AFSC Liaison, MS. 501-3
Rel. and Quality Assur., MS 500-211
L. Berke, MS 49-3
C. P. Blankenship, MS 105-1
R. F. Lark, MS 49-3
J. C. Freche, MS 49-1
R. H. Johns, MS 49-3
C. C. Chamis, MS 49-3 (10 copies)
T. T. Serafini, MS 49-1
Library, MS 60-3 (2 copies)

NASA-Lyndon B. Johnson Space Center
Houston, TX 77001
Attn: S. Glorioso, SMD-ES52
Library

NASA Scientific and Tech. Information Facility
P.O. Box 8757
Balt/Wash International Airport, MD 21240
Attn: Acquisitions Branch (10 copies)

National Aeronautics & Space Administration
Office of Advanced Research & Technology
Washington DC 20546
Attn: L. Harris, Code RWS
M. Greenfield, Code RWS

National Aeronautics & Space Administration
Office of Technology Utilization
Washington DC 20546

National Bureau of Standards
Eng. Mech. Section
Washington DC 20234
Attn: R. Mitchell

National Technology Information Service
Springfield, VA 22161 (6 copies)

National Science Foundation
Engineering Division
1800 G. Street, NW
Washington DC 20540
Attn: Library

Northrop Corporation Aircraft Group
3901 West Broadway
Hawthorne, CA 90250
Attn: R. M. Verette
G. C. Grimes

Pratt & Whitney Aircraft
East Hartford, CT 06108
Attn: J. M. Woodward

Rockwell International
Los Angeles Division
International Airport
Los Angeles, CA 90009
Attn: L. M. Lackman
D. Y. Konishi

Sikorsky Aircraft Division
United Aircraft Corporation
Stratford, CT 06602
Attn: Library

Southern Methodist University
Dallas, TX 75275
Attn: R. M. Jones

Southwest Research Institute
8500 Culebra Road
San Antonio, TX 78284
Attn: P. H. Francis

Space & Missile Systems Organization
Air Force Unit Post Office
Los Angeles, CA 90045
Attn: Technical Data Center

Structural Composites Industries, Inc.
6344 N. Irwindale Avenue
Azusa, CA 91702
Attn: R. Gordon

Texas A&M
Mechanics & Materials Research Center
College Station, TX 77843
Attn: R. A. Schapery

TRW, Inc.
23555 Euclid Avenue
Cleveland, OH 44117
Attn: I. J. Toth

Union Carbide Corporation
P. O. Box 6116
Cleveland, OH 44101
Attn: J. C. Bowman

United Technologies Research Center
East Hartford, CT 06108
Attn: R. C. Novak
Dr. A. Dennis

University of Dayton Research Institute
Dayton, OH 45409
Attn: R. W. Kim

University of Delaware
Mechanical & Aerospace Engineering
Newark, DE 19711
Attn: B. R. Pipes

University of Illinois
Department of Theoretical & Applied Mechanics
Urbana, IL 61801
Attn: S. S. Wang

University of Oklahoma
School of Aerospace Mechanical & Nuclear Engineering
Norman, OK 73069
Attn: C. W. Bert

University of Wyoming
College of Engineering
University Station Box 3295
Laramie, WY 82071
Attn: D. F. Adams

U. S. Army Materials & Mechanics Research Center
Watertown Arsenal
Watertown, MA 02172
Attn: E. M. Leno
D. W. Oplinger

V.P. I. and S. U.
Dept. of Eng. Mech.
Blacksburg, VA 24061
Attn: R. H. Heller
H. J. Brinson
C. T. Herakovich