

REPORT DOCUMENTATION PAGE

Form Approved
OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Service, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE October 31, 1995	3. REPORT TYPE AND DATES COVERED Final, June 1993 - October 1995
4. TITLE AND SUBTITLE Search for Higher Temperature Superconductors by Novel Approaches		5. FUNDING NUMBERS 1601/07 63218C	
6. AUTHOR(S) C. W. Chu		AFOSR-TR-96 ON	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Texas Center for Superconductivity University of Houston Houston, Texas 77204-5932		6148	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) Dr. H. Weinstock AFOSR/NE 110 Duncan Avenue, Suite B-115 Bolling Air Force Base DC 20332-0001		10. SPONSORING/MONITORING AGENCY REPORT NUMBER F49620-93-1-0310	
11. SUPPLEMENTARY NOTES		19960404 056	
12a. DISTRIBUTION/AVAILABILITY STATEMENT APPROVED FOR PUBLIC RELEASE: DISTRIBUTION UNLIMITED		12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) Under the partial support of USAFOSR Grant No. F 49620-93-1-0310 by BMDO from June 1993 through October '95 the Principle Investigator, C. W. Chu, showed that superconductivity occurs at record high temperatures in mercury-based compounds up to 134 K and 164 K at ambient and high pressures, respectively, making it possible to operate superconducting devices in a space environment without the help of liquid coolant and on earth simply with the aid of household air-conditioner technology, and in a compound of Ba-Ca-Cu-O without toxic elements up to 124 K at ambient pressure. A demonstration experiment is under way in collaboration with the National Aeronautics and Space Administration (NASA). He was the first to make thin films of this class of compounds, demonstrating the possible attainment of superconducting electronics with superior performance. He demonstrated the feasibility of constructing an ultra-fast high-powered high-temperature superconducting switch with profound implications for the defense and civilian technologies. Many of the new and improved compounds resulting from the present study also enabled him to examine some crucial issues of high temperature superconductivity and to show that recent claims of superconductivity near room temperature are premature.			
14. SUBJECT TERMS		15. NUMBER OF PAGES	
		16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT

DTIC QUALITY INSPECTED 1

Standard Form 298 (Rev. 2-89)

FINAL REPORT

(June 1993 through October 1995)

to

**Dr. Harold Weinstock
AFOSR/NE, 110 Duncan Avenue, Suite 115
Bolling AFB DC 20332-0001**

Title: Search for Higher Temperature Superconductors by Novel Approaches

Funding Number: AFOSR C/F 49620-93-0310 by BMDO

by

**C. W. Chu
Texas Center for Superconductivity
University of Houston
Houston TX 77204-5932**

October 31, 1995

TABLE OF CONTENTS

	SUMMARY	3
I.	RESEARCH OBJECTIVES	4
II.	ACCOMPLISHMENTS	4
III.	PUBLICATION LIST	5

SUMMARY

Under the partial support of USAFOSR Grant No. F 49620-93-1-0310 by BMDO from June 1993 through October 1995, the Principle Investigator, C. W. Chu, showed that superconductivity occurs at record high temperatures in mercury-based compounds up to 134 K and 164 K at ambient and high pressures, respectively, making it possible to operate superconducting devices in a Space-environment without the help of liquid coolant and on earth simply with the aid of household air-conditioner technology, and in a Ba-Ca-Cu-O compound without any toxic element up to 124 K at ambient pressure. A demonstration experiment is under way in collaboration with the National Aeronautics and Space Administration (NASA). He was the first to make thin films of this class of compounds, demonstrating the possible attainment of superconducting electronics with superior performance. He demonstrated the feasibility of constructing an ultra-fast high-power high-temperature superconducting switch with profound implications for the defense and civilian technologies. Many of the new and improved compounds results from the present study also enabled him to examine some crucial issues of high temperature superconductivity and to show claims of superconductivity near room temperature to be premature.

I. RESEARCH OBJECTIVES

- To carry out a concerted search for superconductors with a transition temperature (T_c) above the record of 125 K in $Tl_2Ba_2Ca_2Cu_3O_{10}$, set in 1988, by adopting an empirical approach and, at the same time, taking advantage of the unusual expertise and capability in material synthesis and characterization of our group and of the Texas Center for Superconductivity at the University of Houston.
- To improve some existing high temperature superconductors (HTS's) for possible applications
- To perform feasibility studies on high temperature superconducting devices

II. ACCOMPLISHMENTS

- $HgBa_2Ca_{n-1}Cu_nO_{2n+n+\delta}$ [Hg-12(n-1)n or HBCCO] System
 - achieved record high T_c in HBCCO up to 134 K and 164 K at ambient and high (30 GPa) pressures, respectively, making it possible to operate HTS devices with passive cooling in Space or with air-conditioner technology on earth
 - synthesized the first Hg-1201 and -1212 films, demonstrating that HTS electronic devices can be made of the HBCCO compounds with superior properties, *e.g.* a $J_c = 10^6$ A/cm² has been achieved at 100 K; and a Hg-1212 SQUID was later successfully operated at 114 K by IBM
 - developed the solid-vapor processing technique to prepare pure samples of HBCCO at ambient pressure
 - determined structure of Hg-1212 by n-diffraction
 - determined magnetic properties of HBCCO and found a moderate flux pinning force in HBCCO, suggesting a significant application potential for these compounds
 - synthesized purest samples, to date, of Hg-12(n-1)n with $n = 1, 2, 3, 4, 5, 6$ under pressure, making it possible to address several critical issues concerning the occurrence of HTS
 - showed the needs for modifications of HTS-models proposed, by observing deviations from predictions of these models, *e.g.* the pressure and doping effects on the T_c 's of HBCCO, the strong covalence bonding between Hg and O(4), and the unusual linearly coordinated Hg-ions
- Ba-Ca-Cu-O [BCCO] System
 - synthesized a superconducting layered BCCO compound with a T_c up to 124 K at ambient, the highest in any HTSs without toxic element
- RM_2B_2C with $R = Y, Sc$ or a rare-earth element; $M =$ transition metal elements
 - identified YPd_2B_2C as the phase responsible for the 23 K-superconductivity reported by AT&T Bell Labs
 - discovered $Y_2Ni_2B_2C_2$ to be superconducting at 3 K in contrast to expectation
 - determined the superconducting and magnetic properties of YPd_2B_2C , YNi_2B_2C , and $Y_2Ni_2B_2C_2$ at ambient and high pressures, demonstrating the small anisotropy in these compounds, and a large difference between the band-structures of the latter two compounds
 - synthesized RCo_2B_2C and RRh_2B_2C , neither is superconducting probably due to the strong magnetic effect of Co in the former and the large magnetic polarization effect of Rh in the latter
- Unidentified Superconducting Objects (USO's)
 - reproduced the resistive anomalies previously reported by J. T. Chen *et al.* in single-grain YBCO samples whose magnetic properties have yet to be determined

- observed resistive but not magnetic anomalies, reminiscent of a superconducting transition in HBCCO at temperatures ranging from 160 to 300 K which are not likely to be associated with the melting of Hg which occurs at 235 K
- observed magnetic but no resistive anomalies in one multi phased oxide sample near 300 K at 0 T and ~ 200 K at 5 T
- Ultra Fast High Power HTS Switches
 - overcome several major material and technical obstacles and demonstrated the workability of such HTS devices whose performance will be enormously enhanced when the materials developed in the program are used

IV. PUBLICATION LIST

"Study of Superconductivity in the Hg-Ba-Ca-Cu-O System," L. Gao, J. Z. Huang, R. L. Meng, G. Lin, F. Chen, L. Beauvais, Y. Y. Sun, Y. Y. Xue and C. W. Chu, *Physica C* 213, 261 (1993).

"Superconductivity at 112-117 K in $\text{HgBa}_2\text{CaCu}_2\text{O}_{6+\delta}$," R. L. Meng, Y. Y. Sun, J. Kulik, Z. J. Huang, F. Chen, Y. Y. Xue and C. W. Chu, *Physica C* 214, 307 (1993).

"Local Charge-Density Transfer and Organic Superconductivity: A Positron Study," Y. Lou, H. L. Yen, J. M. Wrobel, H. Zhang, Y. C. Jean, G. Saito, Z. J. Huang and C. W. Chu, *Phys. Rev. B* 49, 12255 (1994).

"Two Field-Independent Diamagnetizations in $\kappa\text{-(BEDT-TTF)}_2\text{Cu(NCS)}_2$," Z. J. Huang, Y. Y. Xue, Z. Hao, C. W. Chu, Y. C. Jean and G. Saito, submitted to *Phys. Rev. Lett.* (July 7, 1993). WITHDRAWN

"Irreversibility Line of the $\text{HgBa}_2\text{CaCu}_2\text{O}_{6+\delta}$ High Temperature Superconductors," Z. J. Huang, Y. Y. Xue, R. L. Meng and C. W. Chu, *Phys. Rev. B* 49, 4218 (1994).

"Possible Existence of a van Hove Singularity Near the Fermi Surface of $\text{HgBa}_2\text{CaCu}_2\text{O}_{6+\delta}$," F. Chen, Z. J. Huang, R. L. Meng, Y. Y. Sun and C. W. Chu, *Phys. Rev. B* 48, 16047 (1993).

"Superconductivity, Structure and Resistivity in $\text{HgBa}_2\text{Ca}_2\text{Cu}_3\text{O}_{8+\delta}$," Z. J. Huang, R. L. Meng, X. D. Qiu, Y. Y. Sun, J. Kulik, Y. Y. Xue and C. W. Chu, *Physica C* 217, 1 (1993).

"Synthesis of Preferred-Oriented $\text{HgBa}_2\text{CaCu}_2\text{O}_{6+\delta}$ Thin-Films," Y. Q. Wang, R. L. Meng, Y. Y. Sun, Z. J. Huang, K. Ross and C. W. Chu, *Appl. Phys. Lett.* 63, 22 (1993).

"Synthesis of High-Temperature Superconductors: $\text{HgBa}_2\text{CaCu}_2\text{O}_{6+\delta}$ and $\text{HgBa}_2\text{Ca}_2\text{Cu}_3\text{O}_{8+\delta}$," R. L. Meng, L. Beauvais, X. N. Zhang, Z. J. Huang, Y. Y. Sun, Y. Y. Xue and C. W. Chu, *Physica C* 216, 21 (1993).

"Crystal Structure of Annealed and As-Prepared $\text{HgBa}_2\text{CaCu}_2\text{O}_{6+\delta}$ Superconductors," Q. Huang, J. W. Lynn, R. L. Meng and C. W. Chu, *Physica C* 218, 356 (1993).

"Superconductivity Above 150 K in $\text{HgBa}_2\text{Ca}_2\text{Cu}_3\text{O}_{8+\delta}$ Under Pressure," C. W. Chu, L. Gao, F. Chen, Z. J. Huang, R. L. Meng and Y. Y. Xue, *Nature* 365, 323 (1993).

"Superconductivity at Higher Temperatures in the Hg-Ba-Ca-Cu-O Compound System," C. W. Chu, *J. Superconductivity* 7, 1 (1994).

"Micro-Raman Scattering on Superconducting $\text{HgBa}_2\text{Ca}_{n-1}\text{Cu}_n\text{O}_{2n+2+\delta}$ ($n = 1, 2, 3$) Ceramics," Y. T. Ren, H. Chang, Q. Xiong, Y. Q. Wang, Y. Y. Sun, R. L. Meng, Y. Y. Xue and C. W. Chu, *Physica C* 217, 273 (1993).

"Thermopower and Resistivity Measurements on Oxygen Annealed $\text{HgBa}_2\text{CaCu}_2\text{O}_{6+\delta}$," Y. T. Ren, J. Clayhold, F. Chen, Z. J. Huang, X. D. Qiu, Y. Y. Sun, R. L. Meng, Y. Y. Xue and C. W. Chu, *Physica C* 217, 6 (1993).

"Superconductivity in $\text{HgBa}_2\text{Ca}_2\text{Cu}_3\text{O}_{8+\delta}$ Under Hydrostatic Pressure," F. Chen, L. Gao, R. L. Meng, Y. Y. Xue and C. W. Chu, submitted to *Phys. Rev. B* (September 14, 1993).

"Superconductivity up to 147 K in $\text{HgBa}_2\text{CaCu}_2\text{O}_{6+\delta}$ under Quasi-Hydrostatic Pressure," L. Gao, F. Chen, R. L. Meng, Y. Y. Xue and C. W. Chu, *Philosophical Mag. B* 68, 345 (1993).

"Pb-Doping Effects in $\text{Hg}_{1-x}\text{Pb}_x\text{Ba}_2\text{Ca}_2\text{Cu}_3\text{O}_{8+\delta}$," Y. Y. Xue, Z. J. Huang, X. D. Qiu, L. Beauvais, X. N. Zhang, Y. Y. Sun, R. L. Meng and C. W. Chu, *Mod. Phys. Lett. B* 7, 1833 (1993).

"Superconductivity up to 164 K in $\text{HgBa}_2\text{Ca}_{m-1}\text{Cu}_m\text{O}_{2m+2+\delta}$ ($m = 1, 2$, and 3) under Quasihydrostatic Pressures," L. Gao, Y. Y. Xue, F. Chen, Q. Xiong, R. L. Meng, D. Ramirez, C. W. Chu, J. H. Eggert and H. K. Mao, *Phys. Rev. B*, "Rapid Communications," 50, 4260 (1994).

"Local Chemical Composition of HgBaCaCuO High-Temperature Superconductors," A. Alméras, T. dell'Orto, C. Coluzza, J. Almeida, G. Margaritondo, Y. Y. Xue, R. L. Meng and C. W. Chu, *J. Appl. Phys.* 76, 1100 (1994).

"Raman and Thermal Stability Studies on Annealed $\text{HgBa}_2\text{CuO}_{4+\delta}$," by Y. T. Ren, H. Chang, Q. Xiong, Y. Y. Xue and C. W. Chu, *Physica C* 226, 209 (1994).

"Thermomechanical Limitation and Opportunity of Field Trapping in Bulk HTS's," Y. Y. Xue, L. Gao, R. L. Meng and C. W. Chu, *Proceedings of the Sixth US/Japan Workshop on High Temperature Superconductors*, edited by K. Salama, W. K. Chu and C. W. Chu (Singapore: World Scientific, 1994), p. 101.

"Compressibility of $\text{HgBa}_2\text{Ca}_{n-1}\text{Cu}_n\text{O}_{2n+2+\delta}$ ($n = 1, 2, 3$) High-Temperature Superconductors," J. H. Eggert, J. Z. Hu, H. K. Mao, L. Beauvais, R. L. Meng and C. W. Chu, *Phys. Rev. B* 49, 15 299 (1994).

"Unusually Large Shielding Fields in Single-Grain $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$," L. Gao, Y. Y. Xue, R. L. Meng and C. W. Chu, *Appl. Phys. Lett.* 65, 907 (1994).

"Unusual Hole Dependence of T_c in $\text{HgBa}_2\text{CuO}_{4+\delta}$," Q. Xiong, Y. Y. Xue, Y. Cao, F. Chen, Y. Y. Sun, J. Gibson, C. W. Chu, R. M. Liu and A. Jacobson, Phys. Rev. B 50, 10346 (1994).

"Magnetic Properties of the Superconducting Y-Pd-B-C Compound," Y. Y. Xue, Y. Cao, R. L. Meng, C. Kinalidis and C. W. Chu, Physica C 227, 63 (1994).

"Crystal Chemistry of $\text{HgBa}_2\text{CaCu}_2\text{O}_{6+\delta}$ and $\text{HgBa}_2\text{Ca}_2\text{Cu}_3\text{O}_{8+\delta}$: Single-Crystal X-ray Diffraction Results," L. W. Finger, R. M. Hazen, R. L. Meng and C. W. Chu, Physica C 226, 216 (1994).

"Thermal Fluctuation in High Temperature Superconductor $\text{HgBa}_2\text{CaCu}_2\text{O}_{6+\delta}$," Z. J. Huang, Y. Y. Xue, R. L. Meng, X. D. Qiu, Z. D. Hao and C. W. Chu, Physica C 228, 211 (1994).

"23 K Superconducting Phase: $\text{YPd}_2\text{B}_2\text{C}$," Y. Y. Sun, I. Rusakova, R. L. Meng, Y. Cao, P. Gautier-Picard, J. Meen and C. W. Chu, Physica C 230, 435 (1994).

"Fermi-Liquid Behavior and BCS s-Wave Pairing of K_3C_{60} Observed by ^{13}C -NMR," Susumu Sasaki, Azusa Matsuda and C. W. Chu, J. Phys. Soc. Jpn. 63, 1670 (1994).

"Raman Studies on BaCuO_2 , Ba_2CuO_3 and Ba_2Cu_3 and $\text{Ba}_2\text{Cu}_3\text{O}_{5.9}$," H. Chang, Y. T. Ren, Y. Y. Sun, Y. Q. Wang, Y. Y. Xue and C. W. Chu, Physica C 228, 383 (1994).

"Oxygen Annealing and the Related Thermodynamics in $\text{HgBa}_2\text{CuO}_{4+\delta}$," Q. Xiong, Y. Y. Xue, F. Chen, Y. Cao, Y. Y. Sun, L. M. Liu, A. J. Jacobson and C. W. Chu, Physica C 231, 233 (1994).

"Annealing Condition, T_c , and Oxidation Enthalpy in $\text{HgBa}_2\text{CuO}_{4+\delta}$," Y. Y. Xue, Q. Xiong, F. Chen, Y. Cao, L. M. Liu, A. J. Jacobson and C. W. Chu, Physica C 235-240, 901 (1994).

"Universal Enhancement of T_c Under High Pressure in $\text{HgBa}_2\text{Ca}_{m-1}\text{Cu}_m\text{O}_{2m+2+\delta}$," L. Gao, Y. Y. Xue, F. Chen, Q. Xiong, R. L. Meng, D. Ramirez, C. W. Chu, J. Eggert and H. K. Mao, Physica C 235-240, 1493 (1994).

"Measurement of the Nernst Effect in the Normal State of $\text{Tl}_2\text{Ba}_2\text{CaCu}_2\text{O}_{8+\delta}$," J. A. Clayhold, A. W. Linnen, F. Chen and C. W. Chu, Physica C 235-240, 1537 (1994).

"Normal-State Nernst Effect in a $\text{Tl}_2\text{Ba}_2\text{CaCu}_2\text{O}_{8+\delta}$ Epitaxial Film," J. A. Clayhold, A. W. Linnen, Jr., F. Chen and C. W. Chu, Phys. Rev. B "Rapid Communications" 50, 4252 (1994).

"Superconductivity in $(\text{LuC})_2(\text{Ni}_2\text{B}_2)$ and $(\text{LuC})(\text{Ni}_2\text{B}_2)$," L. Gao, X. D. Qiu, Y. Cao, R. L. Meng, Y. Y. Sun, Y. Y. Xue and C. W. Chu, Phys. Rev. B 50, 9445 (1994).

"Hydrostatic Pressure on $\text{HgBa}_2\text{CaCu}_2\text{O}_{6+\delta}$ and $\text{HgBa}_2\text{Ca}_2\text{Cu}_3\text{O}_{8+\delta}$," F. Chen, L. Gao, R. L. Meng, Y. Y. Xue and C. W. Chu, J. Appl. Phys. 76, 6941 (1994).

"Surface Chemical Decomposition of $\text{HgBa}_2\text{CuO}_{4+\delta}$ by High Power Laser Radiation," H. Chang, Q. Xiong, Y. Y. Xue and C. W. Chu, Physica C 248, 15 (1995).

"High Pressure Synthesis of Single-Phase Superconductors $\text{Hg}_z\text{Sr}_x\text{Ba}_{2-x}\text{Ca}_2\text{Cu}_3\text{O}_{8+\delta}$ and $(\text{Hg},\text{M})\text{Sr}_2\text{Ca}_2\text{Cu}_3\text{O}_y$ with $\text{M} = \text{Pb}$ and Mo ," Z. H. He, Q. M. Lin, L. Gao, Y. Y. Sun, Y. Y. Xue and C. W. Chu, *Physica C* 241, 211 (1995).

"Thermal Stability and Chemical Transformation of BaCuO_2 , Ba_2CuO_3 and $\text{Ba}_2\text{Cu}_3\text{O}_{5.9}$," by H. Chang, Y. T. Ren, Y. Y. Sun, Y. Q. Wang, Y. Y. Xue and C. W. Chu, submitted to *J. Raman Spectroscopy*. WITHDRAWN

"High Temperature Superconducting Material Research: Problems and Potentials," L. Gao, Y. Y. Xue, R. L. Meng and C. W. Chu, *Proceedings of the 43rd International Wire and Cable Symposium (1994: Eatontown NJ, IWCS)*, p. 174.

"Unusual High Temperature Superconductors: $\text{HgBa}_2\text{Ca}_{n-1}\text{Cu}_n\text{O}_{2n+2+\delta}$ with $n = 1, 2, 3, \dots$," C. W. Chu, to appear in *Quantum Theory of Real Materials: Festschrift to Honor Marvin Cohen*, (Kluwer Academic, Norwell MA, 1994).

"High Temperature Superconductivity," C. W. Chu, *Proceedings of the International Conference on the History of Original Ideas and Basic Discoveries in Particle Physics*, Erice, Sicily, Italy, July 29 - August 4, 1994, to be published by Plenum, New York.

"High Pressure Study of $\text{La}_3\text{Ni}_2\text{B}_2\text{N}_x$," Y. Cao, R. L. Meng and C. W. Chu, *Mod. Phys. Lett. B* 9, 731 (1995).

"Pressure Effect on the T_c of $\text{HgBa}_2\text{CuO}_{4+\delta}$ with $0.07 \leq \delta \leq 0.39$," Y. Cao, Q. Xiong, Y. Y. Xue and C. W. Chu, *Phys. Rev. B* 52, 6854 (1995).

"Oxygen Dependence of the Crystal Structure of $\text{HgBa}_2\text{CuO}_{4+\delta}$ and Its Relation to Superconductivity," Q. Huang, J. W. Lynn, Q. Xiong and C. W. Chu, *Phys. Rev. B* 52, 462 (1995).

" δ -Influence on the Pressure-Effect on T_c of $\text{HgBa}_2\text{CuO}_{4+\delta}$ and the Inverse Parabolic T_c -Relation," C. W. Chu, Y. Cao, Q. Xiong, and Y. Y. Xue, *J. Superconductivity* 8, 393 (1995).

"Penetration Depth of $\text{HgBa}_2\text{CuO}_{4+\delta}$ with $0.07 \leq \delta \leq 0.35$," Y. Y. Xue, Q. Xiong, Y. Cao and C. W. Chu, *J. Superconductivity* 8, 465 (1995).

"Systematics of the Thermopower Below T_c in $\text{Tl}_2\text{Ba}_2\text{CaCu}_2\text{O}_{8+\delta}$," J. A. Clayhold and C. W. Chu, *Proceedings of the University of Miami Workshop on "High Temperature Superconductivity: Physical Properties and Mechanisms"*, *J. Superconductivity* 8, 627 (1995).

"Excess Thermopower in the Mixed State of $\text{Tl}_2\text{Ba}_2\text{CaCu}_2\text{O}_{8+\delta}$," J. A. Clayhold and C. W. Chu, submitted to *Phys. Rev. Lett.* (January 4, 1995); rewritten as "Unusual Magnetic Field Dependence of the Electrothermal Conductivity in the Mixed State of Cuprate Superconductors," J. A. Clayhold, Y. Y. Xue, C. W. Chu, J. N. Eckstein, I. Bozovic, submitted to *Phys. Rev. B* (November 10, 1995). TCSUH Preprint 95:122

"Raman Study of the Thermal Stability of $\text{HgBa}_2\text{CaCu}_2\text{O}_{6+\delta}$ and $\text{HgBa}_2\text{Ca}_2\text{Cu}_3\text{O}_{8+\delta}$," by H. Chang, Z. H. He, R. L. Meng, Y. Y. Xue and C. W. Chu, *Physica C* 251, 126 (1995).

"Doping Effect on the Penetration Depth of $\text{HgBa}_2\text{CuO}_{4+\delta}$," C. W. Chu, Y. Y. Xue, Y. Cao and Q. Xiong, J. Phys. Chem. 56, 1887 (1995).

"Field-Independent Magnetization and Fluctuations in Hg-Based Cuprates," Y. Y. Xue, Y. Cao, Q. Xiong, F. Chen and C. W. Chu, J. Phys. Chem. Solids 56, 1909 (1995).

"Raman Study of the Laser-Induced Chemical Instabilities of BaCuO_2 , $\text{Ba}_2\text{Cu}_3\text{O}_{5.9}$, and Ba_2CuO_3 ," H. Chang, Y. T. Ren, Y. Y. Sun, Y. Q. Wang, Y. Y. Xue and C. W. Chu, Physica C 252, 333 (1995).

"Quasiparticle Contribution to the Mixed-State Thermopower in $\text{Tl}_2\text{Ba}_2\text{CaCuO}_2\text{O}_{8+\delta}$," J. A. Clayhold and C. W. Chu, J. Phys. Chem. Solids 56, 1907 (1995).

"Variation of the Temperature Dependence of the Penetration Depth in $\text{HgBa}_2\text{CuO}_{4-\delta}$ with Oxidation," Y. Y. Xue, Q. Xiong, Y. Cao and C. W. Chu, to appear in Phys. Rev. B 53, 2811 (1996).

"Vortex Fluctuations and Interlayer Coupling in Cuprates," by Y. Y. Xue, Y. Cao, Q. Xiong, F. Chen and C. W. Chu, to appear in Phys. Rev. B 53, 2815 (1996).

"124 K Superconductivity in Cu-Ba-Ca-Cu-O," L. Gao, Z. L. Du, Y. Cao, I. Rusakova, Y. Y. Sun, Y. Y. Xue and C. W. Chu, Mod. Phys. Lett. B 9, 1397 (1995).

"Precursor effects on the $\text{HgBa}_2\text{Ca}_2\text{Cu}_3\text{O}_8$ formation under high pressure," Q. M. Lin, Z. H. He, Y. Y. Sun, L. Gao, Y. Y. Xue and C. W. Chu, Physica C 254, 207 (1995).

"Synthesis and Start Cation-Composition of $\text{HgBa}_2\text{CuO}_{4+\delta}$," Q. Xiong, F. T. Chan, Y. Y. Xue and C. W. Chu, Physica C 253, 329 (1995).

"Magnetization of $\text{HgBa}_2\text{CuO}_{4+\delta}$ with $0.03 \leq \delta \leq 0.4$," Q. Xiong, S. Afonso, Y. Q. Tang, F. T. Chan, G. Salamo, Y. Y. Xue and C. W. Chu, Proceedings of the 40th Annual Conference on Magnetism and Magnetic Materials, Philadelphia PA, November 6-9, 1995, to appear in J. Appl. Phys., April 1996.

"Unusual Thermopower and the Overdoped State of $\text{HgBa}_2\text{Ca}_{m-1}\text{Cu}_m\text{O}_{2m+2+\delta}$," F. Chen, Q. Xiong, Y. Y. Xue, Z. J. Huang, Z. H. He, Q. M. Lin, J. A. Clayhold and C. W. Chu, submitted to Physical Review B, Rapid Communications (January 17, 1996).

"Unusual Magnetic-Field Dependence of the Electrothermal Conductivity in the Mixed-State of Cuprate Superconductors," J. A. Clayhold, Y. Y. Xue, C. W. Chu, J. N. Eckstein and I. Bozovic, accepted for publication in Physical Review B (submitted December 13, 1995).

"Thermomagnetic Effects Above and Below T_c in the Cuprate Superconductors," J. A. Clayhold, Y. Y. Xue, C. W. Chu, J. N. Eckstein and I. Bozovic, submitted to Proceedings of the SPIE Photonic West '96 Symposium: Conference on Oxide Superconductor Physics and Nano-Engineering II, San Jose, California, January 27 - February 2, 1996.

"Gas Effusion Spectra of $\text{HgBa}_2\text{CuO}_{4+\delta}$," A. Hamed, R. Ortiz, H. H. Feng, Z. G. Li, P. H. Hor, Y. Y. Xue, Y. Y. Sun, Q. Xiong, Y. Cao and C. W. Chu, submitted to Physical Review B (January 24, 1996).

