

AD

AD-E402 727

Technical Report ARAED-TR-96008

**PERFORMANCE TESTING OF SEALING TAPES  
FOR 81-mm MORTAR AMMUNITION FIBER CONTAINER**

Y. H. Lam

April 1996



US ARMY  
TANK AUTOMOTIVE AND  
ARMAMENTS COMMAND  
ARMAMENT RDE CENTER

**U.S. ARMY ARMAMENT RESEARCH, DEVELOPMENT AND  
ENGINEERING CENTER**

Armament Engineering Directorate

**Picatinny Arsenal, New Jersey**

Approved for public release; distribution is unlimited.

19960523 001

2025 RELEASE UNDER E.O. 14176

The views, opinions, and/or findings contained in this report are those of the authors(s) and should not be construed as an official Department of the Army position, policy, or decision, unless so designated by other documentation.

The citation in this report of the names of commercial firms or commercially available products or services does not constitute official endorsement by or approval of the U.S. Government.

Destroy this report when no longer needed by any method that will prevent disclosure of its contents or reconstruction of the document. Do not return to the originator.

**REPORT DOCUMENTATION PAGE**

Form Approved OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operation and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE April 1996		3. REPORT TYPE AND DATES COVERED	
4. TITLE AND SUBTITLE PERFORMANCE TESTING OF SEALING TAPES FOR 81-mm MORTAR AMMUNITION FIBER CONTAINER				5. FUNDING NUMBERS	
6. AUTHOR(S) Y. H. Lam					
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESSES(S) ARDEC, AED Packaging Division (AMSTA-AR-AEP) Picatinny Arsenal, NJ 07806-5000				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(S) ARDEC, DOIM Information Research Center (AMSTA-AR-IMC) Picatinny Arsenal, NJ 07806-5000				10. SPONSORING/MONITORING AGENCY REPORT NUMBER  Technical Report ARAED-TR-96008	
11. SUPPLEMENTARY NOTES					
12a. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution is unlimited.				12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words)  This report details the performance testing conducted on four types of sealing tape systems for 81-mm mortar ammunition fiber container. The purpose of the test was to explore the possibility of applying only one sealing tape to replace the current double taping system. The test results concluded that both the MIL-T-43036, Type II and I tapes were the best alternate choices of replacements. This improvement could reduce the labor cost for the sealing operation by 50% and provide a substantial amount of savings on the taping materials.					
14. SUBJECT TERMS  81-mm mortar      Sealing tape      Moisture migration      Fiber container 81-mm cartridge				15. NUMBER OF PAGES 10	
				16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT SAR		

## CONTENTS

	Page
Introduction	1
Test Procedures	1
Conclusions	2
Distribution List	7

## INTRODUCTION

The 81-mm mortar ammunition is unit-packaged in fiber tube containers. In order to resist moisture migration, for years the adjacent area between the fiber container cap and body was sealed using two layers of tapes. First, apply 1-1/4 turns of 1 in. wide sealing tape (MIL-T-43036, Type I, polyester reinforced) on the closure area. Then, two turns of 2 in. industrial grade of duct tape (PPP-T-60) is applied, overlapped over the MIL-T-43036 tape to complete the sealing. In 1995, the Packaging Division of the U.S. Army Armament Research, Development and Engineering Center (ARDEC) initiated a study program to determine the sealing performance of four taping systems. The purpose of this study was to explore the possibility of changing the double taping system by using only one tape that still retained the current sealing capability. If successful, this improvement could reduce the labor cost for the sealing operation by 50% and provide a substantial amount of savings on the taping materials. This report details this study program.

### Test Procedures

The test sought to measure different sealing tapes' capabilities of preventing moisture penetration. A sealed fiber container represented a test sample. Each sample containing four desiccant bags were exposed to hot and humid environment in accordance with the aggravated temperature-humidity cycles of MIL-STD-810E (fig. 1).

Four types of taping methods were tested to compare their sealing performance:

- Current double tape system:
  - 1-1/4 turns of 1 in. tape, MIL-T-43036, Type I (polyester reinforced)
  - Two turns of 2 in. industrial duct tape, PPP-T-60
- Two turns of 2 in. tape, MIL-T-43036, Type I (polyester reinforced)
- Two turns of 2 in. tape, MIL-T-43036, Type II (non-reinforced)
- Two turns of 2 in. industrial waterproof duct tape, PPP-T-60

The test was conducted at the Environmental Test Laboratory located in Building 60, Picatinny Arsenal, New Jersey. The data collection took place between October 19, 1995 and November 6, 1995, over a period of 18 days. The weights of the empty containers, weights of desiccant bags, and packout weight of the containers were recorded before and after the test (table 1).

## CONCLUSION

Although the test duration was not long enough for typical environmental testing, it did reveal reasonable engineering characteristic trends of these sealing tape materials.

It appeared that the MIL-T-43036, type II out performed the rest in the group as expected. At the end of the test, the average weight gain of the containers sealed with 2 in. MIL-T-43036, type II (non-reinforced) was only 0.011 lb compared to 0.012 lb with the double-tape system (inner-wrapped with 1 in. MIL-T-43036, Type I polyester reinforced tape and wrapped over with two turns of 2 in. industrial duct tape, PPP-T-60), 0.017 lb with 2 in. MIL-T-43036, Type I (polyester reinforced), and 0.02 lb with industrial waterproof duct tape, PPP-T-60.

Both the type I and II tapes of MIL-T-43036 maintained excellent adhesive capability throughout the test. At the end of the test, it was noticed that both the tapes were in excellent condition. The tape surface was smooth and the sealing with the surface of fiber containers was tight and inseparable. However, the performance of the industrial grade of duct tape (applied alone on the containers or as the outer layer of the double tape system) was disappointing. It became extremely wrinkled and easy to peel off. It was concluded that the industrial duct tape was not able to survive under the attack of hot and humid environment and it should not be used to seal the ammunition fiber container.

Based on the test results, the MIL-T-43036 type II tape (non-reinforced) was selected as the first choice of replacing the double tape system to seal the 81-mm ammunition fiber containers. Additionally, because the MIL-T-43036 type I tape (polyester reinforced) performed almost as good as the double tape system, it was chosen as an alternative sealing material for the application. These improvements were implemented into the 81-mm ammunition productions and are expected to provide a substantial cost savings for the current and future ammunition loading, assembling, and packing operations.




Figure 1  
 Two aggravated temperature-humidity cycles  
 (from MIL-STD-810E, figure 507.3.3)

**Table 1**  
**Weight changes of packout containers before and after test**

	Container No.	Weight of Packout Container (lb)		Change	
		Before testing	After testing	lb	%
Double Tape System	1	2.67	2.68	0.01	0.375
	2	2.63	2.64	0.01	0.380
	3	2.67	2.69	0.02	0.749
	4	2.67	2.68	0.01	0.375
	5	2.74	2.75	0.01	0.365
	6	2.66	2.67	0.01	0.375
	Average				0.012
MIL-T-43036, Type I (Polyester reinforced)	1	2.65	2.67	0.02	0.755
	2	2.66	2.67	0.01	0.376
	3	2.68	2.70	0.02	0.746
	4	2.64	2.65	0.01	0.379
	5	2.69	2.71	0.02	0.744
	6	2.69	2.71	0.02	0.744
	Average				0.017
MIL-T-43036, Type II (Non-reinforced)	1	2.68	2.69	0.01	0.373
	2	2.67	2.68	0.01	0.375
	3	2.70	2.71	0.01	0.370
	4	2.63	2.645	0.015	0.570
	5	2.69	2.70	0.01	0.372
	6	2.71	2.72	0.01	0.369
	Average				0.011
PPP-T-60 Industrial Duct Tape	1	2.64	2.65	0.01	0.379
	2	2.71	2.73	0.02	0.738
	3	2.67	2.70	0.03	1.124
	4	2.68	2.70	0.02	0.746
	5	2.70	2.72	0.02	0.741
	6	2.66	2.68	0.02	0.752
	Average				0.02

## DISTRIBUTION LIST

Commander

Armament Research, Development and Engineering Center  
U.S. Army Tank-automotive and Armaments Command

ATTN: AMSTA-AR-IMC

AMSTA-AR-GCL

AMSTA-FSA-M, J. Feneck

D. Walsh

E. Schelenk

R. Wong

G. Eilert

A. Lesaca

J. Smith

O. Eng

AMSTA-AR-AEP, Y. H. Lam (25)

V. Khanna

O. Bogdan

D. Kirshteyn

A. Arnold

L. Rasmussen

J. Zoll

E. Farrell

M. Ivankoe

AMSTA-AR-QAA-C, H. Lee

K. Ng

AMCPM-MO, B. Parr

D. Wright

M. Serban

Picatinny Arsenal, NJ 07806-5000

Defense Technical Information Center (DTIC)

ATTN: DTIC-OCC (12)

8725 John J. Kingman Road, Ste 0944

Fort Belvoir, VA 22060-6218

Director

U.S. Army Materiel Systems Analysis Activity

ATTN: AMXSY-MP

Aberdeen Proving Ground, MD 21005-5066

Commander  
Chemical/Biological Defense Agency  
U.S. Army Armament, Munitions and Chemical Command  
ATTN: AMSCB-CII, Library  
Aberdeen Proving Ground, MD 21010-5423

Director  
U.S. Army Edgewood Research, Development and Engineering Center  
ATTN: SCBRD-RTB (Aerodynamics Technology Team)  
Aberdeen Proving Ground, MD 21010-5423

Director  
U.S. Army Research Laboratory  
ATTN: AMSRL-OP-CI-B, Technical Library  
Aberdeen Proving Ground, MD 21005-5066

Chief  
Benet Weapons Laboratory, CCAC  
Armament Research, Development and Engineering Center  
U.S. Army Armament, Munitions and Chemical Command  
ATTN: SMCAR-CCB-TL  
Watervliet, NY 12189-5000

Director  
U.S. Army TRADOC Analysis Command-WSMRc  
ATTN: ATRC-WSS-R  
White Sands Missile Range, NM 88002

GIDEP Operations Center  
P.O. Box 8000  
Corona, CA 91718-8000

Commander  
Armament, Research, Development and Engineering Center  
U.S. Army Tank-automotive and Armament Command  
ATTN: AMSTA-AR-ESW-F, W. Songaila  
Rock Island, IL 61299-5000