

RL-TR-96-198
In-House Report
February 1997



DEVELOPMENT OF CdS-DOPED GLASS OPTICAL FIBERS FOR ALL-OPTICAL SWITCHING

Sponsored by
Ballistic Missile Defense Organization

APPROVED FOR PUBLIC RELEASE; DISTRIBUTION UNLIMITED.

19970416 008

DEQ QUALITY INSPECTED 4

The views and conclusions contained in this document are those of the authors and should not be interpreted as necessarily representing the official policies, either expressed or implied, of the Ballistic Missile Defense Organization or the U.S. Government.

Rome Laboratory
Air Force Materiel Command
Rome, New York

This report has been reviewed by the Rome Laboratory Public Affairs Office (PA) and is releasable to the National Technical Information Service (NTIS). At NTIS it will be releasable to the general public, including foreign nations.

RL-TR-96-198 has been reviewed and is approved for publication.

APPROVED: 

JAMES W. CUSACK
Chief, Photonics Division
Surveillance and Photonics Directorate

FOR THE COMMANDER: 

DONALD W. HANSON, Director
Surveillance and Photonics Directorate

If your address has changed or if you wish to be removed from the Rome Laboratory mailing list, or if the addressee is no longer employed by your organization, please notify Rome Laboratory/OCPA, Rome, NY 13441. This will assist us in maintaining a current mailing list.

Do not return copies of this report unless contractual obligations or notices on a specific document require that it be returned.

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.			
1. AGENCY USE ONLY (Leave blank)	2. REPORT DATE February 1997	3. REPORT TYPE AND DATES COVERED In-House Mar 95 - Sep 96	
4. TITLE AND SUBTITLE Development of CdS-doped Glass Optical Fibers for All-Optical Switching		5. FUNDING NUMBERS C - NA PE - 61102F PR - 2300 TA - 05 WU - 00	
6. AUTHOR(S) Raymond K. Boncek		8. PERFORMING ORGANIZATION REPORT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Rome Laboratory/OCPA 25 Electronic Pky Rome NY 13441-4515		10. SPONSORING / MONITORING AGENCY REPORT NUMBER RL-TR-96-198	
9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES) Rome Laboratory 26 Electronic Pky Rome NY 13441-4514		Department of Defense BMDO/TRI Washington DC 20301-7100	
11. SUPPLEMENTARY NOTES Rome Laboratory Project Engineer: Raymond K. Boncek, OCPA, 315-330-2937			
12a. DISTRIBUTION AVAILABILITY STATEMENT APPROVED FOR PUBLIC RELEASE; DISTRIBUTION UNLIMITED		12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) We have successfully fabricated samples of CdSSe-doped fibers made from RG630 Schott glass and designed for single-mode operation in the 1300nm and 1550nm communication wavelength region. The linear absorption coefficient of the CdSSe-doped fiber was measured to be 0.14 dB/cm. A comparison between the measured transmittance of a sample of 350um O.D. fiber and a bulk rod of RG630 Schott glass shows the two to have similar characteristics. That is, (i) the absorption edge of the fiber and the RG630 are found to be the same and near 630nm, and (ii) the region of maximum transmittance occurs beyond 680nm for both fiber and RG630. The transmittance remains relatively constant for wavelengths greater than 680nm. These results point to the fact that the fabrication of the fiber yielded good samples. Also we have developed an experimental procedure to gain switch the probe signal. This capability will be employed for time synchronization of pump and probe in the switch implementation. We have measured the nonlinear refractive index of the RG630 glass at 1313nm. The nonresonant nonlinear refractive index for a CdSSe-doped fiber has been determined experimentally, at a wavelength of 1313nm and found to be $1.8 \times 10^{-17} \text{ m}^2/\text{W}$. In comparison, silica fiber has an n_2 value of $4.2 \times 10^{-20} \text{ m}^2/\text{W}$.			
14. SUBJECT TERMS CdSSe-doped fibers, nonlinear refractive index, optical switching		15. NUMBER OF PAGES 28	
		16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT UNLIMITED

TABLE OF CONTENTS

Abstract.....	1
I. Introduction.....	2
II. Activities completed.....	2
III. Summary.....	11
IV. References.....	12

Abstract:

We have successfully fabricated samples of CdSSe-doped fibers made from RG630 Schott glass and designed for single-mode operation in the 1300 nm and 1550 nm communication wavelength region. The linear absorption coefficient of the CdSSe-doped fiber was measured to be 0.14 dB/cm. A comparison between the measured transmittance of a sample of 350 μm O.D. fiber and a bulk rod of RG630 Schott glass shows the two to have similar characteristics. That is, (i) the absorption edge of the fiber and the RG630 are found to be the same and near 630 nm, and (ii) the region of maximum transmittance occurs beyond 680 nm for both fiber and RG630. The transmittance remains relatively constant for wavelengths greater than 680nm. These results point to the fact that the fabrication of the fiber yielded good samples. Also we have developed an experimental procedure to gain switch the probe signal. This capability will be employed for time synchronization of pump and probe in the switch implementation.

We have measured the nonlinear refractive index of the RG630 glass at 1313 nm. The nonresonant nonlinear refractive index for a CdSSe-doped fiber has been determined experimentally, at a wavelength of 1313 nm and found to be $1.8 \times 10^{-17} \text{ m}^2/\text{W}$. In comparison, silica fiber has an n_2 value of $4.2 \times 10^{-20} \text{ m}^2/\text{W}$ [1]. This value of n_2 is therefore 400 times higher than silica fiber. The results obtained to date are promising and the overall project is proceeding in accordance with stated objectives.

I. Introduction:

The goal of this project is to design and implement a compact fiber-based all optical switch actuated at laser diode power levels. The operation of the devices is based on intensity induced wavelength shift of a probe signal in a Kerr medium. A semiconductor (CdSSe -) doped specialty fiber serves as the Kerr medium. The switch is an integrated structure of the specialty fiber with fiber grating. The structure is designed such that the transmission wavelength of the gratings coincides with the probe or signal wavelength. Thus in the absence of a pump pulse the probe will be transmitted. This corresponds to the "ON-state" of the switch. The intensity of the pump is chosen in order to cause a shift in the wavelength of the probe, equal to or greater than the band stop of the grating, and thereby cause the probe to be reflected. This corresponds to the "OFF-State" of the switch. This report is a summary of activities completed to date.

II. Activities Completed.

A. Fabrication Of CdSSe-Doped Fiber

A number of CdSSe-doped fibers have successfully been fabricated and their linear properties characterized. The fiber was fabricated using Schott glass RG630, with a $\text{CdS}_{0.5}\text{Se}_{0.5}$ composition as the core material, and RG6 as the cladding material. The diameters of the fiber core range between 3-8 μm , and the outer diameter of the fiber range between 150 - 350 μm . The table below summarizes the different types of fibers fabricated.

TABLE 1: CdSSe-doped fibers fabricated with RG-630 core glass and RG-6 cladding glass. The refractive index of the cladding (RG6) was measured to be 1.522.

Sample	Estimated Core Diameter (μm)	Outer Diameter (μm)
A	3.2	150
B	4.3	200
C	5.3	250
D	6.4	300
E	7.4	350




Figure 1 White light transmission measurement of RG630 1 mm diameter glass rod (dashed curve) and CdSSe-doped optical fiber (solid curve).

B. Measurement Of the Transmittance Spectra Of CdSSe-Doped Fiber.

The transmittance of the fiber over a wavelength range between 380 and 880 nm was measure using a tungsten filament white light source. The white light source was focused onto one end of an approximately 16 cm length of Sample E fiber. The output end of the sample fiber was focused on to the input aperture of an ANDO AQ1425 Optical Spectrum Analyzer. The transmission measurement of the Sample E fiber is shown in

Figure 1. For comparison, the transmission measurement results of a 2.5 cm long rod of the RG630 core material is also included. The quantitative levels of the two measurements are greatly different. This difference is due to the diffraction limited focusing of the white light filament reducing the available power one is able to launch into the core of the fiber. Qualitatively, however, the position of a measured absorption edge is the same for both materials and located near the expected value of 630 nm for this glass type. This result indicates that the CdSSe of the RG630 glass material has survived the fiber fabrication process and should result in similar properties as that found in the bulk material.

C. Measurement Of The Absorption/Scattering Coefficient Of Fiber.

A cut-back method was used to measure the linear absorption coefficient of the fiber. The set-up for this experiment is as shown in Figure 2. The source is a 1532 nm DFB pig-tailed semiconductor laser diode. The test fiber was mounted on two flexure-stages. The pig-tailed laser was butt-coupled to one end of the fiber. An optical imaging system, located at the opposite end of the test fiber and comprised of an IR photocathode camera and a monitor, was used to observe and ensure that the source signal was well coupled into the core of the fiber before performing the cut-back measurement. Imaging results indicated that a large amount of scattering occurs in the sample fibers and is probably the largest contribution to the measured absorption coefficients. A standard single-mode fiber SMF-28 was used to collect the light from the sample fiber and deliver the power propagating in the core of the fiber to a photodiode detector. A Newport 835 power meter with an 818-IR detector was used to measure the output power.




Figure 2 Schematic diagram of experimental setup used for cut-back measurement of optical fiber absorption coefficient.

An initial length L (about 50 cm) of the test fiber was used. The output power was measured for different input power levels to insure linear absorption. A known length of fiber was then cut-off from the detector end of the test fiber, and the output power again measured for the same set of input power levels. This procedure was repeated for additional cut-backs and an average of the results was made after calculating the absorption coefficient according to,

$$\alpha = \frac{1}{L} 10 \log \frac{P_{out1}}{P_{out2}} \text{ dB/cm}$$

where, P_{out1} is the measured output power prior to cutting and P_{out2} is the measured output power after the cut back.

Table 2 gives a set of measurements for the cut-back experiment and the calculated absorption coefficient. An average value of the absorption coefficient gave a value of 0.14 dB/cm. Excess losses due to butt-coupling totaled -5.4 dB. Assuming -0.6 dB for Fresnel losses at the glass/air interfaces, excess coupling losses are -4.8 dB.

TABLE 2. Cut-back results.

			DL = 25.3 cm	DL = 30.6 cm	Absorption Coefficient (dB/cm) # 1	Absorption Coefficient (dB/cm) # 2
Laser Bias (mA)	Pout DFB (mW)	Pout L=101.6 cm (μ W)	Pout L=76.3 cm (μ W)	Pout L=45.7 cm (μ W)		
20	0.8283	8.9	20.3	54.3	-0.1415439	-0.1396418
22.5	1.0538	11.5	26	70	-0.1400298	-0.1405636
25	1.2805	14	32	82	-0.1419059	-0.1335503
27.5	1.5205	16.4	37	102	-0.1396671	-0.1439211
30	1.76	19.5	43.6	115	-0.1381233	-0.1376508
				Ave. -->	-0.140254	-0.1390655

D. Measurement of n_2 For CdSSe-Doped Glass at 1313 nm

Two experimental studies have been conducted, at present, to study the nonlinear optical properties of the CdSSe-doped fiber. One study is a measurement of the nonlinear refractive index, n_2 , of the fiber at 1313 nm. At this wavelength, the optical nonlinearity of the CdSSe-doped glass fiber is due to a non-resonant mechanism. As such the nonlinearity should have a fast response time. We therefore conducted a comprehensive literature search to obtain n_2 data for CdSSe in a glass matrix composition or bulk-CdSSe. The pertinent results are summarized in Table 3. As seen from the table, the n_2 values given do not include data for 1313 nm.

TABLE 3. Literature references of measured values for the nonlinear refractive index n_2 for various glass compositions and wavelengths.

Material	Type	Energy gap (eV)	Wavelength (μ m)	$n_2 \times 10^{-13}$ cm^2/W	Reference
$\text{CdS}_{0.9}\text{Se}_{0.1}$	glass/comp	2.35	1.06	8.4	Acioli, <i>et al.</i> , Appl. Phys. Lett. 54 (20), 1956 (1989).
$\text{CdS}_{0.9}\text{Se}_{0.1}$	glass/comp	2.35	0.530	420	Olbright <i>et al.</i> , Appl. Phys. Lett., 48 (18), 1184 (1986).
$\text{CdS}_{0.9}\text{Se}_{0.1}$	glass/comp	2.35	0.532	2730	Jain & Lind., J.

					Opt. Soc Am. B, 73 , 647 (1983).
$\text{CdS}_{.8}\text{Se}_{.2}$	glass/comp	2.28	0.589	21100	Remillard, <i>et al.</i> Opt. Lett., 13 (1), 30 (1988).
$\text{CdS}_{0.7}\text{Se}_{0.3}$	glass/comp	2.21	0.570	2110	Roussignol, P., J. Opt. Soc. Am. B, 4 (1), 5 (1987).
CdS (size 3nm)	glass/comp	2.42	1.9	69	Cheng, <i>et al.</i> , J. Appl. Phys, 66 (7), 3417 (1989).
CdS (size 1.5nm)	glass/comp	2.42	1.9	5.3	Cheng, <i>et al.</i> , J. Appl. Phys, 66 (7), 3417 (1989).
fused silica	bulk	7.8	1.06	0.021	Sheik-Bahae, <i>et al.</i> , J. Quantum Elec., 27 (6), 1296 (1991).
fused silica	bulk	7.8	.249	0.034	Sheik-Bahae, <i>et al.</i> , J. Quantum Elec., 27 (6), 1296 (1991).

The approach for the measurement of the nonlinear refractive index follows a Z-Scan method proposed by Sheik-Bahae, *et al.* [2] The experimental set-up is as shown in Figure 3. The laser source is a 1313 nm mode-locked Nd:YLF laser emitting pulses of 95 ps duration and having peak power of 100W at a repetition rate of 100 MHz. A beam splitter (BS) splits part of the pulse to detector, D1. The remaining portion of the beam is focused on to the sample (S). The sample is 3-mm thick RG630 Schott glass, the same material used as the core material for the specialty fiber. An adjustable aperture is placed on one side of the sample as shown in Figure 3. A second detector, D2, is placed behind the detector.

Z-Scan experimental set-up for measuring n_2




Figure 3. Z-scan experimental setup.

The set-up measures the transmittance of the sample as a function of position between the focusing lens and the aperture. The change in the transmittance has been shown to depend on the nonlinearity of the material according to the formula:

$$n_2(esu) = \frac{\Delta T_{p-v}}{I_0(t)} \left[\frac{1}{0.046(1-S)^{0.25}} \right] \frac{2\pi}{\lambda} \frac{\alpha}{1-e^{-\alpha L}} \frac{2n_0}{40\pi}$$

In this equation, ΔT_{p-v} is the peak-to-valley change in transmittance, $I_0(t)$ is the peak intensity of the laser source signal, S is the aperture linear transmittance, L is the sample thickness and n_0 is the linear refractive index of the sample. The result for a position-dependent transmittance of a 3-mm thick sample of RG630 glass is shown in Figure 4. The peak power of the laser pulse was 157W. The experiment was repeated for power levels of 128W, 170W, and 199W. From the measured transmittance and the equation

above, the nonlinear refractive index for the CdSSe/glass composite was determined to be $1.8 \times 10^{-17} \text{ m}^2/\text{W}$.




Figure 4. Z-scan measurement of 3 mm thick RG630 glass.

E. Pump-Probe Experiment.

A pump-probe experiment will be used to measure the intensity induced wavelength shift in the CdSSe-doped fiber samples. The pump signal is the 1.313 μm mode-locked Nd:YLF laser, while the probe signal will be a gain switched 1.532 μm DFB semiconductor laser diode synchronized to a higher harmonic of the repetition rate of the pump laser. The optical spectrum of the gain switched probe laser is shown in Figure 5. The pump is expected to induce a wavelength shift in this optical spectrum. The equation for the wavelength shift is given as [3],

$$\delta\lambda = \frac{2\lambda^2 n_2 P_p L_{eff}}{c\lambda_0 A_{eff} T_0}$$

where, λ is the probe wavelength, λ_0 is the pump wavelength, P_p is the peak power of the pulse, L_{eff} is the effective length of the fiber (since pulse walk off is assumed to be negligible), A_{eff} is the effective core area and T_0 is the 1/e width of the pulse. For the above values, this equation reduces to,

$$\delta\lambda = 4.24 \times 10^{-5} \frac{n_2 P_p}{T_{FWHM}}$$

where T_{FWHM} is the full-width at half maximum of the pump pulse, and where we have used a core radius of 4 μm and a fiber sample length of 100 cm. Assuming a peak pump pulse power of 10 W, a T_{FWHM} of 95 ps and using an n_2 of $8.4 \times 10^{-17} \text{ m}^2/\text{W}$, a wavelength shift of 0.374 nm is expected. This value is clearly resolvable by the optical spectrum analyzer as illustrated in Figure 5.




Figure 5. Optical spectrum of gained switched DFB laser pulse.

III. Summary:

We have successfully fabricated samples of CdSSe-doped fibers designed for single-mode operation in the 1300 nm and 1550 nm communication wavelength region. The linear absorption coefficient of the CdSSe-doped fiber was measured to be 0.14 dB/cm. A comparison between the measured transmittance of a sample of 350 μm O.D. fiber and a bulk rod of RG630 Schott glass depicted in fig. 1 shows the two to have similar characteristics. That is, (i) the absorption edge of the fiber and the RG630 are found to be qualitatively similar and near 630 nm, and (ii) the region of maximum transmittance occurs beyond 680nm for both fiber and RG630. The transmittance remains relatively constant for wavelengths greater than 680nm. These results point to the fact that the fabrication of

the fiber yielded good samples. Also we have developed an experimental procedure to gain switched the probe signal. This capability will be employed for time synchronization of pump and probe in the switch implementation.

The measurement of the nonlinear refractive index of the fiber at 1313 nm along with the measurements performed to date will provide the information that determines the usefulness of these fiber samples in all optical switching. The results obtained to date are promising and the overall project is proceeding in accordance with stated objectives.

IV. References:

1. N. Sugimoto, Appl. Phys. Lett. **66**(8), 923 (1995).
2. M. Sheik-Bahae, *et al.*, IEEE J. Quantum Electron, **27**(6), 1296 (1991).
3. P.L. Baldeck, et al, Appl. Phys. Lett., **52** (23) 1939 (1988).

DISTRIBUTION LIST

addresses	number of copies
RAYMOND K. BONCEK ROME LABORATORY/OCPA 25 ELECTRONIC PKY ROME NY 13441-4515	5
ROME LABORATORY/CA CHIEF SCIENTIST 26 ELECTRONIC PKY ROME NY 13441-4514	1
ROME LABORATORY/SUL TECHNICAL LIBRARY 26 ELECTRONIC PKY ROME NY 13441-4514	1
ATTENTION: DTIC-OCC DEFENSE TECHNICAL INFO CENTER 8725 JOHN J. KINGMAN ROAD, STE 0944 FT. BELVOIR, VA 22060-6218	2
BALLISTIC MISSILE DEFENSE ORGANIZATION 7100 DEFENSE PENTAGON WASH DC 20301-7100	2
ROME LABORATORY/IMPS 26 ELECTRONIC PKY ROME NY 13441-4514	1
ROME LABORATORY/ERD ATTN: MR. EDWARD J. JONES 525 BROOKS RD ROME NY 13441-4505	1
RELIABILITY ANALYSIS CENTER PO BOX 4700 ROME NY 13440-8200	1

ROME LABORATORY/C3AB 1
525 BROOKS RD
ROME NY 13441-4505

ATTN: RAYMOND TADROS 1
GIDEP
P.O. BOX 8000
CORONA CA 91718-8000

ATTN: DR. CARL E. BAUM 1
PHILLIPS LAB/WSQW
3550 ABERDEEN SE
KIRTLAND AFB NM 87117-5776

ATTN: WALTER HARTMAN 1
WRIGHT LABORATORY/AAM, BLDG. 620
2241 AVIONICS CIRCLE, RM N3-F10
WRIGHT-PATTERSON AFB OH 45433-7333

AFIT ACADEMIC LIBRARY/LDEE 1
2950 P STREET
AREA B, BLDG 642
WRIGHT-PATTERSON AFB OH 45433-7765

ATTN: R.L. DENISON 1
WRIGHT LABORATORY/MLPO, BLDG. 651
3005 P STREET, STE 6
WRIGHT-PATTERSON AFB OH 45433-7707

WRIGHT LABORATORY/MTM, BLDG 653 1
2977 P STREET, STE 6
WRIGHT-PATTERSON AFB OH 45433-7739

ATTN: GILBERT G. KUPERMAN 1
AL/CFHI, BLDG. 248
2255 H STREET
WRIGHT-PATTERSON AFB OH 45433-7022

DL AL HSC/HRG, BLDG. 190 1
2698 G STREET
WRIGHT-PATTERSON AFB OH 45433-7604

AUL/LSAD 1
600 CHENNAULT CIRCLE, BLDG. 1405
MAXWELL AFB AL 36112-6424

US ARMY STRATEGIC DEFENSE COMMAND 1
CSSD-IM-PA
P.O. BOX 1500
HUNTSVILLE AL 35807-3801

NAVAL AIR WARFARE CENTER 1
6000 E. 21ST STREET
INDIANAPOLIS IN 46219-2189

COMMANDING OFFICER 1
NCCOSC RDT&E DIVISION
ATTN: TECHNICAL LIBRARY, CODE 0274
53560 HULL STREET
SAN DIEGO CA 92152-5001

COMMANDER, TECHNICAL LIBRARY 1
474700D/C0223
NAVAIRWARCENWPNDIV
1 ADMINISTRATION CIRCLE
CHINA LAKE CA 93555-6001

SPACE & NAVAL WARFARE SYSTEMS 2
COMMAND (PMW 178-1)
2451 CRYSTAL DRIVE
ARLINGTON VA 22245-5200

SPACE & NAVAL WARFARE SYSTEMS 1
COMMAND, EXECUTIVE DIRECTOR (PD13A)
ATTN: MR. CARL ANDRIANI
2451 CRYSTAL DRIVE
ARLINGTON VA 22245-5200

COMMANDER, SPACE & NAVAL WARFARE 1
SYSTEMS COMMAND (CODE 32)
2451 CRYSTAL DRIVE
ARLINGTON VA 22245-5200

CDR, US ARMY MISSILE COMMAND 2
RSIC, BLDG. 4484
AMSMI-RD-CS-R, DOCS
REDSTONE ARSENAL AL 35898-5241

ADVISORY GROUP ON ELECTRON DEVICES 1
SUITE 500
1745 JEFFERSON DAVIS HIGHWAY
ARLINGTON VA 22202

REPORT COLLECTION, CIC-14 1
MS P364
LOS ALAMOS NATIONAL LABORATORY
LOS ALAMOS NM 87545

AEDC LIBRARY 1
TECHNICAL REPORTS FILE
100 KINDEL DRIVE, SUITE C211
ARNOLD AFB TN 37389-3211

COMMANDER 1
USAISC
ASHC-IMD-L, BLDG 61801
FT HUACHUCA AZ 85613-5000

US DEPT OF TRANSPORTATION LIBRARY 1
FB10A, M-457, RM 930
800 INDEPENDENCE AVE, SW
WASH DC 22591

AIR WEATHER SERVICE TECHNICAL 1
LIBRARY (FL 4414)
859 BUCHANAN STREET
SCOTT AFB IL 62225-5118

AFIWC/MSD 1
102 HALL BLVD, STE 315
SAN ANTONIO TX 78243-7016

SOFTWARE ENGINEERING INSTITUTE 1
CARNEGIE MELLON UNIVERSITY
4500 FIFTH AVENUE
PITTSBURGH PA 15213

NSA/CSS 1
K1
FT MEADE MD 20755-6000

DCMAD/WICHITA/GKEP 1
SUITE B-34
401 N MARKET STREET
WICHITA KS 67202-2095

PHILLIPS LABORATORY 1
PL/TL (LIBRARY)
5 WRIGHT STREET
HANSCOM AFB MA 01731-3004

THE MITRE CORPORATION 1
ATTN: E. LADURE
D460
202 BURLINGTON RD
BEDFORD MA 01732

OUSD(P)/DTSA/DUTD 2
ATTN: PATRICK G. SULLIVAN, JR.
400 ARMY NAVY DRIVE
SUITE 300
ARLINGTON VA 22202

ROME LABORATORY/ERO 1
ATTN: RICHARD PAYNE
HANSCOM AFB, MA 01731-5000

ROME LABORATORY/EROC 1
ATTN: JOSEPH P. LORENZO, JR.
HANSCOM AFB, MA 01731-5000

ROME LABORATORY/EROP 1
ATTN: JOSEPH L. HORNER
HANSCOM AFB, MA 01731-5000

ROME LABORATORY/EROC 1
ATTN: RICHARD A. SOREF
HANSCOM AFB, MA 01731-5000

ROME LABORATORY/ERXE
ATTN: JOHN J. LARKIN
HANSCOM AFB, MA 01731-5000

1

ROME LABORATORY/ERDR
ATTN: DANIEL J. BURNS
525 BROOKS RD
ROME NY 13441-4505

1

ROME LABORATORY/IRAP
ATTN: ALBERT A. JAMBERDINO
32 HANGAR RD
ROME NY 13441-4114

1

ROME LABORATORY/OCP
ATTN: BRIAN M. HENDRICKSON
25 ELECTRONIC PKY
ROME NY 13441-4515

1

ROME LABORATORY/OCPC
ATTN: GREGORY J. ZAGAR
25 ELECTRONIC PKY
ROME NY 13441-4515

1

ROME LABORATORY/C3BC
ATTN: ROBERT L. KAMINSKI
525 BROOKS RD
ROME NY 13441-4505

1

ROME LABORATORY/OCP
ATTN: JAMES W. CUSACK
25 ELECTRONIC PKY
ROME NY 13441-4515

1

ROME LABORATORY/OCP
ATTN: JOANNE L. ROSSI
25 ELECTRONIC PKY
ROME NY 13441-4515

1

ROME LABORATORY/OCPA
ATTN: ANDREW R. PIRICH
25 ELECTRONIC PKY
ROME NY 13441-4515

1

ROME LABORATORY/OCP
ATTN: RICHARD J. MICHALAK
25 ELECTRONIC PKY
ROME NY 13441-4515

1

NY PHOTONIC DEVELOPMENT CORP
MVCC ROME CAMPUS
UPPER FLOYD AVE
ROME, NY 13440

1

***MISSION
OF
ROME LABORATORY***

Mission. The mission of Rome Laboratory is to advance the science and technologies of command, control, communications and intelligence and to transition them into systems to meet customer needs. To achieve this, Rome Lab:

- a. Conducts vigorous research, development and test programs in all applicable technologies;
- b. Transitions technology to current and future systems to improve operational capability, readiness, and supportability;
- c. Provides a full range of technical support to Air Force Materiel Command product centers and other Air Force organizations;
- d. Promotes transfer of technology to the private sector;
- e. Maintains leading edge technological expertise in the areas of surveillance, communications, command and control, intelligence, reliability science, electro-magnetic technology, photonics, signal processing, and computational science.

The thrust areas of technical competence include: Surveillance, Communications, Command and Control, Intelligence, Signal Processing, Computer Science and Technology, Electromagnetic Technology, Photonics and Reliability Sciences.