


4-22-74

REPORT NO. NADC-74051-30

NADC



Tech. Info.

# FINITE - ELEMENT ANALYSIS OF EDGE EFFECTS IN ANGLE - PLY COMPOSITE LAMINATES

Thomas F. Neu  
Air Vehicle Technology Department  
NAVAL AIR DEVELOPMENT CENTER  
Warminster, Pennsylvania 18974

19 March 1974

FINAL REPORT  
AIRTASK NO. A320320N/001B/3F41422000  
Work Unit No. HJ204

APPROVED FOR PUBLIC RELEASE; DISTRIBUTION UNLIMITED

DTIC QUALITY INSPECTED 8

Prepared for  
NAVAL AIR SYSTEMS COMMAND  
Department of the Navy  
Washington, D. C. 20360

7400246A

## NOTICES


REPORT NUMBERING SYSTEM - The numbering of technical project reports issued by the Naval Air Development Center is arranged for specific identification purposes. Each number consists of the Center acronym, the calendar year in which the number was assigned, the sequence number of the report within the specific calendar year, and the official 2-digit correspondence code of the Command Office or the Functional Department responsible for the report. For example: Report No. NADC-73015-40 indicates the fifteenth Center report for the year 1973, and prepared by the Crew Systems Department. The numerical codes are as follows:

CODE	OFFICE OR DEPARTMENT
00	Commander, Naval Air Development Center
01	Technical Director, Naval Air Development Center
02	Program and Fiscal Management Department
03	Anti-Submarine Warfare Program Office
04	Remote Sensors Program Office
05	Ship and Air Systems Integration Program Office
10	Naval Air Facility, Warminster
20	Aero Electronic Technology Department
30	Air Vehicle Technology Department
40	Crew Systems Department
50	Systems Analysis and Engineering Department
81	Administration and Technical Services Department
85	Computer Services Department

APPROVED BY: \_\_\_\_\_

*JR Mead*DATE: 19 March 1974

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER NADC-74051-30	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) FINITE-ELEMENT ANALYSIS OF EDGE EFFECTS IN ANGLE-PLY COMPOSITE LAMINATES		5. TYPE OF REPORT & PERIOD COVERED FINAL
		6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) Thomas F. Neu		8. CONTRACT OR GRANT NUMBER(s)
9. PERFORMING ORGANIZATION NAME AND ADDRESS Air Vehicle Technology Department Naval Air Development Center Warminster, Pa. 18974		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS A320320B/001B/4F41422206 W.U. HJ 202
11. CONTROLLING OFFICE NAME AND ADDRESS Naval Air Systems Command Department of the Navy Washington, D. C. 20361		12. REPORT DATE 19 March 1974
		13. NUMBER OF PAGES 14
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		15. SECURITY CLASS. (of this report)  UNCLASSIFIED
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Composite Materials Finite Elements Edge Effects Interlaminar Stress		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) A three-dimensional finite-element modelling and analysis technique has been developed and used in the evaluation of edge stresses in angle-ply composite laminates. Excellent results have been obtained for the initial application to a four-ply $\pm 45^\circ$ laminate in tension, and the method is potentially applicable to holes, notches and other boundaries of arbitrary geometry.		



## I N T R O D U C T I O N

The optimum design of aircraft structures and the maximum exploitation of the advantageous properties of advanced fiber reinforced materials require detailed knowledge of the stress fields within structural elements. Of particular importance are stress concentrations, for it has been indicated that they are of a different nature in composites than in conventional materials. Under reference (a), the NAVAIRDEVGEN (Naval Air Development Center) has conducted a program to evaluate the stress concentrations in composite structures.

The most basic form of stress concentration in a composite laminate is the occurrence of interlaminar shear and normal stresses near free edges, accompanied by variations in in-plane stresses. This stress concentration, often referred to as the edge effect, is caused by the heterogeneity of the laminate, and is, therefore, a characteristic more of the material than of the geometrical configuration of a structural element. The resulting perturbation of the stress field decays within a distance from the edge on the order of the laminate thickness, but may be sufficient to cause delamination and subsequent failure.

Since conventional laminate theory does not account for the edge effect, an alternate method is needed to analyze this localized phenomenon. Several approaches to the special case of a straight edge, using a variety of analytical and numerical methods, have been published. (References (b) through (f)). However, the methods used are either two-dimensional or are applicable only to straight edges. The effort at the NAVAIRDEVGEN has been the development, using NASTRAN, of a three-dimensional finite element modelling and analysis technique which can be applied to edges of arbitrary geometry, including holes and notches, and to bonded joints. The technique developed, and its application to the problem of a four-ply  $\pm 45^\circ$  laminate in tension are described in this report. The results of the analysis of this elementary case are essentially identical to those obtained by other investigators and indicate that the interlaminar shear stress between the  $+45^\circ$  and  $-45^\circ$  plies may be sufficient to cause delamination.

## PRELIMINARY ANALYSIS

Because of the availability of solutions by other methods, the finite element procedure has been first applied to the free edge of a four-ply,  $\pm 45^\circ$  boron-epoxy laminate in tension, as shown in Figure 1. It is postulated that in the middle region of the laminate, away from the areas of load introduction, there is no variation of stress, strain or lateral and transverse displacement in the longitudinal ( $x$ ) direction (parallel to the edge); only the variation of longitudinal displacement ( $\partial u / \partial x = \epsilon_x$ ) is non-zero. In addition, by introducing compatibility relations from reference (g) and setting all partial derivatives with respect to  $x$  equal to zero, it is concluded that  $\epsilon_x$  is a linear function of  $y$  and  $z$  of the form  $Ay + Bz + C$ . However, since the laminate and loading are symmetric, the linear terms must be zero, and therefore,  $\epsilon_x$  is constant over the cross section. Also because of symmetry, there are no shear stresses on the

19970604 019

mid-plane of the laminate, nor is there any displacement normal to it. The most important consequence of the lack of variation in the longitudinal direction and of the problem symmetry is that only two plies of a thin slice normal to the edge need to be modelled and analyzed. In addition, since the edge effect decays by 97 percent within a distance equivalent to the laminate thickness (four plies), the region to be analyzed extends only six ply thicknesses from the edge, to where the stress state can be determined by conventional laminate theory. The region to be analyzed, and the applicable stress, strain and displacement conditions are shown in Figure 2.

#### FINITE ELEMENT MODELLING

The grid point array of the finite element model is shown in Figure 3. To facilitate modelling the orthotropic material, the mesh is square in planform, subdivided to one-eighth ply thickness near the edge, where stress gradients are greatest. A single ply of the laminate is represented by four planes of grid points, as indicated by the shaded region in Figure 3. The grid points are interconnected by one- and two-dimensional elements -- rods, shear panels and quadrilateral membranes -- which together simulate the three-dimensional elastic behavior of the orthotropic material.

An enlarged view of the shaded region of Figure 3 is shown in Figure 4. The boron-epoxy material is modelled as two layers of epoxy separated by a fibrous layer whose thickness is equal to the fiber diameter. The properties of the fibrous layer (Table I) are derived from those of the unidirectional material and the epoxy by means of a three-dimensional laminate analysis. Since each of the layers is orthotropic, its elastic behavior can be described by nine independent stiffness coefficients (Figure 5). The stiffness represented by each coefficient is provided in the finite element model by one or more of the elements. For example, the interlaminar membranes, which are aligned parallel and normal to the fiber directions, contribute to the stiffness represented by the coefficients  $C_{13}$  and  $C_{23}$ . The transverse normal stiffness,  $C_{33}$ , and the interlaminar shear stiffnesses,  $C_{44}$  and  $C_{55}$ , are provided by the rods and shear panels.

#### LOADING AND CONSTRAINTS

The known stress and displacement conditions applicable to the analysis have been shown in Figure 2 and the constraints imposed on the model to simulate the strain/displacement conditions are listed in Table II. Zero displacement across the laminate mid-plane, the lack of variation of displacement in the longitudinal direction, and the uniform normal strain,  $\bar{\epsilon}_x$ , are enforced by means of single- and multi-point constraints. At the interior end of the model ( $23\frac{1}{4} \delta Y \leq 6h$ ), additional constraints ( $\delta U/\delta Y = \delta U/\delta Z = \delta V/\delta Z = \delta W/\delta Y = 0$ ) are applied to simulate the laminate theory solution. No forces are input. Instead, the unknown grid point forces are generated by NASTRAN as constraint forces in response to a sufficient number of known displacement conditions.

## STRESS RECOVERY

To calculate the stresses in the individual fibrous and epoxy layers, the element stresses are transformed as necessary into a common coordinate system (laminare coordinates) and added together. For example, if the longitudinal normal stress,  $\sigma_x$  is expressed as

$$\sigma_x = C_{11} \epsilon_x + C_{12} \epsilon_y + C_{16} \gamma_{xy} + C_{13} \epsilon_z$$

the first three terms are equivalent to the average of the stresses,  $\sigma_x$ , from the upper and lower in-plane membranes and the third term is the sum of the stresses (transformed) of the interlaminar membranes. The stresses obtained by this method are applicable for the middle of each layer. In-plane ply stresses are obtained as the sum of the fibrous and epoxy layer stresses, each weighted in proportion to its thickness.

$$\sigma_x^{ply} = \frac{1}{t^{ply}} (\sigma_x^{epoxy} \times t^{epoxy} + \sigma_x^{fib.} \times t^{fib.})$$

## RESULTS AND DISCUSSION

The in-plane ply stresses,  $\sigma_x$  and  $\tau_{xy}$ , and the interlaminar shear stress,  $\tau_{xz}$ , in the adjoining epoxy layers of the two plies are plotted versus distance from the laminate edge in Figure 6 and are essentially identical to those obtained by other investigators. The remaining stresses,  $\sigma_y$ ,  $\sigma_z$  and  $\tau_{yz}$ , which arise primarily from material dissimilarities between the fibrous and epoxy layers, are two orders of magnitude smaller. At the laminate edge, where the in-plane shear stress,  $\tau_{xy}$ , is zero, the longitudinal tensile stress,  $\sigma_x$ , is the same as would occur in unidirectional material loaded to the same normal strain,  $\epsilon_x$ , at 45 degrees to its fiber direction, and is 20 percent lower than in the interior. In order to maintain equilibrium, the rise of the in-plane shear,  $\tau_{xy}$ , and its asymptotic approach to the value predicted by laminate theory are accompanied by a decay of the interlaminar shear,  $\tau_{xz}$ , from its maximum value at the edge. For each of these stresses, the influence of the free edge decays by 97 percent within four ply thicknesses. From an attempt to fit the data obtained from the finite-element analysis to analytical forms, it has been found that the variation of the major stresses in the direction normal to the edge can be very precisely described by simple exponential functions, as shown below:

$$\sigma_x = \bar{\sigma}_x - (\bar{\sigma}_x - \sigma_x^0) e^{-\frac{zy}{8h}}$$

$$\tau_{xy} = \bar{\tau}_{xy} (1 - e^{-\frac{zy}{8h}})$$

$$\tau_{xz} = \tau_{xz}^0 e^{-\frac{zy}{8h}}$$

where  $h$  is the ply thickness, and the superscripted bar and zero denote values in the interior and at the edge, respectively.

The magnitude of the interlaminar shear stress at the edge, about equal to the inplane shear predicted by laminate theory for the interior, is most important, as the occurrence of so high a stress in the matrix may cause delamination and redistribution of stress leading to failure. This has been experimentally identified as a mode of failure (reference (h)) and some investigators (reference (i)) have applied fracture mechanics methods to quantitatively define failure loads for various angle-ply laminates.

### C O N C L U S I O N S   A N D   R E C O M M E N D A T I O N S

1. Finite element methods can be used in ply-by-ply analyses of local edge effects in composite laminates and will yield valid results. In the analysis described above, only the simplest one- and two-dimensional constant-strain elements were used. Even better results should be obtainable with simpler models by employing newly-developed parametric solid elements.
2. By applying supplementary analytical or numerical methods, it is possible to limit the region which must be modelled to only a small part of a structural element, as demonstrated above. Therefore, a finite-element technique similar to that used in the analysis of the straight edge is potentially applicable to boundaries of arbitrary geometry.
3. The edge effect stresses resulting from the analysis presented may be sufficient to cause delamination and subsequent redistribution of stresses within the plies.

### R E F E R E N C E S

- (a) AIRTASK A320320B/001B/4F41422206 , Work Unit HJ 202 , "Reduction of Stress Concentrations in Composite Aero Structures".
- (b) Puppo, A. H. and Evensen, H. A.: "Interlaminar Shear in Laminated Composites Under Generalized Plane Stress". J. Comp. Materials, Vol. 4, p. 204, 1970
- (c) Pipes, R. B. and Pagano, N. J.: "Interlaminar Stresses in Composite Laminates Under Uniform Axial Extension". J. Comp. Materials, Vol. 4, p. 583, 1970.
- (d) Isakson, G. and Levy, A.: "Finite-Element Analysis of Interlaminar Shear in Fibrous Composites". J. Comp. Materials, Vol. 5, p. 273, 1971.
- (e) Pagano, N. J. and Pipes, R. B.: "The Influence of Stacking Sequence on Laminate Strength". J. Comp. Materials, Vol. 5, p. 50, Jan 1971.

- (f) Rybicki, E. F.: "Approximate Three-Dimensional Solution for Symmetric Laminates Under Inplane Loading". J. Comp. Materials, Vol. 5, p. 354, Jul 1971.
- (g) Timoshenko and Goodier: "Theory of Elasticity". 2nd Ed., McGraw-Hill Books Company, 1951.
- (h) Grossman, D. T.: "Fatigue Behavior of Angle-Ply Fibrous Composite Laminates". Massachusetts Institute of Technology, May, 1971.
- (i) Lauraitis, K.: "Failure Modes and Strength of Angle-Ply Laminates". University of Illinois T.&A.M. Report No. 345, Aug 1971.

TABLE I

## MATERIAL PROPERTIES

	COMPOSITE	FIBROUS LAYER	EPOXY LAYER
$E_{11}$ , msi	20.00	26.30	0.607
$E_{22}$ , msi	2.10	2.56	0.607
$E_{33}$ , msi	2.10	3.89	0.607
$G_{12}$ , msi	0.85	1.05	0.226
$G_{13}$ , msi	0.85	1.05	0.226
$G_{23}$ , msi	0.85	1.05	0.226
$\nu_{12}$	0.21	0.20	0.340
$\nu_{13}$	0.21	0.15	0.340
$\nu_{23}$	0.21	0.11	0.340

TABLE II

## CONSTRAINTS APPLIED TO EDGE EFFECT MODEL

CONDITION*	REGION WHERE APPLIED†
$u = 0$	$x = 0; y = \frac{23h}{4}, 6h; \text{ all } z$
$v = 0$	$y = 6h; \text{ all } x, z$
$w = 0$	$z = 0; \text{ all } x, y$
$\frac{\Delta u}{\Delta x} = \bar{\epsilon}_x$	$\text{all } x, y, z$
$\frac{\Delta v}{\Delta x} = 0$	$0 \leq y \leq 6h; \text{ all } x, z$
$\frac{\Delta v}{\Delta z} = 0$	$x = 0; y = \frac{23h}{4}; \text{ all } z$
$\frac{\Delta w}{\Delta x} = 0$	$0 < z \leq 2h; \text{ all } x, y$
$\frac{\Delta w}{\Delta y} = 0$	$x = 0; \frac{23h}{4} \leq y \leq 6h; 0 < z \leq 2h$

\*u, v, w are displacements in x, y, z coordinates respectively

†h is ply thickness




FIGURE 1. FOUR-PLY  $\pm 45^\circ$  LAMINATE IN TENSION




FIGURE 2. REGION TO BE ANALYZED, SHOWING STRESS, STRAIN AND DISPLACEMENT CONDITIONS




FIGURE 3. FINITE ELEMENT MODEL





FIGURE 4. ELEMENT ASSEMBLAGE FOR A SINGLE PLY






FIGURE 6. FINITE ELEMENT ANALYSIS RESULTS FOR  $\pm 45^\circ$  LAMINATE IN TENSION STRESS (IN LAMINATE COORDINATES) VS. DISTANCE FROM EDGE

D I S T R I B U T I O N   L I S T

REPORT NO. NADC-74051-30

AIRTASK NO. A320320B/001B/4F41422206  
WORK UNIT HJ 202

	<u>No. of Copies</u>
NAVAIRSYSCOM (AIR-50174) . . . . .	15
(2 for retention)	
(1 for AIR-03B)	
(1 for AIR-320)	
(1 for AIR-320A)	
(2 for AIR-320B)	
(1 for AIR-52032D)	
(1 for AIR-5302)	
(1 for AIR-530214)	
(1 for AIR-530215)	
(1 for AIR-535)	
(1 for AIR-5351)	
(1 for AIR-53511B)	
(1 for PMA-247)	
DDC . . . . .	12
CNM (MAT-031) . . . . .	1
Battelle Columbus Laboratories, Columbus Ohio . . . . .	1
(Attn: Dr. Edmund F. Rybicki)	
Director, PLASTEC, Picatinny Arsenal, Dover, N.Y. 07801 . . . . .	1
(Attn: Librarian, Bldg. 176, SARPA-FR-M-D)	
NAVAIRDEVCCEN, Warminster, Pennsylvania 18974. . . . .	26
(3 for 813)	
(3 for 30023)	
(1 for 03)	
(1 for 20)	
(1 for 30-8)	
(1 for 40)	
(1 for 50)	
(1 for 301)	
(1 for 302)	
(1 for 303)	
(10 for 3033)	
(1 for 304)	
(1 for 305)	

7400246A