



Molecular Packing and NPT-Molecular
Dynamics Investigation of the
Transferability of the RDX
Intermolecular Potential
to 2,4,6,8,10,12-
Hexanitrohexaazaisowurtzitane (HNIW)

by Dan C. Sorescu, Donald L. Thompson
and Betsy M. Rice

ARL-TR-1657

May 1998

19980520 021

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Citation of manufacturer's or trade names does not constitute an official endorsement or approval of the use thereof.

Destroy this report when it is no longer needed. Do not return it to the originator.

Army Research Laboratory

Aberdeen Proving Ground, MD 21005-5066

ARL-TR-1657

May 1998

Molecular Packing and NPT-Molecular Dynamics Investigation of the Transferability of the RDX Intermolecular Potential to 2,4,6,8,10,12- Hexanitrohexaazaisowurtzitane (HNIW)

Dan C. Sorescu, Donald L. Thompson
Department of Chemistry, Oklahoma State University

Betsy M. Rice
Weapons and Materials Research Directorate, ARL

DTIC QUALITY INSPECTED 2

Approved for public release; distribution is unlimited.

Abstract

We have explored the degree to which an intermolecular potential for the explosive hexahydro-1,3,5-trinitro-1,3,5-s-triazine (RDX) (J. Phys. Chem. vol 101B, p. 798) is transferable for predictions of crystal structures (within the approximation of rigid molecules) of a similar chemical system, in this case, polymorphic phases of the 2,4,6,8,10,12-Hexanitrohexaazaisowurtzitane (HNIW) crystal. Molecular packing and isothermal-isobaric molecular dynamics calculations performed with this potential reproduce the main crystallographic feature of the ϵ -, β -and γ -HNIW crystals. Thermal expansion coefficients calculated using the present model predict near isotropic expansion for the ϵ - and γ -HNIW crystals phases and anisotropic expansion for β -HNIW.

Acknowledgments

This work was supported by the Strategic Environmental Research and Development Program. The authors wish to thank Dr. Richard Gilardi, U.S. Naval Research Laboratory, for kindly providing the x-ray diffraction data for HNIW. DLT gratefully acknowledges support by the U.S. Army Research Office under grant number DAAH04-93-G-0450.

INTENTIONALLY LEFT BLANK.

Table of Contents

	<u>Page</u>
Acknowledgments	iii
List of Figures	vii
List of Tables	vii
1. Introduction	1
2. Intermolecular Interaction Potential	2
2.1 Details of the Calculations	4
2.1.1 <i>MP Calculations</i>	4
2.1.2 <i>Isothermal-Isobaric Molecular Dynamics Calculations</i>	6
2.2 Results and Discussions	6
2.2.1 <i>MP Calculations</i>	6
2.2.2 <i>NPT Molecular Dynamics Calculations</i>	8
3. Conclusion	13
4. References	19
Distribution List	21
Report Documentation Page	23

INTENTIONALLY LEFT BLANK.

List of Figures

<u>Figure</u>	<u>Page</u>
1. Molecular Configuration of HNIW	3
2. Comparison of the Time-Averaged Mass Center Fractional Positions and Euler Angles (X-Convention [12]) With Experimental Results at 300 K and 0 atm for the ϵ Phase	9
3. Radial Distribution Function (RDF) for Mass-Center–Mass-Center Pairs as Functions of Temperature for the ϵ Phase	13
4. Unit Cell Edge Lengths and Volumes as Functions of Temperature for ϵ -HNIW (Upper Frames); β -HNIW (Middle Frames); and γ -HNIW (Lower Frames)	14

List of Tables

<u>Table</u>	<u>Page</u>
1. Electrostatic Charges for the HNIW Molecule	5
2. Lattice Parameters for Polymorphs of HNIW	7
3. Average Values of the Fractional Coordinates and Euler Angles (X-Convention) of the Molecular Mass Center Calculated From Trajectories at 4.2 and 300 K	11
4. Average Values of the Fractional Coordinates and Euler Angles (X-Convention) of the Molecular Mass Center Calculated From Trajectories at 4.2 and 300 K With the Corresponding Values Determined for the Experimental Geometries ...	12
5. Parameters for Linear Fits in Temperature and Thermal Expansion Coefficients (T = 300 K) of Unit Cell Edge Lengths and Volumes	15
6. Calculated NPT-MD Lattice Dimensions at Various Temperatures	16

INTENTIONALLY LEFT BLANK.

1. Introduction

Satisfying ever-increasing demands for inexpensive, efficient, and rapid development of high-performing energetic materials is extremely challenging. Synthesis and testing of energetics is often costly, dangerous, and time consuming; thus, a screening mechanism is needed to reduce unnecessary measurements on unsuitable candidate materials. Such screening can be accomplished through the application of theoretical chemical models. These models can be used to predict simple thermodynamic properties of the candidates, such as heats of formation or the density of the material, which are sufficient to aid formulators in decisions of whether a candidate energetic material warrants further investigation. Due to timely advances in parallel computer architectures, there is great promise that atomistic modeling will become integral to the development process. In addition to being efficient screening tools, theoretical chemical models can also provide atomic-level information that could not otherwise be readily obtained through measurement.

Our efforts at developing accurate predictive models of energetic crystals have included the development of an intermolecular potential that describes the structure of the α -form of the hexahydro-1,3,5-trinitro-1,3,5-*s*-triazine (RDX) crystal, one of the most commonly used explosives [1]. The potential energy function that describes the system is composed of pairwise atom-atom (6-exp) Buckingham interactions with explicit inclusion of the electrostatic interactions between the charges associated with various atoms of different molecules. The parameterization of the potential function was done such that molecular packing (MP) calculations reproduce the experimental structure of the crystal and its lattice energy. Isothermal-isobaric molecular dynamics (NPT-MD) simulations using this potential energy function predicted crystal structures in excellent agreement with experiment. The main limitation of the model is due to the assumption of rigid molecules. Nevertheless, it can be used to study processes at temperatures and pressures where molecular deformations are negligible.

The development of a simple model that accurately represents a specific chemical system is significant. However, the utility of the model is substantially enhanced if it reasonably represents



a series of chemical systems rather than a single one. This investigation explores the degree of transferability of the RDX crystal potential energy function [1] to another cyclic nitramine crystal—that is, the new explosive, 2,4,6,8,10,12-hexanitrohexaazaisowurtzitane (HNIW) (see Figure 1).

HNIW, a polycyclic nitramine, has been characterized as “the densest and most energetic explosive known” [2]. It exists in at least five polymorphic states [3], four of which (α -hydrate, ϵ , β , and γ) are stable at ambient conditions and have been resolved by x-ray diffraction [4]. The α -hydrate phase has an orthorhombic structure with $Pbca$ symmetry and with $Z = 8$ molecules per unit cell;* the ϵ polymorph crystallizes in the $P2_1/n$ space group and has $Z = 4$ molecules per unit cell; β -HNIW has $Pb2_1a$ symmetry, with $Z = 4$ molecules per unit cell; and the γ phase has $P2_1/n$ symmetry, with $Z = 4$ molecules per unit cell. Figure 1 illustrates these polymorphs of HNIW; the ζ polymorph is evident at high pressure, but its crystal structure has not yet been resolved [4]. As evident in the figure, the molecular structure of the polymorphs differ mainly in the orientation of the nitro groups relative to the ring. Two different rankings of the relative stabilities of these polymorphs have been proposed: α -hydrate $> \epsilon > \alpha$ -anhydrous $> \beta > \gamma$ [5] and $\epsilon > \gamma > \alpha$ -hydrate $> \beta$ [6].

2. Intermolecular Interaction Potential

For this study, we use the same values of the 6-exp potential parameters as in the RDX study [1]. The Coulombic terms are determined by fitting partial charges centered on each atom of the HNIW molecule to a quantum mechanically derived electrostatic potential, performed at the HF/6-31G** level as described in the earlier study [1]. For the treatment of different phases of the HNIW crystal, we also assume that there exists a transferability of the electrostatic charges. Consequently, we have used in all calculations a single set of atom-centered charges determined for an HNIW molecule with

* The x-ray diffraction data correspond to the hydrated crystal, in which the number and orientation of the water molecules are not resolved [7].



ε-HNIW

β-HNIW

α, γ-HNIW

Figure 1. Molecular Configuration of HNIW. Atom Labels Are Consistent With the Indices Given in Table 1. Structures in the Lower Portion of the Figure Illustrate the Differences Between the Polymorphic Phases; the Hydrogen Atoms Are Not Shown for Clarity.

atomic arrangement consistent with the crystallographic configuration of the α - polymorph [4].* The resulting electrostatic charges are given in Table 1, and the parameters for the 6-exp terms are given in Sorescu, Rice, and Thompson [1].

2.1 Details of the Calculations. The tests of this potential were done by MP calculations with and without symmetry constraints and NPT-MD simulations at zero pressure over the temperature range 4.2–425 K for the ϵ , β , and γ polymorphs of HNIW. We do not report results of α -HNIW, since no x-ray diffraction data are available for the anhydrous form of this polymorph. Also, the x-ray diffraction data for α -hydrate HNIW is incomplete.** Thus, a suitable comparison between theoretical predictions and experiment for α -HNIW is not possible at this time. In all calculations reported in this study, the crystal is represented as an ensemble of rigid molecules. The independent degrees of freedom are the six unit cell constants (a , b , c , α , β , γ), the three rotations (θ_1 , θ_2 , θ_3), and the three translations (τ_1 , τ_2 , τ_3) for every molecule considered in the simulation. Details of the MP and NPT-MD calculations are described in Sorescu, Rice, and Thompson [1] and are briefly summarized in following text.

2.1.1 MP Calculations. Two series of MP calculations (minimizations of the lattice energy with respect to the structural degrees of freedom of the crystal) were performed. In the first series, using the program PCK91 [8], the space-group symmetries of the crystals were maintained throughout the energy minimization. In these calculations, all three dimensions of the unit cell and the three rotations and translations of the molecule in the asymmetric unit were allowed to vary, except for the case of the β -phase, where the translation along the b axis was frozen due to the symmetry restrictions. The cell angles α , β , and γ were frozen at 90° for the calculations of the β -polymorph. For the ϵ - and γ -polymorphs, the angle β of the unit cell was allowed to vary, and α and γ were

* MP (PCK91) calculations using HF/6-31G** atomic charges determined for HNIW with molecular arrangements consistent with the β - and γ - polymorphic crystallographic configurations predict lattice parameters similar to those that use HF/6-31G** atomic charges assuming the α -hydrate HNIW molecular configuration. Cell edge lengths differ by no more than 0.015 Å, and cell angles differ by less than 0.17° . The electrostatic energies differ by less than 5 kJ/mol.

** The x-ray diffraction data correspond to the hydrated crystal, in which the number and orientation of the water molecules are not resolved [7].

Table 1. Electrostatic Charges for the HNIW Molecule

Atom ^a	Charge/ e	Atom ^a	Charge/ e
C1	0.256850	O1	-0.362942
C2	0.183418	O2	-0.369093
C3	0.020184	O3	-0.395097
C4	0.089133	O4	-0.377983
C5	0.548294	O5	-0.357808
C6	0.368468	O6	-0.431362
N1	-0.196698	O7	-0.395640
N2	0.680596	O8	-0.372372
N3	-0.357766	O9	-0.401700
N4	0.786509	O10	-0.416611
N5	-0.326781	O11	-0.381535
N6	0.754647	O12	-0.425342
N7	-0.391804	H1	0.112444
N8	0.753909	H2	0.117717
N9	-0.577874	H3	0.182501
N10	0.844354	H4	0.201482
N11	-0.234524	H5	0.081152
N12	0.696675	H6	0.094597

^a The atom indices are consistent with the labels in Figure 1.

frozen at 90°. The positions and orientations of all other molecules in the unit cell are determined through symmetry operations relative to the molecule in the asymmetric unit.

A second series of MP calculations were performed in which the crystal symmetries are not constrained; the methods are described in our previous paper [1], and the algorithm used is that in

the program LMIN [9]. In these calculations, the cutoff parameters P and Q [1] were set equal to 17.5 and 18.0, respectively.

2.1.2 Isothermal-Isobaric Molecular Dynamics Calculations. Simulations of the ϵ -, β -, and γ - phases of the HNIW crystal at various temperatures in the range 4.2–425 K and at zero pressure were performed using the algorithm proposed by Nosé and Klein [10] as implemented in the program MDCSPC [11]. Details of the calculations are given in Sorescu, Rice, and Thompson [1] and remain the same, with the following exceptions: The MD simulation cell consists of a box containing 12 ($3 \times 2 \times 2$), 27 ($3 \times 3 \times 3$), and 12 ($2 \times 3 \times 2$) crystallographic unit cells for phases ϵ , β , and γ , respectively. The lattice sums were calculated in all dimensions in these simulations. The interactions were determined between the sites in the simulation box and the nearest-image sites within the cutoff distance. The cutoff distances are $R_{\text{cut}} = 10.01 \text{ \AA}$, $11.61 \text{ \AA}$, and $9.80 \text{ \AA}$ for phases ϵ , β and γ , respectively. For simulations at 4.2 K, the initial positions of the atoms are identical to those in the experimental structures. The equations of motion were integrated for 2,000 time steps ($1 \text{ time step} = 2 \times 10^{-15} \text{ s}$) to equilibrate the system. After the equilibration, an additional 5,000 (for temperatures below 300 K) or 8,000 (for temperatures between 300 and 425 K) steps were integrated, during which average properties were calculated. In subsequent runs for successively higher temperatures, the initial atomic positions and velocities are identical to those obtained at the end of the preceding lower-temperature simulation. The velocities were scaled over an equilibration period of 2,000 steps, in order to achieve the desired external temperature and pressure, followed by the 5,000- or 8,000-step integration for calculation of averages. The cumulative mass-center radial distribution functions (RDF) and averages are calculated for the mass centers and Euler angles of the molecules. The RDFs and averages were obtained from values calculated at every tenth step during the trajectory integrations.

2.2 Results and Discussions.

2.2.1 MP Calculations. The results of the MP calculations with (denoted as LMIN) and without (denoted PCK91) symmetry constraints are given in Table 2. The relaxation of the symmetry conditions has a very small effect on the final geometric parameters, and both sets of MP

Table 2. Lattice Parameters for Polymorphs of HNIW^a

Lattice Parameter	Experiment [4]	PCK91	LMIN	NPT-MD ^b	
				4.2 K	300 K
ε-HNIW					
a (Å)	8.8278	8.7973 (−0.4)	8.7948 (−0.4)	8.7953 (−0.4)	8.8420 (0.2)
b (Å)	12.5166	12.4986 (−0.1)	12.4999 (−0.1)	12.5006 (−0.1)	12.5837 (0.5)
c (Å)	13.3499	13.4071 (−0.4)	13.4055 (0.4)	13.4066 (0.4)	13.4897 (1.0)
α (°)	90.000	90.000 ^c	89.998 (0.0)	90.000 (0.0)	89.999 (0.0)
β (°)	106.752	105.150 (−1.5)	105.137 (−1.5)	105.134 (−1.5)	105.377 (−1.3)
γ (°)	90.000	90.000 ^c	90.001 (0.0)	90.000 (0.0)	90.012 (0.0)
β-HNIW					
a (Å)	9.6764	9.5242 (−1.6)	9.5239 (−1.6)	9.5272 (−1.5)	9.6106 (−0.7)
b (Å)	13.0063	12.8726 (−1.0)	12.8728 (−1.0)	12.7485 (2.0)	12.9316 (−0.6)
c (Å)	11.6493	11.7025 (0.5)	11.7020 (0.4)	11.7050 (0.5)	11.7566 (0.9)
α (°)	90.000	90.000 ^c	90.000 (0.0)	89.999 (0.0)	90.009 (0.0)
β (°)	90.000	90.000 ^c	89.999 (0.0)	90.000 (0.0)	90.009 (0.0)
γ (°)	90.000	90.000 ^c	90.000 (0.0)	90.000 (0.0)	89.999 (0.0)
γ-HNIW					
a (Å)	13.2310	13.4342 (1.5)	13.4348 (1.5)	13.4370 (−1.6)	13.5144 (2.1)
b (Å)	8.1700	7.9095 (−3.2)	7.9074 (−3.2)	7.9092 (−3.2)	7.9690 (−2.5)
c (Å)	14.8760	14.8531 (−0.2)	14.8519 (−0.2)	14.8548 (−0.1)	14.9413 (0.4)
α (°)	90.000	90.000 ^c	90.000 (0.0)	90.000 (0.0)	89.986 (0.0)
β (°)	109.170	108.84 (0.3)	108.734 (−0.4)	108.863 (−0.3)	109.064 (−0.1)
γ (°)	90.000	90.000 ^c	90.001 (0.0)	90.000 (0.0)	90.013 (0.0)

^a Percent deviations from experiment in parentheses.^b Time-averaged values (see text).^c Fixed throughout calculation.

calculations predict almost identical structures. Deviations of the cell lengths from experiment are less than 0.4%, 1.6%, and 3.2% for the ϵ , β , and γ phases, respectively. For those crystal symmetries in which the β cell angle was allowed to vary during minimization (the ϵ and γ phases), deviations of this angle from experiment are no greater than 1.5%. Lattice energies per molecule for the ϵ , β , and γ -HNIW phases (-210.47 kJ/mol, -207.43 kJ/mol, and -201.42 kJ/mol, respectively) support the polymorph stability ranking of $\epsilon > \beta > \gamma$ given by Russell et al. [5]. Small differences in the total lattice energies (<0.5 kJ/mol) between the constrained and unconstrained calculations are due to the fact that the unconstrained simulations do not use the accelerated convergence method for evaluation of the $\frac{1}{r^6}$ lattice sums.

2.2.2 NPT Molecular Dynamics Calculations. The analysis of time histories (not shown) of the lattice parameters (a , b , c , α , β , and γ) indicate that these properties are well behaved after the equilibrium is reached (i.e., each parameter oscillates about the average value for the duration of the trajectory). Time histories of the rotational and translational temperatures and for the pressure show similar behavior, indicating that the system is at thermodynamic equilibrium.

The crystal structure information resulting from NPT-MD simulations at zero pressure, $T = 4.2$ and 300 K, is given in Table 2. The lattice dimensions obtained at $T = 4.2$ K are in very close agreement with those determined in the MP calculations. This is expected, since the thermal effects at 4.2 K should be minimal and the thermal averages at this temperature should be close to the values corresponding to the potential energy minimum. At 300 K, the average lattice dimensions agree very well with the experimental values—the corresponding differences for a , b , and c cell lengths being, respectively, 0.2%, 0.5%, and 1.0% for the ϵ phase; 0.7%, 0.6% and 0.9% for the β phase; and 2.1%, 2.5%, and 0.4% for the γ phase. For the ϵ and γ phases, the variations of the unit cell angle β from the experimental values are 1.3% and 0.1%, respectively, while the other two angles of the unit cell remain approximately equal to 90° . For the β phase, all three crystallographic angles remain approximately equal to 90° , in agreement with experiment.

Figure 2 provides a visual comparison of the average mass-center fractionals and Euler angles for each of the four molecules within the unit cell of ϵ -HNIW with experimental values; the data for




Figure 2. Comparison of the Time-Averaged Mass Center Fractional Positions and Euler Angles (X-Convention [12]) With Experimental Results at 300 K and 0 atm for the ϵ Phase. These Time Averages for Each Molecule in the Unit Cell Are Over All Unit Cells in the Simulation Box.

the three polymorphs of HNIW are given in Tables 3 and 4. Increasing the temperature from 4.2 to 300 K does not produce any significant displacement of the molecular mass-centers or increase the degree of rotational disorder. In addition, there is a slightly better agreement with experiment for the orientational parameters and fractional coordinates of the molecules at 300 K than at lower temperatures.

Similar good agreement with experiment exists for predictions of β - and γ -HNIW (not shown). The largest deviation between experiment and predictions of molecular orientation occurs for the Euler angle Φ for γ -HNIW; the predicted value is 4.4° larger than the experimental value.

The mass-center–mass-center RDFs for the ϵ polymorph (Figure 3) exhibit well-ordered structures with correlation at long distances at higher temperatures. The positions of the major peaks do not change significantly, and the main temperature effect is the broadening of the peaks and partial overlapping of some of them. The features of the RDFs for the β and γ phases are similar to those shown in Figure 3.

Finally, the cell edge lengths and volumes have a linear dependence on temperature over the range 4.2–425 K, as evident in Figure 4. Linear and volume thermal expansion coefficients are determined from linear least-squares fits to these data, the parameters of which are listed in Table 5. The linear and volume expansion coefficients,

$$C_x = \frac{1}{X} \left(\frac{\partial X}{\partial T} \right), \quad (1)$$

where X denotes cell edge lengths a , b , or c or volume V and C_x is the corresponding thermal expansion coefficient, were calculated at $T = 300$ K; they are given in Table 5 for the three polymorphic phases. The results indicate a near isotropic thermal expansion for the ϵ and γ phases (coefficients are within $\sim 20\%$ of one another), and anisotropic expansion for β -HNIW. For β -HNIW, the linear expansion coefficient for cell edge a is $\sim 70\%$ larger than those for b and c . The volume expansion coefficients for the three polymorphs have similar values ($\sim 6 \times 10^{-5} \text{ K}^{-1}$). At

Table 3. Average Values of the Fractional Coordinates and Euler Angles (X-Convention^a) of the Molecular Mass Center Calculated From Trajectories at 4.2 and 300 K

Molecule	Sx			Sy			Sz		
	T = 4.2 K	T = 300 K	Expt	T = 4.2 K	T = 300 K	Expt	T = 4.2 K	T = 300 K	Expt
ϵ Phase									
1	0.967094	0.967903	0.968537	0.142322	0.141202	0.135782	0.246169	0.263756	0.259561
2	0.532906	0.531829	0.531462	0.642323	0.641145	0.635782	0.235832	0.236223	0.240438
3	0.032906	0.032066	0.031462	0.857679	0.858830	0.864217	0.735830	0.736208	0.740438
4	0.467094	0.468202	0.468537	0.357677	0.358823	0.364217	0.764169	0.763813	0.759561
β Phase									
1	0.003646	0.005167	0.004240	0.914129	0.914117	0.914129	0.757011	0.757211	0.756694
2	0.996353	0.994912	0.995759	0.414127	0.414144	0.414129	0.242990	0.242788	0.243305
3	0.496347	0.494896	0.495759	0.414130	0.414113	0.414129	0.757018	0.757044	0.756694
4	0.503653	0.505025	0.504240	0.914132	0.914144	0.914129	0.242981	0.242957	0.243305
γ Phase									
1	0.509076	0.509185	0.512343	0.371690	0.373221	0.387670	0.259585	0.259383	0.260171
2	0.990923	0.990925	0.987656	0.871684	0.873338	0.887670	0.240417	0.240620	0.239824
3	0.490924	0.490780	0.487656	0.628308	0.626735	0.612329	0.740412	0.740575	0.739824
4	0.009077	0.009110	0.012343	0.128319	0.126705	0.112329	0.759586	0.759422	0.760175

^a Goldstein [12].

Table 4. Average Values of the Fractional Coordinates and Euler Angles (X-Convention^a) of the Molecular Mass Center Calculated From Trajectories at 4.2 and 300 K With the Corresponding Values Determined for the Experimental Geometries

Molecule		Φ ($^{\circ}$)			Θ ($^{\circ}$)			Ψ ($^{\circ}$)		
		T = 4.2 K	T = 300 K	Expt	T = 4.2 K	T = 300 K	Expt	T = 4.2 K	T = 300 K	Expt
ϵ Phase	1	-106.06	-106.32	-106.81	40.40	40.54	41.39	67.45	67.67	67.54
	2	106.06	106.26	106.81	139.59	139.45	138.60	-112.54	-112.33	-112.45
	3	-106.06	-106.32	-106.81	40.40	40.54	41.39	67.45	67.66	67.54
	4	106.06	106.23	106.81	139.59	139.45	138.60	-112.54	-112.37	-112.40
β Phase	1	112.59	112.99	111.92	35.50	35.59	35.21	-81.59	-81.88	-80.95
	2	-112.58	-113.07	-111.92	144.49	144.39	144.78	98.41	98.04	99.04
	3	67.40	69.95	68.07	144.49	144.37	144.78	98.41	98.10	99.04
	4	-67.40	-66.86	-68.07	35.50	35.64	35.21	-81.59	-81.93	-80.95
γ Phase	1	-152.20	-152.06	147.88	12.82	13.13	13.03	-178.52	-178.19	-176.78
	2	152.20	152.26	147.88	167.17	166.86	166.96	1.47	1.98	3.21
	3	-152.20	-152.05	-147.88	12.83	13.12	13.03	-178.52	-178.12	-176.78
	4	152.20	151.95	147.88	167.17	166.85	166.96	1.47	1.70	3.21

^a Goldstein [12].




Figure 3. Radial Distribution Function (RDF) for Mass-Center–Mass-Center Pairs as Functions of Temperature for the ϵ Phase.

present, no experimental data are available to which the calculated thermal coefficients can be compared, and it is hoped that these results will stimulate measurement of these properties.

3. Conclusion

We have performed MP and NPT-MD simulations of three phases (ϵ , β , and γ) of the 2,4,6,8,10,12-hexanitrohexaazaisowurtzitane (HNIW) crystal using 6-exp Buckingham potentials developed for the RDX crystal [1], plus Coulombic interactions using electrostatic charges determined from fits to ab initio electrostatic potentials calculated at the HF/6-31G** level. MP calculations with and without symmetry constraints show good agreement between predicted geometrical parameters and experimental values for all three phases. Additionally, the calculations




Figure 4. Unit Cell Edge Lengths and Volumes as Functions of Temperature for ϵ -HNIW (Upper Frames); β -HNIW (Middle Frames); and γ -HNIW (Lower Frames). The Symbols Denote Time Averages, and the Solid Curves Are Linear Fits of the Points (Coefficients Given in Table 6).

Table 5. Parameters for Linear Fits in Temperature^a and Thermal Expansion Coefficients (T = 300 K) of Unit Cell Edge Lengths and Volumes

Cell Parameter	ϵ -HNIW			β -HNIW			γ -HNIW		
	χ_0^b	χ_1^c	Expansion Coef. (K ⁻¹) ^c	χ_0^b	χ_1^c	Expansion Coef. (K ⁻¹) ^c	χ_0^b	χ_1^c	Expansion Coef. (K ⁻¹)
a	8.7939	1.5537×10^{-4}	1.76×10^{-5}	9.5234	2.8119×10^{-4}	2.93×10^{-5}	13.4285	2.8185×10^{-4}	2.09×10^{-5}
b	12.4982	2.8271×10^{-4}	2.25×10^{-5}	12.8702	2.1988×10^{-5}	1.70×10^{-5}	7.9091	1.9651×10^{-4}	2.47×10^{-5}
c	13.4050	2.876×10^{-4}	2.13×10^{-5}	11.7011	1.9738×10^{-5}	1.68×10^{-5}	14.8493	3.043×10^{-4}	2.03×10^{-5}
V	1422.253	8.2276×10^{-2}	5.69×10^{-5}	1434.150	9.1771×10^{-2}	6.28×10^{-5}	1492.486	9.3136×10^{-2}	6.13×10^{-5}

^a $X = \chi_0 + \chi_1 T$, $X = a, b, c$, or V .

^b Units of Å for a, b, and c; units of Å³ for volume V.

^c Units of Å/K for a, b, and c; units of Å³/K for volume V.

Table 6. Calculated NPT-MD Lattice Dimensions at Various Temperatures

Polymorphic Phase	T (K)	a (Å)	b (Å)	c (Å)	Volume (Å ³)
ϵ Phase	4.2	8.7953	12.5006	13.4066	1422.8883
	100.0	8.8088	12.5232	13.4325	1429.8001
	200.0	8.8247	12.5568	13.4648	1439.1609
	273.1	8.8348	12.5751	13.4841	1444.5670
	300.0	8.8420	12.5837	13.4897	1447.1754
	325.0	8.8446	12.5903	13.4959	1448.8157
	350.0	8.8467	12.5976	13.5048	1450.8332
	375.0	8.8548	12.6056	13.5128	1453.9118
	400.0	8.8552	12.6083	13.5182	1454.5415
	425.0	8.8598	12.6189	13.5298	1457.2820
β Phase	4.2	9.5272	12.8748	11.7050	1435.7761
	100.0	9.5513	12.8904	11.7188	1442.8274
	200.0	9.5776	12.9143	11.7417	1452.3071
	273.1	9.5954	12.9285	11.7520	1457.8772
	300.0	9.6105	12.9316	11.7566	1461.0940
	330.0	9.6116	12.9385	11.7653	1463.1166
	350.0	9.6269	12.9467	11.7715	1467.1411
	375.0	9.6270	12.9570	11.7746	1468.7066
	400.0	9.6359	12.9591	11.7832	1471.3920
	425.0	9.6462	12.9671	11.7867	1474.2993

Table 6. Calculated NPT-MD Lattice Dimensions at Various Temperatures (continued)

Polymorphic Phase	T (K)	a (Å)	b (Å)	c (Å)	Volume (Å ³)
γ Phase	4.2	13.4370	7.9092	14.8548	1493.9136
	100.0	13.4535	7.9281	14.8786	1501.3136
	200.0	13.4771	7.9490	14.9036	1509.8282
	273.1	13.5038	7.9643	14.9318	1517.8931
	300.0	13.5144	7.9690	14.9413	1520.8156
	325.0	13.5205	7.9740	14.9510	1523.1271
	350.0	13.5232	7.9755	14.9510	1523.9162
	375.0	13.5296	7.9840	14.9635	1527.2047
	400.0	13.5515	7.9868	14.9705	1530.8599
	425.0	13.5500	7.9915	14.9824	1532.3298

indicate a stability ranking order $\epsilon > \beta > \gamma$ in agreement with experimental measurement [5]. Predictions of crystal parameters at room temperature and zero pressure agree with the experimental unit cell dimensions to within 1.0% for phase ϵ , 0.9% for phase β , and 2.5% for phase γ . Additionally, little rotational or translational disorder occurs in thermal, unconstrained trajectories.

Temperature dependencies of the physical parameters of the lattice at zero pressure over the temperature range 4.2–425 K indicate that thermal expansion of the three crystalline polymorphs is nearly isotropic for ϵ - and γ -HNIW and is anisotropic for β -HNIW.

The success of the present potential energy parameters in describing different phases of the HNIW crystal at moderate temperatures and low pressures provides incentive to further investigate the transferability of this model to other cyclic nitramine systems (e.g., HMX) and more dissimilar energetic crystals (TNT, TATB). Future work will be directed at determining the degree to which this potential energy function is transferable to other energetic materials. Incorporation of intramolecular motion by relaxing the rigid molecular model will also be investigated.

INTENTIONALLY LEFT BLANK.

4. References

1. Sorescu, D. C., Rice, B. M., Thompson, D. L. *Journal of Physical Chemistry*. Vol. 101B, p. 798, 1997.
2. Miller, R. S. "Decomposition, Combustion and Detonation Chemistry of Energetic Materials." *Materials Research Society Symposium Proceedings*. Vol. 418, p. 3, edited by T. B. Brill, T. P. Russell, W. C. Tao, and R. B. Wardle, Materials Research Society, Pittsburgh, PA, 1995.
3. Filliben, J. D. (editor). *Solid Propellant Ingredients Manual*. Publication Unit 89, CPIA/M3 Chemical Propulsion Information Agency, Columbia, MD, 1997.
4. Chan, M. L., P. Carpenter, R. Hollins, M. Nadler, A. T. Nielsen, R. Nissan, D. J. Vanderah, R. Yee, and R. D. Gilardi. CPIA-PUB-625, Abstract No. X95-07119, AD D606 761, Chemical Propulsion Information Agency, Columbia, MD, April 1995.
5. Russell, T. P., P. J. Miller, G. J. Piermarini, S. Block, R. Gilardi, and C. George. CPIA Abstract No. 92, 0149, AD D604 542, C-D, AD-C048 931 (92-0134), p. 155, Chemical Propulsion Information Agency, Columbia, MD, April 1991.
6. Foltz, M. F., C. L. Coon, F. Garcia, and A. L. Nichols III. AD-C049 633L (93-0001), Contract W-7405-ENG-48, CPIA Abstract No. 93-0003, AD D605 199, U-D, p. 9, Chemical Propulsion Information Agency, Columbia, MD, April 1992.
7. Gilardi, R. D. Private communication. U.S. Naval Research Laboratory, Washington, DC, 1996.
8. Williams, D. E. A Crystal Molecular Packing Analysis Program, PCK91, Department of Chemistry, University of Louisville, Louisville, KY.
9. Gibson, K. D., and H. A. Scheraga. *LMIN: A Program for Crystal Packing*. QCPE No. 664S.
10. Nosé, S., and M. L. Klein. *Molecular Physics*. Vol. 50, p. 1055, 1983.
11. Smith, W. A Program for Molecular Dynamics Simulations of Phase Changes. MDCSPC, Version 4.3, CCP5 Program Library (SERC), May 1991.
12. Goldstein, H. *Classical Mechanics*. Reading, MA: Addison-Wesley, 1980.

INTENTIONALLY LEFT BLANK.

NO. OF
COPIES ORGANIZATION

2 DEFENSE TECHNICAL
INFORMATION CENTER
DTIC DDA
8725 JOHN J KINGMAN RD
STE 0944
FT BELVOIR VA 22060-6218

1 HQDA
DAMO FDQ
DENNIS SCHMIDT
400 ARMY PENTAGON
WASHINGTON DC 20310-0460

1 DPTY ASSIST SCY FOR R&T
SARD TT F MILTON
RM 3EA79 THE PENTAGON
WASHINGTON DC 20310-0103

1 OSD
OUSD(A&T)/ODDDR&E(R)
J LUPO
THE PENTAGON
WASHINGTON DC 20301-7100

1 CECOM
SP & TRRSTRL COMMCTN DIV
AMSEL RD ST MC M
H SOICHER
FT MONMOUTH NJ 07703-5203

1 PRIN DPTY FOR TCHNLGY HQ
US ARMY MATCOM
AMCDCG T
M FISETTE
5001 EISENHOWER AVE
ALEXANDRIA VA 22333-0001

1 DPTY CG FOR RDE HQ
US ARMY MATCOM
AMCRD
BG BEAUCHAMP
5001 EISENHOWER AVE
ALEXANDRIA VA 22333-0001

1 INST FOR ADVNCD TCHNLGY
THE UNIV OF TEXAS AT AUSTIN
PO BOX 202797
AUSTIN TX 78720-2797

NO. OF
COPIES ORGANIZATION

1 GPS JOINT PROG OFC DIR
COL J CLAY
2435 VELA WAY STE 1613
LOS ANGELES AFB CA 90245-5500

1 ELECTRONIC SYS DIV DIR
CECOM RDEC
J NIEMELA
FT MONMOUTH NJ 07703

3 DARPA
L STOTTS
J PENNELLA
B KASPAR
3701 N FAIRFAX DR
ARLINGTON VA 22203-1714

1 US MILITARY ACADEMY
MATH SCI CTR OF EXCELLENCE
DEPT OF MATHEMATICAL SCI
MDN A MAJ DON ENGEN
THAYER HALL
WEST POINT NY 10996-1786

1 DIRECTOR
US ARMY RESEARCH LAB
AMSRL CS AL TP
2800 POWDER MILL RD
ADELPHI MD 20783-1145

1 DIRECTOR
US ARMY RESEARCH LAB
AMSRL CS AL TA
2800 POWDER MILL RD
ADELPHI MD 20783-1145

3 DIRECTOR
US ARMY RESEARCH LAB
AMSRL CI LL
2800 POWDER MILL RD
ADELPHI MD 20783-1145

ABERDEEN PROVING GROUND

4 DIR USARL
AMSRL CI LP (305)

NO. OF
COPIES ORGANIZATION

ABERDEEN PROVING GROUND

16 DIR, USARL
 AMSRL WM B
 A HORST
 AMSRL WM BD
 B RICE (15 CP)

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE May 1998		3. REPORT TYPE AND DATES COVERED Final, Jun - Oct 97
4. TITLE AND SUBTITLE Molecular Packing and NPT-Molecular Dynamics Investigation of the Transferability of the RDX Intermolecular Potential to 2,4,6,8,10,12-Hexanitrohexaazaisowurtzitane (HNIW)			5. FUNDING NUMBERS IL161102AH43	
6. AUTHOR(S) Dan C. Sorescu, Donald L. Thompson, and Betsy M. Rice				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) U.S. Army Research Laboratory ATTN: AMSRL-WM-BD Aberdeen Proving Ground, MD 21005-5069			8. PERFORMING ORGANIZATION REPORT NUMBER ARL-TR-1657	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)			10. SPONSORING/MONITORING AGENCY REPORT NUMBER	
11. SUPPLEMENTARY NOTES				
12a. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution is unlimited.			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) We have explored the degree to which an intermolecular potential for the explosive hexahydro-1,3,5-trinitro-1,3,5-s-triazine (RDX) is transferable for predictions of crystal structures (within the approximation of rigid molecules) of a similar chemical system—in this case, polymorphic phases of the 2,4,6,8,10,12-hexanitrohexaazaisowurtzitane (HNIW) crystal. Molecular packing and isothermal-isobaric molecular dynamics calculations performed with this potential reproduce the main crystallographic feature of the ϵ -, β -, and γ -HNIW crystals. Thermal expansion coefficients calculated using the present model predict near isotropic expansion for the ϵ - and γ -HNIW crystal phases and anisotropic expansion for β -HNIW.				
14. SUBJECT TERMS molecular dynamics, intermolecular potential, crystal packing, HNIW			15. NUMBER OF PAGES 26	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT UL	

INTENTIONALLY LEFT BLANK.

USER EVALUATION SHEET/CHANGE OF ADDRESS

This Laboratory undertakes a continuing effort to improve the quality of the reports it publishes. Your comments/answers to the items/questions below will aid us in our efforts.

1. ARL Report Number/Author ARL-TR-1657 (Sorescu) Date of Report May 1998

2. Date Report Received _____

3. Does this report satisfy a need? (Comment on purpose, related project, or other area of interest for which the report will be used.) _____

4. Specifically, how is the report being used? (Information source, design data, procedure, source of ideas, etc.) _____

5. Has the information in this report led to any quantitative savings as far as man-hours or dollars saved, operating costs avoided, or efficiencies achieved, etc? If so, please elaborate. _____

6. General Comments. What do you think should be changed to improve future reports? (Indicate changes to organization, technical content, format, etc.) _____

CURRENT
ADDRESS

Organization

Name

E-mail Name

Street or P.O. Box No.

City, State, Zip Code

7. If indicating a Change of Address or Address Correction, please provide the Current or Correct address above and the Old or Incorrect address below.

OLD
ADDRESS

Organization

Name

Street or P.O. Box No.

City, State, Zip Code

(Remove this sheet, fold as indicated, tape closed, and mail.)
(DO NOT STAPLE)