

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave blank)	2. REPORT DATE August 16, 1999	3. REPORT TYPE AND DATES COVERED Technical Report # 49		
4. TITLE AND SUBTITLE Tunable Multicolor Electroluminescent Polymer Devices for Full Color Displays.		5. FUNDING NUMBERS N00014-94-1-0540 Kenneth J. Wynne R & T Code 3132111		
6. AUTHOR(S) S. A. Jenekhe and X. Zhang				
7. PERFORMING ORGANIZATION NAMES(S) AND ADDRESS(ES) University of Rochester Department of Chemical Engineering 206 Gavett hall, Box 270166 Rochester, NY 14627-0166		8. PERFORMING ORGANIZATION REPORT NUMBER # 49		
9. SPONSORING / MONITORING AGENCY NAMES(S) AND ADDRESS(ES) Office of Naval Research 800 North Quincy Street Arlington, VA 22217-5000		10. SPONSORING / MONITORING AGENCY REPORT NUMBER		
11. SUPPLEMENTARY NOTES Published in POLYMER PREPRINTS, 1999, 40 (2), 1194-1195.				
a. DISTRIBUTION / AVAILABILITY STATEMENT Reproduction in whole or in part is permitted for any purpose of the United States Government. This document has been approved for public release and sale; its distribution is unlimited.		12. DISTRIBUTION CODE		
13. ABSTRACT (Maximum 200 words)  Efficient light emitting diodes (LEDs) of various colors and suitable methods of their pixelation are essential to incorporating polymer LEDs into full color display systems. We have developed polymer/polymer heterojunction LEDs that exhibit multicolor emission which is tunable by the bias voltage. These LEDs are based on poly(p-phenylenevinylene) (PPV)/n-type polymer structures. ITO/PPV/polyquinoline/Al diodes fabricated under ambient air environment had a turn-on voltage of 3.5 V, luminance levels of over 800 cd/m <sup>2</sup> , and efficiencies of up to 1 %. Such devices, for example, reversibly switch colors (red -- yellow --green) in the 5-12 V range, facilitating easy pixelation. Origin of the color tunability will be discussed.				
14. SUBJECT TERMS Tunable electroluminescence; light emitting diodes; multicolor electroluminescence; polyquinolines; poly(phenylene vinylene); full color displays; bilayer polymer diodes.			15. NUMBER OF PAGES 2	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT Unclassified	18. SECURITY CLASSIFICATION OF THIS PAGE Unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT Unclassified	20. LIMITATION OF ABSTRACT Unlimited	

19990823 069

OFFICE OF NAVAL RESEARCH

GRANT NO: N00014-94-1-0540

R&T Code 3132111

Kenneth J. Wynne

Technical Report NO. 49

Tunable Multicolor Electroluminescent Polymer Devices for Full Color Displays

By

S. A. Jenekhe and X. Zhang

Published

In

POLYMER PREPRINTS

Departments of Chemical Engineering  
and Chemistry  
University of Rochester, New York 14627

August 16, 1999

Reproduction in whole or in part is permitted for any purpose  
of the United States Government

This document has been approved for public release and sale;  
its distribution is unlimited.

# TUNABLE MULTICOLOR ELECTROLUMINESCENT POLYMER DEVICES FOR FULL COLOR DISPLAYS

Samson A. Jenekhe\* and Xuejun Zhang

Departments of Chemical Engineering and Chemistry  
University of Rochester  
Rochester, New York 14627-0166

## Introduction

Light emitting diodes (LEDs) fabricated from luminescent semiconducting polymers are very promising for a range of display applications and may soon be commercialized.<sup>1</sup> Achievement of color tunability in organic or polymer LEDs is important for multicolor or full color display applications. Various approaches to color tunability in organic and polymer LEDs have been explored, including: blends of electroluminescent conjugated polymers,<sup>2</sup> exploitation of microcavity effects,<sup>3</sup> multilayer stacks of LED structures of various colors,<sup>4</sup> and bilayer heterojunctions of electroluminescent (EL) conjugated polymers.<sup>5</sup> Heterojunctions of EL semiconducting polymers of both a *p*-type (hole transport) and an *n*-type (electron transport) provide a simple and yet powerful approach to tunable multicolor LEDs that can be easily pixelated for full color displays. Figure 1 shows a schematic illustration of such a multicolor LED structure which is the focus of our paper.




Figure 1. Schematic of tunable multicolor LED structure.

Most of the EL conjugated polymers investigated to date, such as poly(p-phenylene vinylene) (PPV), poly(p-phenylene) (PPP), polythiophenes, polyfluorenes, and their numerous derivatives, are *p*-type semiconductors. They inject and transport holes more efficiently than electrons. An important exemption are the polyquinolines<sup>6a</sup> and polybenzobisazoles<sup>6b</sup> which are excellent *n*-type semiconductors<sup>6,7</sup> while also being highly luminescent. These latter classes of EL conjugated polymers (Figure 2) tend to inject and transport electrons more efficiently than holes. Thus by combining both *p*-type and *n*-type EL conjugated polymers in bilayer heterojunctions (Figure 1), efficient multicolor emission is in principle possible. However, because of the many possible complications in the photophysics of such polymer/polymer heterojunctions (e.g. exciplex formation,<sup>8</sup> energy transfer, electron transfer, etc.) multicolor emission is not an automatic outcome. In fact only a single color emission was observed from most previous bilayer heterojunction LEDs, for example cyano-PPV/PPV,<sup>9</sup> polyquinoxaline/PPV,<sup>10</sup> and polypyridine/PPV among others. We have found that the key to achieving and controlling multicolor emission in polymer/polymer heterojunction LEDs is in controlling the photophysics at the polymer/polymer interface and, very importantly, control of the *finite size effects*.<sup>5,11</sup> The size effects arise from the limited carrier ranges and exciton diffusion lengths in all organic semiconductors.

## Experimental

The syntheses and characterizations of the *n*-type polyquinolines and polybenzobisazoles have previously been reported by our laboratory.<sup>6,7</sup> The sulfonium precursor of PPV in 1 wt% methanol solution was either purchased from Lark Enterprises (Webster, MA) or the same as previously described.<sup>5a</sup> The ITO/PPV/*n*-type polymer/Al devices (Figure 1) were fabricated and evaluated under ambient laboratory air. The PPV thin films (25-130 nm) were deposited onto ITO-coated glass substrates by spin coating of the sulfonium precursor in methanol solution and followed by thermal conversion in vacuum (~250 °C for 1.5 hr). Thin films (15-100 nm) of an *n*-type semiconducting polymer from those shown in Figure 2 were spin coated from formic acid

solutions onto the PPV layer and dried in vacuum oven overnight. Single layer devices such as ITO/PPV/Al and ITO/*n*-type polymer/Al were also fabricated in similar ways for comparison purposes. Extensive characterization of all the devices and the bilayer heterojunction films was done in ways similar to previously described procedures.<sup>5,11</sup> In particular, measurements of current (I) - voltage (V), luminance (L) - voltage, EL spectra, and EL microscopy were done in air.




Figure 2. Molecular structures of EL polymers used in multicolor LEDs.

## Results and Discussion

Figure 3a shows the EL spectra of a PPQ (67 nm)/PPV (25 nm) bilayer LED. Only orange/red emission from the PPQ layer was observed at all bias voltages from 10-30 V. In this case no emission from the PPV layer is observed and hence the PPV thin film is merely functioning as a hole transport layer for the EL polyquinoline PPQ. On the other hand an LED from a PPQ (33 nm)/PPV (117 nm) gave only green EL emission spectra at all bias voltages from 4.5-30 V (not shown). This means that the polyquinoline thin film is merely functioning as an electron transport layer for the emissive PPV. Shown in Figure 3b are the EL spectra of a PPQ (40 nm)/PPV (25 nm) bilayer LED. Voltage dependent EL spectra are obtained: at low bias voltages (8-10 V) orange/red emission characteristic of the PPQ layer was seen but at higher voltages (~13-20 V or higher) a broad EL band with a more intense green component was observed. Visually, the reversible color switching seen was orange/red ↔ yellow ↔ green as the voltage was varied. These results demonstrate that the emission color from bilayer LED of Figure 1 can be controlled to be a single color from either layer or to be multicolor switchable by voltage depending on the relative layer thicknesses of the polymer/polymer heterojunction.

Similar voltage tunable multicolor LEDs have been fabricated from the *n*-type semiconducting polymers shown in Figure 2 and others.<sup>5,11</sup> Another interesting example is shown in Figure 4. A PBTPV (50 nm)/PPV (25 nm) LED shows only orange/red electroluminescence at all bias voltages above the turn-on voltage (12 V) (Figure 4a). A PBTPV (15 nm)/PPV (60 nm) LED also showed only a single color (green) at all bias voltages above the turn-on voltage (6 V). In the case of a PBTPV (35 nm)/PPV (25 nm) LED, reversible voltage switchable multicolor was observed (Figure 4b) in which green EL appears first (at low voltages, ~5 V) and eventually changes to orange/red. The visually observed voltage switching of colors was green ↔ yellow ↔ orange/red.

In addition to the novel phenomena of voltage tunability of color in these bilayer heterojunction LEDs, all their performance characteristics (turn-on voltage, EL efficiency, luminance or brightness) were substantially enhanced relative to the corresponding single-layer LEDs. For example, the turn-on voltages of the multicolor LEDs were in the range of 3-5 V compared to 7 V for a single-layer PPV diode and 7-15 V for single-layer *n*-type polymer devices. Similarly, the EL efficiencies and luminance levels were

enhanced by up to two orders of magnitude, reaching ~1% and 800 cd/cm<sup>2</sup> respectively.

Studies of the underlying mechanism of EL multicolor switching in these bilayer heterojunction LEDs, including examination of the energetics and barriers at the polymer/polymer interfaces from available HOMO/LUMO levels,<sup>6,7</sup> photophysics and charge transfer processes at the interface, the critical role of film thickness of each polymer in the bilayer heterojunction, and electroluminescence microscopy will be presented and also described in detail elsewhere.

### Conclusions

Efficient and bright bilayer heterojunction LEDs constructed from p-type PPV and an n-type polyquinoline or polybenzobisthiazole have been shown to exhibit reversible multicolor emission tunable by the applied bias voltage. Three or more colors can be obtained from such an LED. The simplicity of multicolor pixelation of display systems made from these multicolor LEDs make them attractive for further development and applications.

**Acknowledgement.** This research was supported by the Office of Naval Research and the National Science Foundation.

### References

- (1) For recent reviews, see: (a) Friend, R. H.; Gymer, R. W.; Holmes, A. B.; Burroughes, J. H.; Marks, R. N.; Taliani, C.; Bradley, D. D. C.; Dos Santos, D. A.; Bredas, J. L.; Logdlund, M.; Salaneck, W. R. *Nature* **1999**, *397*, 121. (b) Kraft, A.; Grimsdale, A. C.; Holmes, A. B. *Angew. Chem. Int. Ed.* **1998**, *37*, 402.
- (2) Berggren, M.; Inganas, O.; Gustafsson, G.; Rasmussen, J.; Andersson, M. R.; Hjertberg, T.; Wennerstrom, O. *Nature* **1994**, *372*, 444.
- (3) Dodabalapur, A.; Rothberg, L. J.; Jordan, R. H.; Miller, T. M.; Slusher, R. E.; Phillips, J. M. *J. Appl. Phys.* **1996**, *80*, 6954.
- (4) (a) Shen, Z. L.; Burrows, P. E.; Bulovic, V.; Forrest, S. R.; Thompson, M. E. *Science* **1997**, *276*, 2009. (b) Burrows, P. E.; Gu, G.; Bulovic, V.; Shen, Z. L.; Forrest, S. R.; Thompson, M. E. *IEEE Trans. Electron. Dev.* **1997**, *44*, 1188. (c) Tada, N.; Fujii, A.; Ohmori, Y.; Yoshino, K. *IEEE Trans. Electron. Dev.* **1977**, *44*, 1234.
- (5) (a) Jenekhe, S. A.; Zhang, X.; Chen, X. L.; Choong, V.-E.; Gao, Y.; Hsieh, B. R. *Chem. Mater.* **1997**, *9*, 409. (b) Zhang, X.; Jenekhe, S. A. *Mater. Res. Soc. Symp. Proc.* **1998**, *488*, 539.
- (6) (a) Agrawal, A. K.; Jenekhe, S. A. *Macromolecules* **1993**, *26*, 895. (b) Agrawal, A. K.; Jenekhe, S. A. *Chem. Mater.* **1996**, *8*, 579.
- (7) (a) Osaheni, J. A.; Jenekhe, S. A. *Macromolecules* **1993**, *26*, 4726. (b) Osaheni, J. A.; Jenekhe, S. A. *Chem. Mater.* **1995**, *7*, 672. (c) Osaheni, J. A.; Jenekhe, S. A. *Chem. Mater.* **1992**, *4*, 1282.
- (8) Jenekhe, S. A.; Osaheni, J. A. *Science* **1994**, *265*, 765.
- (9) Greenham, N. C.; Moratt, S. C.; Bradley, D. D. C.; Friend, R. H.; Holmes, A. B. *Nature* **1993**, *365*, 628.
- (10) (a) Cui, Y.; Zhang, X.; Jenekhe, S. A. *Macromolecules* **1999**, in press. (b) O'Brien, D.; Weaver, M. S.; Lidzey, D. G.; Bradley, D. D. C. *Appl. Phys. Lett.* **1996**, *69*, 881.
- (11) Zhang, X.; Jenekhe, S. A. *J. Am. Chem. Soc.*, to be submitted.




Figure 3. EL spectra of a single-color (a) and multicolor (b) LEDs from PPQ/PPV heterojunctions.




Figure 4. EL spectra of a single-color (a) and multicolor (b) LEDs from PBTPV/PPV heterojunctions.