

## Overload Effect on Fatigue of AerMet 100 Steel

E. U. Lee\* and K. Sadananda\*\*

Overloads have been reported to perturb the steady state fatigue crack growth condition and retard the crack growth. The retardation effect is known to depend on material plasticity, slip planarity, microstructure, overload ratio, and background stress intensity range  $\Delta K$  and load ratio  $R$ . Extensive studies have been conducted to identify the effect of a single overload (or spike load) in terms of the number of delayed cycles.

This study was initiated to understand the effect of a single overload on the threshold fatigue crack growth in AerMet 100 steel as a function of  $R$ -ratio and environment. A single 100% overload (or overload ratio 2) was applied after the fatigue crack growth rate  $da/dN$  reached the threshold one ( $5 \times 10^{-10}$  m/cycle) in the  $K$ -decreasing test of load shedding. The background load and the corresponding overload were stepped up until the crack began to grow after each loading of  $5 \times 10^5$  cycles. Subsequently, the fatigue test was continued under constant amplitude loading at various  $R$ -ratios, ranging from  $-1.1$  to  $0.9$ , and frequency of  $10$  Hz in air and vacuum of  $5 \times 10^{-8}$  torr. The overload-induced increase in the threshold stress intensity range  $\Delta K_{th}$  was taken as the measure of overload retardation effect. Furthermore, the overall results were analyzed in terms of two parameters,  $\Delta K_{th}$  and maximum stress intensity at threshold  $K_{max}$ .

Under background load in air, with increasing  $R$ -ratio, the  $\Delta K_{th}$  changed little for  $R < 0$ , but it decreased linearly for  $R = 0$  to  $0.5$  and then leveled off for  $R > 0.5$ . The corresponding  $K_{max}$  changed a little for  $R < 0$  but increased steeply for  $R > 0$  with increasing  $R$ -ratio. After a 100% overload in air, the  $\Delta K_{th}$  increased linearly for  $R < 0$  but decreased for  $R > 0$  with increasing  $R$ -ratio. The feature of the corresponding  $K_{max}$  change with  $R$ -ratio was similar to that for the background load, except the  $K_{max}$  was increased by overload.

Under background and after a single overload in vacuum,  $\Delta K_{th}$  decreased linearly with increasing  $R$ -ratio for  $R > 0$ . The overload-induced increase in  $\Delta K_{th}$  was less in vacuum than in air.

The fundamental threshold curve of  $\Delta K_{th}$  vs  $K_{max}$  indicates that (a) the resistance to fatigue crack growth is greater in vacuum than in air under the background load and after a single overload, but (b) the overload retardation effect is greater in air than in vacuum.

The related fractography, crack path and crack tip geometry were examined for the fatigue tests.

• Naval Air Warfare Center Aircraft Division, Patuxent River, MD

\*\* Naval Research Laboratory, Washington, DC

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188		
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing this collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.					
1. REPORT DATE		2. REPORT TYPE Abstract		3. DATES COVERED	
4. TITLE AND SUBTITLE  Overload Effect on Fatigue of AerMet 100 Steel			5a. CONTRACT NUMBER		
			5b. GRANT NUMBER		
			5c. PROGRAM ELEMENT NUMBER		
6. AUTHOR(S)  E. Lee     K. Sadananda			5d. PROJECT NUMBER		
			5e. TASK NUMBER		
			5f. WORK UNIT NUMBER		
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)  Naval Air Warfare Center Aircraft Division 22347 Cedar Point Road, Unit #6 Patuxent River, Maryland 20670-1161			8. PERFORMING ORGANIZATION REPORT NUMBER		
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)  Naval Air Systems Command 47123 Buse Road Unit IPT Patuxent River, Maryland 20670-1547			10. SPONSOR/MONITOR'S ACRONYM(S)		
			11. SPONSOR/MONITOR'S REPORT NUMBER(S)		
12. DISTRIBUTION/AVAILABILITY STATEMENT  Approved for public release; distribution is unlimited.					
13. SUPPLEMENTARY NOTES					
14. ABSTRACT  Overloads have been reported to perturb the steady state fatigue crack growth condition and retard the crack growth. The retardation effect is known to depend on material plasticity, slip planarity, microstructure, overload ratio, and background stress intensity range $\Delta K$ and load ratio R. Extensive studies have been conducted to identify the effect of a single overload (or spike load) in terms of the number of delayed cycles.  This study was initiated to understand the effect of a single overload on the threshold fatigue crack growth in AerMet 100 steel as a function of R-ratio and environment. A single 100% overload (or overload ratio 2) was applied after the fatigue crack growth rate $da/dN$ reached the threshold one ( $5 \times 10^{-10}$ m/cycle) in the K-decreasing test of load shedding. The background load and the corresponding overload were stepped up until the crack began to grow after each loading of $5 \times 10^5$ cycles. Subsequently, the fatigue test was continued under constant amplitude loading at various R-ratios, ranging from -1.1 to 0.9, and frequency of 10 Hz in air and vacuum of $5 \times 10^{-8}$ torr. The overload-induced increase in the threshold stress intensity range $\Delta K_{th}$ was taken as the measure of overload retardation effect. Furthermore, the overall results were analyzed in terms of two parameters, $\Delta K_{th}$ and maximum stress intensity at threshold $K_{max}$ .					
15. SUBJECT TERMS  AerMet 100 steel					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT	18. NUMBER OF PAGES	19a. NAME OF RESPONSIBLE PERSON
a. REPORT	b. ABSTRACT	c. THIS PAGE			E. U. Lee
Unclassified	Unclassified	Unclassified	Unclassified	1	19b. TELEPHONE NUMBER (include area code) (301) 342-8069

DTIC QUALITY INSPECTED 4