

OFFICE OF NAVAL RESEARCH

GRANT N0001400AF00002

PR Number 00PR01464-00

Technical Report No. 24

Pressure and temperature variation of the electrical conductivity of poly(propylene glycol) containing LiCF_3SO_3

Prepared for publication in Journal of Chemical Physics

by

J.J. Fontanella

Physics Department, U.S. Naval Academy, Annapolis, MD 21402-5026, USA

1 July 2000

Reproduction in whole or in part is permitted for any purpose of the United States Government.

This document has been approved for public release and sale, its distribution is unlimited.

20000724 062

DTIC QUALITY INSPECTED 4

REPORT DOCUMENTATION PAGE

Form Approved

OMB No. 0704-0188

The reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

1. AGENCY USE ONLY (Leave blank)	2. REPORT DATE July 1, 2000	3. REPORT TYPE AND DATES COVERED Technical Report 6/1/99 to 5/31/00	
4. TITLE AND SUBTITLE Pressure and temperature variation of the electrical conductivity of Poly(propylene glycol) containing LiCF_3SO_3		5. FUNDING NUMBERS Grant Number: N0001400AF00002 PR Number: 00PR01464-00	
6. AUTHOR(S) J.J. Fontanella			
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) United States Naval Academy Physics Department Annapolis, MD 21402		8. PERFORMING ORGANIZATION REPORT NUMBER Technical Report #24	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) Office of Naval Research Physical S&T Div.- ONR 331 800 N. Quincy Street Arlington, VA 22217-5660		10. SPONSORING/MONITORING AGENCY REPORT NUMBER TR#24	
11. SUPPLEMENTARY NOTES Prepared for publication in Journal of Chemical Physics			
12a. DISTRIBUTION/AVAILABILITY STATEMENT Reproduction in whole or in part is permitted for any purpose of the United States Government. This document has been approved for public release and sale; its distribution is unlimited.		12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) Complex impedance and differential scanning calorimetry (DSC) studies have been carried out on poly(propylene glycol) with average molecular weight 1025 (PPG) and PPG containing LiCF_3SO_3 . The impedance studies were made at frequencies from about 1 MHz to 100 MHz at pressures up to 0.3 GPa (3 kbar) over the temperature range 215-365 K. Both the impedance and DSC studies were carried out in vacuum or at atmospheric pressure over a temperature range of about 100-375 K. As a consequence, the impedance studies overlap the DSC glass transition temperature. The inadequacy of the widely used Vogel-Tammann-Fulcher or Williams-Landel-Ferry equations to describe the temperature variation of the vacuum electrical conductivity data is discussed. It is shown that the Bendler-Shlesinger formalism is a better representation of the data, particularly in the region close to the glass transition. The first pressure derivative of the electrical conductivity, and hence apparent activation volume, decreases strongly as temperature increases. In addition, the activation volumes are larger for the low molecular weight liquids than the values reported previously for related, high molecular weight rubbery electrolytes. Next there appears to be an exponential relationship between activation volume and the electrical conductivity. Finally, the pressure variation of the electrical conductance exhibits negative curvature which shows that the activation volume increases as pressure increases. A qualitative explanation of each of these results concerning the relationship between conductivity, temperature, and pressure is given in terms of free volume. However, whether free volume can provide a quantitative explanation remains to be determined.			
14. SUBJECT TERMS Electrical Conductivity, Complex Impedance Lithium Electrolytes, High Pressure		15. NUMBER OF PAGES 32	16. PRICE CODE
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT

Pressure and Temperature Variation of the Electrical Conductivity of Poly(propylene glycol) Containing LiCF_3SO_3

J. J. Fontanella

Physics Department, U.S. Naval Academy, Annapolis, MD 21402-5026, USA

Complex impedance and DSC studies have been carried out on poly(propylene glycol) with average molecular weight 1025 (PPG) and PPG containing LiCF_3SO_3 . The impedance studies were made at frequencies from about 1 mHz to 100 MHz at pressures up to 0.3 GPa (3 kbar) over the temperature range 215-365K. Both the impedance and DSC studies were carried out in vacuum or at atmospheric pressure over a temperature range of about 100-375K. As a consequence, the impedance studies overlap the DSC glass transition temperature. The inadequacy of the widely used Vogel Tammann Fulcher (VTF) or Williams Landel Ferry (WLF) equations to describe the temperature variation of the vacuum electrical conductivity data is discussed. It is shown that the Bendler-Shlesinger (BENSH) formalism is a better representation of the data, particularly in the region close to the glass transition. The first pressure derivative of the electrical conductivity, and hence apparent activation volume, decreases strongly as temperature increases. In addition, the activation volumes are larger for the low molecular weight liquids than the values reported previously for related, high molecular weight rubbery electrolytes. Next, there appears to be an exponential relationship between the activation volume and the electrical conductivity. Finally, the pressure variation of the electrical conductance exhibits negative curvature which shows that the activation volume increases as pressure increases. A *qualitative* explanation of each of these results concerning the relationship between conductivity, temperature and pressure is given in terms of free volume. However, whether free volume can provide a *quantitative* explanation remains to be determined.

Keywords: Electrical Conductivity, Lithium Electrolytes,
Activation Volume, Low Temperature, High Pressure

I. INTRODUCTION

Electrolytes based on poly(propylene glycol) (PPG) continue to be of interest partly because they are related to poly(ethylene glycol) (PEG) and are usually totally amorphous. There have been a large number of studies of various types of PPG and a representative list is given as Refs. 1-25. One reason for new studies of this material is that it has become obvious that a widely used representation for the temperature variation of many of the properties of amorphous or liquid electrolytes, the Vogel-Tammann-Fulcher (VTF) equation or mathematically equivalent Williams-Landel-Ferry (WLF) Equation, has deficiencies.²⁶⁻³² Further, techniques for improving and extending the range of data, have recently been developed and these provide the means by which to test the theories. It is also of interest to study materials such as PPG-1025 which is a liquid in order to compare it with the results for related high equivalent weight solid materials.³³ Finally, it has recently been pointed out that the pressure variation of various dynamical phenomena of PPG-based materials exhibits opposite curvature to those based on PEG.³⁴ In order to gather further information concerning this effect, new high pressure data are presented along with a detailed analysis.

II. EXPERIMENTAL

PPG (average MW 1025) was obtained from Poly Sciences Inc. LiCF_3SO_3 was obtained from Alfa Corporation and dissolved in acetonitrile. The solution was then added to the polymer in a ratio of 20:1 repeat units per lithium. The acetonitrile was then removed from the materials by baking in a vacuum oven at about 80°C for at least 24 hours. The acetonitrile was determined to be removed when a constant

mass was achieved. All of these procedures and subsequent loading of the samples into various sample holders were carried out in a Vac Atmospheres glove box with a nitrogen atmosphere and less than about 0.06 ppm water.

The vacuum temperature electrical conductivity data were obtained using a fixed-electrode, three-terminal cell which has been described elsewhere.³⁵ For the high pressure measurements, the liquids were placed in TeflonTM lined TygonTM tubing the ends of which were plugged with stainless steel electrodes and sealed using a modified SwageLokTM fitting.

Complex impedance studies were carried out at frequencies from about 1 mHz to 1 MHz using either a CGA-83 capacitance measuring assembly or a Solartron 1255 Frequency response analyzer and 1296 Dielectric Interface.

The DSC measurements were carried out beginning at about 130K and ending at about 373K at a scanning rate of 10 K/min using a TA Associates Model 2100 thermal analyzer and Model 910 Cell Base.

III. RESULTS

For the electrical experiments of PPG:LiCF₃SO₃ a complex impedance diagram consisting of a slightly depressed semicircular arc and/or slanted line was observed. That response is typical for the complex impedance of electrolytes with blocking electrodes.³⁶⁻⁴⁴ An example from the present work, for which only the depressed semicircle was observed, is given in Fig. 1. Fig. 1 is interesting because it represents a complex impedance diagram for a material below the central (or midpoint) DSC glass transition temperature, hence the high impedances. In cases where sufficient semicircles are observed, the Cole-Cole equation:⁴⁵

$$Z^* = \frac{Z_0}{1 + (i\omega\tau_0)^{(1-\alpha)}} \quad (1)$$

was best-fit to the data and the bulk resistance, R , was obtained from the intercept of the arc with the Z' axis. The best-fit Cole-Cole expression, intercept and center of the circle are also shown in Fig. 1. In cases where very little arc was observed, R was obtained from the intercept of the slanted line with the Z' axis. The conductance, $G=1/R$, was calculated from the intercept.

In the case of the room temperature, atmospheric pressure data, the conductance was transformed to the electrical conductivity, σ , via the usual equation:

$$\sigma = GL/A \quad (2)$$

where A is the area of the sample and L is the length. It was found that the as-received PPG at atmospheric pressure and room temperature had a conductivity of about 1.7×10^{-10} S/cm and the conductivity of PPG:LiCF₃SO₃ was about 9.9×10^{-6} S/cm.

Values of the electrical conductivity at other temperatures and approximately atmospheric pressure were obtained by assuming that the relative change in electrical conductivity is the same as the relative change in electrical conductance, i.e. no correction was made for changes in the dimensions of the sample holder. The results for the variation of the conductivity with temperature for the PPG are shown in Fig. 2. The results for the variation of the conductance with pressure are shown in Fig. 3 and the DSC data are shown in Fig. 4.

IV. DISCUSSION

A. VTF Formalism

Fig. 2 shows that the temperature variation of the electrical conductivity of PPG:LiCF₃SO₃ is non-Arrhenius and characteristic of a glass-forming liquid. This is consistent with the DSC data in Fig. 4 where it is shown that all that is observed

for PPG:LiCF₃SO₃ is a single endothermic event typical of a glass transition. The central (or midpoint) glass transition temperature, T_g, for PPG-1025 and PPG:LiCF₃SO₃ are about 205.9K and 218.1K, respectively. The onset and endpoint of the transition for PPG-1025 are about 203.4K and 207.2K and are about 213.5K and 223.0K for PPG:LiCF₃SO₃.

The smooth variation of the electrical conductivity with temperature is often analyzed using the Vogel-Tammann-Fulcher (VTF) equation:⁴⁶

$$\sigma = \sigma_0 \exp\left(\frac{-B}{T - T_0}\right) \quad (3)$$

or the modified VTF Equation:

$$\sigma = \frac{A}{\sqrt{T}} \exp\left(\frac{-B'}{T - T_0'}\right) \quad (4)$$

A non-linear least squares procedure was carried out as described elsewhere^{26,27} and the resultant best-fit parameters are listed in Table I along with the RMS deviation.

The small RMS deviation is an indication that the fit is fairly good. However, it has become apparent that Eq. 3 deviates systematically from data such as dielectric relaxation times, viscosity and electrical conductivity in glass-forming systems.^{26,28-32} In order to evaluate the goodness of fit for the electrical conductivity in PPG:LiCF₃SO₃, the deviations of Eq. 3 from the datum points were calculated and the results are shown in Fig. 5. It is clear that a systematic deviation is observed and further, the deviation follows the same trend as that observed previously for electrical conductivity in propylene carbonate based electrolytes²⁶ (Fig. 3 in Ref. 26 is vs. reciprocal temperature.) and for viscosity in

tri- α -naphthylbenzene³² (Fig. 1 in Ref. 32 is vs. reciprocal temperature and viscosity rather than reciprocal viscosity which is analogous to electrical conductivity.).

One consequence of this systematic deviation is that the values of the fitting parameters are not constant in that they depend upon the temperature range of the data. In order to show this, the data in Fig. 2 were grouped into 100K intervals and Eq. 3 was refit to each interval. The resultant fitting parameters are plotted in Figs. 6 and 7 vs. the temperature at the center of each interval. It is clear that the VTF parameters depend upon the temperature interval and that the trends are the same as those observed for a simple electrolyte, a 1M solution of LiPF₆ in propylene carbonate (PC:LiPF₆).²⁶ For example, T_0 increases by about 10K when the position of the temperature interval increases by 35K. This result is notable because T_0 is often assigned significance because it is usually assumed to be related to T_g .^{2,4,20} Also, $\log\sigma_0$ decreases by more than a factor of two over that temperature interval so that σ_0 decreases by about a factor of four. This is important because the preexponential is sometimes taken to be related to the number or concentration of charge carriers.^{20,47} Clearly, because of their temperature dependence, care must be taken when assigning physical significance to the VTF parameters.

Finally, in a recent paper, Chung et al.¹³ have reported data for PPG4000 and PPG 425 containing various salts, including LiCF₃SO₃ at concentrations which bracket those of the present work, which show significant deviations from VTF behavior in the range of 1.2 T_g to 1.4 T_g (Figs. 3 and 4 of Ref. 13). It is clear from Fig. 2 of the present work that the behavior of the conductivity at low temperature observed by Chung et al. is not reproduced in the present work.

B. WLF Formalism

A formalism which is mathematically equivalent to the VTF Equation⁴⁸ and which is also often used to characterize glass-forming liquids is the Williams-Landel-Ferry (WLF) Equation:⁴⁹

$$\log_{10} \left(\frac{\sigma(T)}{\sigma(T^*)} \right) = \frac{C_1(T - T^*)}{C_2 + (T - T^*)} \quad (5)$$

where C_1 , C_2 and $\log_{10}\sigma(T^*)$ are the adjustable parameters and T^* is a reference temperature.

The reason for also considering this equation in detail is that the interpretation of the various parameters for relaxation times and viscosity has recently been pointed out.⁵⁰ Those considerations have been extended to electrical conductivity and applied to PC:LiPF₆.²⁶ In fact, because the temperature range of the present data have been extended to below T_g they allow a test of one of the predictions of Ref. 26 as follows. Eq. 5 was best-fit to the data using the central (or midpoint) DSC value of T_g as the reference temperature ($T^*=T_g$) and the resulting parameters are listed in Table I. (Of course, other reference temperatures, such as the onset or endpoint DSC T_g 's, could be used. However, as is discussed in detail elsewhere,²⁶ no new information would be obtained.) The value of $C_1=11.9$ obtained for data over the full range of temperatures is consistent with results for a variety of ion-conducting polymers (including ion-containing high molecular weight PPG), where values of about 11.5 are observed. A detailed discussion is given elsewhere.²⁶ In Section 3a of that paper, it was pointed out that C_1 represents the difference between the logarithm of the conductivity at very high temperatures $\log(\sigma_0)$ and the value at the reference temperature, in this case T_g . Consequently, since $\log(\sigma_0)=-0.625$, $C_1=11.91$ predicts that the $\log(\sigma(T_g))$ should be about -12.54. The experimental value is -12.52.

The value of $C_2=46.5$ is also of interest. The reason is that C_2 represents the difference between the reference temperature and T_0 and it is often observed that T_g is about 50K below T_0 .

However, it is also important to investigate the extent to which temperature affects the WLF parameters. Towards this end, Eq. 5 was also best-fit to the various temperature intervals of Figs. 6 and 7 and the results are plotted in Figs. 8 and 9. Interestingly, C_1 remains relatively constant varying only from about 12 to 12.4. This is somewhat different from the behavior of PC:LiPF₆ though constancy was observed for the lowest temperature intervals. However, as is apparent from Fig. 9, C_2 varies strongly (35 to 50K) with temperature interval and does not appear to converge to a unique value. Consequently, care must be taken when using C_2 to characterize a material. For example, C_2 is sometimes used to estimate the "fragility" of a liquid.^{50,51}

C. BENSCH Formalism

Bendler and Shlesinger⁵²⁻⁵⁴ have used a phenomenological model to develop an alternative formalism for the glass transition region behavior of relaxation time vs. temperature. That model can be applied to the electrical conductivity and gives rise to the following (BENSCH) equation:

$$\sigma = D \exp\left(\frac{-B''}{(T - T_c)^{1.5\gamma}}\right) \quad (6)$$

The BENSCH equation contains four adjustable parameters D , B'' , T_c and γ though there is justification for setting $\gamma=1$ (mean-field limit). In fact, the BENSCH equation in the mean-field limit (three adjustable parameters) has been found to provide a

better fit to electrical conductivity and viscosity data than the VTF or WLF equations, particularly near T_g .^{26,27}

The BENSHE equation was fit to the present data in two ways. First, a three parameter fit was carried out after setting $\gamma=1$. As seen by the results in Table I, the RMS deviation associated with the BENSHE equation is more than twice as small as for the VTF or WLF equations. Next, the full, four parameter fit was carried out and a minimum was found for $\gamma=1.28$ along with another significant improvement in the RMS deviation. It is interesting that $\gamma=1.28$ is close to 1.33 which would make the exponent, 1.5γ , equal to two. It will be of interest to investigate the theoretical significance of this result.

Further insight can be gained into the applicability of the BENSHE equation by again plotting the difference between the experimental and theoretical values as is done in Fig. 5. It is clear that the BENSHE equation provides a better fit of the data at all temperatures though some systematic deviation remains. In fact, even the 3 parameter fit of the BENSHE equation provides an excellent representation of the data near T_g .

D. Pressure Variation

A second order polynomial:

$$\ln G/G_0 = ap + bp^2 \quad (7)$$

was best-fit to the results for the variation of conductance with pressure and the coefficients a and b are listed in Table II.

1. Linear Variation

The slope of the conductance vs. pressure at zero pressure was converted to the pressure variation of the electrical conductivity using:

$$\left(\frac{\partial \ln \sigma}{\partial p}\right)_T = \left(\frac{\partial \ln G}{\partial p}\right)_T + \frac{\chi_T}{3} \quad (8)$$

where χ_T is the isothermal compressibility. Values of χ_T for PPG:LiCF₃SO₃ do not seem to be available. Since the correction term is a small fraction of the total, an approximation was used. The recently reported values of χ_T for poly(ethylene oxide) in the liquid state⁵⁵ were extrapolated to the temperatures of the present work and the resultant values of $\chi_T/3$ are listed in Table II.

The linear variation of the conductivity is usually used to calculate an apparent activation volume from:

$$\Delta V = -kT \left[\frac{\partial \ln \sigma}{\partial p}\right]_T. \quad (9)$$

As has been pointed out several times,^{40,41} this is only correct for Arrhenius behavior since the true activation volume is defined by:

$$\Delta V = \left[\frac{\partial g}{\partial p}\right]_T. \quad (10)$$

where g is the Gibbs energy and Eq. 9 is only obtained for electrical conductivity which exhibits Arrhenius behavior. However, VTF/WLF/BENSH behavior is often discussed in terms of an activation energy (or Gibbs energy) calculated from the slope of an Arrhenius plot and most of the high pressure results in the literature are discussed in terms of ΔV calculated using Eq. 9. Consequently, the values of ΔV were calculated using Eq. 9 and the results are listed in Table II.

The values of ΔV range from 66.6 to 24.2 cm³/mol as temperature increases from 268 to 363K. The values are on the order of those reported for ions in Parel

elastomer, a high molecular weight ($\approx 10^6$), PPG-based polymer.^{24,25} In order to make a detailed comparison with those results, all results are plotted in Fig. 10.

The variation of the activation volume with temperature for the low molecular weight liquid electrolytes of the present work and for high molecular weight rubbery electrolytes of Refs. 24 and 25 is essentially the same. The major difference is that ΔV for the liquids is slightly larger. Both these results, the temperature dependence of ΔV and the difference due to molecular weight, and the remaining results of the present work presented below, can be understood *qualitatively* on the basis of free volume (per mole), V_f , using the following ideas.

The activation volume represents volume *change* of the material required for ion motion while the free volume represents the volume already available. Consequently, if V_t is defined to be the total volume (per mole) required for ion motion, the following equation applies:

$$V_t = V_f + \Delta V. \quad (11)$$

Most importantly, V_t should be approximately constant i.e. independent of pressure, temperature or conductivity. Consequently, the physical interpretation is that for a given conducting system in cases where V_f is large ΔV will be small, etc.

This applies to the results of the present work as follows. First, the larger values of ΔV for the liquids follows from Eq. (11) if V_f is smaller for the liquids. This is reasonable since it is expected that there should be greater space-filling for the low molecular weight liquids than for the high molecular weight rubbery materials. Next, the decrease of ΔV as temperature increases (negative thermal expansion coefficient of the activation volume) follows immediately from Eq. 11 since it is generally accepted⁵⁷ that free volume increases as temperature increases and thus ΔV should decrease assuming that V_f is a constant. However, whether these

considerations provide a quantitative explanation of the results remains to be determined.

Finally, in order to investigate the relationship between ΔV , V_f and the electrical conductivity, ΔV is plotted vs. $\log(\sigma)$ in Fig. 11. It is clear that the data are reasonably well-represented by the equation:

$$\sigma = 1.8 \times 10^{-3} \exp(-\Delta V/14.5) \quad (12)$$

Eq. (11) then predicts that electrical conductivity increases exponentially as the free volume:

$$\sigma \approx \exp(V_f/14.5) \quad (13)$$

While this is reasonable, it will be of interest to investigate the theoretical basis of this empirical result.

2. Curvature

Next, it is apparent from Table II that the curvature (term b in Eq. (7)) of the variation of conductance with pressure is negative. This is the same as observed previously by the authors for both conductivity and dielectric relaxation in PPG-based materials.^{24,25} The same curvature has also recently been reported for dielectric loss associated with the α relaxation in PPG-400 and PPG-4000.⁵⁸ This implies that the compressibility of the activation volume, $\chi_{\Delta V}$, is negative since if:

$$\frac{\partial^2 \ln \sigma}{\partial p^2} \approx \frac{\partial^2 \ln G}{\partial p^2} \quad (14)$$

it follows that:

$$\chi_{\Delta V} \equiv -\frac{1}{\Delta V} \frac{\partial \Delta V}{\partial p} \approx \frac{2kTb}{\Delta V} \quad (15)$$

In fact, a negative compressibility of the activation volume is expected. The reason is that the free volume should decrease as pressure increases (because of the positive compressibility of the material). Consequently, once again assuming that V_t is a constant, it follows from Eq. (11) that the activation volume should increase as pressure increases. However, whether these considerations provide a quantitative explanation of the results remains to be determined.

V. SUMMARY

In summary, several results have been obtained via DSC and electrical conductivity studies of PPG:LiCF₃SO₃. First is shown that the BENSCH formalism is a better representation of the temperature variation of the vacuum electrical conductivity than the VTF or WLF equations, particularly in the region close to the glass transition. Next, it is found that the first pressure derivative of the electrical conductivity, and hence apparent activation volume, decreases strongly as temperature increases. Also, the activation volume is larger for the low molecular weight liquids than for previously reported values for related, high molecular weight rubbery electrolytes. In addition, there appears to be an exponential relationship between the activation volume and the electrical conductivity. Finally, the pressure variation of the electrical conductance exhibits negative curvature. A *qualitative* explanation of each of these results reflecting on the relationship between conductivity, temperature and pressure is given in terms of free volume.

ACKNOWLEDGMENTS--This work was supported in part by the U. S. Office of Naval Research.

- ¹M. McLin and C. A. Angell, *J. Phys. Chem.* **92**, 2083 (1988).
- ²M. G. McLin and C. A. Angell, *J. Phys. Chem.* **95**, 9464 (1991).
- ³M. G. McLin and C. A. Angell, *Solid St. Ionics* **53-56**, 1027 (1992).
- ⁴M. G. McLin and C. A. Angell, *Polymer* **37**, 4713 (1996).
- ⁵M. McLin and C. A. Angell, *J. Phys. Chem.* **100**, 1181 (1996).
- ⁶Q. Lu, E. Sanchez and C. A. Angell, *Electrochim. Acta* **40**, 2239 (1995).
- ⁷A. Ferry, *J. Chem. Phys* **107**, 9168 (1997).
- ⁸A. Ferry, G. Oradd and P. Jacobsson, *Macromolecules* **30**, 7329 (1997).
- ⁹I. Albinsson and B. -E. Mellander, in *Fast Ion Transport in Solids* ed. B. Scrosati, (Kluwer Academic, Netherlands, 1993).
- ¹⁰M. Xu, E. M. Eyring and S. Petrucci, *J. Chem. Soc. Far. Trans.* **92**, 4969 (1996).
- ¹¹R. Bergman, L. Borjesson, G. Fytas and L. M. Torell, *J. Non-Cryst. Solids* **172-174**, 830 (1994).
- ¹²L. Borjesson, J. R. Stevens and L. M. Torell, *Polymer* **28**, 1803 (1987).
- ¹³S. H. Chung, K. Such, W. Wiczorek and J. R. Stevens, *J. Polym. Sci.: Part B: Polym. Phys.* **32**, 2733 (1994).
- ¹⁴L. M. Torell and C. A. Angell, *Br. Poly. J.* **20**, 173 (1988).
- ¹⁵M. Watanabe, J. Ikeda and I. Shinohara, *Poly. J.* **15**, 175 (1983).
- ¹⁶T. Furukawa, M. Imura and H. Yuruzume, *Jpn. J. Appl. Phys.* **36**, 1119 (1997).
- ¹⁷K. Mitani and K. Adachi, *J. Polym. Sci.: Part B: Polym. Phys.* **33**, 937 (1995).
- ¹⁸K. Mitani and K. Adachi, *J. Polym. Sci.: Part B: Polym. Phys.* **33**, 947 (1995).
- ¹⁹I. Albinsson, B. -E. Mellander and J. R. Stevens, *Solid St. Ionics*, **72**, 177 (1994).
- ²⁰I. Albinsson, B. -E. Mellander and J. R. Stevens, *J. Chem. Phys.* **96**, 681 (1992).
- ²¹S. Schantz, *J. Chem. Phys.* **94**, 6296 (1991).
- ²²Y. Fu, K. Pathmanathan and J. R. Stevens, *J. Chem. Phys.* **94**, 6323 (1991).
- ²³W. Wixwat, Y. Fu and J. R. Stevens, *Polymer*, **32**, 1181 (1991).

- ²⁴J. J. Fontanella, M. C. Wintersgill, M. K. Smith, J. Semancik and C. G. Andeen, *J. Appl. Phys.* **60**, 2665 (1986).
- ²⁵S. G. Greenbaum, Y. S. Pak, M. C. Wintersgill, J. J. Fontanella, J. W. Schultz and C. G. Andeen, *J. Electrochem. Soc.* **135**, 235 (1988).
- ²⁶J. J. Fontanella, M. C. Wintersgill and J. J. Immel, *J. Chem. Phys.* **101**, 5392 (1999).
- ²⁷J. J. Fontanella, M. C. Wintersgill, C. S. Coughlin, P. Mazaud and S. G. Greenbaum, *J. Polym. Sci.: Part B: Polym. Phys.* **29**, 747 (1991).
- ²⁸D. J. Plazek and J. H. Magill, *J. Chem. Phys.* **46**, 3678 (1968).
- ²⁹A. J. Barlow, J. Lamb and A. J. Matheson, *Proc. Roy. Soc. (London)* **A292**, 322 (1966).
- ³⁰F. Stickel, E. W. Fischer and R. Richert, *J. Chem. Phys.* **105**, 2043 (1996).
- ³¹A. Bondeau and J. Huck, *J. Physique* **46**, 1717 (1985).
- ³²J. Huck, A. Bondeau, G. Noyel and L. Jorat, *IEEE Trans. Electrical Insulation* **23**, 615 (1988).
- ³³D. Baril, C. Michot and M. Armand, *Solid St. Ionics* **94**, 35 (1997) 35.
- ³⁴J. J. Fontanella, M. C. Wintersgill, P. E. Stallworth, S. A. Newman, S. H. Chung, Y. Wang and S. G. Greenbaum, *Solid St. Ionics*, submitted.
- ³⁵H. W. Starkweather, Jr., P. Avakian, R. R. Matheson, Jr., J. J. Fontanella and M. C. Wintersgill, *Macromolecules* **25**, 1475 (1992).
- ³⁶M. C. Wintersgill, J. J. Fontanella, M. K. Smith, S. G. Greenbaum, K. J. Adamic and C. G. Andeen, *Polymer* **28**, 633 (1987).
- ³⁷K. J. Adamic, S. G. Greenbaum, M. C. Wintersgill and J. J. Fontanella, *J. Appl. Phys.* **60**, 1342 (1986).
- ³⁸Y. S. Pak, K. J. Adamic, S. G. Greenbaum, M. C. Wintersgill, J. J. Fontanella and C. S. Coughlin, *Solid State Ionics* **45**, 277 (1991).

- ³⁹J. J. Fontanella, M. G. McLin and M. C. Wintersgill, *J. Polymer Sci.: Polymer Phys.* **32**, 501 (1994).
- ⁴⁰J. J. Fontanella, M. C. Wintersgill, J. P. Calame, M. K. Smith and C. G. Andeen, *Solid State Ionics* **18&19**, 253 (1986).
- ⁴¹C. A. Edmondson, M. C. Wintersgill, J. J. Fontanella, F. Gerace, B. Scrosati and S. G. Greenbaum, *Solid State Ionics* **85**, 173 (1996).
- ⁴²J. J. Fontanella, C. A. Edmondson, M. C. Wintersgill, Y. Wu and S. G. Greenbaum, *Macromolecules* **29**, 4944 (1996).
- ⁴³M. C. Wintersgill and J. J. Fontanella, *Electrochim. Acta* **43**, 1533 (1998).
- ⁴⁴J. J. Fontanella, M. C. Wintersgill, J. S. Wainright, R. F. Savinell and M. Litt, *Electrochim. Acta* **43**, 1289 (1998).
- ⁴⁵K. S. Cole and R. R. Cole, *J. Chem. Phys.* **9**, 341 (1941).
- ⁴⁶H. Vogel, *Physik Z.* **22**, 645 (1921); V. G. Tammann and W. Hesse, *Z. Anorg. Allg. Chem.* **156**, 245 (1926); G. S. Fulcher, *J. Amer. Ceram. Soc.* **8**, 339 (1925).
- ⁴⁷H. V. St. A. Hubbard, J. P. Southall, J. M. Cruickshank, G. R. Davies and I. M. Ward, *Electrochim. Acta*, **43**, 1485 (1998).
- ⁴⁸A. Kovacs, *Adv. Polym. Sci.* **3**, 394 (1964).
- ⁴⁹M. L. Williams, R. F. Landel, and J. D. Ferry, *J. Am. Chem. Soc.* **77**, 3701 (1955).
- ⁵⁰C. A. Angell, *Polymer* **26**, 6261 (1997).
- ⁵¹M. D. Ediger, C. A. Angell and S. R. Nagel, *J. Phys. Chem.* **100**, 13200 (1996).
- ⁵²J. T. Bendler and M. F. Shlesinger, *J. Stat. Phys.* **53**, 531 (1988).
- ⁵³J. T. Bendler and M. F. Shlesinger, *Nuc. Phys.* **5A**, 82 (1988).
- ⁵⁴J. T. Bendler and M. F. Shlesinger, *J. Mol. Liquids* **36**, 37 (1987).
- ⁵⁵M. Schmidt and F. H. J. Maurer, *J. Polym. Sci. Part B: Polym. Phys* **36**, 1061 (1998).

- 56J. J. Fontanella, M. C. Wintersgill, J. P. Calame, F. P. Pursel and D. R. Figueroa, *Solid St. Ionics* **9&10**, 1139 (1983).
- 57J. J. Aklonis, W. J. MacKnight and M. Shen, *Introduction to Polymer Viscoelasticity*, (Wiley, New York, 1972).
- 58S. P. Andersson and O. Andersson, *Macromolecules* **31**, 2999 (1998).
- 59G. Williams, *Trans. Far. Soc.* **61**, 1464 (1965).
- 60S. W. Smith, B. D. Freeman, C. K. Hall, *Macromolecules* **30**, 2052 (1997).

Table I. Best-fit parameters for various formalisms. All of the results are for the temperature range 215.7 to 345.3K.

VTF	$\log_{10}(\sigma_0(\text{S/cm}))$	B (K)	T_0 (K)	RMS dev	
	-0.625	1273	171.7	0.0348	
Modified VTF	$\log_{10}(A(\text{K}^{1/2}\text{S/cm}))$	B' (K)	T_0' (K)	RMS dev	
	+0.722	1312	170.9	0.0322	
WLF	$\log_{10}(\sigma(T_g))$	C_1	C_2 (K)	RMS dev	
	-12.54	11.91	46.43	0.0348	
BENSH	$\log_{10}(D(\text{S/cm}))$	B'' ($\text{K}^{3/2}$)	T_c (K)	γ	RMS dev
	-1.68	13450	151.9	1	0.0157
	-2.12	116175	134.9	1.28	0.0098

Table II. Effect of pressure on the electrical conductivity for PPG-1025:LiCF₃SO₃ and other materials from the literature.

T	a	b	$\chi_T/3^a$	$\frac{\partial \ln \sigma}{\partial p}$	ΔV
(K)	(GPa) ⁻¹	(GPa) ⁻²	(GPa) ⁻¹	(GPa) ⁻¹	(cm ³ /mol)
PPG:LiCF ₃ SO ₃					
268.1	-30.00	-9.57	0.13	-29.87	66.6
273.1	-27.25	-9.44	0.13	-27.12	61.6
285.1	-23.00	-4.04	0.13	-22.87	54.2
295.1	-20.48	-0.74	0.14	-20.34	49.9
308.1	-16.92	-0.81	0.14	-16.78	43.0
323.2	-13.83	-1.42	0.15	-13.68	36.8
343.3	-10.91	-0.99	0.15	-10.76	30.7
363.2	-8.17	-2.48	0.16	-8.01	24.2

FIGURE CAPTIONS

Figure 1. Complex impedance diagram for PPG-1025:LiCF₃SO₃ at 215.7K. The data are shown as squares. The best-fit Cole-Cole expression (Eq. (1)) is shown by the solid line. The circle represents the center of the best-fit arc and the x represents the intercept of the arc with the Z' axis which is identified as the bulk resistance.

Figure 2. Electrical conductivity vs. reciprocal temperature for PPG-1025:LiCF₃SO₃. The best-fit 3 parameter BENSH expression (Eq. (6) with $\gamma=1$) is shown by the solid line.

Figure 3. Relative conductance vs. pressure for PPG-1025:LiCF₃SO₃ at various temperatures.

Figure 4. DSC thermograms for PPG-1025 and PPG-1025:LiCF₃SO₃.

Figure 5. Difference between the experimental and theoretical electrical conductivity for various formalisms vs. temperature.

Figure 6. VTF fitting parameters B and T_0 vs. temperature for 100°C intervals of electrical conductivity data. The temperature is the temperature at the middle of the interval.

Figure 7. VTF fitting parameter σ_0 vs. temperature for 100°C intervals of electrical conductivity data. The temperature is the temperature at the middle of the interval.

Figure 8. WLF fitting parameters C_1 and $\sigma(T_g)$ vs. temperature for 100°C intervals of electrical conductivity data. The temperature is the temperature at the middle of the interval.

Figure 9. WLF fitting parameters C_2 vs. temperature for 100°C intervals of electrical conductivity data. The temperature is the temperature at the middle of the interval.

Figure 10. Apparent activation volume vs. reduced temperature ($T-T_g$) for various PPG-based materials. (a) Value from Ref. 24 for the relaxation time of the α relaxation in high molecular weight PAREL™ elastomer containing no salt. The following results are from Ref. 24 for high molecular weight PAREL™ elastomer containing the following salts in an 8:1 repeat unit to lithium ion ratio: (b) LiCF_3SO_3 ; (c) LiClO_4 ; (d) LiI ; (e) LiSCN . The results represented by (f) are from Ref. 25 for high molecular weight PAREL™ elastomer containing NaClO_4 in an 8:1 repeat unit to sodium ion ratio. (f) Value from Ref. 58 for the relaxation time of the α relaxation in PPG-4000. (g) Values from Refs. 59 and 60 for the relaxation time of the α relaxation in PPG-4000.

Figure 11. Apparent activation volume vs. electrical conductivity for PPG-1025: LiCF_3SO_3 .





Fig. 1.






Fig 3




Fig 7




Fig. 5




Fig 6




Fig 7




Fig. 5




Fig 7




Fig. 10




Fig. 1