


REPORT DOCUMENTATION PAGE

Form Approved
OMB NO. 0704-0188

Public Reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comment regarding this burden estimates or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188,) Washington, DC 20503.

1. AGENCY USE ONLY (Leave Blank)		2. REPORT DATE 5/18/01	3. REPORT TYPE AND DATES COVERED Final Report 7/01/98- 12/31/00 31 Oct 00	
4. TITLE AND SUBTITLE Electro-Optics based on Novel Materials Modifications			5. FUNDING NUMBERS ARO Contract No. DAAG55-98-C-0045	
6. AUTHOR(S) Charles A. Evans, Jr. & Robert G. Wilson				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Charles Evans & Associates			8. PERFORMING ORGANIZATION REPORT NUMBER FINAL	
9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES) U. S. Army Research Office P.O. Box 12211 Research Triangle Park, NC 27709-2211			10. SPONSORING / MONITORING AGENCY REPORT NUMBER 38761.1-EL	
11. SUPPLEMENTARY NOTES The views, opinions and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy or decision, unless so designated by other documentation.				
12 a. DISTRIBUTION / AVAILABILITY STATEMENT Approved for public release; distribution unlimited.			12 b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) This report describes work done and results obtained from 1 July 1998 through 31 Dec 2000. The report is divided into sections by technical area. Aims or goals of this work included growth, doping, and characterization of new materials of interest to ARO for electro-optics and electronics applications within the DoD, often involving support for university research through collaborative programs initiated by Dr. John Zavada. A concomitant goal is the publication of papers that describe the results of this work and these collaborations. The principal investigators for this program were Dr. C.A. Evans, Jr., of Charles Evans & Associates, and Dr. R.G. Wilson, Consultant.				
			15. NUMBER OF PAGES 11	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OR REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION ON THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT UL	



20010607 073

REPORT DOCUMENTATION PAGE (SF298)
(Continuation Sheet)

MASTER COPY: PLEASE KEEP THIS "MEMORANDUM OF TRANSMITTAL" BLANK FOR REPRODUCTION PURPOSES. WHEN REPORTS ARE GENERATED UNDER THE ARO SPONSORSHIP, FORWARD A COMPLETED COPY OF THIS FORM WITH EACH REPORT SHIPMENT TO THE ARO. THIS WILL ASSURE PROPER IDENTIFICATION. NOT TO BE USED FOR INTERIM PROGRESS REPORTS; SEE PAGE 2 FOR INTERIM PROGRESS REPORT INSTRUCTIONS.

MEMORANDUM OF TRANSMITTAL

U.S. Army Research Office
ATTN: AMSRL-RO-BI (TR)
P.O. Box 12211
Research Triangle Park, NC 27709-2211

- | | |
|----------------------------------------------------|------------------------------------------------------------------------|
| <input type="checkbox"/> Reprint (Orig + 2 copies) | <input type="checkbox"/> Technical Report (Orig + 2 copies) |
| <input type="checkbox"/> Manuscript (1 copy) | <input type="checkbox"/> Final Progress Report (Orig + 2 copies) |
| | <input type="checkbox"/> Related Materials, Abstracts, Theses (1 copy) |

CONTRACT/GRANT NUMBER:

REPORT TITLE:

is forwarded for your information.

SUBMITTED FOR PUBLICATION TO (applicable only if report is manuscript):

Sincerely,

FINAL REPORT

Electro-Optics Based on Novel Materials Modifications

ARO Contract Number DAAG55-98-C-0045

Period covered: 1 July 1998 through 31 Dec 2000

Performed at: Charles Evans and Associates

Principal Investigators: Drs. C.A. Evans, Jr. and R.G. Wilson

Introduction

This report describes work done and results obtained from 1 July 1998 through 31 Dec 2000. The report is divided into sections by technical area.

Aims or goals of this work included growth, doping, and characterization of new materials of interest to ARO for electro-optics and electronics applications within the DoD, often involving support for university research through collaborative programs initiated by Dr. John Zavada. A concomitant goal is the publication of papers that describe the results of this work and these collaborations.

The principal investigators for this program were Dr. C.A. Evans, Jr. of Charles Evans and Associates, and Dr. R.G. Wilson, Consultant.

Summary of work carried out, and results

III-Nitrides

Research related to the growth, characterization, and fabrication of devices in III-nitrides, including GaN, AlN, GaAlN, InGaN, and InAlN, are intended to be a significant effort on this contract. III-nitrides are currently of great interest for both optical and electronic devices and applications, including blue, green, and violet LEDs and high power/high temperature electronics (microelectronics, especially microwave). Our contributions in this field include ion implantation for doping and co-doping (Mg, Ca, P, C, Si, Er, Pr) and for

impurity characterization using SIMS (H, C, O, Si); SIMS measurements of both intentional and unintentional impurities -- both concentration and depth profiles.

Photoluminescence measurements are another important area of work in these nitrides. Band edge measurements are being made at Kansas State Univ. (Prof. X. Jiang) and longer wavelength measurements are being made at Hampton University (Prof. U. Hoemmerich). Related papers are listed in the last section on Publications. Figure 4 shows a representative PL measurement of band edge luminescence (Kansas State Univ.) and Fig. 5 shows a representative PL measurement of 1.54 μ m stimulated radiation (Hampton Univ.).

GaN and rare earth implantation

III-nitrides, and GaN in particular, have become important for high temperature and high voltage devices and for optical devices, including all color LEDs and lasers. AlN and AlGaIn are used in these devices. Many laboratories are working on the growth and doping of device structures using III-nitrides. Because of this and our involvement in this work, we continued to improve our SIMS analysis capability for III-nitrides. We continued to prepare ion implanted standards for SIMS analyses and to improve SIMS analysis techniques for III-nitrides using these standards. Because GaN is often grown on sapphire substrates (when not on SiC), which are good insulators, the best SIMS technology was often in the past to use a quadrupole instrument. We improve the technology for using CAMECA sector magnet SIMS equipment, which will improve quantification, consistency, increased sputtering rate (an advantage for deep analyses), and allow the use of high mass resolution. We spent considerable time implanting SIMS standards and studying SIMS analysis approaches in this work. An important result is that this work has provided a good SIMS analysis capability for III-nitrides at Charles Evans and Associates. Government programs such as this ARO contract benefit from this SIMS analysis capability.

We implanted various GaN materials with Er and Pr, and also with oxygen to act as a co-activator, although we stopped this latter process during the year (because we determined that sufficient oxygen exists in these materials as-grown). We annealed some of these samples, and sent all of them on to Kansas State and Hampton Univ. for band edge luminescence and for stimulated PL emission measurements at 1.5 or 1.3 μ m, for Er and Pr, respectively. The results of these measurements were sent to John Zavada, who keeps the various involved people informed.

We prepared Si 'witness' samples of our implants of Er and Pr for SIMS measurements of the depth profiles of Er or Pr, and for RBS measurements of the implanted Er or Pr as checks on the implantation process. This is critical because implants of Er and especially Pr are very difficult and often contain impurities in the ion beam at masses close to those of Er and Pr that are the result of the high required temperature that causes Fe

chlorides from the ion source, and from prior implants of elements that also combine with Cl in the ion source, or have interfering molecular ions in the mass range from 135 to 175. We spend a significant effort performing SIMS and RBS measurements on these samples, and re-implanting samples when these measurements show that the implants are not what was intended.

We mounted pieces of GaN from UTA, KSU, and UFL, plus witness Si for Pr implantation, and attempted to implant Pr - unsuccessfully once; with what turned out to be a low fluence of Pr on the second attempt; and with what turned out to be the desired fluence ($5.7 \times 10^{13} \text{ cm}^{-2}$) on the third attempt. These Pr-implanted samples of GaN were studied at Kansas State and Hampton Universities for band edge and infrared PL in conjunction with fairly high annealing temperatures. Now that the optical testing of these samples is completed, we will measure (early 2001), using SIMS, the depth profiles of Pr to determine whether any redistribution of Pr has occurred during the associated annealing. The quality of these implants was determined using both SIMS and RBS measurements, made in our laboratory.

Certain rare earth elements emit light of specific wavelengths under electrical or optical stimulation from essentially any matrix into which they are introduced. The presence of oxygen in some host materials is known to enhance the intensity of this emission. Important examples of these elements are Er and Pr because of the application to optical communication systems, namely $1.5 \mu\text{m}$ for Er and $1.3 \mu\text{m}$ for Pr. We pursued the development of an implantation capability for Er and Pr and implanted these elements in a variety of materials. This technology for Er and Pr is now well established, but implanting Pr proved to be more difficult. The problems were solved by using a separate ion source dedicated to rare earth elements.

In collaboration with Professor Steve Bishop of University Illinois, we studied Mg- and Er-doped GaN for Mg, Er, and other elements using SIMS and calibrated using implanted standards in the same material. We measured the density of Mg and of Er in several samples on GaN. We implanted Mg and Er into samples of material that University of Illinois had been studying for photoluminescence (PL) emission. We determined the doping level of Mg in Er-implanted Mg-doped GaN. We implanted Er in some GaN. We also measured the amount of C and O in these samples.

A project was initiated to study PL emission from samples of GaN doped with two rare earth elements or one rare earth element and another element. We implanted Er plus Yb, Er plus Cr, and Yb plus Cr, and Yb and Cr only. These samples were submitted for PL measurements. Some of these samples were annealed at Kansas State University at temperatures of 900, 1000, and 1100°C. We measured the depth distributions of the implanted species using SIMS.

GaN SIMS analysis

In support of the improved SIMS analysis capability described in the preceding section, some work with implanted SIMS standards in GaN are described here. We have implanted various elements into samples of GaN and performed various SIMS analyses using those standards. Included are: ^1H and ^2H , ^{12}C , ^{16}O and ^{18}O , ^{24}Mg , ^{28}Si and ^{30}Si , ^{32}S and ^{34}S , ^{54}Fe and ^{56}Fe , ^{58}Ni , ^{80}Se , ^{128}Se , and ^{130}Se . All of these elements produce depth profiles, but some are better than others. Sometimes densities of impurities in nitride materials cause high background levels. This emphasizes the need to use the rarer isotopes, which are included in the above listing. We have studied and compared the relative value of different SIMS analysis approaches, namely oxygen bombardment and positive secondary ions, cesium bombardment and positive secondary ions using Cs molecules (e.g. MgCs^+ and ZnCs^+), and cesium bombardment and negative secondary ions using atomic ions and molecular ions (e.g. SiN^-).

Implanted dopants in GaN

We implanted Be, C, Mg, S, Se, Te into GaN (to go with Si already done), annealed samples at temperatures up to 900°C (CE&A/RGW) and at 1000 , 1100 , 1200 , 1300 , and 1400°C (Univ. Florida), then measured the resulting depth distributions using SIMS. Results: Be, C, Mg, S, Se, and Te do not redistribute for temperatures up to 1450°C in GaN (1200°C for Be). This result is in contrast to all other materials studied so far, and demonstrates the great thermal stability of GaN and dopants in GaN. This is a significant result that has been demonstrated under this program. Several publications have put these results into the 1998/99 literature; See the list of Publications at the end of this report. This result is also in some disagreement with previous data measured and reported under this program, namely: redistribution of Be and S were observed. The explanation is probably that the quality of the early material was poor. Much improvement has been made in the last two years in the quality of GaN. Probably defects or columnar structure with associated grain boundaries existed in previous material. The material used in this 1998 set of measurements was all the same and all from EMCORE. In particular, the new S data are very nice, and the new Be data show only a slight decrease in intensity for the highest temperature, but no significant redistribution. Thus, only H shows redistribution for temperature greater than 1000°C , and then only really in p-type material, very little in n-type.

Study of behavior of hydrogen in n- and p-type GaN

We collaborated in a study of the behavior of H in n- and p-type GaN with Univ. Florida (UFL) (Profs. S. Pearton, C. Abernathy, and F. Ren). We performed anneals at temperatures up to 900°C in a furnace. Then UFL did anneals at temperatures of 1000, 1100, and 1200°C in a special flash lamp annealer. We subsequently measured the depth distributions of H using SIMS. Results: The two sets of anneals match up to some extent, but not exactly. UFL's anneals were 10 s RTP; ours were 10-min furnace anneals -- something might be different about the two processes. Another difference to note is that there is a substrate interface shallower for the p-type than for the n-type, an interface that could be the source of defects and "gettering" of the H. The first profiles showed a pile-up of H at that interface for 800 and 900°C. The higher temp RTP anneals show no H at all. The data for the n-type material are consistent - and better. The profiles for 1000, 1100, & 1200°C are similar and fit with the lower temperatures but there is less change than might have been expected.

Er implanted materials

Following is a summary list of the materials that were implanted with Er (and some with Pr) during the three years of this ARO program: diamond, Si, SiC, SiGe, Ge, AlN, GaN, GaP, GaAs, AlGaAs, InP, InAs, InSb, SiO₂, Si₃N₄, Al₂O₃, LiNbO₃, ZnSe, Al, Ni, and Au. Annealing studies were carried out on some of these materials, with SIMS measurements made to determine thermal stability and redistribution.

Hydrogen in Other Materials

Studies of the properties and effects of H in III-nitride materials and other optoelectronic materials was one thrust of our research, especially in collaboration with the group at University of Florida. A summary of that work is given below.

Residual hydrogen in MOVCD-grown device structures such as heterojunction bipolar transistors, thyristors, and p-i-n diodes intended for high power, high temperature applications, that originates from the growth precursors decorates Mg-doped layers and AlGaIn/GaN interfaces. There is a significant difference in the diffusion characteristics and thermal stability of implanted H between n- and p-type GaN, caused by the stronger affinity of H to pair with acceptor dopants and possibly to the difference in H₂ formation probability.

Atomic H permeates GaN during various device processing steps. This indiffusion is enhanced by the presence of high defect densities in heteroepitaxial materials. SIMS

profiling after processing using deuterated chemicals (to enhance the SIMS detection sensitivity) show that H can diffuse into GaN at temperatures as low as 80°C. The primary effect of this H is passivation (electrical de-activation) of Mg acceptors in p-GaN via formation of neutral Mg-H complexes, which can be dissociated through either minority carrier (electron) injection or simple annealing. We have evidence that all acceptors in GaN, viz. C, Mg, Ca, Zn, and Cd, form complexes with H.

GaN device structures for LEDs and other optical devices

We collaborated with Univ. California at Santa Barbara (UCSB) (Profs. J. Speck and S. denBaars) for characterization and rare-earth doping of GaN (and other III-nitride materials). SIMS results of GaN layers and structures received from UCSB (grad. student Monica Hansen)

We measured depth distributions of H, C, O, and Si, using SIMS, in a sample of template GaN for the subsequent growth of laser diode structures for Er pumping (implanted and or grown-in). Results: This material is very clean, for GaN. The measured densities of H, C, O, and Si were essentially the background densities or the SIMS measurement (10^{17} for C, and about 10^{18} for H, O, and Si). However, the sample is not Si-doped, as was intended, unless the intended doping was less than $5 \times 10^{17} \text{ cm}^{-2}$.

An MBE-grown layer of Si-doped GaN grown on MOCVD GaN was studied for comparison of H, C, and O impurity concentrations - between MBE and MOCV. We carried out the same measurements for an MBE-grown Si-doped layer of GaN on an MOCVD-grown GaN layer. Results: This sample had a 60-nm surface layer doped with Si at $1 \times 10^{20} \text{ cm}^{-2}$. H, C, and O were all modest impurities (mid 10^{19} cm^{-2}) in both the MBE and MOCVD layers, compared with the template material GAl.

We analyzed the LED structure for both the elements, H, C, O, and Si, and also for composition of structure. In general, the structure agreed with the intended one, but with the following differences: There was no significant Si doping of the deep GaN, AlGaN (thick), or InGaN layers, unless that doping was intended to be less than 5×10^{17} or $1 \times 10^{18} \text{ cm}^{-2}$. The In content appeared to be low; it was about 1 % of the Ga. A strong C impurity (mid to high 10^{19} cm^{-2}) tracks the Al content.

Er was successfully implanted into pieces of the above samples along with other materials. The Er implants were verified using SIMS measurements made on a witness piece of Si implanted beside these samples, and the fluence was verified to be approximately $5 \times 10^{13} \text{ cm}^{-2}$. These samples were then delivered to UCSB for subsequent device layer growth and characterization.

3C SiC

We carried out research on 3C SiC with both Professors A. Steckl of Univ. of Cincinnati, and Prof. James Kolodzey of Univ. of Delaware. We received a sample of 3C SiC (a film grown on a Si wafer) from post doc Cyril Guedj at Univ. Delaware - for implantation of high dose Ge alone and also plus H. These implants were performed, and the samples were returned to UDE. Some interesting results are being obtained.

ZnSe, ZnTe, and CdTe

II-VI materials can have large or small bandgaps. They are of interest for a variety of applications, one of which is detectors, especially for long wavelengths. We carried out a modest investigation of some undoped and doped II-VI materials by performing materials analyses using SIMS. We determined the annealing behavior of H in ZnSe by implanting H, annealing, and measuring the resulting depth distributions using SIMS. We obtained some undoped and some Al-doped ZnSe, and some undoped ZnTe from France. We included some of our own CdTe (obtained originally from SBRC). We performed mass surveys of these materials using SIMS to determine what impurities are present and in what approximate densities. Some of the ZnTe samples had been treated with a ^2H plasma. We measured the resulting depth distributions of ^2H using SIMS. We implanted the undoped and Al-doped samples of ZnSe with ^2H and annealed pieces of these at temperatures of 300, 400, and 500°C, and measured the resulting depth profiles using SIMS.

More work for other annealing temperatures was prevented by the small amount of materials available. Some of these results are summarized below. For the undoped sample, at 400°C the ^2H profile moved deeper into the ZnSe and did not disappear. For the 500°C anneal, the ^2H density decreased some and the profile moved even deeper into the ZnSe material. Clearly, the behavior of H in ZnSe varies significantly depending on whether or not the material is doped (with Al in this case).

Before we received the ZnTe samples from France, they had been treated with a ^2H plasma and had been profiled for ^2H . We also profiled these samples for ^2H and obtained agreement with the previous profiles, but obtained substantially greater detection sensitivity, which allowed us to measure better the details of the ^2H at lower impurity densities, and with better depth resolution. Two or three growth interfaces could be measured in our analyses (two in one sample and three in the other sample).

University Support

During the course of this contract work, we collaborated with research groups and university professors and their graduate students and post doctoral fellows. These collaborations are listed below. (9 universities and about 55 personnel)

Hampton University: Prof. U. Hoemmerich, J.T. Seo, M.Thaik, X. Wu, G. Ofori-Boadu, J. Prejean

Kansas State University: Prof. H. X. Jiang, R.A. Mair, C.J. Ellis, J.Y. Lin

Lehigh University: M.G. Weinstein, C.Y. Song, Prof. M. Stavola C.Y. Song

University of California at Santa Barbara: Prof. J. Speck and student Monica Hansen

University of Cincinnati: Prof. A. Steckl

University of Delaware: Prof. J. Kolodzey, Post-doc Cyril Guedj, M. Dashiell, G. Katulka C. Swann, M.W. Tsao, J. Rabolt

University of Texas at Austin: Prof. R. Dupuis, P.A. Grudowski

University Illinois: Prof. S. Bishop

University Florida: Professors S.J. Pearton, C. Abernathy, and F. Ren, and M. Overberg, X.A. Cao, R.K. Singh, M. Fu, J.A. Sekhar, J.D. MacKenzie, H.J. Guo, S.J. Pennycook, V. Scarvepalli, J.R. LaRoche, J.R. Lothian, J.W. Lee, D. Johnson, C.-M. Lee, C.-C. Chuo, G.-C. Chi, G.T. Dang, A.P. Zhang, S.N.G. Chu, L. Zhang, S.M. Donovan, H. Cho, K.B. Jung, R.F. Kopf, C.B. Vartuli, W.S. Hobson, M.M. Mshewa, J.-I. Chyi
This has been a major collaboration - 31 persons and many papers.

Meetings with ARO personnel

Because John Zavada was located in London during the time of this contract work, communication between Wilson and Zavada was carried out via email whenever appropriate (about once each month) and by fax or phone about once every two months. Zavada and Wilson did meet in Boston at the MRS meeting there during 2-4 Dec 1999. All aspects of the this contract (past, present, and future) were discussed. Several days of face-to-face meetings were held early in June, 2000, in Strasbourg France during the EMRS (European Materials Research Society) conference. Again, all aspects of the program were discussed - data, collaborations, papers, past work, and work to be done. Other collaborators were also present at the Strasbourg meeting and productive joint discussions of past and future work were held. Javada came to California to meet with Wilson once, but was called to Washington DC before this meeting could occur. There were many subsequent conversations via telephone and facsimile.

Publications that resulted from this program

Many of the technical details of the work that was performed under this contract are described in the 50 references listed below, published during the years 1998, 1999, and 2000, the duration of this contract.

- S.J. Pearton, J.W. Lee, C.R. Abernathy, R.G. Wilson, J.M. Zavada, and J.C. Zolper, "Electrical and optical properties of C, O, and H in III-nitrides," *Electrochem. Soc. Proc.* **97-34**, 209 (1998)
- J. Kolodzey, O. Gauthier-Lafaye, S. Sauvage, J.-L. Perrossier, P. Boucaud, F.H. Julien, J.-M. Lourtioz, F. Ren, B.A. Omer, K. Roe, C. Guedj, R.G. Wilson, and J. Spear, "The effects of composition and doping on the response of GeC-Si photodiodes," *IEEE J. Selected Topics in Quantum Electron.* **4**, 964-69 (1998)
- X. A. Cao, C.R. Abernathy, R. K. Singh, S.J. Pearton, M. Fu, V. Sarvepalli, J. A. Sekhar, J.C. Zolper, D.J. Reiger, J. Han, T.J. Drummond, R.J. Shul, and R.G. Wilson, "Ultra-high Si⁺ implant activation efficiency in GaN using novel high temperature rapid thermal process system," *Appl. Phys. Lett.* **73**, 229-31 (1998)
- U. Hoemmerich, M. Thaik, T. Robinson-Brown, J.D. MacKenzie, C.R. Abernathy, S.J. Pearton, R.G. Wilson, R.M. Schwartz, and J.M. Zavada, "High temperature photoluminescence and electroluminescence excitation spectroscopy of Er-doped GaN," *Mat. Res. Soc. Symp. Proc.* **482**, 653 (1998)
- M. Thaik, U. Hoemmerich, R.N. Schwartz, R.G. Wilson, and J.M. Zavada. "Photoluminescence spectroscopy of erbium-implanted gallium nitride," *Appl. Phys. Lett.* **71**, 2641-43 (1997)
- S.J. Pearton, R.G. Wilson, J.C. Zolper, and J.M. Zavada, "Diffusion of dopants and impurities in GaN and related materials," *Defect and Diffusion Forum Vols.* **157-159**, 63-82 (1998)
- M.G. Weinstein, C.Y. Song, M. Stavola, S.J. Pearton, R.G. Wilson, R.J. Shul, K.P. Killeen, and M.J. Ludowise, "Hydrogen-decorated lattice defects in proton-implanted GaN," *Appl. Phys. Lett.* **72**, 1703-05 (1998)
- A.Y. Polyakov, N.B. Smirnov, A.V. Govorkov, M.G. Mil'vidskii, J.M. Redwing, M. Shin, M. Skowronski, D.W. Greve, and R.G. Wilson, "Properties of Si donors and persistent photoconductivity in AlGaIn," *Solid State Electron.* **42**, 627-35 (1998)
- J.D. MacKenzie, C.R. Abernathy, S.J. Pearton, U. Hoemmerich, J.T. Seo, R.G. Wilson, and J.M. Zavada, "Er doping of GaN during growth by metalorganic molecular beam epitaxy," *Appl. Phys. Lett.* **72**, 2710-12 (1998)
- S.J. Pearton, R.G. Wilson, J.M. Zavada, J. Han, and R.J. Shul, "Thermal stability of ²H-implanted n- and p-type GaN," *Appl. Phys. Lett.* **73**, 1877-79 (1998)
- X.A. Cao, R.K. Singh, S.J. Pearton, M. Fu, J.A. Sekhar, R.G. Wilson, J.C. Zolper, J. Han, D.J. Rieger, and R.J. Shul, "Ultra high temperature rapid thermal annealing of GaN," *E-MRS 1998, Mat. Issues Semicond. Processing* **1**, 267 (1999)
- S.J. Pearton, C.R. Abernathy, R.G. Wilson, J.M. Zavada, C.Y. Song, M.G. Weinstein, M. Stavola, J. Han, and R.J. Shul, "Effects of hydrogen implantation in GaN," *E-MRS 1998, Nucl. Instrum. Meth. Phys. Res.* **B147**, 171-74 (1999)
- X.A. Cao, R.G. Wilson, J.C. Zolper, S.J. Pearton, J. Han, R.J. Shul, D.J. Rieger, R.K. Singh, M. Fu, V. Scarvepalli, J.A. Sekhar, and J.M. Zavada, "Redistribution of implanted dopants in GaN," *Special Issue J. Electron. Mat.* **28**, 261 (1999)
- F. Ren, C.R. Abernathy, J.M. van Hove, P.P. Chow, R. Hickman, J.J. Klaasen, R.F. Kopf, H. Cho, K.B. Yung, J.R. LaRoche, R.G. Wilson, J. Han, R.J. Shul, A.G. Baca, and S.J. Pearton, "300° C GaN/AlGaIn heterojunction bipolar transistor," *MRS Internet J. Nitride Semicond. Res.* **3**, 41 (1998)

- X.A.Cao, S. J. Pearton, R.K. Singh, C.R. Abernathy, J. Han, R.J. Shul, D.J. Rieger, J.C. Zolper, R.G. Wilson, M. Fu, J.A. Sekhar, H.J. Guo, and S.J. Pennycook, "Rapid thermal processing of implanted GaN up to 1500°C," MRS Internet J. Semicond. Res. **451**, G 6.33.1 (1999)
- M.G. Weinstein, M. Stavola, C.Y. Song, C. Bozdog, H. Przbylinska, G.D. Watkins, S.J. Pearton, and R.G. Wilson, "Spectroscopy of proton-implanted GaN," MRS Internet J. Semicond. Res. **451**, G 5.9.1 (1999)
- U. Hoemmerich, M. Thaik, G. Ofori-Boadu, J. Prejean, J.T. Seo, J.D. MacKenzie, C.R. Abernathy, S.J. Pearton, R.G. Wilson, J.M. Zavada, and O. Ambacher, "Optical characterization of Er-doped III-nitrides prepared using MOMBE," MRS Internet J. Semicond. Res. **451**, G 11.6.1 (1999)
- R.G. Wilson, J.M. Zavada, X.A. Cao, R.K. Singh, S.J. Pearton, H.J. Guo, S.J. Pennycook, M. Fu, J.A. Sekhar, V. Scarvepalli, R.J. Shul, J. Han, D.J. Rieger, J.C. Zolper, and C.R. Abernathy, "Redistribution and activation of implanted S, Se, Te, Be, Mg, and C in GaN," J. Vac. Sci. Technol. **A17**, 1226-29 (1999)
- X.A. Cao, J.R. LaRoche, F. Ren, S.J. Pearton, J.R. Lothian, R.K. Singh, R.G. Wilson, H.J. Guo, and S.J. Pennycook, "Implanted p-n junctions in GaN," Solid State Electron. **43**, 1235-38 (1999)
- J. Han, A.G. Baca, R.J. Shul, C.G. Willison, L. Zhang, F. Ren, A.P. Zhang, G.T. Dang, S.M. Donovan, X.A. Cao, H. Cho, K.B. Jung, C.R. Abernathy, S.J. Pearton, and R.G. Wilson, "Growth and fabrication of GaN/AlGaIn heterojunction bipolar transistor," Appl. Phys.Lett. **74**, 2702-04 (1999)
- F. Ren, J. Han, R. Hickman, J.M. van Hove, P.P. Chow, J.J. Klaassen, J.R. LaRoche, K.B. Jung, H. Cho, X.A. Cao, S.M. Donovan, R.F. Kopf, R.G. Wilson, A.G. Baca, R.J. Shul, L. Zhang, C.G. Willison, C.R. Abernathy, and S.J. Pearton, "GaN/AlGaIn, HBT fabrication," Special Issue of Solid State Electron. **44**, 239-244 (2000)
- F. Ren, J.R. Lothian, S.J. Pearton, R.G. Wilson, J.R. LaRoche, J.W. Lee, D. Johnson, and J.M. Zavada, "Novel in-situ ion bombardment process for a thermally stable (>800°C) plasma-deposited dielectric," Electrochem & Solid-State Lett. **2**, 537 (1999)
- J.-I. Chyi, C.-M. Lee, C.-C. Chuo, G.-C. Chi, G.T. Dang, A.P. Zhang, F. Ren, X.A. Cao, S.J. Pearton, S.N.G. Chu, and R.G. Wilson, "Growth and device performance of GaN Schottky rectifiers," MRS Internet J. Nitride Semicond. Res. **4**, 8 (1999)
- S.J. Pearton, H. Cho, J.R. LaRoche, F. Ren, R.G. Wilson, and J.W. Lee, "Oxygen diffusion into SiO₂-capped GaN during annealing," Appl. Phys. Lett, **75**, 2939-41 (1999)
- G.T. Dang, A.P. Zhang, F. Ren, S.M. Donovan, C.R. Abernathy, W.S. Hobson, J. Lopata, S.N.G. Chu, X.A. Cao, R.G. Wilson, and S.J. Pearton, "p-ohmic contact resistance for GaAs(C)/GaN(Mg)," Solid State Electron. **44**, 105-109 (2000)
- G.T. Dang, A.P. Zhang, M.M. Mshewa, F. Ren, J.-I. Chyi, C.-M. Lee, C.C. Chuo, G.C. Chi, J. Han, S.N.G. Chu, R.G. Wilson, X.A. Cao, and S.J. Pearton, "High breakdown voltage Au/Pt/GaN Schottky diodes," J. Vac. Sci. Technol. **A18**, 1135 (2000)
- G.T. Dang, A.P. Zhang, F. Ren, X.A. Cao, S.J. Pearton, H. Cho, J. Han, J.-I. Chyi, C.-M. Lee, C.C. Chuo, S.N.G. Chu, and R.G. Wilson, "High voltage Schottky rectifiers," IEEE Trans. Electron Devices, **47**, 692-96 (2000)
- J.M. Zavada, R.A. Mair, C.J. Ellis, J.Y. Lin, H.X. Jiang, R.G. Wilson, P.A. Grudowski, and R.D. Dupuis, "Optical transitions in Pr-implanted GaN," Appl. Phys. Lett. **75**, 790-92 (1999)
- S.J. Pearton, C.R. Abernathy, R.G. Wilson, J.M. Zavada, C.Y. Song, M.G. Weinstein, M.Stavola, J. Han, and R.J. Shul, "Effects of hydrogen implantation into GaN," Nucl. Instrum. Meth. Phys. Res. **B147**, 171-74 (1999)
- X.A. Cao, S.J. Pearton, G.T. Dang, A.P. Zhang, F. Ren, R.G. Wilson, and J.M. van Hove, "Creation of high resistivity GaN by implantation of Ti, O, Fe, or Cr," J. Appl. Phys. **87**(3) Feb (2000)
- A.Y. Polyakov, N.B. Smirnov, A.V. Govorkov, J. Han, G. Dang, A.P. Zhang, F. Ren, X.A. Cao, S.J. Pearton, and R.G. Wilson, "Electrical properties and defect states in undoped, high resistivity GaN films used in high-power rectifiers," J. Vac. Sci. Technol. **B18**, 1237-43 (2000)

- S.J. Pearton, H. Cho, F. Ren, J.-I. Chyi, J. Han, and R.G. Wilson, "Properties and effects of H in GaN," MRS Internet J. Nitride Semicond. Res. **551**, w 10.6 (2000)
- X.A. Cao, G.T. Dang, A.P. Zhang, F. Ren, S.J. Pearton, C.-M. Lee, C.C. Chuo, J.-I. Chyi, G.C. Chi, J. Han, S.N.G. Chu, and R.G. Wilson, "Temperature dependent performance of GaN Schottky diode rectifiers," Internat. Conf. on SiC and Related Materials, Oct 1999; Mat. Sci. Forum **338-342**, 1631 (2000)
- S.J. Pearton, F. Ren, J. Han, J.-I. Chyi, C.-C. Chuo, J.M. Lee, G.T. Dang, A.P. Zhang, X.A. Cao, C.-M. Lee, S.N.G. Chu, R.G. Wilson, and J.M. van Hove, "GaN-based materials for microelectronics," Mat. ??? Proc. 1999 Internet. Semicond. Device Res. Symp. Charlottesville NC Dec 1999
- J.-I. Chyi, C.-M. Lee, C.C. Chuo, X.A. Cao, G.T. Dang, A.P. Zhang, F. Ren, S.J. Pearton, S.N.G. Chu, and R.G. Wilson, "Temperature dependence of GaN high breakdown voltage diode rectifiers," Solid State Electron. **44**, 613 (2000)
- C.R. Abernathy, M. Overberg, J.D. MacKenzie, U. Hoemmerich, S.J. Pearton, R.G. Wilson, and J.M. Zavada, "Effect of impurity concentration on 1.54- μ m emission from GaN:Er," SPIE Proc. **674**, 83 (2000)
- M. Overberg, C.R. Abernathy, S.J. Pearton, R.G. Willson, and J.M. Zavada, "Photoluminescence enhancement and morphological properties of C co-doped GaN:Er," MRS Boston 1999; MRS Internet J. Nitride emicond. Res. **551**, W11-62 (2000)
- A.P. Zhang, G.T. Dang, X.A. Cao, H. Cho, F. Ren J. Han, J.-I. Chyi, S.N.G. Chu, R.G. Wilson, and S.J. Pearton, "Processing and device performance of GaN power rectifiers," MRS Boston 1999; MRS Internet J. Nitride Semiconductor Res. **551**, W11-67 (2000)
- G.T. Dang, X.A. Cao, F. Ren, S.J. Pearton, J. Han, A.G. Baca. A.J. Shul, and R.G. Wilson, "Comparison of implant isolation species for GaN FET structures," MRS Boston 1999; MRS Internet J. Nitride Semicond. Res. **551**, W11-68 (2000)
- X.A. Cao, G.T. Dang, F. Ren, S.J. Pearton, R.G. Willson, J.M. van Hove, "High resistance implant isolation in n- and p-GaN," APR Mar Mtg., Minneapolis MN, Mar 2000 Paper V17 006
- M. Overberg, K.N. Lee, C.R. Abernathy, S.J. Pearton, W.S. Hobson, R.G. Wilson, and J.M. Zavada, "Characterization and annealing of Eu-doped GaN," E-MRS Strasbourg France, June 2000
- M. Overberg, C.R. Abernathy, J.D. MacKenzie, S.J. Pearton, R.G. Wilson, and J.M. Zavada, "Effect of carbon doping on GaN:Er," E-MRS Strasbourg France, June 2000
- J.M. Zavada, C.J. Ellis, J.Y. Lin, H.X. Jiang, J.T. Seo, U. Hoemmerich, M. Thaik, R.G. Wilson, P.A. Grudowski, and R.D. Dupuis, "Annealing behavior of luminescence from Er-implanted GaN films," E-MRS Strasbourg France, June 2000
- R.G. Wilson, "Impurities and dopants in III-nitrides measured using secondary ion mass spectrometry," E-MRS Strasbourg France, June 2000
- C.D. Brandle, F. Ren, R.G. Wilson, J.W. Lee, S.J. Pearton, and J.M. Zavada, "Etching and hydrogen incorporation in ScAlMgO₄," Mat. Res. Soc. Symp. Proc. **482**, 163 (1998)
- S.J. Pearton, J.W. Lee, R.G. Wilson, J.M. Zavada, M.G. Weinstein, C.Y. Song, and M. Stavola, "Hydrogen-in-GaN experiments," Mat. Res. Soc. Symp. Proc. **513**, 229 (1998)
- G. Katulka, C. Guedj, J. Kolodzey, R.G. Wilson, C. Swann, M.W. Tsao, and J. Rabolt, "Electrical and optical properties of Ge-implanted 4H-SiC," Appl. Phys. Lett. **74**, 540-42 (1999)
- R.G. Wilson, "SIMS analysis of wide band gap semiconductors," **Processing of wide band gap semiconductors** [xxxxxxxxxxxx, 1999] pp. 396-431