

			Form Approved OMB NO. 0704-0188	
Public Reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comment regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave Blank)		2. REPORT DATE 8/1/02		3. REPORT TYPE AND DATES COVERED Annual Technical, 10/1/00-9/30/01
4. TITLE AND SUBTITLE "Metamorphic HBTs: InP/InGaAs/InP devices grown on GaAs substrates"			5. FUNDING NUMBERS C-N00014-01-1-0065	
6. AUTHOR(S) Mark Rodwell				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) UCSB, Santa Barbara, CA 93106			8. PERFORMING ORGANIZATION REPORT NUMBER 442530-23091	
9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES) U. S. Army Research Office P.O. Box 12211 Research Triangle Park, NC 27709-2211			10. SPONSORING / MONITORING AGENCY REPORT NUMBER	
11. SUPPLEMENTARY NOTES The views, opinions and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy or decision, unless so designated by the documentation.				
12 a. DISTRIBUTION / AVAILABILITY STATEMENT Approved for public release; distribution unlimited.			12 b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words)  Please see attached.  <div style="text-align: center; font-size: 2em; font-weight: bold;">20020903 077</div>				
14. SUBJECT TERMS Metamorphic HBTs			15. NUMBER OF PAGES 11	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OR REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION ON THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT UL	

NSN 7540-01-280-5500

Standard Form 298 (Rev.2-89)  
Prescribed by ANSI Std. Z39-18  
298-102

## Enclosure 1

**GENERAL INSTRUCTIONS FOR COMPLETING SF 298**

The Report Documentation Page (RDP) is used for announcing and cataloging reports. It is important that this information be consistent with the rest of the report, particularly the cover and title page. Instructions for filling in each block of the form follow. It is important to **stay within the lines** to meet **optical scanning requirements**.

**Block 1. Agency Use Only (Leave blank)****Block 2. Report Date.** Full publication date including day, month, and year, if available (e.g. 1 Jan 88). Must cite at least year.**Block 3. Type of Report and Dates Covered.** State whether report is interim, final, etc. If**Block 12a. Distribution/Availability Statement.**

Denotes public availability or limitations. Cite any availability to the public. Enter additional limitations or special markings in all capitals (e.g. NORFORN, REL, ITAR).

**DOD** - See DoDD 4230.25, "Distribution Statements on Technical Documents."

**Enclosure 2**

Technical Report, ONR Program (N00014-01-1-0065)  
Program period: October 1, 2000 to September 30, 2001

"Metamorphic HBTs: InP/InGaAs/InP devices grown on GaAs substrates"

Mark Rodwell

Department of Electrical & Computer Engineering  
University of California, Santa Barbara, CA 93106

### Abstract

This program supported the development of metamorphic heterojunction bipolar transistors (MHBTs). We accomplished this by growing an InP based HBT layer structure on GaAs substrates. InP metamorphic buffer layer was chosen in thermal point of view. Peak values of current-gain cutoff frequency ( $f_t = 207$  GHz) and power-gain cutoff frequency ( $f_{max} = 140$ ) were obtained from *rf* devices at bias conditions of  $V_{CE} = 1.5$  Volts and  $J_C = 4 \times 10^5$  A/cm<sup>2</sup>. These are the highest values reported for metamorphic HBTs.

### Objectives

In recent years, research in high speed heterojunction bipolar transistors (HBTs) has been driven by circuit applications involving fiber IC chipsets at 40 Gb/sec, high frequency power amplifiers and new radar systems. HBTs with layers lattice-matched to InP substrates (InP HBTs) presently show the best high-frequency performance to realize these systems. These HBTs can have In<sub>0.52</sub>Al<sub>0.48</sub>As or InP emitters, In<sub>0.53</sub>Ga<sub>0.47</sub>As or GaAs<sub>0.52</sub>Sb<sub>0.48</sub> base layers, and InP or In<sub>0.53</sub>Ga<sub>0.47</sub>As collector layers. Their advanced performance results from the superior properties of In-based materials—including high electron mobility, large  $\Gamma$ -L energy separation, and low contact resistances. Unfortunately, InP substrates are small (10 cm) and much more expensive compared to GaAs substrates that are available in 15 cm diameters. Further, larger InP substrates are fragile and are readily broken during semiconductor manufacturing.

Extensive progress has been reported regarding metamorphic growth of InAlAs/InGaAs high mobility electron transistors (HEMTs) on GaAs substrates<sup>1,2</sup>. More recently, several groups<sup>3,4</sup> have reported InP-based HBTs grown on GaAs substrates, using InGaP or InGaAs metamorphic buffer layers. There the work focused on the physical quality of

---

<sup>1</sup> L. Edgar, N. I. Cameron, H. McLelland, M. C. Holland, M. R. S. Taylor, I. G. Thayne, C. R. Stanley, S. P. Beaumont, *Electron Lett.*, 35, 1114 (1999)

<sup>2</sup> S. Bollaert, Y. Cordier, V. Hoel, M. Zaknour, H. Happy, S. Lepilliet, A. Cappy, *IEEE Electron Device Lett.*, 20, 123 (1999)

<sup>3</sup> H. Q. Zheng, K. Radhakrishnan, H. Wang, K. H. Yuan, S. F. Yoon, G. I. Ng, *Appl. Phys. Lett.*, 77, 869 (2000)

<sup>4</sup> H. Hwang, J. Shieh, J. Chyi, *Solid State Electron.*, 43, 463 (1999)

the HBT epitaxial layers and the electrical performance of the device. Compared to HEMTs, HBTs have a larger active device area, the scales of integration are higher for HBT integrated circuits, and the devices typically operate at much higher power densities. Therefore, the crystal defect density *and* buffer layer thermal conductivity are both serious concerns that must be addressed in order for metamorphic HBTs to be practical.

Our goals were to develop high speed InP/InGaAs/InP and InAlAs/InGaAs heterojunction bipolar transistors (HBTs), grown and fabricated on GaAs substrates. We sought to demonstrate low leakage current HBT devices, even with metamorphic growth. Lastly we wanted to demonstrate that the thermal resistance of InP-related layers grown on GaAs can be made small, so that the high power densities associated with large integrated circuits and power amplifiers can be managed in the buffer layer and substrate.

### Approach

Metamorphic HBTs were developed with emphasis placed on the characterization and the reduction of defects that are associated the leakage currents in metamorphic growth, and on reducing the thermal resistance of the metamorphic buffer layer. In order to accomplish this, several materials were tried, (InAlAs, AlGaAsSb, InP)—with InP chosen because of its high thermal conductivity.

Material property measurements of the metamorphic HBTs included surface roughness measurement by AFM, thermal conductivity, and MHBT junction leakage currents. Surface roughness and thermal conductivity data are shown in table 1.


Material	Thermal conductivity (W/mK)	RMS roughness (nm)
Metamorphic AlGaAsSb	8.4	4.0
Metamorphic InAlAs	10.5	11.7
Metamorphic InP	16.1	9.5
GaAs bulk	44	
InP bulk	68	

**Table 1: Surface roughness and thermal conductivity data of three metamorphic buffer layers**

Buffer layer thermal conductivities were determined by measuring the thermal impedance of  $1\ \mu\text{m} \times 100\ \mu\text{m}$  Pt conductors of 50 nm thickness<sup>5</sup>. These conductors were deposited on the buffer layers after removing the HBT layer structure. The InP buffer layer shows the highest measured thermal conductivity, although it is much smaller than known for bulk InP. This is most probably due to the poor crystal quality of the metamorphic layer.

<sup>5</sup> A. W. Jackson, J. P. Ibbetson, A. C. Gossard, U. K. Mishra, Appl. Phys. Lett., 74, 2325 (1999)

In order to determine the influence of the metamorphic buffer layer's thermal conductivity on device temperature, the expected HBT collector junction temperature was calculated by solving the Laplace heat flow equation in 3 dimensions. A 45  $\mu\text{m}$  device-device separation was assumed for 30 HBTs—typical of smaller HBT integrated circuits. The assumed HBT emitter size was  $8 \times 0.5 \mu\text{m}^2$  and the operating power density was  $2 \cdot 10^5 \text{ W/cm}^2$ . A 1.5  $\mu\text{m}$  thick metamorphic buffer layer on a GaAs substrate was assumed. The heat flow simulations in figure 1 indicate that the HBT junction temperature is strongly influenced by the thermal conductivity of the metamorphic layer, and that the measured differences in thermal conductivity between AlGaAsSb (8.4 W/mK), InAlAs (10.5 W/mK), and InP (16.1 W/mK) buffer layers will have a considerable impact on the HBT operating temperature.




**Fig 1. Dependence of MHBT operating temperature on the thermal conductivity of the metamorphic layer. A metamorphic buffer layer thickness of 1.5  $\mu\text{m}$  is assumed.**

The expected HBT junction temperature was calculated to be 128°C, 112°C, and 89°C for AlGaAsSb, InAlAs, and InP buffer layers for the above device dimensions and power densities. This should be compared to a computed 65°C junction temperature which would result for a buffer layer of negligible thickness. Using the InP-based HBT reliability data<sup>6</sup>, the calculated HBT life-time is reduced by two orders of magnitude

<sup>6</sup> K.Kiziloglu, S. Thomas, F.Williams, B.M.Paine, IEEE Conference on Indium Phosphide and Related Materials, May, Williamsburg, VA, 294 (2000)

when the junction temperature is increased from 100°C to 150°C. The lifetimes of HBTs operating at a  $2 \cdot 10^5 \text{ W/cm}^2$  power density using InAlAs and AlGaAsSb buffer layers would approximately be 20:1 and 100:1 shorter than that of an HBT using an InP buffer layer. As HBT device and circuit speed is increased, the HBT operating power density must be increased beyond  $2 \cdot 10^5 \text{ W/cm}^2$ . Improvements in the thermal conductivity of the metamorphic layer are thus extremely important in future device design. Computed device junction temperatures as a function power density are shown in figure 2.



**Fig 2. Dependence of HBT device temperature with operating power density**

### Accomplishments

The devices fabricated employed an MBE epitaxial double-hetero layer structure with an InP emitter, 400 Å graded  $\text{In}_{0.53}\text{GaAs}$  highly doped base layer ( $\text{Be}: 4.0 \cdot 10^{19} \text{ cm}^{-3}$ ), a 100 Å InGaAs setback layer, a 240 Å CSL base-collector grade and a 1630 Å InP collector layer, resulting in a total collector depletion layer thickness of  $2 \text{ k}\text{\AA}$ . HBTs were fabricated in a narrow triple-mesa process using optical projection lithography and selective wet chemical etching. The use of narrow base-emitter and collector-base junctions reduces both the base resistance and the collector-base capacitance, and hence the charging times associated with these parasitics. While the emitter contact metal is  $0.7 \times 8 \text{ }\mu\text{m}^2$ , the emitter semiconductor is laterally undercut during the InP HCl-based etch. Because of this undercut, the physical base-emitter junction is  $0.4 \times 7.5 \text{ }\mu\text{m}^2$ . The collector-base capacitance is reduced by employing self-aligned, narrow base ohmic contacts of  $0.25 \text{ }\mu\text{m}$  width on both sides of the emitter stripe—producing a small  $1.2 \text{ }\mu\text{m} \times 11 \text{ }\mu\text{m}$  collector-

base junction area. After the deposition of base metal, the base and collector semiconductor are etched, exposing the device subcollector. Collector contacts are deposited and then devices are isolated by etching the remaining HBT semiconductor to the metamorphic layer. Polyimide is then deposited, cured, and etched for passivation and mesa planarization prior to interconnect deposition.

Figure 3 shows the common emitter characteristics, with a measured current density from 0 to  $4 \cdot 10^5$  A/cm<sup>2</sup>. The measured DC current gain is approximately 76, with a common-emitter open-circuit breakdown voltage  $BV_{CEO}$  at low current densities greater than 6 V, while  $V_{CE, Sat} < 0.8$  V at a current density of  $4 \cdot 10^5$  A/cm<sup>2</sup>. The measured sheet resistance of the metamorphic InP buffer layer is roughly 150 MΩ / square. The base sheet resistance is 1020 Ω / square — measured after the emitter mesa etch (which removed the upper 100 Å of the base layer) and base metal deposition. The corresponding hole mobility is 51 cm<sup>2</sup> / V·sec — 10% lower than we observe for similar lattice-matched DHBT growths.





Fig 3. DC characteristics for common emitter MHBT—  $0.4 \times 7.5 \mu\text{m}^2$  emitter area. The base current steps are 40  $\mu\text{A}$ .

Figure 4 shows the HBT Gummel [ $\log(I_C, I_B)$  vs  $V_{CE}$ ] characteristics, indicating a collector current ideality factor of 1.1 and a base current ideality factor of 2.2. The characteristics are measured with a non-zero (0.3 V) reverse bias applied to the collector-base junction, so that base-collector junction leakage, if present, will be observed. For comparison, figure 4 also shows the Gummel characteristics of a large-area HBT— $60 \times 60 \mu\text{m}^2$  base-emitter and  $100 \times 130 \mu\text{m}^2$  base-collector junctions fabricated from the same epitaxial material. Despite the large collector-base junction area, the Gummel characteristics indicate that  $I_{cbo}$  of the large-area HBT is below  $0.1 \mu\text{A}$ , signifying a collector-base leakage current per unit junction area below  $10^{-3} \text{ A/cm}^2$ .

The small-area HBTs were fabricated on a mask set designed with microwave on-wafer probe cal standards using the line-reflect-line method in a  $50 \Omega$  coplanar waveguide (CPW) environment. The line length between the probe pad and device terminal is  $230 \mu\text{m}$ . The leakage currents observed at low  $V_{BE}$  in figure 4 for the small-area HBT are dominated by those associated with conduction through the buffer layer between these long interconnects. And while HBTs are minority-carrier devices, and defect-induced leakage currents resulting from metamorphic growth are potential concerns, high DC current gains and low  $< 10^{-3} \text{ A/cm}^2$  base-collector leakage are nevertheless observed.




**Fig 4. Metamorphic HBT Gummel characteristics—**


**Device A (solid lines) represents a  $0.4 \times 7.5 \mu\text{m}^2$  base-emitter junction and a  $1.2 \times 11 \mu\text{m}^2$  base-collector junction,**

**Device B (dashed lines) represents a  $60 \times 60 \mu\text{m}^2$  base-emitter junction and a  $100 \times 130 \mu\text{m}^2$  base-collector junction.**

Figure 5 shows the short circuit current gain ( $h_{21}$ ) and unilateral power gain ( $U$ ) of the small-area HBTs, computed from the measured 45 MHz to 45 GHz S-parameters. A current-gain cutoff frequency  $f_{\tau} = 207$  GHz and power-gain cutoff frequency  $f_{max} = 140$  GHz were measured at  $I_C = 12.0$  mA ( $J_C = 4 \cdot 10^5$  A/cm<sup>2</sup>) and  $V_{CE} = 1.5$  V, as determined by a -20 dB/decade extrapolation. These are the highest values reported for metamorphic HBTs. Figure 6, shows the variation of  $f_{\tau}$  and  $f_{max}$  with collector current density, as measured at  $V_{CE} = 0.7$  V and  $V_{CE} = 1.5$  V. The observed decrease in  $f_{\tau}$  at very high current densities ( $2.5 \cdot 10^5$  A/cm<sup>2</sup> at  $V_{CE} = 0.7$  V,  $4.5 \cdot 10^5$  A/cm<sup>2</sup> at  $V_{CE} = 1.5$  V) is due to the Kirk effect.



**Fig 5. Short-circuit current gain,  $h_{21}$  and Mason's unilateral power gain,  $U$  for an MHBT. Device dimensions:  $0.4 \times 7.5 \mu\text{m}^2$  base-emitter junction and a  $1.2 \times 11 \mu\text{m}^2$  base-collector junction. DC bias conditions:  $I_C = 12.0$  mA,  $J_C = 4 \text{ mA} / \mu\text{m}^2$ , and  $V_{CE} = 1.5$  V**



**Fig 6. Measured current-gain cutoff frequency  $f_{\tau}$ , and power-gain cutoff frequency  $f_{max}$  vs. current density  $J_C$  at  $V_{CE} = 0.7$  Volts and  $V_{CE} = 1.5$  Volts.**

Postdoc Supported (Partial or complete support)  
YoungMin Kim, PhD. 1997

Publications for work supported under the contract

- |    |      |  |   |                     |
|----|------|--|---|---------------------|
| 1  | 2002 | Y.M.Kim, M.J.W.Rodwell,<br>A.C.Gossard, Thermal characteristics<br>of InP,InAlAs, and AlGaAsSb<br>metamorphic buffer layers used in<br>InAlAs/InGaAs heterojunction<br>bipolar transistors grown on GaAs<br>substrates, ,          | Journal of Electronic<br>Materials, Vol.31,<br>pp.196-199, 2002   | Journal Paper       |
| 2  | 2001 | Y.M. Kim, M. Dahlstrom, S. Lee,<br>M.J.W. Rodwell, A.C. Gossard.<br>InP/In <sub>0.53</sub> Ga <sub>0.47</sub> As/InP Double<br>Heterojunction Bipolar Transistors<br>on GaAs<br>Substrate Using InP Metamorphic<br>Buffer Layer    | . International<br>Semiconductor<br>Device Research<br>Symposium<br>December 5-7,<br>2001 Washington,<br>D.C. p 638-639 | Conference<br>Paper |
| 3. | 2002 | Y.M. Kim, M. Dahlstrom, S. Lee,<br>M.J.W. Rodwell, A.C. Gossard,<br>"InP/In <sub>0.53</sub> Ga <sub>0.47</sub> As/InP Double<br>Heterojunction Bipolar Transistors<br>on GaAs<br>Substrate Using InP Metamorphic<br>Buffer Layer." | Solid State<br>Electronics, Vol.46,<br>pp.1541-1544,<br>2001. Journal Paper   | Journal Paper       |
| 4  | 2002 | Y.M. Kim, M. Dahlstrom, S. Lee,<br>M.J.W. Rodwell, A.C. Gossard,<br>High-Performance<br>InP/In <sub>0.53</sub> Ga <sub>0.47</sub> As/InP Double<br>Heterojunction Bipolar<br>Transistors on GaAs Substrates.                       | IEEE Electron Device<br>Letters Vol.23, No.6,<br>pp. 297-299, 2002  | Journal Paper       |