

# REPORT DOCUMENTATION PAGE

Form Approved  
OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing this collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.

<b>1. REPORT DATE (DD-MM-YYYY)</b> 03-03-2003	<b>2. REPORT TYPE</b> View Graphs	<b>3. DATES COVERED (From - To)</b>
--	--------------------------------------	-------------------------------------

<b>4. TITLE AND SUBTITLE</b>  Review of POSS Effects on Polymers	<b>5a. CONTRACT NUMBER</b>
	<b>5b. GRANT NUMBER</b>
	<b>5c. PROGRAM ELEMENT NUMBER</b>

<b>6. AUTHOR(S)</b>  Rene Gonzalez	<b>5d. PROJECT NUMBER</b> 2303
	<b>5e. TASK NUMBER</b> M1A3
	<b>5f. WORK UNIT NUMBER</b>

<b>7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)</b>  Air Force Research Laboratory (AFMC) AFRL/PRSM 10 E. Saturn Blvd. Edwards AFB, CA 93524-7680	<b>8. PERFORMING ORGANIZATION REPORT NUMBER</b>  AFRL-PR-ED-VG-2003-063
--	---

<b>9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES)</b>  Air Force Research Laboratory (AFMC) AFRL/PRS 5 Pollux Drive Edwards AFB CA 93524-7048	<b>10. SPONSOR/MONITOR'S ACRONYM(S)</b>
	<b>11. SPONSOR/MONITOR'S NUMBER(S)</b> AFRL-PR-ED-VG-2003-063

**12. DISTRIBUTION / AVAILABILITY STATEMENT**  
  
Approved for public release; distribution unlimited.

**13. SUPPLEMENTARY NOTES**

**14. ABSTRACT**

20030617 170

**15. SUBJECT TERMS**

<b>16. SECURITY CLASSIFICATION OF:</b>			<b>17. LIMITATION OF ABSTRACT</b>	<b>18. NUMBER OF PAGES</b>	<b>19a. NAME OF RESPONSIBLE PERSON</b> Sheila Benner
<b>a. REPORT</b> Unclassified	<b>b. ABSTRACT</b> Unclassified	<b>c. THIS PAGE</b> Unclassified	A		<b>19b. TELEPHONE NUMBER</b> (include area code) (661) 275-5963

FILE

MEMORANDUM FOR PRS (In-House Publication)

FROM: PROI (STINFO)

10 Mar 2003

SUBJECT: Authorization for Release of Technical Information, Control Number: **AFRL-PR-ED-VG-2003-063**  
Capt. Rene I. Gonzalez, PhD, "Review of POSS Effects on Polymers"



**Lab Visitors and Scientists Briefing**  
**(Deadline: 14 Apr 2003)**

(Statement A)

# REVIEW OF POSS EFFECTS ON POLYMERS AND THE FUTURE 6.1 RESEARCH DIRECTION OF THE POSS PWG



*AFOSR Review for*

*Dr. Charles Y-C Lee*

*13 December 2002*

**Capt. Rene I. Gonzalez, Ph.D.**

**Project Leader**

**POSS-Polymer Working Group**

**Air Force Research Laboratory**

**(661)275-5252**

**rene.gonzalez@edwards.af.mil**


**DISTRIBUTION STATEMENT A**  
Approved for Public Release  
Distribution Unlimited




# OVERVIEW

---


---



- I. **POSS Programs/ People**
- II. **What is POSS and why use it?**
  - a) POSS polymer incorporation
  - b) Theorizing a POSS Model
  - c) Why POSS in not just a sphere & the importance of R
  - d) POSS synthesis / Cage variation
- III. **Quantitatively, What does POSS do in different polymer systems? (Our and Collaborators work / Including Highlights from the POSS Conference)**
  - a) Semicrystalline Polymers (Polyethylenes, PEO, PET)
  - b) Blends
  - c) Rubbers and TPE's (PN, Kraton)
  - d) Glassy Polymers (Polystyrene, PMMA)
  - e) Thermosets
  - f) Polyimides Space-Survivability AO Results
- IV. **POSS Lubricants**
- V. **Plan for refocusing our AFOSR sponsored 6.1 effort**



# Polymer Working Group - Research



## Basic R&D (6.1) PROGRAMS AFOSR

POSS Synthesis and Characterization  
POSS Polymer Processing  
POSS for Space-Survivable Materials



## Applied R&D (6.2) PROGRAMS AFRL

Solid Rocket Motor Insulation/Casing  
Liquid Rocket Engine Ducting  
High Temp Lubes/Jet Canopies/Radomes




Technology Transfer



# AFRL/PRSM People and Projects

---

---



**Dr. Tim Haddad:**  
**Mr. Brian Moore**

Basic R&D - POSS size and R group effects, reactivity ratios  
Appl. - Thermosets, POSS-polymers

**Dr. Rusty Blanski:**  
**Mr. Delbert Jung**

Basic R&D - POSS blends and additives  
Appl. - Lubricants, Rocket Motor Insulation

**Dr. Brent Viers:**

Basic R&D - Surface Science/Mechanical Properties, Li Batteries  
Nanotechnology POC for Propulsion Directorate  
Appl. - Coatings/Surface Properties, Mech. Tests

**Mr. Patrick Ruth:**

Basic R&D - Polymer processing, Blending  
Appl. - All Processing, Insulation, Electronic Encapsulants

**Capt. Rene Gonzalez:**  
**Dr. Sandra Tomczak:**


Basic R&D - Polymer Synthesis/Characterization, AO resistance,  
surface degradation, reactivity studies, POSS-Polyimides  
Appl. - Space Survivable Materials

**Dr. Joe Mabry**  
**Mrs. Becky Morello**


Basic R&D - High performance polymers, POSS Lubricants  
Appl. - LRE ducting tubing/Insulation

**Dr. Shawn Phillips**


Branch Chief




# Hybrid Inorganic/Organic Polymers





Goal: Develop High Performance Polymers that REDEFINE material properties



• Hybrid plastics bridge the differences between ceramics and polymers <sup>5</sup>





# Anatomy of a POSS Nanostructure





Precise three-dimensional structure for molecular level reinforcement of polymer segments and coils.




# Why POSS and Why Nano?



Field	Property	Critical Length
Electronics	Tunneling	1-100 nm
Optical	Quantum Well	1-100 nm
	Wave Decay	10-1000 nm
Polymers	Primary Structure	0.1-10 nm
	Secondary Structure	10-1000 nm
Mechanics	Dislocation Interaction	1-1000 nm
	Crack Tip Radius	1-100 nm
	Entanglement Rad.	10-50 nm
Therm-Mech.	Chain Motion	0.5-50 nm
Nucleation	Defect	0.1-10 nm
	Critical Nucleus Size	1-10 nm
	Surface Corrugation	1-10 nm
Catalysis	Surface Topology	1-10 nm
Biology	Cell Walls	1-100 nm
Membranes	Porosity Control	0.1-5 nm




# POSS Polymer Incorporation




Cross-linker

Pendant Polymer


Bead Copolymer







POSS Blending



# Structure/Property Relationships



## Conceptual Model for POSS Polymers




**POSS-POSS interactions?**  
**Entanglement?**  
**Aggregation?**

Maximizing property enhancements through changes at the nano level



- Polymer compatibility vs. POSS/POSS interactions



# Coughlin Model for POSS Polymers




POSS-Polyethylenes  
Dual crystalline system with limited  
crystallization  
-chain folded PE lamellae  
-2 dimensional raft/sheet like POSS structures



Line Profiles of Wide-angle  
X-ray Scattering Data of  
PE-POSS Copolymers.


- (f) POSS Monomer
- (e) PE+56wt% POSS
- (d) PE+37wt% POSS
- (c) PE+27wt% POSS
- (b) PE+19wt% POSS
- (a) PE




Macromolecules 2002, 35, 2375-2379

Bryan Coughlin-UMass











# Coughlin Model for POSS Polymers Continued




Bottom-up Approach  
(Self-Assembly)







Top-down Approach








# Coughlin Model for POSS Polymers Continued





# Coughlin Model for POSS Polymers Continued



PBD-POSS4 (43wt%POSS)





Bryan Coughlin-UMass




# POSS Synthesis








RSiX<sub>3</sub> acid or base hydrolysis



Blendables




Resin




Incompletely condensed cages



Brown, Feher, AFRL, Hybrid Plastics <sup>15</sup>



# POSS Macromers For Nanocomposites



## Completely New Polymer Feedstock Technology



Halides

Nitriles

Silanes

Styryls

Alcohols

Amines

Silanols

$\alpha$ -olefins

Esters

Isocyanates

Silylchlorides

Acrylics

Bisphenols

Epoxides

Norbornenyls


POSS-based macromers are available through either **Gelest** or **Aldrich**

POSS technology is commercialized by **Hybrid Plastics** in Fountain Valley CA











# POSS Polypropylene Blends




	Dow data	Neat <i>i</i> -PP (processed)	<i>i</i> -PP blended 2 wt% Methyl <sub>8</sub> T <sub>8</sub>	<i>i</i> -PP blended 5 wt% Methyl <sub>8</sub> T <sub>8</sub>	<i>i</i> -PP blended 10 wt% Methyl <sub>8</sub> T <sub>8</sub>
Tensile Strength @ Yield; ASTM D638	5000 psi (34.5 MPa)	4800 psi (33.0 MPa)	5000 psi (34.5 MPa)	5100 psi (35.1 MPa)	5200 psi (35.8 MPa)
Flexural Modulus (0.05 in/min, 1% secant); ASTM D790A	240,000 psi (1.655 GPa)	235,000 psi (1.620 GPa)	251,000 psi (1.730 GPa)	255,000 psi (1.757 GPa)	262,000 psi (1.80 GPa)
HDT @ 66 psi, as injected; ASTM D648	210 °F (99 °C)	210 °F (99 °C)	221 °F (105 °C)	239 °F (115 °C)	255 °F (124 °C)
Impact Izod @25C ASTM D256A	0.5 ft-lb/in	0.55 ft-lb/in	0.55 ft-lb/in	0.62 ft-lb/in	0.75 ft-lb/in




- The above data (other than Dow's data) is an average of at least 10 samples for each test with acceptable S.D. of 5% or better.



# POSS Kraton Blends




## Kraton-iButyl<sub>7</sub>T<sub>8</sub>StyrylPOSS






**2.5 wt% POSS nearly doubles toughness!**



# POSS Kraton Blends



## Kraton-5%wt POSS



iButyl<sub>7</sub>T<sub>8</sub>Styryl      50wt% POSS-PS copolymer


Strain



## POSS Blends with Semi-Crystalline Thermoplastics


---

---





- POSS R-group determines compatibility
- POSS copolymers can also blend
- POSS improves thermomechanical properties
  - 25 °C improvements in HDT with just 10 wt % POSS
  - A doubling or better of toughness using 2.5 wt % POSS
- Processing / mixing methods are critical


# **POSS Bead & Pendent Siloxanes**




# POSS PDMS TMA Characterization

The POSS/Siloxane copolymers with four or more Si-O repeat units in the siloxane segment have softening temperatures well below the decomposition temperatures.








# DMA Characterization




The copolymers with low softening temperatures can also be molded into bars for mechanical testing. Dynamic mechanical analysis reveals a  $T_g$  (64°C) and the tail end of a sub  $T_g$  relaxation (-20°C).








# Tg's For Bead Siloxane Copolymers






Glass Transition vs % Siloxane





**POSS Bead acts as a hard segment**




# TMA of Pendent POSS Siloxanes






# Hydrosilation to High MW PDMS



There are about 7 POSS-  
macromers per PDMS chain

Used 5 weight % POSS




# Experimental Setup for Rheology



$$\gamma(\omega) = \gamma_0 \sin(\omega t)$$


$$\omega = 2\pi \text{ (sec}^{-1}\text{)}$$





- 25 mm diameter cone-and plate with cone angle of 2° was used.
- The strain amplitude  $\gamma_0$  is 1% and angular frequency  $\omega$  is  $2\pi$  per second.
- The temperature is ramped from -60°C to 70°C with a rate of 2°C/min.

The loss modulus  $G''$  and  $\tan\delta = G''/G'$  were obtained as a function of temperature.





# Comparison of Three T8-POSS Macromers





PDMS + 5 wt % POSS

Blue = cyclopentyl


Red = cyclohexyl

Purple = isobutyl



tan ( $\delta$ )




Temperature °C



# Comparison of Two POSS Polyhedra




PDMS + 5 wt %  
CyclohexylPOSS  
Red = T8-POSS  
Blue = T7-POSS



Temperature °C


Continue this collaboration with Andre Lee 33



# POSS Siloxane Copolymers


---

---





- A pendent POSS is more effective than a bead POSS
  - For bead siloxanes, POSS acts as a hard segment; 75 wt % POSS raises the  $T_g$  almost 200 °C.
  - For pendent siloxanes, 30 wt% POSS raises the  $T_g$  over 200 °C.
- Rheology of 5 wt% POSS High Mw PDMS demonstrates the effect of R-group solubility and POSS cage shape on POSS-polymer interaction.


# **POSS Pendent Rubbery Polymers**




# Polymerization of POSS Norbornenes




Both block and random copolymers were synthesized.  
The wt. % POSS was varied from 0 to 50 wt. % POSS.





# DSC Data for POSS Norbornenes




CyNorb(0-50)-block




CyNorb(0-50)-random






# TEM of Diblock POSS Norbornenes




10wt % of CpPOSS



30wt% of CpPOSS




60wt% of CpPOSS



10wt% of CyPOSS




30wt % of CyPOSS




60wt% of CyPOSS



# TEM of Random POSS Norbornenes




50CyPOSS/PN




“Coarse” Cylinder Nanostructure  
(Diameter ~ 12nm)

50CpPOSS/PN



“Fine” Cylinder Nanostructure  
(Diameter ~ 6nm)

Cyclohexyl POSS-rich domains may entrain more unoriented polynorbornene chains than Cyclohexyl POSS-rich domains.




# Mather/Haddad Model for POSS Polymers




## Importance of R!



- POSS-norbornyl and POSS-PS random copolymers
- significant sensitivity of thermomechanical properties to R = Cy and Cp
- morphological analyses reveals strong correlation to the nature of aggregation




This suggests an optimized (yet unknown) length-scale of aggregation and aggregation nature for property improvements related to the level of compatibility between the POSS group and the host matrix.




# Glass Transition Temperature Variation





The random copolymers with CyPOSS show a larger increase in the glass transition than do their CpPOSS analogs. This subtle difference demonstrates that a small change to the nanoscale POSS filler can have a profound effect on polymer chain dynamics.



# Storage Modulus and Loss Tangent




Cyclohexyl Relaxation: 14.7 kcal/mol







No Maximum for 50% CyPOSS

Various Wt % Cyclohexyl POSS Polynorbornene Random Copolymers




# Tensile Storage Modulus Variation with POSS Content at Three Temperatures






# Fracture Surface After Uniaxial Tensile Testing





10 Wt % POSS

Zero Wt % POSS

The failure mechanism appears to be different.  
Continue this collaboration with Pat Mather






# TPE POSS Kraton Grafts




- A new more reactive POSS-hydride developed for hydrosilation
- Comparison of Grafted POSS to PB vs blends of POSS to PS or PB <sup>45</sup>




# Ben Hsaio: POSS EP Elastomers



**EP 10% Me<sub>8</sub>T<sub>8</sub> Blend  
Increase in Modulus and Tg Observed**




# POSS Rubbery Copolymers






- POSS significantly enhances thermal mechanical properties of rubbers
  - 50 wt% POSS leads to a 25°C increase in  $T_g$  and retains structural integrity at elevated temperatures.
  - 30 wt % cyclohexyl POSS doubles the modulus at low temperature.
  - 20 wt % cyclohexyl POSS needed to enhance the modulus of the PN relative to the POSS-free rubber.
- TEM images highlight the structure property relationship that is a function of POSS R group.
- FY03 Collaborations
  - FY03 collaboration with Pat Mather will elucidate the structure-property relationship for the full suite of POSS R groups.
  - FY03 collaboration with Andre Lee to compare blending Vs. grafting in POSS-Kraton TPE's.
  - FY03 collaboration with Brian Coughlin to begin investigating POSS EPDM copolymers as compatibilizers between POSS blendables and EPDM


# **POSS Pendent Glassy Polymers**




# POSS Styrene Monomer Synthesis




- High-yield syntheses
- Phenyl derivative requires inverse addition
- J. Inorg. Organomet. Polym., Vol 11, 2002, p. 155






# POSS Styrene Copolymer Synthesis





- Solution polymerization in toluene or bulk polymerization possible
- Polymerization is limited by solubility of the POSS-macromer
- Isobutyl-POSS is the most soluble, Phenyl-POSS the least soluble
- Macromolecules Vol. 29, 1996 p. 7302




# TGA Data for POSS Styryl Polymers









# TMA Comparison: POSS Group Effect




*Low DP Solution Polymerized Materials*








# DSC Data for POSS Styryl Polymers









# TMA Plot For POSS Styrenes (R = Cyclohexyl)






# TMA Plot For POSS Styrenes (R = Cyclopentyl)







# TMA Evidence for a Blocky Copolymer



— R = Cyclohexyl  
— R = Cyclopentyl




Only this particular cyclopentylPOSS copolymer shows two transitions.

Total TMA Dimension Change 3.5 mm






# Rheology of Unentangled PolyStyrene






$T_g = 119\text{ C}$   
 $M_n = 21\text{ K}$   
 $D_p = 178$

*Low DP Solution Polymerized Materials*





# Rheology of a 8 Mole % POSS Polymer



$R = C_6H_{11}$   
 $T_g = 136\text{ C}$   
 $M_n = 72\text{ K}$   
 $D_p = 360$



# Rheology of a 16 Mole % POSS Polymer




$R = C_5H_9$   
 $T_g = 126\text{ C}$   
 $T_g = 199\text{ C}$   
 $M_n = 42\text{ K}$   
 $D_p = 160$

*Low DP Solution Polymerized Materials*

Pat Mather, AFRL <sup>59</sup>



# Reactivity Ratio For POSS Styrene



$$r_1 = \frac{k_{11}}{k_{12}}$$

$$r_2 = \frac{k_{22}}{k_{21}}$$

These reactivity ratios were determined by analysis of seven polymerizations, which yielded 21 pairs of equations and the two variables ( $r_1$  and  $r_2$ )

Data by  $^1\text{H NMR}$

$r_1$  Styrene = 1.09

$r_2$  POSS-Styrene = 0.34

Data by FTIR



$r_1$  Styrene = 1.19

$r_2$  POSS-Styrene = 0.17

*Reactivity ratios show that random copolymers are to be expected* <sup>60</sup>




# Solubility of High Molecular Weight Copolymers





Both bulk and solution polymerization methods were used to find that highly entangled POSS-polystyrene can form an insoluble gel. If the R-group is cyclohexyl, then this gel effect occurs at very low POSS content. Much higher loadings of isoButylPOSS are required to obtain similar insoluble materials.

POSS-POSS Interactions can Dominate to form insoluble "Gels"

<u>POSS type</u>	<u>Degree of polymerization</u>	<u>Wt% POSS</u>	<u>Styrene/POSS</u>
Cyclohexyl	> 3000	5-10	~150:1
isoButyl	~4000	35-40	~17:1




# DMA of 30 Wt. % POSS Polystyrenes



- Comparison of isobutyl, cyclopentyl & cyclohexyl
- High Molecular Weight Bulk polymerized samples


Continue this collaboration with Pat Mather



# POSS Glassy Copolymers Summary

---

---





- The aforementioned results for POSS-polystyrenes are mirrored by POSS-acrylics
- Thermal properties of PS are greatly enhanced by POSS incorporation
  - Softening temperature can be raised to 325 °C!
- POSS enhancements are R-group dependant
  - Below 50 wt % cyclohexyl has a stronger effect than cyclopentyl
- Rheology revealed a rubbery plateau modulus caused by POSS-POSS physical crosslinks
- Future Work: FY03 Mechanical Properties of High MW polymers will be obtained


# POSS Thermosets




# Synthesis of Polyfunctional POSS Epoxys



Styrene  
Ruthenium Olefin  
Metathesis Catalyst




Partial oxidation with  
meta-Chloroperoxybenzoic Acid






Diglycidyletherbisphenol A  
and amine curative

Completely compatible  
POSS-Epoxy network  
Several formulations and  
complete thermomechanical  
testing is underway



# Charles Pittman POSS Phenolics



POSS-phenolic thermosets- with and w/o VGCF

5 wt% POSS raises  $T_g$  10°C



30% VGCF raises  $T_g$  55°C

30% VGCF and 3.5% POSS raises  $T_g$  80°C !!!

*POSS Conference 2002*



# Andre Lee DER 332 Aircraft structure Epoxy




Just 1 wt% POSS causes a 5°C increase in  $T_g$  !!

# **POSS Semi-Crystalline Polyethylene Oxides**




# Pat Mather: Semi-Crystalline POSS PEO



**POSS PEOs are Amphiliphilic**

**Single POSS Cage acts as a block**

**Physical junction: POSS crystals**



**Mather Model agrees with Coughlin Model**

**Two crystalline domains:**  
1) PEG10K crystals ( $T_{m1}$ )  
2) POSS crystals ( $T_{m2}$ )

**Rubber-like behaviors**  
(A physical network in higher temperature)

**Viscous liquid-like behaviors**


**Mather Macromolecules 2002, 8378.**




# Stephanie Wunder: POSS Based PEO Electrolytes




Conductivity of  $Q_8M_8PEO(m)$  and  $LiClO_4$



DSC Data: Crystallinity completely suppressed on attachment of PEO(n=4)




$\sigma$  of PEO at RT is  $\sim 10^{-5}$   
 $\sigma$  goal for PEO-based solid polymer electrolytes is  $10^{-3}$







# Dave Scheraldi: POSS PET



## TrisilanolisoctylPOSS PET Blend



Tires are typically Reinforced with PET Fabrics

PET Tg polymer 78° C  
HMLS yarn ~ 110° C

Internal Tire Temperature ~ 120° C


Scheraldi (Case Western) and KOSA investigating processing parameters for POSS blended with PET tire cord












# **POSS Modeling and Simulation**



# Ravindra Pandey: Ab Initio POSS Calculations





Relative energy per silicon atom  
(kcal/mol) for the Methyl<sub>n</sub>T<sub>n</sub> series

								
$D_{5h}^-T_{10}$	$C_{2v}^-T_{14}$	$O_h^-T_8$	$D_{4d}^-T_{16}$	$D_{6h}^-T_{12}$	$C_{2v}^-T_8$	$D_{3h}^-T_6$	$T_d^-T_4$	$D_{3h}^-T_{14}$
$D_{2d}^-T_{12}$			$D_{2d}^-T_{16}$	unknown	unknown	unknown	unknown	unknown
$D_{3h}^-T_{14}$	-7.9	-7.8	-7.7	-7.5	-7.4	-6.7	0	+19.1
			unknown					

Increasing Stability



# Mike Bowers: POSS MALDI-TOF



EXPT: ATDS  $\rightarrow$  mobilities (K)  $\rightarrow$  collision cross-sections ( $\Omega$ )

$$v_d = \frac{l}{t_d} = K \cdot E = \frac{C}{\Omega}$$


THEORY: molecular mechanics  $\rightarrow$  structures  $\rightarrow$  collision cross-sections ( $\Omega$ ) (AMBER)




# Mark Gordon: Ab Initio POSS Calculations

---



---



- Calculations on POSS synthesis
- Calculations on POMS synthesis
- Calculations on POSS cages and permeability to  $N_2$  and  $O_2$




# John Kieffer: POSS Simulations



POSS tethered with decane chains agglomerate based on cage-cage and chain-chain attractions. There is an apparent repulsion between cages and chains, leading to nano-segregation and a low equilibrium density.




# Alan Esker: POSS in thin films




*Will answer fundamental question if POSS can diffuse through a matrix.*

*Alan Esker is in a position to finally Determine if the diffusion/surface Segregation of POSS is of significance.*


*Experiments already underway (2+ years in the making for payoff)*



*Can generate an "interfacial" region-compare to known self assembled surfactant structures*



*Functionalized but still a surfactant!*





*Esker, Viers JACS., 2002, in press.*

*POSS Conference 2002*



# Space Survivable Materials

# AO undercutting of LDEF Aluminized-Kapton Multilayer Insulation







# POSS High Performance Polyimides




POSS-Kapton polyimide





POSS processable ether-imide




POSS-Fluorinated colorless polyimide




# POSS Kapton Polyimides




- transparent films
- no aggregates formed




10wt% POSS-Kapton Polyimide




10wt% POSS-Kapton Polyimide






10wt% POSS-Kapton Polyimide



10wt% POSS-Kapton Polyimide







**O-Atom etching experiment of POSS-Kapton polyimides  
Total AO fluence of  $2.62 \times 10^{20}$  atoms/cm<sup>2</sup> (~ 3 Days in LEO)**



**Hyperthermal AO Beam**





**Screen  
Sample**




20 wt% POSS in Kapton results in over 20 time improvement in erosion resistance.






O-Atom Etching Experiment (~10 DAYS IN LEO)  
Total AO fluence of  $8.47 \times 10^{20}$  atoms  $\text{cm}^{-2}$  (100,000 pluses)

Hypertothermal AO Beam




### Kapton 10 wt% POSS

Average etch depth:  $2.2 \mu\text{m}$



### Kapton H Standard



Average etch depth:  $25.4 \mu\text{m}$



Significantly improved oxidation resistance due to a rapidly formed ceramic-like, passivating and **self-healing** silica layer preventing further degradation of underlying virgin polymer.



# AFM Images of Unexposed POSS Polyimide Films



**0% POSS**

rms roughness:  
1.09 nm


**10% POSS**

rms roughness:  
1.03 nm


**20% POSS**

rms roughness:  
1.55 nm






# AFM Images of Exposed POSS Polyimide Films 100,000 Pulses of Hyperthermal (5 eV) AO Beam




**0% POSS**

rms roughness:  
**102 nm**



**10% POSS**


rms roughness:  
**17.7 nm**





**20% POSS**

rms roughness:  
**6.75 nm**







# Erosion of POSS Polyimides by a Beam of Hyperthermal (5eV) O Atoms






Tri-collaborative Effort for Proposed High-Risk, High-Payoff Program (Industry, Academia & Government)




POSS-Polymeric Materials Group  
Materials Application Branch  
AFRL, Edwards AFB



**Hybrid  
Plastics™**



TRITON  
SYSTEMS INC






## Program Goals

---

---




- The proposed program is based on the synthesis, development, characterization and testing of superior POSS-polyimide composite materials.
- Focus: Attainment of processable polyimides while retaining their high temperature stability and imparting enhanced space-survivability.
- Rapid Transition of POSS Polyimide Technology to Industry







# Cost Effective Route for POSS- Aniline Synthesis




**Hybrid  
Plastics™**





**Cp7T8 aniline**




# POSS Lubricants




# Present AF Lubricants Technology



Pentaerithritol Ester



Trimethylpropane Ester




Pentaerithritol Dimer Ester


- The above polyol ester compounds are the main components of some AF turbine lubricants
- Operating range of  $-40\text{ }^{\circ}\text{C}$  to  $200\text{ }^{\circ}\text{C}$
- Aminic antioxidants used




# POSS Diesters as Lubricants




- One possible approach for lubricants is the use of a heat sink: POSS may be usable in this capacity
- 3 grams made to prove concept
- Research problems (separation of unreacted TMP diester from POSS diester was not trivial due to similar solubilities) were overcome: vacuum distillation!
- Waxy Solid at room temperature
- Solubility in Grade 4 ester base stock: High, can be used in additive testing
- Further Physical testing will be done shortly





Triethylpropane Ester






# Isooctyl<sub>n</sub>T<sub>n</sub> as a Lubricant




**R = Isooctyl**

**major component**



**R = Isooctyl**


**minor component**





**R = Isooctyl**

**minor component**

- Advantages:
- Commercially available; relatively low cost.
- Proven stability under nitrogen to 275 °C without volatilization
- Accomplishments:
- Resin inherent in sample removed by distillation!
- AF Aminic AOs decompose POSS so compatible phenolic AO used



# TGA of Isooctyl<sub>n</sub>T<sub>n</sub> w/AO




Material	TGA temp	TGA temp	Time to 10% mass loss	% lost after 9 hrs	residue
POSS Diester	200 °C	392 °F	4.6 hr	Stopped @ 4.6hrs	Solid
POSS Diester w/AO	200 °C	392 °F	7.5 hr	11	Solid
Isooctyl <sub>n</sub> T <sub>n</sub> with 5% I-1076	200 °C	392 °F	--	2.2	Oil
Isooctyl <sub>n</sub> T <sub>n</sub> with 5% I-1076	225 °C	437 °F	--	9.0	Oil
Isooctyl <sub>n</sub> T <sub>n</sub> with 5% I-1076	250 °C	482 °F	3.5 hrs	Stopped @ 3.5hrs	Oil
Isooctyl <sub>n</sub> T <sub>n</sub> with 5% I-1076	275 °C	527 °F	1hr	70	Grit

Temp °C	Vis cP
20	13100
30	7950
40	3100
50	1600
60	725
80	260
90	166
100	112.6
110	79
120	57
130	44
140	32
150	25
160	20.4
170	16.3
180	13.8




## FY03 6.1 Future Direction



- Focus internal & collaborative work on specific polymer systems
  - Complete story on **POSS-PN**
  - Fully develop **POSS-PS** glassy polymer story
  - Begin **POSS-Kraton** TPE
  - Quantify blends vs. copolymer property enhancements (**POSS-PS, POSS-Kraton**)
- Develop definitive models for specific polymer systems
  - TEM, AFM = pictures of structure
  - Physical/mechanical data = structure/property relationship



## Complete story on POSS PN



- Synthesis of POSS-PN polymers containing Ethyl & Phenyl R groups
- Obtain TEM images of polymers
- Obtain mechanical properties of polymer systems
- Compare data to refine Coughlin Model


Does new model apply to other polymer systems?



## Fully develop POSS glassy polymer story

---


---



- With understanding obtained from POSS-PN, fully characterize high molecular weight PS
    - cyclohexyl, isobutyl & ethyl co-polymers need to be synthesized
    - rheology, DMTA data
    - Obtain TEM, AFM images
    - Develop structure/property relationship
    - Apply Coughlin model to glassy polymers
- Does new model apply to other polymer systems?



## Develop POSS TPE Model



- Synthesize POSS-Kraton polymers
  - Develop POSS-hydride monomers with variable R groups
  - Graft onto Kraton
  - Rheology/DMTA data
  - Obtain TEM/AFM images
  - Develop structure/property relationship
  - Apply Coughlin model to TPE polymers


Does new model apply to other polymer systems?



# Blends & Copolymers

---

---




- **POSS-PS (MIT Durint)**
  - MIT group with perform blends work
  - Compare with our ongoing POSS-PS copolymers
  - Quantify results and develop model
- **POSS-Kraton**
  - Andre Lee will perform rheological/DMTA data on blends and copolymers synthesized in-house
  - Quantify results and develop model

Compare POSS-PS to POSS-Kraton?



## 3-Year Plan



- Quantified property enhancements of POSS for POSS-PN, POSS-PS, POSS-Kraton
- Develop a working model or models that defines the role of POSS-POSS and POSS-polymer interactions for all types of polymers systems (e.g., glassy, rubbery, semi-crystalline, thermoset)