

REPORT DOCUMENTATION PAGE

Form Approved
OMB NO. 0704-0188

Public Reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comment regarding this burden estimates or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188,) Washington, DC 20503.

1. AGENCY USE ONLY (Leave Blank)		2. REPORT DATE	3. REPORT TYPE AND DATES COVERED Reprint	
4. TITLE AND SUBTITLE Modeling Dislocations and Disclinations with Finite Micropolar Elastoplasticity			5. FUNDING NUMBERS DAAD19-99-1-0221	
6. AUTHOR(S) J.D. Clayton, D.L. McDowell, D.J. Bammann				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Georgia Institute of Technology Atlanta, GA 30330-0420			8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES) U. S. Army Research Office P.O. Box 12211 Research Triangle Park, NC 27709-2211			10. SPONSORING / MONITORING AGENCY REPORT NUMBER 39511.18-EG	
11. SUPPLEMENTARY NOTES The views, opinions and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy or decision, unless so designated by other documentation.				
12 a. DISTRIBUTION / AVAILABILITY STATEMENT Approved for public release; distribution unlimited.			12 b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) See Attached Report				
20031031 068				
14. SUBJECT TERMS			15. NUMBER OF PAGES	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OR REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION ON THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT UL	

MODELING DISLOCATIONS AND DISCLINATIONS WITH FINITE MICROPOLAR ELASTOPLASTICITY

J.D. Clayton*, D.L. McDowell**, and D.J. Bammann***

*Army Research Laboratory, Aberdeen Proving Ground, MD 21005-5066
jclayton@arl.army.mil

**Georgia Institute of Technology, Atlanta, GA 30332-0405
david.mcdowell@me.gatech.edu

***Sandia National Laboratories, Livermore, CA 94550
bammann@sandia.gov

ABSTRACT Presented are aspects of a constitutive model for crystalline metals containing dislocation and disclination defects. Kinematics and balance laws are developed simultaneously at two scales of observation. The macroscopic kinematic description is characterized by a multiplicative decomposition of the deformation gradient, while the meso-level description follows from an additive decomposition of a connection into objects reflecting dislocations and disclinations. At the macroscale, the standard linear and angular momentum balances are enforced, while at the mesoscale, we postulate additional momentum equations for driving forces conjugate to defect densities.

INTRODUCTION Experiments have indicated the formation of misoriented rotational and/or laminar defect substructures within grains of ductile metals subjected to large deformations [cf. Ortiz & Repetto, 1999]. Following previous generalized continuum theories of crystal defects [Minagawa, 1979; Peçherski, 1983; Bammann, 2001], we develop a finite strain micropolar model wherein continuously distributed dislocations and disclinations capture the physics of evolving defect patterns at multiple length scales.

PROCEDURES, RESULTS, AND DISCUSSION The deformation gradient F^a_A is decomposed multiplicatively as

$$F^a_A \equiv \partial x^a / \partial X^A = F^{e\alpha}_\alpha \hat{R}^\alpha_{\bar{\lambda}} F^{p\bar{\lambda}}_{\bar{A}} \quad (1)$$

where Cartesian current coordinates $x^a = \phi^a(X^A, t)$, and where $F^{e\alpha}_\alpha$, $\hat{R}^\alpha_{\bar{\lambda}}$, and $F^{p\bar{\lambda}}_{\bar{A}}$ are the elastic deformation, the lattice rotation due to the time history of disclination flux, and the plastic deformation attributed to the time history of dislocation flux. We can further decompose the elastic deformation into compatible and incompatible parts:

$$F^{e\alpha}_\alpha = F^{c\alpha}_{\bar{\alpha}} F^{i\bar{\alpha}}_{\alpha}, \quad 2F^{c-1\bar{\alpha}}_{[a,b]} \equiv F^{c-1\bar{\alpha}}_{a,b} - F^{c-1\bar{\alpha}}_{b,a} = 0, \quad (2)$$

with the subscripted comma denoting partial coordinate differentiation. Disclinations are assumed to only induce rotation, i.e., $\hat{R}^{r\bar{\lambda}}_{\bar{\alpha}} = \hat{R}^{-1\bar{\lambda}}_{\bar{\alpha}}$ [Lardner, 1973; Peçherski, 1983]. We next introduce linear connection coefficients Γ^a_{bc} and the rank two metric tensor C^e_{ab} :

DISTRIBUTION STATEMENT A
Approved for Public Release
Distribution Unlimited

$$\Gamma_{bc}^a \equiv F^{\epsilon a} F^{\epsilon-1 \alpha}{}_{.c.b} + Q_{bc}^a, \quad C^{\epsilon}{}_{ab} \equiv F^{\epsilon-1 \alpha}{}_{.a} \delta_{\alpha\beta} F^{\epsilon-1 \beta}{}_{.b}, \quad (3)$$

with $F^{\epsilon a} F^{\epsilon-1 \alpha}{}_{.c.b}$ the so-called "crystal connection" of non-Riemannian dislocation theories, and with Q_{bc}^a a micropolar rotation mode associated with disclinations [Minagawa, 1979], subject to the anti-symmetry requirements $Q_{bca} \equiv Q_{bc}^d C^{\epsilon}{}_{da} = Q_{b[ca]}$. The torsion and curvature, respectively, of Γ_{bc}^a are written as [Schouten, 1954]

$$T_{bc}^a = F^{\epsilon a} (F^{\epsilon-1 \alpha}{}_{.b} F^{\epsilon-1 \beta}{}_{.c} - F^{\epsilon-1 \alpha}{}_{.b.c} F^{\epsilon-1 \beta}{}_{.c}) + 2Q_{[bc]}^a, \quad R_{abcd} = R_{[ab][cd]} = 2\nabla_{[c} Q_{d][ba]} + T_{cd}^e Q_{e[ba]}, \quad (4)$$

where ∇_a denotes covariant differentiation with respect to Γ_{bc}^a . The dislocation density α^{ab} and the disclination density θ^{ab} , both referred to the spatial frame, are then found as

$$2\alpha^{ab} \equiv \epsilon^{bcd} T_{cd}^a, \quad 4\theta^{ef} \equiv \epsilon^{eba} \epsilon^{fcd} R_{abcd}. \quad (5)$$

Using Schouten's [1954] identity $R_{a[bcd]} = T_{d[bc,a]}$ and Bianchi's equations $R_{ab[cd,e]} = 0$, conservation laws for the defect densities are written as [Minagawa, 1979]

$$C^{\epsilon}{}_{ab} \alpha^{bc} + \epsilon_{abc} \theta^{bc} = 0, \quad \theta^{ab}{}_{.b} = 0. \quad (6)$$

We assume a general free energy potential, per unit mass, with the functional dependency

$$\psi = \psi(\tilde{C}^{\epsilon}{}_{\alpha\beta}, \alpha^{ab}, \theta^{ab}, \epsilon), \quad (7)$$

where $\tilde{C}^{\epsilon}{}_{\alpha\beta} \equiv F^{\epsilon a} g_{ab} F^{\epsilon b}{}_{\beta}$ (with the Euclidean spatial metric g_{ab}) and where $\epsilon = b\sqrt{\rho}$ is a dimensionless measure of the statistically-stored dislocation line length per unit current volume ρ , with b the magnitude of the Burgers vector. The local energy balance and entropy inequality, under strictly isothermal conditions, are written, respectively, as

$$(1/2)\sigma^{ab}(\mathcal{L}, g)_{ba} + \chi_{ab} \dot{\alpha}^{ab} + \xi_{ab} \dot{\theta}^{ab} = \rho \dot{e} \geq \rho \dot{\psi}, \quad (8)$$

with ρ the current mass density, e the internal energy, σ^{ab} the symmetric Cauchy stress satisfying $\sigma^{ab}{}_{.b} + \rho f^a = \rho \dot{v}^a$, χ_{ab} and ξ_{ab} generalized meso-level stresses, and \mathcal{L} , the Lie derivative with respect to the velocity field $v^a \equiv \dot{x}^a \circ \phi_t^{-1}$. Substituting (7) into (8)₂ gives

$$\sigma^{ab} = 2\rho(\partial\psi/\partial g_{ab}), \quad \sigma^{ab} g_{bc} F^{\epsilon c}{}_{.a} \hat{F}^{\epsilon a}{}_{.A} \hat{F}^{\epsilon-1 A}{}_{.B} F^{\epsilon-1 B}{}_{.a} - \kappa \dot{\epsilon} \geq 0, \quad (9)$$

where we define $\hat{F}^{\epsilon a}{}_{.A} \equiv \hat{R}^{\epsilon a}{}_{.A} F^{\epsilon A}{}_{.a}$ and $\kappa \equiv \rho \partial\psi/\partial\epsilon$, and also provides the conjugate thermodynamic force relations $\chi_{ab} = \rho \partial\psi/\partial\alpha^{ab}$ and $\xi_{ab} = \rho \partial\psi/\partial\theta^{ab}$. We now make the more specific assumption

$$\rho\psi = \rho\psi_1(\tilde{C}^{\epsilon}{}_{\alpha\beta}) + (1/2)\mu(l_\alpha^2 \alpha^{ab} g_{ac} g_{bd} \alpha^{cd} + l_\theta^4 \theta^{ab} g_{ac} g_{bd} \theta^{cd} + c\epsilon^2), \quad (10)$$

with ψ_1 the recoverable energy and μ , l_α , l_θ , and c an elastic shear modulus, length parameter associated with dislocations, length parameter associated with disclinations, and dimensionless scalar. Quasi-static mesoscopic momentum balances are postulated as [Bammann, 2001]

$$g^{cb} \chi_{\alpha,b} = 0, \quad g^{cb} \xi_{\alpha,b} + g_{ad} \varepsilon^{abc} \chi_{bc} = 0. \quad (11)$$

To complete the kinetic description, expressions for the defect density fluxes are needed:

$$\dot{F}^{p\bar{A}} = \dot{F}^{p\bar{A}}(\{\mathcal{A}^p\}), \quad \dot{R}^{\alpha}_{\bar{A}} = \dot{R}^{\alpha}_{\bar{A}}(\{\mathcal{A}\}), \quad \dot{Q}^a_{bc} = \dot{Q}^a_{bc}(\{\mathcal{A}^a\}), \quad \dot{\varepsilon} = \dot{\varepsilon}(\{\mathcal{A}^a\}), \quad (12)$$

where $\{\mathcal{A}^p\}$, $\{\mathcal{A}\}$, $\{\mathcal{A}^a\}$, and $\{\mathcal{A}^e\}$ denote tensor functions of the appropriate rank depending explicitly upon the members of the set $(\sigma^{ab}, \chi_{ab}, \xi_{ab}, \kappa, \chi_{ab,c})$ mapped to suitable configurations. Spatial gradients of the dislocation density reflecting the contribution of pile-ups to hardening are embodied by the term $\chi_{ab,c}$. Specific forms of (12) must be developed, subject to constraints imposed by inequality (9)₂ and the force balances (11). As an alternative to (12)₂, $\dot{R}^{\alpha}_{\bar{A}}$ can be found explicitly in terms of θ^{ab} assuming stationary disclinations [Lardner, 1973]. If we further assume that Q^a_{bc} satisfies the integrability conditions $Q^a_{bc} = q^a_{bc} = Q^a_{cb}$, then the six equations in (11) are sufficient to determine the six independent components of Q^a_{bc} and (12)₃ is not needed. Characteristic defect patterns are expected to emerge as a result of certain prescriptions of l_α , l_θ , c , and Eqs. (12) leading to non-convexity of the energy potential (10) [Ortiz & Repetto, 1999].

ACKNOWLEDGEMENTS J.D.C. and D.L.M. acknowledge support of the Army Research Office (ARO Award DAAG559810213). D.J.B. acknowledges support of Sandia Laboratories under U. S. Department of Energy contract DE-AC04-94AL85000.

REFERENCES

- Bammann, D.J., 2001. A model of crystal plasticity containing a natural length scale. *Mat. Sci. Eng. A* **309-310**, 406-410.
- Lardner, R.W., 1973. Foundations of the theory of disclinations. *Arch. Mech.* **25**, 911-922.
- Minagawa, S., 1979. A non-Riemannian geometrical theory of imperfections in a Cosserat continuum. *Arch. Mech.* **31**, 783-792.
- Ortiz, M. and Repetto, E.A., 1999. Nonconvex energy minimization and dislocation structures in ductile single crystals. *J. Mech. Phys. Solids* **47**, 397-462.
- Peçherski, R.B., 1983. Relation of microscopic observations to constitutive modelling for advanced deformations and fracture initiation of viscoplastic materials. *Arch. Mech.* **35**, 257-277.
- Schouten, J.A., 1954. *Ricci Calculus*. 2nd Edition, Springer-Verlag, Berlin.