



Australian Government
Department of Defence
Defence Science and
Technology Organisation

A large, bold, grey, textured letter 'O' with a white center, positioned at the top of the vertical text column.

A large, bold, grey, textured letter 'H' with a white center, positioned below the 'O' in the vertical text column.

A large, bold, grey, textured letter 'S' with a white center, positioned below the 'H' in the vertical text column.

A large, bold, grey, textured letter 'D' with a white center, positioned at the bottom of the vertical text column.

**Review of Improved Methods for
Analysing Load Attraction and
Thermal Effects in Bonded
Composite Repair Design**

A.B. Harman and K.F. Walker.

DSTO-TR-1546

DISTRIBUTION STATEMENT A
Approved for Public Release
Distribution Unlimited

20040713 108



Australian Government
Department of Defence
Defence Science and
Technology Organisation

Review of Improved Methods for Analysing Load Attraction and Thermal Effects in Bonded Composite Repair Design

A.B. Harman and K.F. Walker

Air Vehicles Division
Platforms Sciences Laboratory

DSTO-TR-1546

ABSTRACT

Adhesive bonded repairs to aircraft involving metallic and composite structures have proven to be an effective, efficient means of repair and life extension. The simplified closed form equations used by the RAAF in an Engineering Standard (DEF(AUST)9005) have proven to be effective and conservative. Recent work, however, has identified improved equations to account for load attraction into the stiffened repaired area, and evaluate the thermally induced stresses in the repaired structure and the patch. The improved equations were compared with the current methods, using the repair to a 2024-T851 aluminium alloy F-111 lower wing skin with a boron epoxy repair patch, bonded with FM-73 film adhesive. The improved methods will reduce the unnecessary conservatism inherent in DEF(AUST)9005 and therefore allow some repairs to proceed where they may otherwise have been rejected. Repairs will also be designed to operate more efficiently.

RELEASE LIMITATION

Approved for public release

AQ F04-09-1067

Published by

*DSTO Platforms Sciences Laboratory
506 Lorimer St
Fishermans Bend, Victoria 3207 Australia*

*Telephone: (03) 9626 7000
Fax: (03) 9626 7999*

*© Commonwealth of Australia 2003
AR-013-020
December 2003*

APPROVED FOR PUBLIC RELEASE

Review of Improved Methods for Analysing Load Attraction and Thermal Effects in Bonded Composite Repair Design

Executive Summary

Adhesive bonded repairs to aircraft involving metallic and composite structures have proven to be an effective, efficient means of repair and life extension. The simplified closed form equations used by the RAAF in an Engineering Standard (DEF(AUST)9005) have proven to be effective and conservative.

Recent work, however, has identified improved equations to account for load attraction into the stiffened repaired area, and evaluate the thermally induced stresses in the repaired structure and the patch. The improved equations were compared with the current methods using the repair to a 2024-T851 Aluminium Alloy F-111 lower wing skin with a boron epoxy repair patch bonded with FM-73 film adhesive as an example.

The improved equations produce small increases in the stress in the skin under the patch, the adhesive strain and the repaired stress intensity factor. However, the stress in the skin at the edge of the patch and the stress in the patch itself are considerably reduced. By removing unnecessary conservatism in DEF(AUST)9005, repairs to RAAF aircraft may now be able to safely proceed whereas previously they could have been rejected. The improved methods presented in this report will allow an increase in the scope of application of adhesive bonded repair methods. This will increase the availability and extend the structural life of RAAF aircraft.

This page intentionally left blank

Authors

A.B. Harman

Air Vehicles Division

Alex Harman is a Professional Officer at DSTO. He holds a B.Eng (Hons.) in Aerospace Engineering from RMIT and is currently a graduate member of both the Institution of Engineers and the Royal Aeronautical Society. He joined DSTO in 1999 and has performed dynamic loads analyses for the F/A-18, structural integrity analyses for the F-111, composites and metallic finite element analyses and testing, bonded joint design and composite design. He is currently working with the Composites and Bonded Repair group in the Air Vehicles Division.

K.F. Walker

Air Vehicles Division

Mr Walker graduated in 1983 with a Bachelor of Aeronautical Engineering (with distinction) from RMIT. He then served for eight years with the RAAF, including a posting to the USA where he gained a Masters of Science in Aeronautics and Astronautics from Purdue University. He then worked for three years in private industry before joining DSTO AVD in early 1994. His work at DSTO has included fatigue crack growth and damage tolerance analysis studies (mainly related to the F-111 aircraft), fatigue monitoring systems, development, design, validation and substantiation of bonded composite repairs, and development of improved fatigue crack growth analysis software. He is currently also Task Manager "F-111 Aircraft Structural Integrity Sole Operator Program".

This page intentionally left blank

Contents

1. INTRODUCTION.....	1
2. CURRENT AND IMPROVED METHODS.....	1
2.1 Load Attraction.....	1
2.1.1 Current Method.....	1
2.1.2 Improved Method.....	2
2.2 Thermal Effects.....	3
2.2.1 Current Method.....	3
2.2.2 Improved Method.....	5
3. EXAMPLE CASE BASED ON F-111C LOWER WING SKIN REPAIR.....	8
3.1 Material Properties.....	9
3.1.1 FM-73 Structural Film Adhesive.....	9
3.1.2 2024-T851 Aluminium Alloy.....	9
3.1.3 Boron Epoxy 5521/4.....	9
3.2 Results.....	10
4. DISCUSSION.....	11
5. CONCLUSION AND RECOMMENDATIONS.....	12
6. ACKNOWLEDGEMENTS.....	12
7. REFERENCES.....	12
APPENDIX A CALCULATIONS FOR F-111 REPAIR EXAMPLE.....	14
A.1. Current Method - Operating Temperature = -40 °F.....	15
A.2. Current Method - Operating Temperature = 75 °F.....	18
A.3. Current Method - Operating Temperature = 167 °F.....	21
A.4. Improved Method - Operating Temperature = -40 °F.....	24
A.5. Improved Method - Operating Temperature = 75 °F.....	28
A.6. Improved Method - Operating Temperature = 167 °F.....	32

This page intentionally left blank

1. Introduction

Adhesive bonded repairs to aircraft involving metallic and composite structures have proven to be an effective means of repair and life extension (References 1-4). In Australia, the procedures for designing such repairs have been documented in References 5 and 6. The design equations have been derived from a number of sources. The main sources are References 1 and 7.

The equations are in closed form and are relatively simple to apply. Despite their simplicity, they have proven to be effective for real life practical examples, including a repair to primary aircraft structure in one case (References 3 and 4).

The equations are, however, restricted basically to cases of either a double sided symmetric repair, or single sided repair where full out of plane support or restraint is provided by the sub-structure (eg a spar). Although the equations as currently contained in References 5 and 6 have proven to work well, it has recently become evident that improvements are possible in the following areas;

1. Calculating the load attraction factor, and
2. Accounting for the thermally induced stresses in the repaired structure and patch.

The improvements are drawn from References 8 and 9, and are clearly identified and articulated in this report. The final results in terms of stresses and stress intensity factors do not change significantly as a result. However, the revised equations are considered superior and recommended for use in future versions of References 5 and 6.

2. Current and Improved Methods

2.1 Load Attraction

2.1.1 Current Method

The load attraction factor, Ω_L , allows for load attraction into the repaired area due to stiffness added by the patch. Currently, the guidance given in Reference 6 is as follows:

“Typical values are $\Omega_L = 1.2$ for a square patch to 2.0 for a patch which is very long in the major load direction”

2.1.2 Improved Method

Using the equations detailed in Section 7.4 of Reference 8, it is possible to estimate Ω_L based on the patch width and length. The procedure is as follows:

$$\text{Patch Shape Ratio, } Shape = W_h/L_h$$

$$\text{Stiffness Ratio : } s = \frac{E_o t_o}{E_i t_i}$$

Where:

- $W_h =$ Half Patch Width
- $L_h =$ Half Patch Length
- $E_i =$ Youngs Modulus of Skin or Plate
- $t_i =$ Thickness of Skin or Plate
- $E_o =$ Youngs Modulus of Patch
- $t_o =$ Thickness of Patch

From Reference 8, Equation 7.18,

$$z = 3(1+s)^2 + 2(1+s)[(1/Shape) + Shape + \nu s] + 1 - \nu^2 s^2$$

Where:

- $\nu =$ Poisson's Ratio of Skin

$$\text{Stress reduction factor, } \Phi = \frac{1}{z} \left[4 + 2\left(\frac{1}{Shape}\right) + 2Shape + s\left(3 + \nu + \frac{2}{Shape}\right) \right]$$

From Reference 8, Equation 7.20

$$\text{Load attraction factor, } \Omega_L = (1+s)\Phi$$

These equations are for the simplified case of uniaxial loading and where the plate or skin and the patch are both isotropic and have the same poisson's ratio. In fact, the skin or plate is normally isotropic, but the patch is often orthotropic. The shape of the patch is also assumed to be semi elliptic. Nevertheless, the equations presented will provide a close approximation for the load attraction factor. For the case of a patch with a shape ratio of one, the load attraction factor is approximately 1.2.

2.2 Thermal Effects

2.2.1 Current Method




Figure 1 Relevant Parameters for Single-Sided, Fully Supported Bonded Repair Design Analysis

The main quantities to be calculated are as follows (see Figure 1):

- σ^* : Far field applied stress
- σ^{**} : Stress in the skin or plate at the edge of the patch
- σ_o : Stress in the skin or plate under the repair (ignoring the crack)
- σ_p : Stress in the patch
- K_{inf} : Repaired stress intensity factor
- γ_{max} : Maximum shear strain in the adhesive

The equations for σ^{**} and σ_o are updated with the improved method, and as such the existing formulae within Reference 5 and 6 are presented below. With regard to the other related formulae, the equations for K_{inf} and γ_{max} do not change and remain as per References 5 and 6. The equation for σ_p does not change if there is a crack present. If there is no crack in the parent material under the patch, such as in the case of a composite reinforcement doubler, the equation for σ_p changes.

Existing equation for σ^{**} :

The equation given in References 5 and 6 is as follows:

$$\sigma^{**} = \Omega_L \sigma^* + E_i [(\alpha_o - \alpha_{ieff})(RT - T_{CURE}) + (\alpha_o - \alpha_i)(T_{OP} - RT)]$$

Where:

- Ω_L = Load Attraction Factor
- σ^* = Remote Applied Stresses

α_o =	Coefficient of Thermal Expansion (CTE) of the Patch
α_{ieff} =	Effective CTE of the Skin/Plate accounting for Constraint of Surrounding Unheated Structure
RT =	Room Temperature (75°F)
T_{CURE} =	Cure Temperature
α_i =	CTE of the Skin/Plate
T_{OP} =	Operating Temperature

The concept is that during cooling the structure from the cure temperature back to ambient temperature, the effective skin or plate CTE will be less than the full material value. This is due to the constraint provided by the surrounding unheated structure (i.e. the localised nature of heating for cure).

The effective CTE is calculated using the following simple formula (References 5 and 6):

$$\alpha_{ieff} = \frac{\alpha_i(v+1)}{2}$$

This effective CTE is applied only to the temperature change from cure to ambient. The change from ambient to operating temperature affects the whole structure (eg. an aircraft flying to altitude) so the full CTE is applied.

Existing equation for σ_o :

The equation given in Reference 6 is as follows:

$$\sigma_o = \frac{\sigma^{**}(E_i t_i)}{E_o t_o + E_i t_i}$$

Or

$$\sigma_o = \frac{\sigma^{**}}{1+s}$$

Existing equation for σ_p :

In cases where a crack is present, the equation given in Reference 6, Appendix 2 to Annex C, Chapter 6 equation (6.C.2.18), is as follows:

$$\sigma_p = \frac{t_i}{t_o} \sigma^{**}$$

For cases where there is no crack, the equation given in Reference 6, Appendix 4 to Annex C, Chapter 6 equation (6.C.4.16), is as follows:

$$\sigma_p = \frac{E_o t_i}{E_o t_o + E_i t_i} \sigma^{**}$$

2.2.2 Improved Method

The approach for the improved method is taken from References 8 and 9. The concept is that the repair application process is broken down into individual stages to account for effects due to temperature changes. The stages are as follows:

- Stage 1 : Localised heating to cure the adhesive
- Stage 2 : Localised cooling from the cure temperature to ambient
- Stage 3 : Total heating or cooling to the "operating" temperature at which the repair is evaluated

The applied stress is added to the thermal stresses.

As discussed in References 8 and 9, the closed form equations are greatly simplified to enable analytic derivation. The primary simplifying assumption is that the parent/skin/plate and patch/reinforcement are made from isotropic material. In the typical repair case, the structure being repaired is metallic and is approximately isotropic. However, the repair patch is often made from non-isotropic composite laminae.

It is demonstrated in Reference 9 that the effect of this assumption on the stress predictions in the patch and plate is insignificant. If the repair designer assumes the major or longitudinal properties of the orthotropic patch apply as its isotropic properties, then the results for the skin/plate stresses are reasonable and conservative in the primary load direction.

Another assumption made is that the structure surrounding the repair patch is infinite and only the area of the repair patch itself is heated. This is also considered to be a reasonable approximation for the typical repair situation in a real aircraft repair. In other words, the area of the repair is small compared to the overall dimensions of the structure.

Revised/improved equation for σ^{**} :

The component due to the applied stress is given by:

$$\sigma_{\text{applied}}^{**} = \Omega_L \sigma^*$$

The component due to heating (Stage 1) is given by Reference 9, Equation 3:

$$\sigma_{heating}^{**} = \frac{-\alpha_i E_i (T_{CURE} - RT)}{2}$$

The component due to cooling to ambient (Stage 2) is given by Reference 8, Equation 7.102:

$$\sigma_{cooling}^{**} = -\alpha_i E_i (RT - T_{CURE}) \frac{[1 - \nu_{12o} + s(1 - \nu) \frac{\alpha_o}{\alpha_i}]}{[2(1 - \nu_{12o}) + (1 - \nu^2)s]}$$

Where:

ν_{12o} = Longitudinal Poisson's Ratio of the Patch

The component due to heating or cooling the whole structure to the operating temperature (Stage 3) is given by Reference 8, Equation 7.104:

$$\sigma_{operating}^{**} = -\alpha_i E_i (T_{OP} - RT) \frac{[(1 - \nu)(1 - \frac{\alpha_o}{\alpha_i})s]}{[2(1 - \nu_{12o}) + (1 - \nu^2)s]}$$

The total is given by:

$$\sigma^{**} = \sigma_{applied}^{**} + \sigma_{heating}^{**} + \sigma_{cooling}^{**} + \sigma_{operating}^{**}$$

Revised/improved equation for σ_o stress in the skin/plate under the patch ignoring the crack¹:

The component due to the applied stress is given by:

$$\sigma_{o_applied} = \frac{(\Omega_L \sigma^*)}{1 + s}$$

The component due to heating (Stage 1) is given by Reference 9, Equation 3:

$$\sigma_{o_heating} = \frac{-\alpha_i E_i (T_{CURE} - RT)}{2}$$

¹ Note that the equations given in Reference 6 for calculating the repaired stress intensity rely on a value of σ_o in the absence of the crack

The component due to cooling to ambient (Stage 2) is given by Reference 8, Equation 7.99:

$$\sigma_{o_cooling} = -\alpha_i E_i (RT - T_{CURE}) \left[\frac{[1 - \nu_{12o} + (1 - \frac{\alpha_o}{\alpha_i})(1 + \nu)]s}{[2(1 - \nu_{12o}) + (1 - \nu^2)s]} \right]$$

The component due to further cooling the whole structure to the operating temperature (Stage 3) is given by Reference 8, Equation 7.104:

$$\sigma_{o_operating} = -\alpha_i E_i (T_{OP} - RT) \left[\frac{[(1 + \nu)(1 - \frac{\alpha_o}{\alpha_i})s]}{[2(1 - \nu_{12o}) + (1 - \nu^2)s]} \right]$$

The total is given by:

$$\sigma_o = \sigma_{o_applied} + \sigma_{o_heating} + \sigma_{o_cooling} + \sigma_{o_operating}$$

Revised/improved equation for σ_p :

In the case where a crack is present, the equation given in Reference 6 for stress in the patch is reasonable. It is based on the concept of load compatibility, i.e. the load transmitted at the edge of the patch must be transmitted fully through the patch at the crack location.

However, for situations where we want to obtain the stress in the patch in the absence of a crack, the equation in Reference 6 is not correct. In that situation, all load transferring into the patch is assumed to shed from the parent material, and pass through the patch over the defect. As such, it can be seen in Reference 6 that the following formulae apply:

The applied stress is given by:

$$\sigma_{p_applied} = \frac{E_o t_i}{E_o t_o + E_i t_i} \sigma_{applied}^{**}$$

Or

$$\sigma_{p_applied} = \frac{s t_i}{(1 + s) t_o} \sigma_{applied}^{**}$$

Note that this equation is basically the same as the existing equation in Reference 6, and it is based on load and strain compatibility. However, this is only for the applied stress. The heating, cooling and operating components must be added separately.

Stress due to heating (Stage 1) is zero because the patch is free to expand, i.e.:

$$\sigma_{p_heating} = 0$$

Stress due to cooling to ambient (Stage 2) is given by Reference 8, Equation 7.103:

$$\sigma_{p_cooling} = \alpha_i E_o (RT - T_{CURE}) \left[\frac{(1 + \nu - 2 \frac{\alpha_o}{\alpha_i})}{[2(1 - \nu_{12o}) + (1 - \nu^2)s]} \right]$$

The stress due to heating or cooling the whole structure to the operating temperature (Stage 3) is given by Reference 8, Equation 7.105:

$$\sigma_{p_operating} = \alpha_i E_o (T_{OP} - T_{CURE}) \left[\frac{2(1 - \frac{\alpha_o}{\alpha_i})}{[2(1 - \nu_{12o}) + (1 - \nu^2)s]} \right]$$

The total is given by:

$$\sigma_p = \sigma_{p_applied} + \sigma_{p_heating} + \sigma_{p_cooling} + \sigma_{p_operating}$$

3. Example Case Based on F-111C Lower Wing Skin Repair

The revised formulae have been compared with the current method for an example case based on the F-111C lower wing skin repair (References 3 and 4). The case involved the application of a 14 layer boron epoxy (5521/4) patch bonded with FM 73 film adhesive cured under positive pressure at 180°F.

The patch only needed 10 layers of unidirectional boron epoxy oriented in the 0° direction. The other 4 layers were orientated at ± 45° to the primary load direction. For the purposes of simplifying the comparison, a 10 layer unidirectional patch was assumed for repair design. As such, the extensional stiffness (Et) of the patch and skin approximately matched.

The wing skin is manufactured from 2024-T851 aluminium alloy. The repair was evaluated at operating temperatures of -40, 75 and 167°F. The remote applied stress is

37,100 psi (37.1 ksi). Results are provided in this section and mathematical workings are provided in Appendix A.

3.1 Material Properties

The relevant material properties are as follows:

3.1.1 FM-73 Structural Film Adhesive

FM-73 Structural film adhesive properties were obtained from Reference 6 and are detailed in Table 1 below.

Table 1 FM-73 Structural Film Adhesive Properties

Parameter	Values		
	-40°F	RT (75°F)	167°F
τ_p , Shear Stress at Linear Limit (psi)	8230	6052	3534
G, Shear Modulus (psi)	115306	73323	13522
γ_{max} , Shear Strain at Failure	0.1915	0.5774	0.8276
γ_e , Elastic Shear Strain Limit	0.0723	0.0804	0.5896
γ_p , Plastic Shear Strain Limit	0.1192	0.497	0.2380
η , Adhesive Thickness (inches)	0.013"	0.013"	0.013"

3.1.2 2024-T851 Aluminium Alloy

The properties of 2024-T851 aluminium alloy are as per Reference 10 and are detailed in Table 2 below:

Table 2 2024-T851 Aluminium Alloy Properties

Parameter	Value
t_i , Skin Thickness (inches)	0.14"
σ_{yi} , Yield Stress (psi)	59000
σ_{ui} , Ultimate Stress (psi)	65000
K_c , Fracture toughness (psi \sqrt{inch})	42000
E_i , Youngs Modulus (psi)	10.5 x 10 ⁶
ν , Poisson's Ratio	0.31
α_i , CTE (in/in/°F)	12.6 x 10 ⁻⁶

3.1.3 Boron Epoxy 5521/4

The properties of Boron Epoxy 5521/4 are as per Reference 6 and are detailed in Table 3 below:

Table 3 Boron Epoxy 5521/4 Properties

Parameter	Value
ϵ_o , Ultimate longitudinal strain	0.00655
E_o , Youngs Modulus (psi)	30×10^6
α_o , CTE (in/in/°F)	2.3×10^{-6}

3.2 Results

The equations detailed in Section 2 were assembled in MATHCAD worksheets provided in Appendix A. For comparison purposes, the load attraction factor, Ω_L , was set to a value of 1.2. The key results are provided in Table 4 below.

Table 4 Comparison of results

Parameter	DEF(AUST)9005 (current)			Proposed Equations		
	-40°F	RT (75°F)	167°F	-40°F	RT (75°F)	167°F
σ^{**} (ksi)	63.52	51.08	41.13	39.04	42.63	45.50
σ_o (ksi)	30.82	24.78	19.96	32.00	25.19	19.74
γ_{max}	0.151	0.142	0.242	0.160	0.146	0.240
K_{inf} (ksi \sqrt{inch})	23.81	21.16	25.69	24.84	21.54	25.41
σ_p (ksi) (cracked)	171.0	137.50	110.70	105.10	114.80	122.50
σ_p (ksi) (no crack)	88.05	70.81	57.02	18.95	46.94	69.33




Figure 2 σ^{**} , Stress in the Skin/Plate at the End of the Patch vs Operating Temperature




Figure 3 σ_p , Stress in the Patch (with crack in the skin) vs Operating Temperature

4. Discussion

From the results provided in Table 4 and shown in Figure 2, it is clear that the proposed procedure will result in significantly reduced values of σ^{**} , the stress in the skin or plate at the end of the patch. The exception to this is the high temperature (167 °F) case where the proposed procedure gives 45.5 ksi compared with 41.3 ksi from the current equation.

A more important observation however comes from a close examination of the trend of stress level as a function of operating temperature. The improved equations capture the trend expected for a physical problem of this type, whereas the existing equations give a contradictory result. In the case of the current equations, the stress decreases as operating temperature increases. The reverse is true for the proposed equations.

An explanation, in physical terms, is offered as follows. The stress due to the applied load, the heating stage, and the cooling to ambient is consistent for each case. The difference comes in during the stage from ambient to the operating condition. When you cool the entire structure from 75 °F down to -40 °F, it makes sense that the surrounding structure will want to contract more than the inclusion (the patch/skin combination is referred to as an inclusion). This is due to the inclusion having a lower

CTE than the skin/structure. Displacement compatibility dictates that the inclusion is forced to fit into a smaller hole. As such, compressive stresses develop. The reverse is true when you move to a higher than ambient operating temperature. The existing equations do not capture this physical trend.

As seen in Table 4 and Figure 3, the stress in the patch for the cracked case is also significantly less for the proposed equations apart from the 167 °F case. Once again, the trends for the stress in the patch, both cracked and uncracked, as a function of operating temperature are reversed. The results from the proposed equations are considered superior in terms of both absolute accuracy and in capturing the physical trends expected from structure subjected to temperature change.

Also from Table 4, the values of σ_o , γ_{max} and K_{inf} do not change significantly.

5. Conclusion and Recommendations

Improved methods for analysing load attraction and thermal effects in bonded composite repair design have been evaluated by way of example calculations. The proposed equations are considered to be more accurate than those currently in use, but remain conservative.

The use of the proposed equations in the next update to Reference 6 is strongly recommended.

6. Acknowledgements

The authors greatly appreciate the input and advice from Drs C. Wang, A. Baker and A. Rider.

7. References

1. Baker, A.A., and Jones, R., (eds), 1988, Bonded Repair of Aircraft Structures, Martinus Nijhoff.
2. Baker, A.A., October 3-5, 1994, Bonded Composite Repair of Metallic Aircraft Components - Overview of Australian Activities, AGARD Specialists Meeting on Composite Repair of Military Aircraft Structures, Seville.

3. Baker, A.A., et.al., 1999, Repair Substantiation for a Bonded Composite Repair to F-111 Lower Wing Skin, *Journal of Applied Composite Materials* 6:251-667, Kluwer Academic Publishers, Netherlands.
4. Boykett, R., and Walker, K., 1996, F-111C Lower Wing Skin Bonded Composite Repair Substantiation Testing", DSTO-TR-0480.
5. Anon, 4 Sept., 1995, Composite Materials and Adhesive Bonded Repairs, Standard DEF(AUST)9005 Issue A (Draft) replacing RAAF STD (ENG) C5033.
6. Anon, Draft 2002, Composite Materials and Adhesive Bonded Repairs - Engineering and Design Procedures", RAAF AAP 7021.016-1.
7. Hart-Smith, L.J., 1973, Adhesive Bonded Double Lap Joints, NASA-CR-012235, California.
8. Rose, L.R.F., Wang, C.H., 2002, Analytical Methods for Designing Composite Repairs (Chapter 7), *Advances in the Bonded Composite Repair of Metallic Aircraft Structure*, Vol. 1, Baker, A.A. et.al., Elsevier, Oxford, pp 137-175.
9. Wang, C.H., et.al., 2000, Thermal Stresses in a Plate with a Circular Reinforcement, *International Journal of Solids and Structures*, Vol 37, 4577-4599.
10. Anon, 3 May 1994, Repair Design Package for A8-145, ASI/4080/14/A8-12 Pt 4(34).

Appendix A Calculations for F-111 Repair Example

This appendix details the mathematical workings for the F-111 repair design example application. Both the current analytic formulae and the proposed analytic formulae have been used independently, as a means of quantifying the effect of implementing the improved methods.

The calculations have been performed using MATHCAD worksheets. Therefore, each of the repair examples are set up in a sequential fashion, much like the way specified in the current RAAF standard for bonded repair design. Worksheets have been provided for both the current methodology and the improved methodology, for the following temperature conditions:

- -40 F
- 75 F (Ambient)
- 167 F

A.1. Current Method - Operating Temperature = -40 °F

Single-Sided Fully-Supported Bonded Repair Evaluation of Current Equations

ADHESIVE PROPERTIES

FM73 FILM ADHESIVE (Minus 40 deg F CONDITIONS)

ADHESIVE THICKNESS	ADHESIVE SHEAR MODULUS	ADHESIVE SHEAR STRESS
$\eta := 0.013$ <i>inch</i>	$G := 115306$ <i>psi</i>	$\tau_p := 8230$ <i>psi</i>
ADHESIVE STRAINS	ELASTIC $\gamma_e := 0.0723$	
	PLASTIC $\gamma_p := 0.1192$	
CURE TEMPERATURE	$T_{cure} := 180$ <i>F</i>	

2024-T851 ALUMINIUM SKIN PROPERTIES

SKIN THICKNESS	$t_i := 0.14$ <i>in</i>	
YIELD STRESS	$\sigma_{yi} := 59 \cdot 10^3$ <i>psi</i>	
ULTIMATE STRESS	$\sigma_{ui} := 65 \cdot 10^3$ <i>psi</i>	
FRACTURE TOUGHNESS	$K_{ci} := 42000$ <i>psi rt in</i>	
YOUNGS MODULUS	$E_i := 10.5 \cdot 10^6$ <i>psi</i>	
POISSON'S RATIO	$\nu := 0.31$	
THERMAL EXPANSN COEFFICIENT	$\alpha_i := 12.6 \cdot 10^{-6}$ <i>in/in/F</i>	$\alpha_{ieff} := \alpha_i \cdot \frac{(\nu + 1)}{2}$

BORON EPOXY 5521/4 PROPERTIES

BORON EPOXY PRE-PREG

ULTIMATE LONGITUDINAL STRAIN	$\epsilon_o := 0.00655$ <i>in/in</i>	
YOUNGS MODULUS	$E_o := 30 \cdot 10^6$ <i>psi</i>	
THERMAL EXPANSN COEFFICIENT	$\alpha_o := 2.3 \cdot 10^{-6}$ <i>in/in/F</i>	
THICKNESS	$t_o := 0.052$ <i>in</i>	

DESIGN OPERATING TEMPERATURE	$T_{op} := -40$ <i>deg F</i>	$RT := 75$ <i>deg F</i>
---------------------------------	------------------------------	-------------------------

EVALUATION OF STRUCTURAL INTEGRITY OF REPAIRED STRUCTURE

CALCULATE THE STRESS APPLIED

Input remote applied stress $\sigma_{star} := 37100 \quad \text{psi}$

CHECK THE STRUCTURAL INTEGRITY OF THE STRUCTURE AT THE EDGE OF THE PATCH

Load Attraction Factor $\Omega_L := 1.2$

Stress at the edge of the patch

$$\sigma_{2star} := \Omega_L \cdot \sigma_{star} + E_i \left[(\alpha_o - \alpha_{ieff}) \cdot (RT - T_{cure}) + (\alpha_o - \alpha_i) \cdot (T_{op} - RT) \right]$$

$$\sigma_{2star} = 6.352 \times 10^4$$

CALCULATE THE STRESS UNDER THE REPAIR

$$\sigma_o := \frac{\sigma_{2star} \cdot (E_i \cdot t_i)}{E_o \cdot t_o + E_i \cdot t_i} \quad \sigma_o = 3.082 \times 10^4$$

CHECK THE ADHESIVE SHEAR STRAIN

$$\lambda := \sqrt{\left(\frac{G}{\eta}\right) \cdot \left[\left(\frac{1}{E_i \cdot t_i}\right) + \left(\frac{1}{E_o \cdot t_o}\right)\right]} \quad \lambda = 3.423$$

Elastic Shear Strain $\gamma_{maxE} := \sigma_o \cdot t_i \cdot \frac{\lambda}{G} \quad \gamma_{maxE} = 0.128$

Plastic Shear Strain $\gamma_{maxP} := \left(\frac{\tau_p}{2 \cdot G}\right) \cdot \left[1 + \left(\sigma_o \cdot t_i \cdot \frac{\lambda}{\tau_p}\right)^2\right] \quad \gamma_{maxP} = 0.151$

$$\gamma_{max} := \text{if}(\gamma_{maxE} > \gamma_e, \gamma_{maxP}, \gamma_{maxE})$$

Maximum Shear Strain in Adhesive $\gamma_{max} = 0.151$

CALCULATE THE STRESS INTENSITY IN A REPAIRED METALLIC STRUCTURE

$$K_{infE} := \sigma_o \cdot \sqrt{\frac{(E_i \cdot t_i \cdot \lambda \cdot \eta)}{G}} \quad K_{infE} = 2.321 \times 10^4$$

$$K_{infP} := \sqrt{\frac{E_i \cdot \eta}{G} \cdot \left[\sigma_o \cdot \tau_p \cdot \left[1 + \left(\frac{\sigma_o \cdot \lambda \cdot t_i}{\tau_p}\right)^2\right] - \frac{\tau_p^2}{\lambda \cdot t_i \cdot 3} \cdot \left[1 + 2 \cdot \left(\frac{\sigma_o \cdot \lambda \cdot t_i}{\tau_p}\right)^3\right] \right]}$$

$$K_{infP} = 2.381 \times 10^4$$

$$K_{inf} := \text{if}(\gamma_{maxE} > \gamma_e, K_{infP}, K_{infE})$$

Repaired SIF $K_{inf} = 2.381 \times 10^4 \quad \text{psi rt in}$

CHECK THE STRUCTURAL INTEGRITY OF THE PATCH

$$\sigma_p := \frac{(\sigma_{2star} \cdot t_i)}{t_o}$$
$$\sigma_p = 1.71 \times 10^5 \text{ psi}$$
$$\sigma_{2star} = 6.352 \times 10^4$$

IN THE ABSENCE OF THE CRACK

$$\sigma_p := \frac{(E_o \cdot t_i \cdot \sigma_{2star})}{(E_o \cdot t_o + E_i \cdot t_i)}$$

$$\sigma_p = 8.805 \times 10^4$$

A.2. Current Method – Operating Temperature = 75 °F

Single-Sided Fully-Supported Bonded Repair Evaluation of Current Equations

ADHESIVE PROPERTIES

FM73 FILM ADHESIVE (ROOM TEMP CONDITIONS)

ADHESIVE THICKNESS ADHESIVE SHEAR MODULUS ADHESIVE SHEAR STRESS

$\eta := 0.013$ *inch* $G := 73323$ *psi* $\tau_p := 6052$ *psi*

ADHESIVE STRAINS ELASTIC $\gamma_e := 0.0804$

PLASTIC $\gamma_p := 0.497$

CURE TEMPERATURE $T_{cure} := 180$ *F*

2024-T851 ALUMINIUM SKIN PROPERTIES

SKIN THICKNESS $t_i := 0.14$ *in*

YIELD STRESS $\sigma_{yi} := 59 \cdot 10^3$ *psi*

ULTIMATE STRESS $\sigma_{ui} := 65 \cdot 10^3$ *psi*

FRACTURE TOUGHNESS $K_{Ic} := 42000$ *psi rt in*

YOUNGS MODULUS $E_i := 10.5 \cdot 10^6$ *psi*

POISSON'S RATIO $\nu := 0.31$

THERMAL EXPANSN
COEFFICIENT $\alpha_i := 12.6 \cdot 10^{-6}$ *in/in/F* $\alpha_{ieff} := \alpha_i \frac{(\nu + 1)}{2}$

BORON EPOXY 5521/4 PROPERTIES

BORON EPOXY PRE-PREG

ULTIMATE LONGITUDINAL
STRAIN $\epsilon_o := 0.00655$ *in/in*

YOUNGS MODULUS $E_o := 30 \cdot 10^6$ *psi*

THERMAL EXPANSN
COEFFICIENT $\alpha_o := 2.3 \cdot 10^{-6}$ *in/in/F*

THICKNESS $t_o := 0.052$ *in*

DESIGN OPERATING
TEMPERATURE $T_{op} := 75$ *deg F* $RT := 75$ *deg F*

EVALUATION OF STRUCTURAL INTEGRITY OF REPAIRED STRUCTURE

CALCULATE THE STRESS APPLIED

Input remote applied stress $\sigma_{star} := 37100 \text{ psi}$

CHECK THE STRUCTURAL INTEGRITY OF THE STRUCTURE AT THE EDGE OF THE PATCH

Load Attraction Factor $\Omega_L := 1.2$

Stress at the edge of the patch

$$\sigma_{2star} := \Omega_L \cdot \sigma_{star} + E_i \left[(\alpha_o - \alpha_{ieff}) \cdot (RT - T_{cure}) + (\alpha_o - \alpha_i) \cdot (T_{op} - RT) \right]$$

$$\sigma_{2star} = 5.108 \times 10^4$$

CALCULATE THE STRESS UNDER THE REPAIR

$$\sigma_o := \frac{\sigma_{2star} \cdot (E_i \cdot t_i)}{E_o \cdot t_o + E_i \cdot t_i} \quad \sigma_o = 2.478 \times 10^4$$

STEP3(d): CHECK THE ADHESIVE SHEAR STRAIN

$$\lambda := \sqrt{\left(\frac{G}{\eta}\right) \left[\left(\frac{1}{E_i \cdot t_i}\right) + \left(\frac{1}{E_o \cdot t_o}\right) \right]} \quad \lambda = 2.73$$

Elastic Shear Strain $\gamma_{maxE} := \sigma_o \cdot t_i \cdot \frac{\lambda}{G} \quad \gamma_{maxE} = 0.129$

Plastic Shear Strain $\gamma_{maxP} := \left(\frac{\tau_p}{2 \cdot G}\right) \left[1 + \left(\sigma_o \cdot t_i \cdot \frac{\lambda}{\tau_p}\right)^2 \right] \quad \gamma_{maxP} = 0.142$

$$\gamma_{max} := \text{if}(\gamma_{maxE} > \gamma_e, \gamma_{maxP}, \gamma_{maxE})$$

Maximum Shear Strain in Adhesive $\gamma_{max} = 0.142$

CALCULATE THE STRESS INTENSITY IN A REPAIRED METALLIC STRUCTURE

$$K_{infE} := \sigma_o \cdot \sqrt{\frac{(E_i \cdot t_i \cdot \lambda \cdot \eta)}{G}} \quad K_{infE} = 2.09 \times 10^4$$

$$K_{infP} := \sqrt{\frac{E_i \cdot \eta}{G} \left[\sigma_o \cdot \tau_p \left[1 + \left(\frac{\sigma_o \cdot \lambda \cdot t_i}{\tau_p}\right)^2 \right] - \frac{\tau_p^2}{\lambda \cdot t_i \cdot 3} \left[1 + 2 \cdot \left(\frac{\sigma_o \cdot \lambda \cdot t_i}{\tau_p}\right)^3 \right] \right]}$$

$$K_{infP} = 2.116 \times 10^4$$

$$K_{inf} := \text{if}(\gamma_{maxE} > \gamma_e, K_{infP}, K_{infE})$$

Repaired SIF $K_{inf} = 2.116 \times 10^4 \text{ psi rt in}$

CHECK THE STRUCTURAL INTEGRITY OF THE PATCH

$$\sigma_p := \frac{(\sigma_{2star} \cdot t_i)}{t_o}$$

$$\sigma_p = 1.375 \times 10^5 \text{ psi}$$

IN THE ABSENCE OF THE CRACK

$$\sigma_p := \frac{(E_o \cdot t_i \cdot \sigma_{2star})}{(E_o \cdot t_o + E_i \cdot t_i)}$$

$$\sigma_p = 7.081 \times 10^4$$

A.3. Current Method - Operating Temperature = 167 °F

Single-Sided Fully-Supported Bonded Repair Evaluation of Current Equations

ADHESIVE PROPERTIES

FM73 FILM ADHESIVE (167 deg F CONDITIONS)

ADHESIVE THICKNESS	ADHESIVE SHEAR MODULUS	ADHESIVE SHEAR STRESS
$\eta := 0.013$ inch	$G := 13522$ psi	$\tau_p := 3534$ psi
ADHESIVE STRAINS	ELASTIC	$\gamma_e := 0.5896$
	PLASTIC	$\gamma_p := 0.2380$
CURE TEMPERATURE	$T_{cure} := 180$ F	

2024-T851 ALUMINIUM SKIN PROPERTIES

SKIN THICKNESS	$t_i := 0.14$ in	
YIELD STRESS	$\sigma_{yi} := 59 \cdot 10^3$ psi	
ULTIMATE STRESS	$\sigma_{ui} := 65 \cdot 10^3$ psi	
FRACTURE TOUGHNESS	$K_c := 42000$ psi rt in	
YOUNGS MODULUS	$E_i := 10.5 \cdot 10^6$ psi	
POISSON'S RATIO	$\nu := 0.31$	
THERMAL EXPANSN COEFFICIENT	$\alpha_i := 12.6 \cdot 10^{-6}$ in/in/F	$\alpha_{ieff} := \alpha_i \cdot \frac{(\nu + 1)}{2}$

BORON EPOXY 5521/4 PROPERTIES

BORON EPOXY PRE-PREG

ULTIMATE LONGITUDINAL STRAIN	$\epsilon_o := 0.00655$ in/in
YOUNGS MODULUS	$E_o := 30 \cdot 10^6$ psi
THERMAL EXPANSN COEFFICIENT	$\alpha_o := 2.3 \cdot 10^{-6}$ in/in/F
THICKNESS	$t_o := 0.052$ in

DESIGN OPERATING TEMPERATURE	$T_{op} := 167$ deg F	$RT := 75$ deg F
---------------------------------	-----------------------	------------------

EVALUATION OF STRUCTURAL INTEGRITY OF REPAIRED STRUCTURE

CALCULATE THE STRESS APPLIED

Input remote applied stress $\sigma_{star} := 37100 \text{ psi}$

CHECK THE STRUCTURAL INTEGRITY OF THE STRUCTURE AT THE EDGE OF THE PATCH

Load Attraction Factor $\Omega_L := 1.2$

Stress at the edge of the patch

$$\sigma_{2star} := \Omega_L \cdot \sigma_{star} + E_i \left[(\alpha_o - \alpha_{ieff}) \cdot (RT - T_{cure}) + (\alpha_o - \alpha_i) \cdot (T_{op} - RT) \right]$$

$$\sigma_{2star} = 4.113 \times 10^4$$

CALCULATE THE STRESS UNDER THE REPAIR

$$\sigma_o := \frac{\sigma_{2star} \cdot (E_i \cdot t_i)}{E_o \cdot t_o + E_i \cdot t_i} \quad \sigma_o = 1.996 \times 10^4$$

CHECK THE ADHESIVE SHEAR STRAIN

$$\lambda := \sqrt{\left(\frac{G}{\eta}\right) \left[\left(\frac{1}{E_i \cdot t_i}\right) + \left(\frac{1}{E_o \cdot t_o}\right) \right]} \quad \lambda = 1.172$$

Elastic Shear Strain $\gamma_{maxE} := \sigma_o \cdot t_i \cdot \frac{\lambda}{G} \quad \gamma_{maxE} = 0.242$

Plastic Shear Strain $\gamma_{maxP} := \left(\frac{\tau_p}{2 \cdot G}\right) \left[1 + \left(\sigma_o \cdot t_i \cdot \frac{\lambda}{\tau_p}\right)^2 \right] \quad \gamma_{maxP} = 0.243$

$$\gamma_{max} := \text{if}(\gamma_{maxE} > \gamma_e, \gamma_{maxP}, \gamma_{maxE})$$

Maximum Shear Strain in Adhesive $\gamma_{max} = 0.242$

CALCULATE THE STRESS INTENSITY IN A REPAIRED METALLIC STRUCTURE

$$K_{infE} := \sigma_o \cdot \sqrt{\frac{(E_i \cdot t_i \cdot \lambda \cdot \eta)}{G}} \quad K_{infE} = 2.569 \times 10^4$$

$$K_{infP} := \sqrt{\frac{E_i \cdot \eta}{G} \left[\sigma_o \cdot \tau_p \left[1 + \left(\frac{\sigma_o \cdot \lambda \cdot t_i}{\tau_p}\right)^2 \right] - \frac{\tau_p^2}{\lambda \cdot t_i \cdot 3} \left[1 + 2 \cdot \left(\frac{\sigma_o \cdot \lambda \cdot t_i}{\tau_p}\right)^3 \right] \right]}$$

$$K_{infP} = 2.568 \times 10^4$$

$$K_{inf} := \text{if}(\gamma_{maxE} > \gamma_e, K_{infP}, K_{infE})$$

Repaired SIF $K_{inf} = 2.569 \times 10^4 \text{ psi rt in}$

CHECK THE STRUCTURAL INTEGRITY OF THE PATCH

$$\sigma_p := \frac{(\sigma_{2star} \cdot t_i)}{t_o}$$

$$\sigma_p = 1.107 \times 10^5 \text{ psi}$$

IN THE ABSENCE OF THE CRACK

$$\sigma_p := \frac{(E_o \cdot t_i \cdot \sigma_{2star})}{(E_o \cdot t_o + E_i \cdot t_i)}$$

$$\sigma_p = 5.702 \times 10^4$$

A.4. Improved Method - Operating Temperature = -40 °F

Single-Sided Fully-Supported Bonded Repair Evaluation of Proposed Equations

ADHESIVE PROPERTIES

FM73 FILM ADHESIVE (Minus 40 deg F CONDITIONS)

ADHESIVE THICKNESS	ADHESIVE SHEAR MODULUS	ADHESIVE SHEAR STRESS
$\eta := 0.013 \text{ inch}$	$G := 115306 \text{ psi}$	$\tau_p := 8230 \text{ psi}$
YOUNGS MODULUS:		
$\mu := 0.30$		
$E_c := 2 \cdot G \cdot (1 + \mu)$	$E_c = 2.998 \times 10^5 \text{ psi}$	
ADHESIVE STRAINS	ELASTIC	$\gamma_e := 0.0723$
	PLASTIC	$\gamma_p := 0.1192$
CURE TEMPERATURE	$T_{\text{cure}} := 180 \text{ F}$	

2024-T851 ALUMINIUM SKIN PROPERTIES

SKIN THICKNESS	$t_i := 0.14 \text{ in}$	
YIELD STRESS	$\sigma_{yi} := 59 \cdot 10^3 \text{ psi}$	
ULTIMATE STRESS	$\sigma_{ui} := 65 \cdot 10^3 \text{ psi}$	
FRACTURE TOUGHNESS	$K_{ci} := 42000 \text{ psi rt in}$	
YOUNGS MODULUS	$E_i := 10.5 \cdot 10^6 \text{ psi}$	
POISSON'S RATIO	$\nu := 0.31$	
THERMAL EXPANSN COEFFICIENT	$\alpha_i := 12.6 \cdot 10^{-6} \text{ in/in/F}$	$\alpha_{ieff} := \alpha_i \frac{(\nu + 1)}{2}$

BORON EPOXY 5521/4 PROPERTIES

BORON EPOXY PRE-PREG

ULTIMATE LONGITUDINAL STRAIN	$\epsilon_0 := 0.00655 \text{ in/in}$	
YOUNGS MODULUS	$E_0 := 30 \cdot 10^6 \text{ psi}$	
THERMAL EXPANSN COEFFICIENT	$\alpha_0 := 2.3 \cdot 10^{-6} \text{ in/in/F}$	
POISSON'S RATIO	$\nu_{210} := 0.019$	$\nu_{120} := 0.21$
THICKNESS	$t_0 := 0.052 \text{ in}$	
DESIGN OPERATING TEMPERATURE	$T_{op} := -40 \text{ deg F}$	$RT := 75 \text{ deg F}$

EVALUATION OF STRUCTURAL INTEGRITY OF REPAIRED STRUCTURE**CALCULATE THE STRESS APPLIED**

Input remote applied stress $\sigma_{\text{star}} := 37100 \text{ psi}$

CHECK THE STRUCTURAL INTEGRITY OF THE STRUCTURE AT THE EDGE OF THE PATCH

$$\text{Stiffness Ratio} \quad S := \frac{(E_o \cdot t_o)}{(E_i \cdot t_i)} \quad S = 1.061$$

$$\text{Load Attraction Factor} \quad \Omega_L := 1.2$$

Stress at the edge of the patch due to applied load

$$\begin{aligned} \sigma_{2\text{starapplied}} &:= \Omega_L \cdot \sigma_{\text{star}} \\ \sigma_{2\text{starapplied}} &= 4.452 \times 10^4 \end{aligned}$$

Stress at the edge of the patch due to heating during cure

$$\sigma_{2\text{starheating}} := -\alpha_i \cdot E_i \cdot \frac{(T_{\text{cure}} - RT)}{2} \quad \sigma_{2\text{starheating}} = -6.946 \times 10^3$$

Stress at the edge of the patch due to cooling to ambient during cure

$$\begin{aligned} \sigma_{2\text{starcooling}} &:= -\alpha_i \cdot E_i \cdot (RT - T_{\text{cure}}) \cdot \frac{\left[1 - \nu_{12o} + S \cdot (1 - \nu) \cdot \frac{\alpha_o}{\alpha_i} \right]}{2 \cdot (1 - \nu_{12o}) + (1 - \nu^2) \cdot S} \\ \sigma_{2\text{starcooling}} &= 5.053 \times 10^3 \end{aligned}$$

Stress at the edge of the patch due to change to operating temperature

$$\begin{aligned} \sigma_{2\text{staroperating}} &:= \alpha_i \cdot E_i \cdot (T_{\text{op}} - RT) \cdot \frac{\left[(1 - \nu) \cdot \left(1 - \frac{\alpha_o}{\alpha_i} \right) \cdot S \right]}{2 \cdot (1 - \nu_{12o}) + (1 - \nu^2) \cdot S} \\ \sigma_{2\text{staroperating}} &= -3.587 \times 10^3 \end{aligned}$$

$$\sigma_{2\text{star}} := \sigma_{2\text{starapplied}} + \sigma_{2\text{starheating}} + \sigma_{2\text{starcooling}} + \sigma_{2\text{staroperating}}$$

$$\sigma_{2\text{star}} = 3.904 \times 10^4$$

CALCULATE THE STRESS UNDER THE REPAIR

Stress under patch due to applied load

$$\sigma_{\text{oapplied}} := \frac{(\Omega_L \cdot \sigma_{\text{star}})}{(1 + S)} \quad \sigma_{\text{oapplied}} = 2.16 \times 10^4$$

Stress under patch due to heating during cure

$$\sigma_{\text{oheating}} := -\alpha_i \cdot E_i \cdot \frac{(T_{\text{cure}} - RT)}{2} \quad \sigma_{\text{oheating}} = -6.946 \times 10^3$$

Stress under patch due to cooling during cure

$$\sigma_{\text{ocooling}} := -\alpha_i E_i (RT - T_{\text{cure}}) \cdot \left[\frac{\left[1 - \nu_{12o} + \left(1 - \frac{\alpha_o}{\alpha_i} \right) \cdot (1 + \nu) \cdot S \right]}{\left[2 \cdot (1 - \nu_{12o}) + (1 - \nu^2) \cdot S \right]} \right]$$

$$\sigma_{\text{ocooling}} = 1.054 \times 10^4$$

Stress under patch due to change to operating temperature

$$\sigma_{\text{operating}} := -\alpha_i E_i (T_{\text{op}} - RT) \cdot \left[\frac{\left[(1 + \nu) \cdot \left(1 - \frac{\alpha_o}{\alpha_i} \right) \cdot S \right]}{\left[2 \cdot (1 - \nu_{12o}) + (1 - \nu^2) \cdot S \right]} \right]$$

$$\sigma_{\text{operating}} = 6.809 \times 10^3$$

Stress under patch (total)

$$\sigma_o := \sigma_{\text{applied}} + \sigma_{\text{heating}} + \sigma_{\text{ocooling}} + \sigma_{\text{operating}}$$

$$\sigma_o = 3.2 \times 10^4$$

CHECK THE ADHESIVE SHEAR STRAIN

$$\lambda := \sqrt{\left(\frac{G}{\eta} \right) \cdot \left[\left(\frac{1}{E_i \cdot t_i} \right) + \left(\frac{1}{E_o \cdot t_o} \right) \right]} \quad \lambda = 3.423$$

$$\text{Elastic Shear Strain} \quad \gamma_{\text{maxE}} := \sigma_o \cdot t_i \cdot \frac{\lambda}{G} \quad \gamma_{\text{maxE}} = 0.133$$

$$\text{Plastic Shear Strain} \quad \gamma_{\text{maxP}} := \left(\frac{\tau_p}{2 \cdot G} \right) \cdot \left[1 + \left(\sigma_o \cdot t_i \cdot \frac{\lambda}{\tau_p} \right)^2 \right] \quad \gamma_{\text{maxP}} = 0.16$$

$$\gamma_{\text{max}} := \text{if}(\gamma_{\text{maxE}} > \gamma_e, \gamma_{\text{maxP}}, \gamma_{\text{maxE}})$$

$$\text{Maximum Shear Strain in Adhesive} \quad \gamma_{\text{max}} = 0.16$$

CALCULATE THE STRESS INTENSITY IN A REPAIRED METALLIC STRUCTURE

$$K_{\text{infE}} := \sigma_o \cdot \sqrt{\frac{E_i \cdot t_i \cdot \lambda \cdot \eta}{G}} \quad K_{\text{infE}} = 2.41 \times 10^4$$

$$K_{\text{infP}} := \sqrt{\frac{E_i \cdot \eta}{G} \left[\sigma_o \cdot \tau_p \left[1 + \left(\frac{\sigma_o \cdot \lambda \cdot t_i}{\tau_p} \right)^2 \right] - \frac{\tau_p^2}{\lambda \cdot t_i \cdot 3} \left[1 + 2 \cdot \left(\frac{\sigma_o \cdot \lambda \cdot t_i}{\tau_p} \right)^3 \right] \right]}$$

$$K_{\text{infP}} = 2.484 \times 10^4$$

$$K_{\text{inf}} := \text{if}(\gamma_{\text{maxE}} > \gamma_e, K_{\text{infP}}, K_{\text{infE}})$$

$$\text{Repaired SIF} \quad K_{\text{inf}} = 2.484 \times 10^4 \quad \text{psi rt in}$$

*CHECK THE STRUCTURAL INTEGRITY OF THE PATCH**Assuming a crack is present*

$$\sigma_p := \frac{(\sigma_{2\text{star}} \cdot t_i)}{t_o}$$

$$\sigma_p = 1.051 \times 10^5 \quad \text{psi}$$

*Assuming no crack**Stress in patch due to applied load*

$$\sigma_{\text{applied}} := \frac{\Omega_L \cdot \sigma_{\text{star}} \cdot S \cdot t_i}{(1 + S) \cdot t_o} \quad \sigma_{\text{applied}} = 6.171 \times 10^4$$

*Stress in patch due to heating during cure**There is no stress in the patch due to heating because it is free to expand*

$$\sigma_{\text{pheating}} := 0$$

Stress in patch due to cooling during cure

$$\sigma_{\text{pcooling}} := \alpha_i \cdot E_o \cdot (RT - T_{\text{cure}}) \cdot \left[\frac{\left(1 + \nu - 2 \cdot \frac{\alpha_o}{\alpha_i} \right)}{\left[2 \cdot (1 - \nu_{12o}) + (1 - \nu^2) \cdot S \right]} \right]$$

$$\sigma_{\text{pcooling}} = -1.477 \times 10^4$$

Stress in patch due to change to operating temperature

$$\sigma_{\text{poperating}} := \alpha_i \cdot E_o \cdot (T_{\text{op}} - RT) \cdot \left[\frac{2 \cdot \left(1 - \frac{\alpha_o}{\alpha_i} \right)}{\left[2 \cdot (1 - \nu_{12o}) + (1 - \nu^2) \cdot S \right]} \right]$$

$$\sigma_{\text{poperating}} = -2.799 \times 10^4$$

Stress in patch (total)

$$\sigma_p := \sigma_{\text{applied}} + \sigma_{\text{pheating}} + \sigma_{\text{pcooling}} + \sigma_{\text{poperating}}$$

$$\sigma_p = 1.895 \times 10^4$$

A.5. Improved Method – Operating Temperature = 75 °F

Single-Sided Fully-Supported Bonded Repair Evaluation of Proposed Equations

ADHESIVE PROPERTIES

FM73 FILM ADHESIVE (ROOM TEMP CONDITIONS)

ADHESIVE THICKNESS ADHESIVE SHEAR MODULUS ADHESIVE SHEAR STRESS

$$\eta := 0.013 \quad \text{inch} \quad G := 73323 \quad \text{psi} \quad \tau_p := 6052 \quad \text{psi}$$

YOUNGS MODULUS:

$$\mu := 0.30$$

$$E_c := 2 \cdot G \cdot (1 + \mu) \quad E_c = 1.906 \times 10^5 \quad \text{psi}$$

ADHESIVE STRAINS ELASTIC $\gamma_e := 0.0804$

PLASTIC $\gamma_p := 0.497$

CURE TEMPERATURE $T_{\text{cure}} := 180 \quad F$

2024-T851 ALUMINIUM SKIN PROPERTIES

SKIN THICKNESS $t_i := 0.14 \quad \text{in}$

YIELD STRESS $\sigma_{yi} := 59 \cdot 10^3 \quad \text{psi}$

ULTIMATE STRESS $\sigma_{ui} := 65 \cdot 10^3 \quad \text{psi}$

FRACTURE TOUGHNESS $K_{Ic} := 42000 \quad \text{psi rt in}$

YOUNGS MODULUS $E_i := 10.5 \cdot 10^6 \quad \text{psi}$

POISSON'S RATIO $\nu := 0.31$

THERMAL EXPANSN
COEFFICIENT $\alpha_i := 12.6 \cdot 10^{-6} \quad \text{in/in/F}$ $\alpha_{\text{ieff}} := \alpha_i \frac{(\nu + 1)}{2}$

BORON EPOXY 5521/4 PROPERTIES

BORON EPOXY PRE-PREG

ULTIMATE LONGITUDINAL
STRAIN $\epsilon_o := 0.00655 \quad \text{in/in}$

YOUNGS MODULUS $E_o := 30 \cdot 10^6 \quad \text{psi}$

THERMAL EXPANSN
COEFFICIENT $\alpha_o := 2.3 \cdot 10^{-6} \quad \text{in/in/F}$

POISSON'S RATIO $\nu_{21o} := 0.019$ $\nu_{12o} := 0.21$

THICKNESS $t_o := 0.052 \quad \text{in}$

DESIGN OPERATING
TEMPERATURE $T_{\text{op}} := 75 \quad \text{deg F}$ $RT := 75 \quad \text{deg F}$

EVALUATION OF STRUCTURAL INTEGRITY OF REPAIRED STRUCTURE**CALCULATE THE STRESS APPLIED**

Input remote applied stress $\sigma_{star} := 37100 \quad psi$

CHECK THE STRUCTURAL INTEGRITY OF THE STRUCTURE AT THE EDGE OF THE PATCH

$$\text{Stiffness Ratio} \quad S := \frac{(E_o \cdot t_o)}{(E_i \cdot t_i)} \quad S = 1.061$$

$$\text{Load Attraction Factor} \quad \Omega_L := 1.2$$

Stress at the edge of the patch due to applied load

$$\sigma_{2starapplied} := \Omega_L \cdot \sigma_{star}$$

$$\sigma_{2starapplied} = 4.452 \times 10^4$$

Stress at the edge of the patch due to heating during cure

$$\sigma_{2starheating} := -\alpha_i \cdot E_i \cdot \frac{(T_{cure} - RT)}{2} \quad \sigma_{2starheating} = -6.946 \times 10^3$$

Stress at the edge of the patch due to cooling to ambient during cure

$$\sigma_{2starcooling} := -\alpha_i \cdot E_i \cdot (RT - T_{cure}) \cdot \frac{\left[1 - \nu_{12o} + S \cdot (1 - \nu) \cdot \frac{\alpha_o}{\alpha_i} \right]}{2 \cdot (1 - \nu_{12o}) + (1 - \nu^2) \cdot S}$$

$$\sigma_{2starcooling} = 5.053 \times 10^3$$

Stress at the edge of the patch due to change to operating temperature

$$\sigma_{2staroperating} := \alpha_i \cdot E_i \cdot (T_{op} - RT) \cdot \frac{\left[(1 - \nu) \cdot \left(1 - \frac{\alpha_o}{\alpha_i} \right) \cdot S \right]}{2 \cdot (1 - \nu_{12o}) + (1 - \nu^2) \cdot S}$$

$$\sigma_{2staroperating} = 0$$

$$\sigma_{2star} := \sigma_{2starapplied} + \sigma_{2starheating} + \sigma_{2starcooling} + \sigma_{2staroperating}$$

$$\sigma_{2star} = 4.263 \times 10^4$$

CALCULATE THE STRESS UNDER THE REPAIR

Stress under patch due to applied load

$$\sigma_{oapplied} := \frac{(\Omega_L \cdot \sigma_{star})}{(1 + S)} \quad \sigma_{oapplied} = 2.16 \times 10^4$$

Stress under patch due to heating during cure

$$\sigma_{oheating} := -\alpha_i \cdot E_i \cdot \frac{(T_{cure} - RT)}{2} \quad \sigma_{oheating} = -6.946 \times 10^3$$

Stress under patch due to cooling during cure

$$\sigma_{\text{ocooling}} := -\alpha_j \cdot E_i \cdot (RT - T_{\text{cure}}) \cdot \left[\frac{\left[1 - \nu_{12o} + \left(1 - \frac{\alpha_o}{\alpha_j} \right) \cdot (1 + \nu) \cdot S \right]}{\left[2 \cdot (1 - \nu_{12o}) + (1 - \nu^2) \cdot S \right]} \right]$$

$$\sigma_{\text{ocooling}} = 1.054 \times 10^4$$

Stress under patch due to change to operating temperature

$$\sigma_{\text{operating}} := -\alpha_j \cdot E_i \cdot (T_{\text{op}} - RT) \cdot \left[\frac{\left[(1 + \nu) \cdot \left(1 - \frac{\alpha_o}{\alpha_j} \right) \cdot S \right]}{\left[2 \cdot (1 - \nu_{12o}) + (1 - \nu^2) \cdot S \right]} \right]$$

$$\sigma_{\text{operating}} = 0$$

Stress under patch (total)

$$\sigma_o := \sigma_{\text{applied}} + \sigma_{\text{heating}} + \sigma_{\text{ocooling}} + \sigma_{\text{operating}}$$

$$\sigma_o = 2.519 \times 10^4$$

CHECK THE ADHESIVE SHEAR STRAIN

$$\lambda := \sqrt{\left(\frac{G}{\eta} \right) \cdot \left[\left(\frac{1}{E_i \cdot t_j} \right) + \left(\frac{1}{E_o \cdot t_o} \right) \right]} \quad \lambda = 2.73$$

Elastic Shear Strain $\gamma_{\text{maxE}} := \sigma_o \cdot t_j \cdot \frac{\lambda}{G}$ $\gamma_{\text{maxE}} = 0.131$

Plastic Shear Strain $\gamma_{\text{maxP}} := \left(\frac{\tau_p}{2 \cdot G} \right) \cdot \left[1 + \left(\sigma_o \cdot t_j \cdot \frac{\lambda}{\tau_p} \right)^2 \right]$ $\gamma_{\text{maxP}} = 0.146$

$$\gamma_{\text{max}} := \text{if}(\gamma_{\text{maxE}} > \gamma_e, \gamma_{\text{maxP}}, \gamma_{\text{maxE}})$$

Maximum Shear Strain in Adhesive $\gamma_{\text{max}} = 0.146$

CALCULATE THE STRESS INTENSITY IN A REPAIRED METALLIC STRUCTURE

$$K_{\text{infE}} := \sigma_o \cdot \sqrt{\frac{E_i \cdot t_j \cdot \lambda \cdot \eta}{G}} \quad K_{\text{infE}} = 2.125 \times 10^4$$

$$K_{\text{infP}} := \sqrt{\frac{E_i \cdot \eta}{G} \left[\sigma_o \cdot \tau_p \cdot \left[1 + \left(\frac{\sigma_o \cdot \lambda \cdot t_j}{\tau_p} \right)^2 \right] - \frac{\tau_p^2}{\lambda \cdot t_j \cdot 3} \cdot \left[1 + 2 \cdot \left(\frac{\sigma_o \cdot \lambda \cdot t_j}{\tau_p} \right)^3 \right] \right]}$$

$$K_{\text{infP}} = 2.154 \times 10^4$$

$$K_{\text{inf}} := \text{if}(\gamma_{\text{maxE}} > \gamma_e, K_{\text{infP}}, K_{\text{infE}})$$

Repaired SIF $K_{\text{inf}} = 2.154 \times 10^4$ *psi rt in*

*CHECK THE STRUCTURAL INTEGRITY OF THE PATCH**Assuming a crack is present*

$$\sigma_p := \frac{(\sigma_{2\text{star}} \cdot t_i)}{t_o}$$

$$\sigma_p = 1.148 \times 10^5 \quad \text{psi}$$

*Assuming no crack**Stress in patch due to applied load*

$$\sigma_{\text{pplied}} := \frac{\Omega_L \cdot \sigma_{\text{star}} \cdot S \cdot t_i}{(1 + S) \cdot t_o} \quad \sigma_{\text{pplied}} = 6.171 \times 10^4$$

*Stress in patch due to heating during cure**There is no stress in the patch due to heating because it is free to expand*

$$\sigma_{\text{pheating}} := 0$$

Stress in patch due to cooling during cure

$$\sigma_{\text{pcooling}} := \alpha_i \cdot E_o \cdot (RT - T_{\text{cure}}) \cdot \left[\frac{\left(1 + \nu - 2 \cdot \frac{\alpha_o}{\alpha_i} \right)}{\left[2 \cdot (1 - \nu_{12o}) + (1 - \nu^2) \cdot S \right]} \right]$$

$$\sigma_{\text{pcooling}} = -1.477 \times 10^4$$

Stress in patch due to change to operating temperature

$$\sigma_{\text{poperating}} := \alpha_i \cdot E_o \cdot (T_{\text{op}} - RT) \cdot \left[\frac{2 \cdot \left(1 - \frac{\alpha_o}{\alpha_i} \right)}{\left[2 \cdot (1 - \nu_{12o}) + (1 - \nu^2) \cdot S \right]} \right]$$

$$\sigma_{\text{poperating}} = 0$$

Stress in patch (total)

$$\sigma_p := \sigma_{\text{pplied}} + \sigma_{\text{pheating}} + \sigma_{\text{pcooling}} + \sigma_{\text{poperating}}$$

$$\sigma_p = 4.694 \times 10^4$$

A.6. Improved Method - Operating Temperature = 167 °F

Single-Sided Fully-Supported Bonded Repair Evaluation of Proposed Equations

ADHESIVE PROPERTIES

FM73 FILM ADHESIVE (167 deg F CONDITIONS)

ADHESIVE THICKNESS ADHESIVE SHEAR MODULUS ADHESIVE SHEAR STRESS

$$\eta := 0.013 \quad \text{inch} \quad G := 13522 \quad \text{psi} \quad \tau_p := 3534 \quad \text{psi}$$

YOUNGS MODULUS:

$$\mu := 0.30$$

$$E_c := 2 \cdot G \cdot (1 + \mu) \quad E_c = 3.516 \times 10^4 \quad \text{psi}$$

ADHESIVE STRAINS ELASTIC $\gamma_e := 0.5896$
PLASTIC $\gamma_p := 0.2380$

CURE TEMPERATURE $T_{\text{cure}} := 180 \quad \text{F}$

2024-T851 ALUMINIUM SKIN PROPERTIES

SKIN THICKNESS $t_i := 0.14 \quad \text{in}$

YIELD STRESS $\sigma_{yi} := 59 \cdot 10^3 \quad \text{psi}$

ULTIMATE STRESS $\sigma_{ui} := 65 \cdot 10^3 \quad \text{psi}$

FRACTURE TOUGHNESS $K_{Ic} := 42000 \quad \text{psi rt in}$

YOUNGS MODULUS $E_i := 10.5 \cdot 10^6 \quad \text{psi}$

POISSON'S RATIO $\nu := 0.31$

THERMAL EXPANSN COEFFICIENT $\alpha_j := 12.6 \cdot 10^{-6} \quad \text{in/in/F}$ $\alpha_{ieff} := \alpha_j \cdot \frac{(\nu + 1)}{2}$

BORON EPOXY 5521/4 PROPERTIES

BORON EPOXY PRE-PREG

ULTIMATE LONGITUDINAL STRAIN $\epsilon_0 := 0.00655 \quad \text{in/in}$

YOUNGS MODULUS $E_0 := 30 \cdot 10^6 \quad \text{psi}$

THERMAL EXPANSN COEFFICIENT $\alpha_0 := 2.3 \cdot 10^{-6} \quad \text{in/in/F}$

POISSON'S RATIO $\nu_{210} := 0.019$ $\nu_{120} := 0.21$

THICKNESS $t_0 := 0.052 \quad \text{in}$

DESIGN OPERATING TEMPERATURE $T_{op} := 167 \quad \text{deg F}$ $RT := 75 \quad \text{deg F}$

EVALUATION OF STRUCTURAL INTEGRITY OF REPAIRED STRUCTURE**CALCULATE THE STRESS APPLIED**

Input remote applied stress $\sigma_{star} := 37100 \text{ psi}$

CHECK THE STRUCTURAL INTEGRITY OF THE STRUCTURE AT THE EDGE OF THE PATCH

$$\text{Stiffness Ratio} \quad S := \frac{(E_o \cdot t_o)}{(E_i \cdot t_i)} \quad S = 1.061$$

$$\text{Load Attraction Factor} \quad \Omega_L := 1.2$$

Stress at the edge of the patch due to applied load

$$\begin{aligned} \sigma_{2starapplied} &:= \Omega_L \cdot \sigma_{star} \\ \sigma_{2starapplied} &= 4.452 \times 10^4 \end{aligned}$$

Stress at the edge of the patch due to heating during cure

$$\sigma_{2starheating} := -\alpha_i \cdot E_i \cdot \frac{(T_{cure} - RT)}{2} \quad \sigma_{2starheating} = -6.946 \times 10^3$$

Stress at the edge of the patch due to cooling to ambient during cure

$$\begin{aligned} \sigma_{2starcooling} &:= -\alpha_i \cdot E_i \cdot (RT - T_{cure}) \cdot \frac{\left[1 - \nu_{12o} + S \cdot (1 - \nu) \cdot \frac{\alpha_o}{\alpha_i} \right]}{2 \cdot (1 - \nu_{12o}) + (1 - \nu^2) \cdot S} \\ \sigma_{2starcooling} &= 5.053 \times 10^3 \end{aligned}$$

Stress at the edge of the patch due to change to operating temperature

$$\begin{aligned} \sigma_{2staroperating} &:= \alpha_i \cdot E_i \cdot (T_{op} - RT) \cdot \frac{\left[(1 - \nu) \cdot \left(1 - \frac{\alpha_o}{\alpha_i} \right) \cdot S \right]}{2 \cdot (1 - \nu_{12o}) + (1 - \nu^2) \cdot S} \\ \sigma_{2staroperating} &= 2.869 \times 10^3 \end{aligned}$$

$$\sigma_{2star} := \sigma_{2starapplied} + \sigma_{2starheating} + \sigma_{2starcooling} + \sigma_{2staroperating}$$

$$\sigma_{2star} = 4.55 \times 10^4$$

CALCULATE THE STRESS UNDER THE REPAIR

Stress under patch due to applied load

$$\sigma_{oapplied} := \frac{(\Omega_L \cdot \sigma_{star})}{(1 + S)} \quad \sigma_{oapplied} = 2.16 \times 10^4$$

Stress under patch due to heating during cure

$$\sigma_{oheating} := -\alpha_i \cdot E_i \cdot \frac{(T_{cure} - RT)}{2} \quad \sigma_{oheating} = -6.946 \times 10^3$$

Stress under patch due to cooling during cure

$$\sigma_{\text{ocooling}} := -\alpha_j \cdot E_i \cdot (RT - T_{\text{cure}}) \cdot \left[\frac{\left[1 - \nu_{120} + \left(1 - \frac{\alpha_o}{\alpha_j} \right) \cdot (1 + \nu) \cdot S \right]}{\left[2 \cdot (1 - \nu_{120}) + (1 - \nu^2) \cdot S \right]} \right]$$

$$\sigma_{\text{ocooling}} = 1.054 \times 10^4$$

Stress under patch due to change to operating temperature

$$\sigma_{\text{operating}} := -\alpha_j \cdot E_i \cdot (T_{\text{op}} - RT) \cdot \left[\frac{\left[(1 + \nu) \cdot \left(1 - \frac{\alpha_o}{\alpha_j} \right) \cdot S \right]}{\left[2 \cdot (1 - \nu_{120}) + (1 - \nu^2) \cdot S \right]} \right]$$

$$\sigma_{\text{operating}} = -5.447 \times 10^3$$

Stress under patch (total)

$$\sigma_o := \sigma_{\text{applied}} + \sigma_{\text{heating}} + \sigma_{\text{ocooling}} + \sigma_{\text{operating}}$$

$$\sigma_o = 1.974 \times 10^4$$

CHECK THE ADHESIVE SHEAR STRAIN

$$\lambda := \sqrt{\left(\frac{G}{\eta} \right) \cdot \left[\left(\frac{1}{E_i \cdot t_i} \right) + \left(\frac{1}{E_o \cdot t_o} \right) \right]} \quad \lambda = 1.172$$

$$\text{Elastic Shear Strain} \quad \gamma_{\text{maxE}} := \sigma_o \cdot t_i \cdot \frac{\lambda}{G} \quad \gamma_{\text{maxE}} = 0.24$$

$$\text{Plastic Shear Strain} \quad \gamma_{\text{maxP}} := \left(\frac{\tau_p}{2 \cdot G} \right) \cdot \left[1 + \left(\sigma_o \cdot t_i \cdot \frac{\lambda}{\tau_p} \right)^2 \right] \quad \gamma_{\text{maxP}} = 0.241$$

$$\gamma_{\text{max}} := \text{if}(\gamma_{\text{maxE}} > \gamma_e, \gamma_{\text{maxP}}, \gamma_{\text{maxE}})$$

$$\text{Maximum Shear Strain in Adhesive} \quad \gamma_{\text{max}} = 0.24$$

CALCULATE THE STRESS INTENSITY IN A REPAIRED METALLIC STRUCTURE

$$K_{\text{infE}} := \sigma_o \cdot \sqrt{\frac{E_i \cdot t_i \cdot \lambda \cdot \eta}{G}} \quad K_{\text{infE}} = 2.541 \times 10^4$$

$$K_{\text{infP}} := \sqrt{\frac{E_i \cdot \eta}{G} \cdot \left[\sigma_o \cdot \tau_p \cdot \left[1 + \left(\frac{\sigma_o \cdot \lambda \cdot t_i}{\tau_p} \right)^2 \right] - \frac{\tau_p^2}{\lambda \cdot t_i \cdot 3} \cdot \left[1 + 2 \cdot \left(\frac{\sigma_o \cdot \lambda \cdot t_i}{\tau_p} \right)^3 \right] \right]}$$

$$K_{\text{infP}} = 2.541 \times 10^4$$

$$K_{\text{inf}} := \text{if}(\gamma_{\text{maxE}} > \gamma_e, K_{\text{infP}}, K_{\text{infE}})$$

$$\text{Repaired SIF} \quad K_{\text{inf}} = 2.541 \times 10^4 \quad \text{psi rt in}$$

*CHECK THE STRUCTURAL INTEGRITY OF THE PATCH**Assuming a crack is present*

$$\sigma_p := \frac{(\sigma_{2\text{star}} \cdot t_i)}{t_o}$$

$$\sigma_p = 1.225 \times 10^5 \quad \text{psi}$$

*Assuming no crack**Stress in patch due to applied load*

$$\sigma_{\text{papplied}} := \frac{\Omega_L \cdot \sigma_{\text{star}} \cdot S \cdot t_i}{(1 + S) \cdot t_o} \quad \sigma_{\text{papplied}} = 6.171 \times 10^4$$

*Stress in patch due to heating during cure**There is no stress in the patch due to heating because it is free to expand*

$$\sigma_{\text{pheating}} := 0$$

Stress in patch due to cooling during cure

$$\sigma_{\text{pcooling}} := \alpha_i \cdot E_o \cdot (RT - T_{\text{cure}}) \cdot \left[\frac{\left(1 + \nu - 2 \cdot \frac{\alpha_o}{\alpha_i} \right)}{\left[2 \cdot (1 - \nu_{12o}) + (1 - \nu^2) \cdot S \right]} \right]$$

$$\sigma_{\text{pcooling}} = -1.477 \times 10^4$$

Stress in patch due to change to operating temperature

$$\sigma_{\text{poperating}} := \alpha_i \cdot E_o \cdot (T_{\text{op}} - RT) \cdot \left[\frac{2 \cdot \left(1 - \frac{\alpha_o}{\alpha_i} \right)}{\left[2 \cdot (1 - \nu_{12o}) + (1 - \nu^2) \cdot S \right]} \right]$$

$$\sigma_{\text{poperating}} = 2.239 \times 10^4$$

Stress in patch (total)

$$\sigma_p := \sigma_{\text{papplied}} + \sigma_{\text{pheating}} + \sigma_{\text{pcooling}} + \sigma_{\text{poperating}}$$

$$\sigma_p = 6.933 \times 10^4$$

This page intentionally left blank

DISTRIBUTION LIST

Review of Improved Methods for Analysing Load Attraction and Thermal Effects in
Bonded Composite Repair Design

A. B. Harman and K. F. Walker

AUSTRALIA

DEFENCE ORGANISATION

	No. of copies
Task Sponsor	
DGTA	1
S&T Program	
Chief Defence Scientist	} shared copy
FAS Science Policy	
AS Science Corporate Management	
Director General Science Policy Development	
Counsellor Defence Science, London	Doc Data Sheet
Counsellor Defence Science, Washington	Doc Data Sheet
Scientific Adviser to MRDC, Thailand	Doc Data Sheet
Scientific Adviser Joint	1
Navy Scientific Adviser	Doc Data Sht & Dist List
Scientific Adviser - Army	Doc Data Sht & Dist List
Air Force Scientific Adviser	1
Scientific Adviser to the DMO M&A	1
Scientific Adviser to the DMO ELL	Doc Data Sht & Dist List
Director of Trials	1
Platforms Sciences Laboratory	
Chief of Air Vehicles Division	Doc Data Sht & Dist List
Research Leader Aircraft Materials	1
Research Leader Aircraft Structures	1
Kevin Walker	3
Alex Harman	2
Andrew Rider	1
Chun Wang	1
John Wang	1
Alan Baker	1
Richard Bartholomeusz	1
DSTO Library and Archives	
Library Fishermans Bend	Doc Data Sheet
Library Edinburgh	1
Australian Archives	1
Capability Systems Division	
Director General Maritime Development	Doc Data Sheet
Director General Aerospace Development	1
Director General Information Capability Development	Doc Data Sheet

Office of the Chief Information Officer

Deputy CIO	Doc Data Sheet
Director General Information Policy and Plans	Doc Data Sheet
AS Information Structures and Futures	Doc Data Sheet
AS Information Architecture and Management	Doc Data Sheet
Director General Australian Defence Simulation Office	Doc Data Sheet

Strategy Group

Director General Military Strategy	Doc Data Sheet
Director General Preparedness	Doc Data Sheet

HQAST

SO (Science) (ASJIC)	Doc Data Sheet
----------------------	----------------

Navy

SO (SCIENCE), COMAUSNAVSURFGRP, NSW	Doc Data Sht & Dist List
Director General Navy Capability, Performance and Plans, Navy Headquarters	Doc Data Sheet
Director General Navy Strategic Policy and Futures, Navy Headquarters	Doc Data Sheet

Air Force

SO (Science) - Headquarters Air Combat Group, RAAF Base, Williamtown NSW 2314	Doc Data Sht & Exec Summ
----------------------------------------------------------------------------------	--------------------------

Army

ABCA National Standardisation Officer, Land Warfare Development Sector, Puckapunyal	e-mailed Doc Data Sheet
SO (Science), Deployable Joint Force Headquarters (DJFHQ) (L), Enoggera QLD	Doc Data Sheet
SO (Science) - Land Headquarters (LHQ), Victoria Barracks NSW	Doc Data & Exec Summ

Intelligence Program

DGSTA Defence Intelligence Organisation Manager, Information Centre, Defence Intelligence Organisation	1 1 (PDF version)
Assistant Secretary Corporate, Defence Imagery and Geospatial Organisation	Doc Data Sheet

Defence Materiel Organisation

Head Airborne Surveillance and Control	Doc Data Sheet
Head Aerospace Systems Division	Doc Data Sheet
Head Electronic Systems Division	Doc Data Sheet
Head Maritime Systems Division	Doc Data Sheet
Head Land Systems Division	Doc Data Sheet
Head Industry Division	Doc Data Sheet
Chief Joint Logistics Command	Doc Data Sheet
Management Information Systems Division	Doc Data Sheet
Head Materiel Finance	Doc Data Sheet

Management Information Systems Division
Head Materiel Finance

Doc Data Sheet
Doc Data Sheet

Defence Libraries

Library Manager, DLS-Canberra
Library Manager, DLS - Sydney West

Doc Data Sheet
Doc Data Sheet

OTHER ORGANISATIONS

National Library of Australia
NASA (Canberra)

1
1

UNIVERSITIES AND COLLEGES

Australian Defence Force Academy
Library
Head of Aerospace and Mechanical Engineering
Serials Section (M list), Deakin University Library, Geelong, VIC
Hargrave Library, Monash University
Librarian, Flinders University

1
1
1
Doc Data Sheet
1

OUTSIDE AUSTRALIA**INTERNATIONAL DEFENCE INFORMATION CENTRES**

US Defense Technical Information Center
UK Defence Research Information Centre
Canada Defence Scientific Information Service
NZ Defence Information Centre

2
2
e-mail link to pdf
1

ABSTRACTING AND INFORMATION ORGANISATIONS

Library, Chemical Abstracts Reference Service
Engineering Societies Library, US
Materials Information, Cambridge Scientific Abstracts, US
Documents Librarian, The Center for Research Libraries, US

1
1
1
1

INFORMATION EXCHANGE AGREEMENT PARTNERS

National Aerospace Laboratory, Japan
National Aerospace Laboratory, Netherlands

1
1

SPARES

5

Total number of copies:

44

This page intentionally left blank

DEFENCE SCIENCE AND TECHNOLOGY ORGANISATION DOCUMENT CONTROL DATA				1. PRIVACY MARKING/CAVEAT (OF DOCUMENT)	
2. TITLE Review of Improved Methods for Analysing Load Attraction and Thermal Effects in Bonded Composite Repair Design		3. SECURITY CLASSIFICATION (FOR UNCLASSIFIED REPORTS THAT ARE LIMITED RELEASE USE (L) NEXT TO DOCUMENT CLASSIFICATION) Document (U) Title (U) Abstract (U)			
4. AUTHOR(S) A.B. Harman and K.F. Walker		5. CORPORATE AUTHOR Platforms Sciences Laboratory 506 Lorimer St Fishermans Bend Victoria 3207 Australia			
6a. DSTO NUMBER DSTO-TR-1546	6b. AR NUMBER AR-013-020	6c. TYPE OF REPORT Technical Report	7. DOCUMENT DATE December 2003		
8. FILE NUMBER 2003/51573	9. TASK NUMBER A21387	10. TASK SPONSOR DGTA	11. NO. OF PAGES 35	12. NO. OF REFERENCES 10	
13. URL on the World Wide Web http://www.dsto.defence.gov.au/corporate/reports/DSTO-TR-1546.pdf			14. RELEASE AUTHORITY Chief, Air Vehicles Division		
15. SECONDARY RELEASE STATEMENT OF THIS DOCUMENT <i>Approved for public release</i>					
OVERSEAS ENQUIRIES OUTSIDE STATED LIMITATIONS SHOULD BE REFERRED THROUGH DOCUMENT EXCHANGE, PO BOX 1500, EDINBURGH, SA 5111					
16. DELIBERATE ANNOUNCEMENT No Limitations					
17. CITATION IN OTHER DOCUMENTS Yes					
18. DEFTEST DESCRIPTORS Adhesive bonding, Repair, Heat stress, Composite materials, Metals, Aircraft , Reviews, Load attraction					
19. ABSTRACT Adhesive bonded repairs to aircraft involving metallic and composite structures have proven to be an effective, efficient means of repair and life extension. The simplified closed form equations used by the RAAF in an Engineering Standard (DEF(AUST)9005) have proven to be effective and conservative. Recent work, however, has identified improved equations to account for load attraction into the stiffened repaired area, and evaluate the thermally induced stresses in the repaired structure and the patch. The improved equations were compared with the current methods, using the repair to a 2024-T851 aluminium alloy F-111 lower wing skin with a boron epoxy repair patch, bonded with FM-73 film adhesive. The improved methods will reduce the unnecessary conservatism inherent in DEF(AUST)9005 and therefore allow some repairs to proceed where they may otherwise have been rejected. Repairs will also be designed to operate more efficiently.					