

Implementation of 3D Angular Selective Achromatic Diffraction Optical Grating device

L. Glebov, V. Smirnov, N. Tabirian, B. Zeldovich

BEAM: Beam Engineering for Advanced Measurements Co., 686 Formosa Ave., Winter Park, FL 32789 and School of Optics / CREOL,
University of Central Florida; 4000 Central Florida Blv , Orlando, FL 32816-2700
Voice (407) 823-6831, FAX (407) 823-6880, boris@creol.ucf.edu

Abstract: Angular Selective Achromatic Diffraction Optical Grating (ASADOG) device has been implemented. Surface reflective grating had 1200 lines per mm. Two identical volume holograms were implemented using Photo-Thermo-Refractive (PTR) glass technology, with spatial frequency 1697 lines per mm. Sequential diffraction of incident light by surface grating, by first volume grating and then by second one oriented at 90 degrees resulted in angular selection of incident beam, completely achromatic within the spectral range from red to blue including.

©2003 Optical Society of America

OCIS codes: (050.7330) Volume holographic Gratings

1. Introduction

Filtering of narrow angular component of incident light is a necessary function in numerous optical devices, including lasers, star tracking in orientation systems etc. Simplest design is an aberration-less mirror or lens that focuses incident light, and a pinhole to select the necessary direction. High concentration of energy may hurt the device in laser applications. Other possible device is a volume holographic grating, or a pair of them for 3-D angular selection. However, volume gratings may trade the angle to the wavelength, and thus are applicable for monochromatic beams only.

2. ASADOG device.

We report in this talk the implementation of 3-D angular selection device. The idea of the device's performance is based on the combination of spectrally-dispersive action of surface grating (Edmund reflection grating, $f_s = 1200$ lines/mm in our case) with two volume diffraction gratings positioned in sequence, and possessing spatial frequency $f_{vol} = f_s \cdot \sqrt{2} = 1697$ lines/mm. Fringes of each volume hologram were normal to the surfaces of the plates. Positioning the fringes of the first hologram at 45 degrees to the grooves of surface grating and the grooves of second hologram at 90 degrees to those of the first hologram resulted in the following. Out of all angular components of the incident wide-angle polychromatic beam, only components propagating exactly at a normal to all 5 surfaces of the device satisfied Bragg condition in both holograms and thus were efficiently diffracted and selected. Volume holograms used were prepared by the process of UV recording in Photo-Thermo-Refractive glass, and had thickness 1.28 mm. Angular selectivity with respect to both angular coordinates was better than 2 mrad.



Figure. The beams diffracted on the first Bragg grating appear in the direction perpendicular to the diffraction plane of the surface grating (bottom part of the photo).

Report Documentation Page				Form Approved OMB No. 0704-0188	
Public reporting burden for the collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to a penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.					
1. REPORT DATE 10 AUG 2004		2. REPORT TYPE N/A		3. DATES COVERED -	
4. TITLE AND SUBTITLE Implementation of 3D Angular Selective Achromatic Diffraction Optical Grating device				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S)				5d. PROJECT NUMBER	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Beam Engineering for Advanced Measurements Co., 686 Formosa Ave., Winter Park, FL 32789; School of Optics / CREOL, University of Central Florida; 4000 Central Florida Blv , Orlando, FL 32816-2700				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)				10. SPONSOR/MONITOR'S ACRONYM(S)	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release, distribution unlimited					
13. SUPPLEMENTARY NOTES See also ADM001691, Phase Conjugation for High Energy Lasers., The original document contains color images.					
14. ABSTRACT					
15. SUBJECT TERMS					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT UU	18. NUMBER OF PAGES 16	19a. NAME OF RESPONSIBLE PERSON
a. REPORT unclassified	b. ABSTRACT unclassified	c. THIS PAGE unclassified			

Implementation of 3D ASADOG:

Angular Selective Achromatic Diffraction Optical Grating device

**L. Glebov¹, V. Smirnov¹, N. Tabirian²,
B. Zeldovich^{1, 2}**

**[¹] School of Optics / CREOL,
University of Central Florida; Orlando, FL 32816-2700
and**

**[²] BEAM: Beam Engineering for Advanced Measurements Co.,
686 Formosa Ave., Winter Park, FL 32789**

boris@creol.ucf.edu

Overview

Introduction: Angular selective devices, a.k.a. spatial filters

Principles of particular devices:

- ASADOOG for angular selection in one direction (1-d)
- ASADOOG for angular selection in both directions (2-d)

Tolerances and how to make the device

- a. Auto-collimating procedure of recording
- b. Inequality for the period of volume grating
- c. 2-d via two fixed volume gratings with adjustable angle

Implementation via Photo-Thermo-Refractive recording in glass


Conclusion

Angular selection devices

Spatial filtering with pinhole is achromatic.

Drawbacks:

- May require vacuum chamber to eliminate breakdown at the focus.
- Requires large length or aspherical optics to overcome spherical aberration;
- Chromatic aberration may still be a problem.




Volume diffraction grating possesses good angular selectivity.

Drawbacks:

Works properly for a fixed wavelength only.

Trades angle θ to the wavelength λ :

diffraction efficiency $\eta = F(\alpha \cdot \theta - \beta \cdot \lambda)$.




Our recent device, **ASADOG**, has been implemented

(Angular Selective Achromatic Diffraction Optical Grating).


Towards the basic idea of the device

1. **Surface diffraction grating** does not have any selectivity, but possesses dispersive power:



whatever is the direction or color of incident light, there will be corresponding direction of diffracted beam, while the diffraction angle depends on the wavelength.

Towards the basic idea of the device



2. Volume diffraction grating possesses both, Angular selectivity and Spectral selectivity.

However, one property may be traded for the other one. Namely, diffraction efficiency η depends on the incidence angle θ and on the wavelength λ in a manner

$$\eta = \eta(c_1\lambda - c_2\theta)$$

Basic idea of the ASADOG device


(Angular Selective Achromatic Diffraction Optical Grating)

Let us combine:

surface diffraction grating, with the period Λ_{surf} ,
and
volume diffraction grating, with the period Λ_{vol} .


Let us require also that

$$\Lambda_{\text{surf}} = 2\Lambda_{\text{vol}}$$






Then all normally incident waves of all colors satisfy Bragg condition for the volume diffraction.

Proof of the Bragg condition for all colors




$$\begin{aligned} \mathbf{k}_b' &= \mathbf{k}_b + \mathbf{q} \\ \mathbf{k}_g' &= \mathbf{k}_g + \mathbf{q} \\ \mathbf{k}_r' &= \mathbf{k}_r + \mathbf{q} \end{aligned}$$

$$\mathbf{Q} = -2\mathbf{q}, \quad |\mathbf{Q}| = 2\pi / \Lambda_{vol}$$



Symmetric configuration guarantees that $\mathbf{k}''$ has the same length as $\mathbf{k}'$, and hence Bragg condition is satisfied.

Auto-collimating procedure to record $\Lambda_v = \Lambda_s/2$.



What is important and what is not


(we understood it only in the process of actually making the device)

It is important that the **volume fringes are vertical**.

It is important that the **volume fringes have $Q_v \leq 2q_s$** .

It is not so important that
the volume fringes have $Q_v = 2q_s$ exactly.
One can satisfy Bragg condition
by azimuthal adjustment of surface grating
with respect to volume grating.

Geometry of wave-vectors




If the end of the vector $\mathbf{Q}$ lies on the circle of radius $|\mathbf{q}|$,
and the circle's plane is perpendicular to $\mathbf{k}_{\text{inc}}$,
then Bragg condition is satisfied for any color.

Selection in both angular directions


Angular selection by a volume grating discriminates those directions only, which are along the $\mathbf{Q}$ -vector of the grating.

We use **two volume gratings in a sequence**, with non-collinear vectors $\mathbf{Q}_1$ and $\mathbf{Q}_2$. We actually made them perpendicular, but this may be somewhat disadvantageous.



The best foreseeable scheme

The beam may be restored to the original direction by the second surface grating, like this:




or in a scheme with 2-d angular selection, where two volume gratings work between two surface gratings.

What was actually done


We used **Photo-Thermo-Refractive** process of recording volume phase holograms in special glass (developed at CREOL by Dr. Glebov and his team). Those holograms have diffraction efficiency better than 95%. They are extremely stable, even under $100 \text{ KW} / \text{cm}^2$ of true CW laser light.

We used **surface reflecting grating** instead of transmission one.



These two volume gratings had their **Q**-vectors perpendicular (I failed to draw it properly here).

Demonstration of simultaneous 3-color 2-d angular selection



The beams diffracted on the first Bragg grating appear in the direction perpendicular to the diffraction plane of the surface grating (bottom part of the photo).

CONCLUSION

1. We invented the acronym **ASADOG**:
Angular **S**elective **A**chromatic **D**iffraction **O**ptical **G**rating.
2. We suggested the scheme of ASADOG for angular selection in one or in both angular directions.
3. We have actually implemented 1-d and 2-d ASADOGs.
4. Photo-Thermo-Refractive volume glass holograms were specially recorded for that.
5. We are still looking for potential applications.