

# Development of Large Strain Actuator Controlled by Hydrogen Pressure for artificial muscle

ATSUSHI KADOWAKI, BYUNGSUK KIM, HIROMASA YABE AND YOSHITAKE NISHI

*Department of Materials Science, TOKAI University,*

*1117 Kitakaname, Hiratsuka, Kanagawa, 259-1292 JAPAN*

**ABSTRACT:** The large strain actuator controlled by hydrogen pressure for artificial muscle was developed. The actuator was constructed with two kinds of soft rubbers for driving and supporting like bimetal. The LaNi<sub>5</sub> hydrogen storage alloy powder was dispersed in the driving rubber. The reversible shape change was by hydrogen absorption and desorption. Large strain was observed on long operation time. The large strain over 2000 ppm was observed at above 10000 s of operation time. The actuator developed shows large shape change as large as that of a typical shape memory alloy.

## INTRODUCTION

Shape memory materials can be one of the reliable actuator for artificial muscle. However, it is difficult to apply them for artificial muscle because thermal changes often destroy cellular tissues and hardness of Ti-Ni shape memory alloy is too hard for artificial muscle. Thus, a new type actuator for artificial muscle induced by volume expansion of hydrogen storage alloy was developed. Silicone rubber has been used as parts of human body because of soft material. This actuator was constructed with two kinds of soft rubbers for driving and supporting like bimetal. One of them was a driving rubber with hydrogen storage alloy powder dispersed, and another was pure silicone supporting rubber. This soft actuator using silicone rubber can move variable directions with and without temperature change. The size of driving rubber is controlled by hydrogen pressure. In past study, LaNi<sub>3</sub>Co<sub>2</sub> hydrogen storage alloy has been proposed for soft catheter (Kim, et al., 2001). Because the volume expansion of LaNi<sub>3</sub>Co<sub>2</sub> alloy by formation of hydride is as large as 20.5 % at human body temperature (Willems, et al., 1984), therefore big power and displacement can be expected. The soft actuator shows large strain yield by shape change as large as Ti-Ni shape memory alloy (Kim, et al., 2001). On the other hand, LaNi<sub>5</sub> alloy shows large volume expansion by formation of hydride is as large as 24 % (Sakai, et al., 1990).

Since the volume expansion of LaNi<sub>5</sub> alloy generates a high power, plastic deformation of 18-8 stainless steel reaction tube was observed (Yabe, et al. 2003). Therefore, hydrogen storage alloys applied for soft actuator has been expected to become high potential candidates for powerful actuators. In this study, a soft actuator driven by hydrogen storage LaNi<sub>5</sub> alloy for artificial muscle has been studied.

## EXPERIMENTAL PROCEDURE


LaNi<sub>5</sub> hydrogen storage alloys were prepared by arc melting (ACM-DS01, DIAVAC Ltd.) and subsequent annealing for homogenization. The block sample was pulverized by several hydrogen cycles of adsorption and desorption using ultra high purity H<sub>2</sub> gas (7N); the resulting powder was classified to obtain a mean grain size between 45 and 90 μm in diameter. The chemical composition of hydrogen storage alloy powder was analyzed by energy dispersive X-ray spectroscopy (EDS: JSM-6301F, JEOL Ltd.). Hydrogen storage alloy powder (0.65 g) was mixed and dispersed within pure silicone rubber (KE45, Shin-etsu Silicon Ltd., 0.065 g). Pure silicone rubber (B) attached was supporting materials to bend the composite material (Kim, et al., 2001). The sample size of the composite material (30 × 5 × 1.0 mm<sup>3</sup>; length × width × thickness) is shown in Figure 1.

## Report Documentation Page

*Form Approved*  
*OMB No. 0704-0188*


Public reporting burden for the collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to a penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.

1. REPORT DATE <b>00 JUN 2003</b>	2. REPORT TYPE <b>N/A</b>	3. DATES COVERED <b>-</b>	
4. TITLE AND SUBTITLE <b>Development of Large Strain Actuator Controlled by Hydrogen Pressure for artificial muscle</b>		5a. CONTRACT NUMBER	
		5b. GRANT NUMBER	
		5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S)		5d. PROJECT NUMBER	
		5e. TASK NUMBER	
		5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) <b>Department of Materials Science, TOKAI University, 1117 Kitakaname, Hiratsuka, Kanagawa, 259-1292 JAPAN</b>		8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)		10. SPONSOR/MONITOR'S ACRONYM(S)	
		11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION/AVAILABILITY STATEMENT <b>Approved for public release, distribution unlimited</b>			
13. SUPPLEMENTARY NOTES <b>See also ADM001697, ARO-44924.1-EG-CF, International Conference on Intelligent Materials (5th)(Smart Systems &amp; Nanotechnology)., The original document contains color images.</b>			
14. ABSTRACT			
15. SUBJECT TERMS			
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT
a. REPORT <b>unclassified</b>	b. ABSTRACT <b>unclassified</b>	c. THIS PAGE <b>unclassified</b>	<b>UU</b>
			18. NUMBER OF PAGES <b>3</b>
			19a. NAME OF RESPONSIBLE PERSON



**Figure 1.** Schematic diagram of soft actuator preparation.

Using a reaction bed made of SUS316, the soft actuator was activated using ultra high purity  $H_2$  (7N) of about 30 bar. Activation was performed by the hydrogen absorption for 10 minutes and subsequent evacuation of 10 minutes. The number of the operation cycles was 30 times. An activated bi-polymer was then transported to reaction bed made of glass (See Figure 2). Activation was performed by the hydrogen absorption for 10 minutes and subsequent evacuation of 10 minutes. After evacuation for hydrogen desorption, shape memory effect for 0 ~ 80000 s was monitored by a video recorder (Kim, et al., 2001).



**Figure 2.** Schematic diagram of shape change observation system.

The measurement of the strain of the soft actuator was defined, as shown in Figure 3 and equation (1) to (5). The movable strain ( $\varepsilon$ ) was calculated by equation (1) to (4) using the radius of curvature at the interface ( $\rho$ ) and a half thickness of sample ( $\eta$ ).

$$\varepsilon = \eta / \rho \quad (1)$$


$$\rho = (r + d) / 2 \quad (2)$$

$$\eta = d / 2 \quad (3)$$

Therefore,

$$= d / (2r + d) \quad (4)$$

Here,  $d$  and  $r$  are the thickness of test device and radius of curvature, respectively.



**Figure 3.** Schematic diagram for estimation of strain ( $\varepsilon$ ).


The strain difference ( $\Delta\varepsilon$ ) yielded by shape change of the soft actuator before and after hydrogen gas absorption was defined as equation (5).

$$\Delta\varepsilon = \varepsilon - \varepsilon_0 \quad (5)$$


Here,  $\varepsilon_0$  is initial strain before the first hydrogen absorption in glassy reaction tube.

## RESULTS AND DISCUSSIONS

Figure 3 shows photographs of the shape of the soft actuator at different operation times. The large shape changes were observed at long operation time. This soft actuator showed reversible shape change by hydrogen absorption and desorption.



**Figure 3.** Photographs of the shape of the bi-polymer on each operation time (0 and 50000 s) after hydrogen absorption at  $297.0 \pm 1.0$  K by applying hydrogen pressure of  $2.9 \pm 0.5$  bar.



**Figure 4.** Relationship between the applied hydrogen operation time (s) and the strain yielded by shape change  $\Delta\epsilon$  (ppm) of hydrogen storage soft actuator, together with relationship between the applied hydrogen operation time (s) and the changing the radius of curvature (mm).

Figure 4 shows the relationship between the applied hydrogen operation time (s) and the strain yielded by shape change  $\Delta\epsilon$  (ppm) of hydrogen storage soft actuator, together with the relationship between the applied hydrogen operation time (s) and the changing the radius of curvature (mm). Large strain was found at long hydrogen operation time. On the other hand, the long hydrogen operation time

shortened the radius of curvature. The large strain over 2000 ppm was observed at above 10000 s of operation time.

## CONCLUSION

In this study, the hydrogen storage alloy dispersed soft actuator showed reversible shape change by hydrogen absorption and desorption. Large strain was found at long hydrogen operation time. The long hydrogen operation time shortened the radius of curvature. The large strain over 2000 ppm was observed at above 10000 s of operation time. The soft actuator shows large shape change as large as that of shape memory alloy.

## ACKNOWLEDGEMENT

The authors would like to thank Mr. Naoki Okada in Tokai University. In addition, parts of this study were carried out by grant-in-aids for Scientific Research (No. 06659) from the Japan Society for the Promotion of Science.

## REFERENCES

- BS. Kim, H. Yabe, H-H. Uchida & Y. Nishi 2001. "Development of a high power shape memory materials using hydrogen storage alloy dispersed in polymer" *Proceedings of 7th Japan International SAMPE Symposium*, 13-16 November 2001, Tokyo, Japan 943-946.
- BS. Kim, N. Motai, H. Yabe, H-H. Uchida & Y. Nishi 2001. "Load dependence of shape memory effect of hydrogen storage alloy bi-polymer" *Proceedings of 6th Japan-Korea Joint Symposium on Hydrogen Energy*, 18 October 2001, Kanagawa, Japan 189-194.
- J.J.G.Willems 1984. "Metal hydride electrodes stability of  $\text{LaNi}_5$ -related compounds" *Phi. J. Res.*, 39:1-94.
- T. Sakai, K. Oguro, H. Miyamura, N. Kuriyama, A. Kato & H. Ishikawa 1990. "Some factors affecting the cycle lives of  $\text{LaNi}_5$ -based alloy electrodes of hydrogen batteries" *Journal of Less-Common Metals*, 61:193-202.
- H. Yabe, T. Honjo, S. Tsubuteishi, H-H. Uchida & Y. Nishi 2003. "Influence of tensile stress on active motion of hydrogen storage alloy film actuator" *Transactions of the Materials Research Society of Japan*, in press.