

Carbon Materials Research

Wesley P. Hoffman

AFRL/PRSM
10 E. Saturn Blvd.
Edwards AFB CA 93524-7680

August 2005

Final Report

APPROVED FOR PUBLIC RELEASE; DISTRIBUTION UNLIMITED.



**AIR FORCE RESEARCH LABORATORY
AIR FORCE MATERIEL COMMAND
EDWARDS AIR FORCE BASE CA 93524-7048**

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188		
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing this collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.					
1. REPORT DATE (DD-MM-YYYY) 07-04-2005		2. REPORT TYPE Final Report		3. DATES COVERED (From - To) 01 Nov 1986 – 31 Oct 2004	
4. TITLE AND SUBTITLE Carbon Materials Research			5a. CONTRACT NUMBER		
			5b. GRANT NUMBER		
			5c. PROGRAM ELEMENT NUMBER 61102F		
6. AUTHOR(S) Wesley P. Hoffman			5d. PROJECT NUMBER 2303		
			5e. TASK NUMBER M1B3		
			5f. WORK UNIT NUMBER 343120		
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) AFRL/PRSM 10 E. Saturn Blvd. Edwards AFB CA 93524-7680			8. PERFORMING ORGANIZATION REPORT NO.		
9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES) Air Force Research Laboratory (AFMC) AFRL/PRSM 10 E. Saturn Blvd. Edwards AFB CA 93524-7680			10. SPONSOR/MONITOR'S ACRONYM(S)		
			11. SPONSOR/MONITOR'S REPORT NUMBER(S) AFRL-PR-ED-TR-2005-0029		
12. DISTRIBUTION / AVAILABILITY STATEMENT Approved for public release; distribution unlimited.					
13. SUPPLEMENTARY NOTES					
14. ABSTRACT A basic research study in carbon materials for propulsion applications led to research in seemingly diverse areas, which include carbon-carbon composite fabrication, oxidation protection of carbon, microelectromechanical (MEMs) devices, and surface tension phenomenon. Carbon-carbon composites are the material of choice in many high temperature thermostructural applications, such as, rocket nozzles and exit cones, missile nosetips, and leading edges of hypersonic vehicles. Although these material are stronger than steel, stiffer than steel, lighter than aluminum, and resistant to thermal shock, they are susceptible to oxidation above 450°C. In addition they are very costly due principally to the process of densification in which a carbon matrix is placed among the carbon fibers in a perform that has been constructed to have certain mechanical properties. This study has addressed both the problems of oxidation resistance and cost of carbon-carbon composites. In addressing the issue of cost, a completely new and innovative densification approach called In Situ densification was conceived and implemented. This process has the dual advantage of both a significant cost reduction as well as a significant reduction in the time needed to densify these composites. In addressing the oxidation protection of carbon-carbon composites, the entirely new field of microtube technology was born. This technology allows the fabrication of free-standing or imbedded microscopic tubes that can possess any cross-sectional or axial shape. Numerous devices have been conceived and fabricated utilizing this technology. Since surface tension is a dominant force at microscopic dimensions, devices employing non-wetting liquids and surface tension were conceived and fabricated. During the fabrication of some of these devices, an entirely new wetting phenomena was discovered. That is, it is possible to make a non-wetting surface wetting and a wetting surface to be non-wetting simply by changing the geometry of the surface that the liquid contacts.					
15. SUBJECT TERMS carbon; carbon materials; propulsion; carbon-carbon composites; rocket nozzle; exit cone; missile nosetip; hypersonic vehicle; oxidation resistance; cost; densification; MEMs; surface tension; microtube					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT	18. NUMBER OF PAGES	19a. NAME OF RESPONSIBLE PERSON Dr. Wesley P. Hoffman
a. REPORT Unclassified	b. ABSTRACT Unclassified	c. THIS PAGE Unclassified			19b. TELEPHONE NO (include area code) (661) 275-5768

NOTICE

When U.S. Government drawings, specifications, or other data are used for any purpose other than a definitely related Government procurement operation, the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise, or in any way licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may be related thereto.

FOREWORD

This final report, entitled "Carbon Materials Research," presents the results of a research study performed under JON 2308M1B3 by AFRL/PRSM, Edwards AFB CA. The Project Manager for the Air Force Research Laboratory was Dr. Wesley P. Hoffman.

This report has been reviewed and is approved for release and distribution in accordance with the distribution statement on the cover and on the SF Form 298.

/signed/
WESLEY P. HOFFMAN
Project Manager

/signed/
STEVEN A. SVEJDA
Chief
Propulsion Materials Applications Branch

/signed/
PHILIP A. KESSEL
Technical Advisor
Space & Missile Propulsion Division

This Page Intentionally Left Blank

1.0 EXECUTIVE SUMMARY

1.1 Abstract

A basic research study in carbon materials for propulsion applications led to research in seemingly diverse areas, which include carbon-carbon composite fabrication, oxidation protection of carbon, microelectromechanical (MEMs) devices, and surface tension phenomenon.

Carbon-carbon composites are the material of choice in many high-temperature thermostructural applications, such as rocket nozzles and exit cones, missile nosetips, and leading edges of hypersonic vehicles. Although these material are stronger than steel, stiffer than steel, lighter than aluminum, and resistant to thermal shock, they are susceptible to oxidation above 450°C. In addition, they are very costly, due principally to the process of densification in which a carbon matrix is placed among the carbon fibers in a preform that has been constructed to have certain mechanical properties.

This study has addressed both the problems of oxidation resistance and the cost of carbon-carbon composites. In addressing the issue of cost, a completely new and innovative densification approach called In Situ Densification was conceived and implemented. This process has the dual advantage of both a significant cost reduction and a significant reduction in the time needed to densify these composites.

In addressing the oxidation protection of carbon-carbon composites, the entirely new field of microtube technology was born. This technology allows the fabrication of free-standing or imbedded microscopic tubes that can possess any cross-sectional or axial shape. Numerous devices have been conceived and fabricated utilizing this technology. Since surface tension is a dominant force at microscopic dimensions, devices employing non-wetting liquids and surface tension were conceived and fabricated. During the fabrication of some of these devices, an entirely new wetting phenomena was discovered. That is, it is possible to make a non-wetting surface wetting and a wetting surface to be non-wetting simply by changing the geometry of the surface that the liquid contacts.

1.2 Summary and Recommendations

The In Situ Densification process produces a very high quality matrix at a fraction of the cost and in a fraction of the time required by current commercial processes. The electrical and thermal conductivity of these composites produced by the In Situ Process is equivalent to the conductivity of the best commercial composites. In addition, the density of these composites is more uniform than what is available with commercial composites. This is a result of the complete penetration of the liquid matrix precursor into the fiber preform, which is one of the keys of this process. These composites have a wide range of uses in both DOD and commercial applications because of their excellent properties, low cost, and rapid processing time. Application of these composites into full-scale applications, such as exit cones, should be pursued.

Microtubes also have a wide range of application in both DOD and the commercial sector. Applications – including cooling, separation technologies, venting and sensors – should continue to be pursued.

In normal situations, to change how a liquid interacts with a surface, it is necessary to change either the character of the surface by applying a coating or a surface treatment or the liquid by, for example, adding a surfactant or solvent. The geometric surface wetting phenomena allows you to change the wetting character of a surface without changing the character of either the surface or the surface tension of the liquid. This is done simply by physically modifying the surface so that there is an angular surface. This phenomena has important applications in areas as diverse as heat exchange and catalysis.

JOURNAL PAPERS

W.P. Hoffman, F.J. Vastola, and P.L. Walker Jr., "Pyrolysis of Propylene Over Carbon Active Sites II. Products," *Carbon*, **26**, 485 (1988)

W.P. Hoffman, V.B. Elings, and J.A. Gurley, "Scanning Tunneling Microscopy of Carbon Fibers," *Carbon*, **26**, 754 (1988)

W.P. Hoffman and P. Ehrburger, "The Pyrolysis of Tetraethoxysilane over Carbon and Silica Substrates," *J. Anal. and Appl. Pyrolysis*, **15**, 275 (1989)

W.P. Hoffman, "The Importance of Active Surface Area in the Heterogeneous Reactions of Carbon," *Carbon*, **29**, 769 (1991)

W.P. Hoffman and H.T. Phan, "Passivation of Carbon Active Sites For Oxidation Protection," in *Fundamental Issues in Control of Carbon Gasification Reactivity*, J. Lahaye and P. Ehrburger, eds., Kluwer Academic Publisher, 515 (1991)

I.M.K. Ismail and W.P. Hoffman, "Surface Characterization of a Graphitized Rayon Fabric," *Carbon*, **29**, 587 (1991)

W.P. Hoffman, W.C. Hurley, P.M. Liu, and T.W. Owens, "The Surface Topography of Non-Shear Treated Pitch and PAN Carbon Fibers as viewed by the STM," *J. Mat. Res.*, **6**, 1685 (1991)

W.P. Hoffman, W.C. Hurley, T.W. Owens, and H.T. Phan, "The Advantage of the STM in Documenting Changes in Carbon Fiber Surface Morphology Resulting From Various Surface Treatments," *J. Mat. Sci.*, **26**, 4545 (1991)

W.P. Hoffman, "Chemical Vapor Deposition of Silica on Carbon Surfaces," in *Processing and Fabrication of Advanced Materials for High Temperature Applications*, V.A. Ravi and T.S. Srivatsan Eds., The Minerals, Metals, and Materials Soc., 307 (1992)

W.P. Hoffman, "Scanning Probe Microscopy of Carbon Fiber Surfaces," *Carbon*, **30**, 315 (1992)

W.P. Hoffman, "Characterizing the Surface of Carbon Fibers in Order to Gain a Better Understanding of the Interfaces That They Form," *Composite Interfaces*, **1**, 15 (1993)

W.P. Hoffman, "The Application of Microtubes to Microstructures and Microfabricated Systems," Proc. Symposium on Microstructures and Microfabricated Systems, Vol. 94-14, 1, The Electrochemical Soc., 1994

K. Upadhya and W. P. Hoffman, "Advanced Composite Microtubes for Micro-electromechanical Systems," *JOM*, **46**, 54 (1994)

G. Krekel, K. J. Huttinger, W.P. Hoffman, and D.S. Silver, "The Relevance of the Surface Structure and Surface Chemistry of Carbon Fibers in Their Adhesion to High Temperature Thermoplastics Part I: Surface Structure and Morphology" *J. Mat. Sci.*, **29**, 2968 (1994).

G. Krekel, K. J. Huttinger, and W.P. Hoffman, "The Relevance of the Surface Structure and Surface Chemistry of Carbon Fibers in Their Adhesion to High Temperature Thermoplastics Part II: Surface Chemistry" , *J Mat. Sci.*, **29**, 3461 (1994)

G. Krekel, U. J. Udo, K. J. Huttinger, and W.P. Hoffman, "The Relevance of the Surface Structure and Surface Chemistry of Carbon Fibers in Their Adhesion to High Temperature Thermoplastics Part III: Interface Adhesion and Reinforcement Effects," *J. Mat. Sci.*, **29**, 3984 (1994)

W.P. Hoffman, M.B. Fernandez, and M.B. Rao, "Characterization of Porosity in Nanoporous Carbons Using Scanning Tunneling Microscopy," *Carbon*, **32**, 1383 (1994)

W.P. Hoffman, H.T. Phan, and A. Groszek, "The Deposition of Silica on Carbon as a Model System for Oxidation Protection Coatings," *Carbon*, **33**, 509 (1995)

W.P. Hoffman, H.T. Phan, and A. Groszek, "The Deposition of Silica on Carbon as a Model System for Oxidation Protection Coatings," in *High Temperature High Performance Materials For Rocket Engines and Space Applications*, pp 141-167, K. Upadhya, ed., TMS, Warrendale PA, 1995

U. Zielke, K.J. Huttinger, and W.P. Hoffman, "Surface Structure and Chemistry of Surface Oxidized and Chemically Modified surface oxidized Carbon Fibers- Part 1 Surface Structure," *Carbon*, **34**, 983 (1996)

U. Zielke, K.J. Huttinger, and W.P. Hoffman, "Surface Structure and Chemistry of Surface Oxidized and Chemically Modified surface oxidized Carbon Fibers- Part 2 Surface Chemistry of Chemically Modified Surfaces", " *Carbon*, **34**, 999 (1996)

U. Zielke, K.J. Huttinger, and W.P. Hoffman, "Surface Structure and Chemistry of Surface Oxidized and Chemically Modified surface oxidized Carbon Fibers- Part 3

Characterization of Carbon Fiber Surfaces by WSL /pH-value Diagram,” *Carbon*, **34**, 1007 (1996)

U. Zielke, K.J. Huttinger, and W.P. Hoffman, "Surface Structure and Chemistry of Surface Oxidized and Chemically Modified surface oxidized Carbon Fibers- Part 4 Interaction of Surface Oxides and Chemically Modified Carbon Fibers with High Temperature Thermoplastics,” *Carbon*, **34** 1015 (1996)

K Upadhyya, W.P. Hoffman and S.L. Rodgers, "Synthesis and Hot Isostatic Pressing of Nanocrystalline Silicon Nitride Powder, *J of Materials Synthesis and Processing*, **5**, 141 (1997)

K. Upadhyya, J.M. Yang, and W.P. Hoffman, “Advanced Materials for Ultrahigh Temperature Structural Applications Above 2000° C.” *Am Cer. Soc. Bul.*, **76**, 51 (1997)

W.P. Hoffman, H.T. Phan, and P.G. Wapner, “The Far-Reaching Nature of Microtube Technology,” *Mat. Res. Innovations*, **2**, 87 (1998)

W.P. Hoffman, “Microtubes—An Enabling Technology in Many Fields,” *Materials Technology*, **13**, 145 (1998)

W.P. Hoffman, "Chemisorption Processes by Carbon,” Chapter 13 in *Sciences of Carbon Materials*, H. Marsh and F.R. Rienso, Eds. Universidad de Alicante (2000)

P. Wapner and W.P. Hoffman, “Utilization of Surface Tension and Wettability in the Design and Operation of Microsensors,” *Sensors and Actuators B*, **71**, 60 (2000)

P. Wapner and W.P. Hoffman, “Partial Wetting of Non-Smooth Surfaces and Shaped Micro-Channels,” *Langmuir*, **18**, 1225 (2002)

P. Wapner and W.P. Hoffman, “Hydraulic Actuation Based on Flow of Non-Wetting Fluids in Micro-Channels,” *Sensors and Actuators B*, **85**, 52-60 (2002)

W.P. Hoffman and Phillip Wapner, “Microtubes,” Chapter in Encyclopedia of Smart Materials, Swartz, ed., Wiley, NY, 2002

W.P. Hoffman, “*In Situ* Rapid Densification with Low-Viscosity Impregnant Reduces Processing Time to Produce Uniform Density Carbon-Carbon Composites,” *MRS Bulletin*, 27, 437 (June 2002)

P.G. Wapner, R.H. Hurt, Gernot Krammer, W.P. Hoffman, ” Equilibrium and Non-Equilibrium Effects in Pitch Wetting,” *Proceedings Carbon 2003*, Oviedo, Spain , July 2003

K. M. Chioujones, W. Ho, P. C. Chau, B. Fathollahi, P. G. Wapner, and W. P. Hoffman, "Microstructural Studies of In-Situ Mesophase Transformation in the Fabrication of Carbon-Carbon Composites," *Proceedings Carbon 2004*, Providence RI, July 2004

M.B. Dickerson, P.J. Wurm, J.R. Schorr, W.P. Hoffman, P.G. Wapner, and K.H. Sandhage, "Near Net-Shaped, Ultra High Melting, Recession-Resistant Zrc/W-Based Rocket Nozzle Liners Via The Displacive Compensation Of Porosity (DCP) Method," *J. Mat. Sci.*, **39**, 6005-6015 (2004)

PATENTS

"Method of manufacturing microscopic tube material," Hoffman, W.P., US Pat. No 5,011,566 (4/30/91)

"Activation of carbon fiber surfaces by means of catalytic oxidation," Hoffman, W.P., US Pat. No 5,271,917 (12/21/93)

"Microscopic tube material," Hoffman, W.P., US Pat. No 5,298,298 (3/29/94)

"Microscopic tube material and its method of manufacture," Hoffman, W.P., US Pat. No 5,352,512 (10/04/94)

"Densification of porous articles by plasma enhanced chemical vapor infiltration," Upadhyaya, K. and Hoffman W.P., US Pat. No 5,468,357 (11/21/95)

"Tungsten-copper composite material with rhenium protective layer, and its preparation," Upadhyaya, K., US Pat. No 5,705,283 (1/06/98)

"Microtubes devices based on surface tension and wettability," Wapner, P.G., Hoffman, W.P., and Price, G.J., US Pat. No 5,789,045 (8/04/98)

"Apparatus for manufacturing microtubes with axially variable geometries," Wapner, P.G., Hoffman, W.P., and Price, G.J., US Pat. No 6,059,001 (5/09/00)

"Microscopic tube devices and method of manufacture," Hoffman, W.P., and Wapner P.G., US Pat. No 6,113,722 (9/05/00)

"Microdevices based on surface tension and wettability that function as sensors, actuators, and other devices," Wapner, P.G., and Hoffman, W.P., US Pat. No 6,152,181 (10/28/00)

"Microscopic tube devices and method of manufacture," Hoffman W.P., US Pat. No 6,194,066 (2/27/01)

“Carbon and ceramic matrix composites fabricated by a rapid low-cost process incorporating in-situ polymerization of wetting monomers” Wapner, P.G., Hoffman, W.P., and Jones, S.P., US Pat. No 6,309,703 (10/30/01)

“Synthesis of nanoscale aluminum alloy powders and devices therefrom,” Upadhyay, K., and Hoffman, W.P., US Pat. No 6,312,643 (10/06/01)

“Method of making microtubes with axially variable geometries,” Wapner, P.G., and Hoffman, W.P., US Pat. No 6,458,231 (10/1/02)

“Baby-feeding nipple,” Pechenik, A., Hoffman, W.P., and Wapner, P.G., US Pat. No 6,588,613 (6/08/03)

“Carbon matrix composites fabricated by a rapid and low-cost process incorporating in-situ polymerization of wetting monomers,” Wapner, P.G., Hoffman, W.P., and Jones, S.P., US Pat. No 6,706,401 (3/16/04)

“Carbon matrix composites fabricated by a rapid and low-cost process incorporating in-situ polymerization of wetting monomers,” Wapner, P.G., Hoffman, W.P., and Jones, S.P., US Pat. No 6,756,112 (6/29/04)

“Method of manufacture of baby-feeding nipple” Hoffman, W.P., Pechenik, A., and Wapner, P.G., US Pat. No 6,818,162 (11/16/04)

“Liquid to solid angle of contact measurement,” Wapner, P.G., and Hoffman, W.P., US Pat. No 6,867,854 (03/15/05)

AFRL-PR-ED-TR-2005-0029
Primary Distribution of this Report:

AFRL/PRSM (3 CD + 2 HC)
Dr. Wesley P. Hoffman
10 E. Saturn Blvd.
Edwards AFB CA 93524-7680

AFRL/PROI (1 CD + 1 HC)
Ranney Adams
2 Draco Drive
Edwards AFB CA 93524-7808

AFRL/PR Technical Library (2 CD + 1 HC)
6 Draco Drive
Edwards AFB CA 93524-7130

Chemical Propulsion Information Agency (1 CD)
Attn: Tech Lib (Dottie Becker)
10630 Little Patuxent Parkway, Suite 202
Columbia MD 21044-3200

Defense Technical Information Center
(1 Electronic Submission via STINT)
Attn: DTIC-ACQS (Pat Mawby)
8725 John J. Kingman Road, Suite 94
Ft. Belvoir VA 22060-6218