

Submitted to “The Encyclopedia of Materials: Science and Technology”, Elsevier Science Ltd.
(2000).

(i)

**Real-Time Process Monitoring by P-Polarized Reflectance Spectroscopy and Closed-Loop
Control of Vapor Phase Epitaxy**

H.T. Banks^{a,b}, N. Dietz^{a,c} and K. Ito^{a,b}

^aCenter for Research in Scientific Computation, ^bDepartment of Mathematics; North Carolina
State University, Raleigh, NC 27695

^cDepartment of Physics and Astronomy, Georgia State University, Atlanta, GA 30303

Report Documentation Page				Form Approved OMB No. 0704-0188	
Public reporting burden for the collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to a penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.					
1. REPORT DATE 2000		2. REPORT TYPE		3. DATES COVERED 00-00-2000 to 00-00-2000	
4. TITLE AND SUBTITLE Real-Time Process Monitoring by P-Polarized Reflectance Spectroscopy and Closed-Loop Control of Vapor Phase Epitaxy				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S)				5d. PROJECT NUMBER	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) North Carolina State University, Center for Research in Scientific Computation, Raleigh, NC, 27695-8205				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)				10. SPONSOR/MONITOR'S ACRONYM(S)	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution unlimited					
13. SUPPLEMENTARY NOTES					
14. ABSTRACT see report					
15. SUBJECT TERMS					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT	18. NUMBER OF PAGES 20	19a. NAME OF RESPONSIBLE PERSON
a. REPORT unclassified	b. ABSTRACT unclassified	c. THIS PAGE unclassified			

6.6.xx Real-Time Process Monitoring by P-Polarized Reflectance Spectroscopy and Closed-Loop Control of Vapor Phase Epitaxy

Controlling and optimizing growth processes require improved methods of characterization and understanding of decomposition pathways and surface reaction kinetics. They also require the development of advanced nonlinear filtering and feedback control concepts. This contribution describes results on real-time optical monitoring of thin film growth processes by p-polarized reflectance (PR) utilizing a pulsed chemical beam epitaxy (PCBE) approach, where the growth surface is sequentially exposed to organometallic precursors. Under these conditions the surface reaction kinetics can be followed by analyzing a periodically (in composition and thickness) modulated surface reaction layer (SRL). This modulation can be captured in the PR-signals as a fine structure that is superimposed on the interference fringes produced by underlying growing film. The optical response is linked to the growth process via a reduced order surface kinetics (ROSK) model and integrated as a control signal in the implementation of filter and control algorithms for closed-loop controlled growth. The control concept has been applied for thickness and compositional graded multi-heterostructure $\text{Ga}_x\text{In}_{1-x}\text{P}$ epilayers and validated by ex-situ post-growth analysis. This results in superior tracking of composition and thickness targets under closed loop controlled conditions when compared to films grown using pre-designed source injection profiles (open-loop conditions).

1. Introduction

Real-time optical characterization of thin film inherits the challenge of relating macroscopic optical signatures to microscopic surface chemistry processes that drive the growth process, to growth/film properties, such as composition, instantaneous growth rate or structural layer quality. The need for stringent tolerances in control of film thickness and composition is especially acute for chemical deposition methods, where organometallic precursor decomposition at the growth surface dominates the nucleation kinetics, surface atoms mobility, and steady-state growth reaction kinetics. The limited knowledge about the nucleation and deposition kinetics has impeded progress in understanding and controlling thin film growth. To improve the understanding of the driving mechanisms of growth processes, non-intrusive real-time techniques have been developed. The focus has been on the monitoring of surface processes by reflection high energy electron diffraction (RHEED) (Yoshimoto, M. et al. 1994), reflectance difference spectroscopy (RDS) (Aspnes, D.E. 1998), surface photo absorption (SPA) (Kobayashi, N. et al. 1989, Kobayashi, N. et al. 1990, Kobayashi, N. et al. 1991) and p-polarized reflectance spectroscopy, PRS, (Dietz, N. et al. 1995, Dietz, N. et al. 1996, Dietz, N. et al. 1997).

Presently, the only two techniques that combine the advantage of high surface sensitivity with bulk film properties characterization are (a) an integrated spectral ellipsometry (SE) / RDS spectrometer developed by D. Aspnes et al. (Aspnes, D.E. 1996, Ebert, M. 2000) and (b) PRS (Dietz, N. et al. 1995). Both techniques aim to integrate the optical response to surface processes with the optical response to bulk properties to monitor and facilitate control of the deposition process with sub-monolayer resolution.

This contribution describes p-polarized reflectance spectroscopy (PRS) for closed-loop deposition control during pulsed chemical beam epitaxy (PCBE) using III-V heteroepitaxial growth as an example. The demonstrated high sensitivity of PRS toward surface reaction

processes in the context of real-time monitoring of PCBE has opened new possibilities for characterization and control of thin film deposition processes. For instance, during heteroepitaxial $\text{GaP}/\text{Ga}_x\text{In}_{1-x}\text{P}$ growth on Si under PCBE conditions the surface is periodically exposed to metalorganic precursors, which causes a periodic-in-composition-and-thickness altered surface reaction layer (SRL). The control of a growth process using the optical signature from the SRL that feeds the underlying growth requires detailed instantaneous simulation and prediction of the surface chemistry and its link to the optical properties of the outer most layer in a multilayer medium. A reduced order surface kinetics (ROSK) model has been developed that describes the growth process with a mathematically reduced number of surface reactions equations using heteroepitaxial $\text{Ga}_x\text{In}_{1-x}\text{P}$ growth as an example. The dynamics in the molar concentrations of surface constituents evolution gives information on SRL thickness, its optical response in a four media layer approximation, the instantaneous growth rate, and the composition of the growing film. For real-time closed-loop deposition control a virtual substrate approach was used, an approach recently introduced by D.E. Aspnes for product-driven deposition control (see 6.6.43: Monitoring and Closed-loop Feedback Control of III-V Epitaxy by Spectroscopic Ellipsometry).

2. Growth Monitoring By P-Polarized Reflection Spectroscopy

For monitoring both the bulk and surface properties during heteroepitaxial $\text{Ga}_x\text{In}_{1-x}\text{P}$ growth on Si, p-polarized reflectance spectroscopy (PRS) together with laser light scattering (LLS) has been integrated in a pulsed chemical beam epitaxy (PCBE) system as schematically depicted in Figure 1. During heteroepitaxial $\text{Ga}_x\text{In}_{1-x}\text{P}$ growth on Si under pulsed chemical

beam epitaxy (PCBE) conditions, the surface of the substrate is exposed to pulsed ballistic beams of TBP $[(C_4H_9)PH_2]$, TEG $[Ga(C_2H_5)_3]$ and TMI $[In(CH_3)_3]$ at typically 350 - 470°C. The total pressure during growth in the reactor is kept in the range of 10^{-3} - 10^{-4} mbar and all precursors are supplied sequentially separated by pauses. In Figure 2 we present the typical evolution of the PR signals during growth of $Ga_{1-x}In_xP/GaP$ on Si(001) at 420°C, recorded for PR70 and PR75 at $\lambda=650\text{ nm} \pm 5\text{nm}$ and at $\lambda=632.8\text{ nm}$, respectively. The growth process is composed in 3 sections:

- (a) substrate and surface preconditioning,
- (b) deposition of a GaP buffer layer lattice-matched to the substrate, and
- (c) growth of a $Ga_{1-x}In_xP$ layer with a fixed composition x .

During the preconditioning period, the PR signals change in response to the temperature dependency of the dielectric function of the substrate. After initiating growth, interference fringes are observed in the temporal evolution of the PR signals as the film growth progresses. Note in Figure 2 that both PR signals are phase shifted due to the fact that one angle of incidence (PR75) is above - and the other (PR70) below - the pseudo-Brewster angle of the growing film material. As graphed in the insets of Figure 2, superimposed on the interference oscillations of the reflected intensity is a fine structure that is strongly correlated to the timing sequence of the precursors employed as their effects contribute to the growth surface.

In addition, the amplitude of the fine structure undergoes at least two modulations: (a) a modulation in amplitude due to the exposure of the growth surface to different doses and different species of precursors, and (b) a long-period modulation of the fine structure tagged to the position on the interference fringe. The first effect contains information about surface relevant constituents related to instantaneous growth and film composition and will be discussed in more detail below. The later effect can be modeled as a superficial overlayer containing the

average optical properties and thickness of a surface reaction layer feeding the underlying growth process (Beeler, S. et al. 1999).

The correlation of the PR fine structure with the precursor pulsing sequence is shown in Figure 3 for various TMI:TEG flow ratios. The PR responses are taken from several different growth experiments on the increasing flank of PR₇₀ interference fringe. The increase in slope with increasing TMI:TEG ratio correlates to increase in growth rate per cycle sequence, while the change in the fine structure response to the individual precursor pulse relates to the change in molar concentrations of constituents in the surface reaction layer. We observe that the PR fine structure response not only depends on the molar concentrations of constituents in the surface reaction layer but also on the optical response factors for each constituent associated with transitions characteristic for each specific molecular fragment. As depicted in Figure 3, the approximate same flux of TMI and TEG (TMI:TEG ratio = 1) results in different PR amplitude changes. Under steady-state growth conditions, the observed differences in amplitudes are correlated to concentration of surface constituents and their optical response factors as discussed in the next section. Effects related to differences in surface sites and mobility are neglected.

3. Reduced Order Surface Kinetics (ROSK) Model For $\text{Ga}_{1-x}\text{In}_x\text{P}$ Growth

A surface kinetics model for the ternary compound semiconductor $\text{Ga}_x\text{In}_{1-x}\text{P}$ growth from trimethylindium (TMI), triethylgallium (TEG), and tertiary-butylphosphine TBP $[(\text{C}_4\text{H}_9)\text{PH}_2]$ must describe the surface defragmentation processes of employed precursors, the chemical reactions between the precursor fragments, and the incorporation of the surface constituents in the underlying growing film. The relevant regions are depicted in Figure 4. For growth under

low-pressure CVD conditions, the precursor decomposition process can be described to first order by surface reactions and no gas phase reactions need to be considered.

The understanding and control of the kinetics of heteroepitaxy requires detailed information on the surface structure that depends on both reconstruction and the nature and distribution of defects in the epitaxial film. Over the last decades, several studies on the pyrolysis of TEG (Murrell, A.J. et al. 1990), TMI and TBP (Li, S.H. et al. 1989), on GaAs (Murrell, A.J. et al. 1990, McCaulley, R.J.S.J.A. et al. 1991), InP (Larsen, C.A. et al. 1987), GaP (Li, S.H. et al 1989, Garcia, J.C. et al. 1991), and Si (Lin, R. et al. 1989) surfaces have been reported. However, the progress in understanding and controlling thin film growth has been very slow since little is known about chemical reaction pathways and reaction kinetics parameters during the decomposition process of the organometallic precursors.

The reduced order surface kinetics (ROSK) model for GaP (Beeler, S. et al. 1999) and $\text{Ga}_x\text{In}_{1-x}\text{P}$ (Dietz, N. et al. 1999) under PCBE growth conditions that we use embodies the simplifying assumption that many reactions which make up the TBP pyrolysis can be combined into one step and the reactions which make up the TEG and the TMI decomposition can be combined into two steps for each precursor. The formation of $\text{Ga}_x\text{In}_{1-x}\text{P}$ is one final step made up from the formation of the binaries GaP and InP. The process is driven by a periodic source vapor cycle as schematically shown in Figure 3. The resulting kinetic model representing the SRL reactions is given by the following system of ordinary differential equations:

$$\frac{d}{dt}n_1(t) = u_{TBP} - \tilde{a}_1 n_1(t) - \tilde{a}_4 n_3(t) n_1(t) - \tilde{a}_7 n_6(t) n_1(t), \quad (1)$$

$$\frac{d}{dt}n_2(t) = u_{TEG} - \tilde{a}_2 n_2(t), \quad (2)$$

$$\frac{d}{dt}n_3(t) = \tilde{a}_2 n_2(t) - \tilde{a}_3 n_3(t) - \tilde{a}_4 n_3(t) n_1(t), \quad (3)$$

$$\frac{d}{dt}n_5(t) = u_{TMI} - k_5 n_5(t) , \quad (4)$$

$$\frac{d}{dt}n_6(t) = \tilde{a}_5 n_5(t) - \tilde{a}_6 n_6(t) - \tilde{a}_7 n_6(t) n_1(t) , \quad (5)$$

with the two incorporation reactions

$$\frac{d}{dt}n_4(t) = \tilde{a}_4 n_3(t) n_1(t) , \quad (6)$$

$$\frac{d}{dt}n_7(t) = \tilde{a}_7 n_6(t) n_1(t) , \quad (7)$$

for GaP and InP, respectively.

The variables n_1 , n_2 , n_3 , n_5 , and n_6 represent the number of moles of the surface constituent in the surface reaction layer (SRL). The periodic supply functions expressed in terms of the molar concentration of TBP, TEG, and TMI reaching the surface are denoted by u_{TBP} , u_{TEG} , and u_{TMI} , respectively. The system of differential equations (1) through (5) approximate the decomposition kinetics, taking in account desorption losses for the arriving precursors and for intermediate products. The differential equations (6) and (7) contain the reaction terms for forming GaP and InP, using two generalized reaction parameters $\tilde{a}_4$ and $\tilde{a}_7$. Note that the surface structure, number of reaction sides, and inhomogeneous reactions are not explicitly addressed at this point and are integrated into the reaction parameters $\tilde{a}_4$ and $\tilde{a}_7$. At this point, the time-dependency of the reaction parameter $\tilde{a}_4$ and $\tilde{a}_7$ are neglected for simplicity. A more accurate model would have to take into account the changes in surface reconstruction and density of reaction sites during the periodic exposure of the growth surface to precursors.

The solution of this coupled differential equations system, together with appropriate initial conditions, can be obtained numerically for the number of moles n_1 through n_7 . From these

solutions, the film and SRL thicknesses are found. The composition, x , for the compound semiconductor $\text{Ga}_{1-x}\text{In}_x\text{P}$ is expressed as the averaged ratio of molar concentration over a cycle sequence:

$$x = \frac{\int \frac{d}{dt} n_7(t) dt}{\int \left(\frac{d}{dt} n_4(t) + \frac{d}{dt} n_7(t) \right) dt}, \quad (8)$$

and the instantaneous film growth rate g_{fl} is given by

$$g_{fl} = \frac{1}{A} \left[\tilde{V}_{\text{GaP}} \frac{d}{dt} n_4(t) + \tilde{V}_{\text{InP}} \frac{d}{dt} n_7(t) \right], \quad (9)$$

where $\tilde{V}_{\text{GaP}}$ and $\tilde{V}_{\text{InP}}$ are the molar volumes for GaP and InP, respectively. The temporal thickness evolution of the SRL is given by

$$d_1(t) = \frac{1}{A} \left[n_1(t) \tilde{V}_1 + n_2(t) \tilde{V}_2 + n_3(t) \tilde{V}_3 + n_5(t) \tilde{V}_5 + n_6(t) \tilde{V}_6 \right], \quad (10)$$

where $\tilde{V}_i$ are the partial molar volumes of the constituents in the SRL, assumed to be constants.

This surface kinetics model provides a description of how one uses changes in composition and thickness of the SRL to obtain the instantaneous composition, x , and growth rate $g_{fl}(t)$ of the $\text{Ga}_x\text{In}_{1-x}\text{P}$ film. The ROSK data can be incorporated in Fresnel's equation that determines the reflectance amplitude, rr , of the p-polarized light, using the four layer media composed of ambient / SRL / film / substrate combined with a virtual substrate approach as described in the following section on control methodology.

4. Control Methodology For Thin Film Growth

To utilize the real time optical observations and apply a feedback control methodology for controlling $\text{Ga}_{1-x}\text{In}_x\text{P}$ film growth, we consider a four layer media composed of ambient / surface-reaction layer / film / substrate as described previously (Dietz, N. et al 1999). For the case of multi-layer media of films we adapted a virtual interface method (Aspnes, D.E. 1996, Aspnes, D.E. 1995), where the reflectance r of the p-polarized light is given by

$$r = \frac{r_{01} - \hat{r} e^{-2i\Phi_1}}{1 + r_{01} \hat{r} e^{-2i\Phi_1}} \quad \text{with} \quad \hat{r} = \frac{r_{12} - r_k e^{-2i\Phi_2}}{1 + r_{12} r_k e^{-2i\Phi_2}}. \quad (11)$$

The virtual reflection index r_k is updated at the end of each cycle by

$$r_k = \frac{r_{k,k-1} - r_{k-1} e^{-2i\Phi_2}}{1 + r_{k,k-1} r_{k-1} e^{-2i\Phi_2}} \quad \text{with} \quad r_k = A_k e^{-i\theta_k}, \quad (12)$$

where θ_k defines the phase factor and

$$r_{k,k-1} \equiv \frac{\epsilon_k \sqrt{\epsilon_{k-1} - \epsilon_0 \sin^2 \varphi_0} - \epsilon_{k-1} \sqrt{\epsilon_k - \epsilon_0 \sin^2 \varphi_0}}{\epsilon_k \sqrt{\epsilon_{k-1} - \epsilon_0 \sin^2 \varphi_0} + \epsilon_{k-1} \sqrt{\epsilon_k - \epsilon_0 \sin^2 \varphi_0}}.$$

Based on the phase factor θ_2 , the thickness d_2 of the grown layer is estimated by

$$d_2 = \frac{\lambda}{4\pi \sqrt{\epsilon_2 - \epsilon_0 \sin^2 \varphi_0}} (\theta_{\text{end}} - \theta_{\text{begin}}), \quad (13)$$

where θ_{end} , θ_{begin} are the phase factors at the end and beginning of the layer, respectively.

Similarly, the growth gr_k per each cycle k is given by

$$gr_k = \frac{\lambda}{4\pi \sqrt{\epsilon_2 - \epsilon_0 \sin^2 \varphi_0}} (\theta_k - \theta_{k-1}). \quad (14)$$

The thickness of the specific compound is estimated by equation (13) and the growth ratio of GaP and InP for each cycle determined by equation (14) provides a composition estimate.

We use a nonlinear filtering algorithm (Ito, K. et al. 2000) for estimating the state consisting of the virtual reflection index $r_k = e^{x_1 + i x_2}$, the film dielectric constant $\varepsilon_2 = x_3 + i x_4$, and growth per cycle x_5 in real time, as schematically outlined in Figure 6.

Let y_k denote the PR signal at the end of the k -th cycle. Then the filtering problem is to estimate the signal process x^k defined by

$$\begin{pmatrix} x_1^k \\ x_2^k \\ x_3^k \\ x_4^k \\ x_5^k \end{pmatrix} = \begin{pmatrix} f_1(x^k) \\ f_2(x^k) \\ x_3^{k-1} \\ x_4^{k-1} \\ x_5^{k-1} \end{pmatrix} + \omega_k \quad (15)$$

based on the observation process $y_k = h(x^k) + v_k$.

We assume that the reflectance coefficient $|r_{k,k-1}|$ is sufficiently small at the point of evaluation, so that we can approximate equation (12) and use $r_k = r_{k-1} e^{-2i\Phi_2}$ for updating the virtual index r_k . If we let f_{r_k} be the growth ratio of GaP or InP to each nominal flow rate, then the functions f_1 , f_2 and h are defined by

$$f_1 + i f_2 = x_1 + i x_2 + 2 i \varphi_2, \quad h = \frac{r_{02} + r_v}{1 + r_{02} r_v}, \quad (16)$$

where $d_2 = f_{r_k} x_5$. We assume that noise processes w_k , v_k are independent (identically distributed) Gaussian random variables. The growth of GaP and InP is determined in terms of n_{GaP} and n_{InP} which are given by

$$\frac{d n_{GaP}}{dt} = k_4 n_p n_{Ga} , \quad \frac{d n_{InP}}{dt} = k_5 n_p n_{In}, \quad (17)$$

where n_p , n_{Ga} , and n_{In} denote the concentration of surface active phosphorus, gallium and indium, respectively. We consider the model for the concentration change of active Ga in the SRL by

$$n_{Ga} = u_{TEG} S_{GaP} - n_{GaP}, \quad (18)$$

where S_{GaP} is a pre-determined constant. Integrating the first equation in (17), we obtain

$$n_{GaP}(t_{k+1}) = e^{-C} (n_{GaP}(t_k) - S_{GaP} u_{TEG}) + S_{GaP} u_{TEG} \quad (19)$$

where t_k is the starting time of the k -th cycle and $C = k_4 \int_{t_k}^{t_{k+1}} n_p(t) dt$. The rate constant k_4 varies and we estimate it in real time. We use our filtering algorithm to estimate the concentration n_k of n_{GaP} and the accumulated rate constant C_k for the k -th GaP cycle based on

$$\begin{pmatrix} n_k \\ C_k \end{pmatrix} = \begin{pmatrix} n_{k-1} + C_{k-1} (u_{TEG} - n_{k-1}) \\ C_{k-1} \end{pmatrix} + \tilde{w}_k, \quad (20)$$

with measurement $gr_k = V_{GaP} n_k + \tilde{v}_j$. Here gr_k is the growth rate of k -th GaP cycle, determined by equation (14). The growth of the InP is modeled analogously. We determine the input flow rates u_{TEG}^k and u_{TMI}^k by performing

$$\min_{u_{TEG}^k} \left| (1 + z_k) n_{GaP}^+ - gr_d \right|^2 + \beta \left| u_{TEG}^k - u_{TEG}^{k-1} \right|^2, \quad (21)$$

$$\min_{u_{TMI}^k} \left| \frac{n_{InP}^+}{n_{GaP}^+} - \frac{z_k}{1 - z_k} \right|^2 + \beta \left| u_{TMI}^k - u_{TMI}^{k-1} \right|^2,$$

subject to

$$n_{\text{GaP}}^+ = e^{-C_{\text{TEG}}^k} \left(n_{\text{GaP}}^c - S_{\text{GaP}} u_{\text{TEG}}^k \right) + S_{\text{GaP}} u_{\text{TEG}}^k, \text{ and} \quad (22)$$

$$n_{\text{InP}}^+ = e^{-C_{\text{TMI}}^k} \left(n_{\text{InP}}^c - S_{\text{InP}} u_{\text{TMI}}^k \right) + S_{\text{InP}} u_{\text{TMI}}^k,$$

respectively. Here C_{TEG}^k and C_{TMI}^k are the current estimates of C for the GaP and InP cycles respectively, and z_k is the desired composition at the k cycle. That is, we control the growth rate by u_{TEG} and then the composition by u_{TMI} for each cycle.

5. Controlled Growth of $\text{Ga}_{1-x}\text{In}_x\text{P}$ Heterostructures

From a series of experiments we established the correlation of composition and growth rate dependency as a function of flow-ratio. For this, epilayers with thick constant composition x in $\text{Ga}_{1-x}\text{In}_x\text{P}$ were grown and analyzed by x-ray diffraction (XRD) to obtain the compositional relationship with the established flow-ratio TMI:TEG. The growth rates were calculated from the interference fringes obtained in the PR signals. Figure 7 depicts the results of these ex-situ analyses, clearly indicating the nonlinear correlation between growth rate and composition as a function of an established flow ratio TMI:TEG. The established correlation between growth rate and composition x with the TMI:TEG flow ratio was next used to estimate the growth parameter for compositionally graded heterostructures under open-loop control conditions. The correlation was also used as initial data base for closed-loop control.

For the growth of a parabolic $\text{Ga}_{1-x}\text{In}_x\text{P}$ heterostructure under open-loop control, a predetermined time-dependent flow profile was employed in which the flow of TEG is kept constant and the flow of TMI is varied to match desired composition and thickness. The target profile is shown in Figure 8a together with the calculated time-dependent precursor flux profile

for TEG and TMI in Figure 8b. The grown parabolic $\text{Ga}_{1-x}\text{In}_x\text{P}$ heterostructure was analyzed by secondary mass ion spectroscopy (SIMS), the depth profile of which is shown in Figure 8c. The instrumental broadening of approximately 50 Å and a depth integration of typically 40 Å to 50 Å leads to two errors in the SIMS analysis: (a) a compositional smear-out of profiles over 100 Å to 150 Å and (b) the compositional dependency of the sputtering rate, which leads to an accumulative error in the depth estimate. For SIMS depth profiling using a primary Cs^+ -ion beam and detecting the In^+ -Cs and $^{71}\text{Ga}^{++}$ -Cs-ion intensities, the sputtering rate varies from 2.46 Å/s to 4.23 Å/s with strong compositional dependency. The error accumulation in the thickness calculation is estimated to be 10% of the film thickness, while the error in the compositional estimate is about 10% and remains independent of layer thickness. This leads to large thickness uncertainties with increasing layer thickness. The instrumental broadening factor and the given integration time leads to an error in composition, also estimated to be about 10%. Even if we take these error estimates into account, the open-loop control algorithm results depicted in Fig. 8 clearly indicate a much larger discrepancy between the target profile and measured profile.

The closed-loop control algorithm uses the open-loop control parameters as initial values. However, the precursor flux values are updated in real-time integrating the real-time estimate of the optical PR-signals as described in section 2. The real-time updated closed-loop control flow profile is shown in Figure 9a. During closed-loop control, variation of the flow of TMI is employed to control composition x while variation in the flow of TEG is used to control the growth rate. A SIMS depth profile analysis for a typical $\text{Ga}_{1-x}\text{In}_x\text{P}$ heterostructure grown in this manner is shown in Figure 9b. The deviations from the target values are 5% in composition and about 8% of thickness. These observed deviations from the target profile lay well within the estimated error range of the SIMS profile analysis and the results clearly demonstrate superior tracking ability under closed-loop control, particularly in maintaining a constant composition

before and after the parabolic heterostructure. For more accurate error analysis in achievable thickness- and compositional control tolerances, more precise ex-situ analysis techniques - presently not available - are needed.

6. Summary

We have described thin film growth monitoring via p-polarized reflectance and demonstrated its effectiveness in compositional and thickness controlled growth of $\text{Ga}_x\text{In}_{1-x}\text{P}$ heterostructures on Si. A reduced order surface kinetics model has been established to link the optical sensor to a nonlinear filtering algorithm that estimates the optimal flow rates of the source vapors required to achieve the desired composition and growth per cycle in real time. Parabolically graded $\text{Ga}_{1-x}\text{In}_x\text{P}$ heterostructure wells grown under open- and closed-loop conditions demonstrated that the on-line estimate of growth rate and composition provided by the PR probe adjusts to the nonlinearity in growth kinetics present in our system and provides better tracking to the desired profile than do open loop approaches currently used in practice.

7. Acknowledgment

Research described in this paper was supported by the DOD-MURI Grant AFOSR-F49620-95-1-0447.

8. References

- Aspnes, D. E., Harbison, J. P., Studna, A. A. and Florez, L. T., 1995, "Reflectance-difference spectroscopy system for real-time measurement of crystal growth", *Appl. Phys. Lett.* **52**(12), 957-959.
- Aspnes, D. E., 1995, "Optical approaches to the determination of composition of semiconductor alloys during epitaxy", *IEEE Journal on Selected Topics in Quantum Electronics* **1**, 1054-1063.
- Aspnes, D.E., 1996, "Optical approaches to determine near-surface compositions during epitaxy", *J. Vac. Sci. Technol. A* **14**, 960-966.
- Beeler, S., Tran, H. T. and Dietz, N., 1999, "Representation of GaP formation by a reduced order model using P-polarized reflectance measurements", *J. Appl. Phys.*, **86**(1), 674-682.
- Dietz, N. and Bachmann, K.J., 1995, "Real -time monitoring of epitaxial processes by parallel-polarized reflectance spectroscopy", *MRS Bull.*, **20**, 49-55.
- Dietz, N. and Bachmann, K. J., 1996, "P-polarized reflectance spectroscopy: a highly sensitive real-time monitoring technique to study surface kinetics under steady state epitaxial deposition conditions", *Vacuum*, **47**, 133-140.
- Dietz, N, Sukidi, N., Harris, C. and Bachmann, K.J., 1997, "Real-time monitoring of surface processes by P-polarized reflectance", *J. Vac. Sci. Technol.*, A **15**, 807-815.
- Dietz, N., Woods, V., Ito, K. and Lauko, I., 1999, "Real-time optical control of $\text{Ga}_{1-x}\text{In}_x\text{P}$ film growth by P-polarized reflectance", *J. Vac. Sci. Technol. A*, **17**(4), 1300-1306.
- Ebert, M., Bell, K.A., Yoo, S.D., Flock, K. and Aspnes, D.E., 2000, "In-situ monitoring of MOVPE growth by combined spectroscopic ellipsometry and reflectance difference spectroscopy", *Thin Solid Films*, in print.

- Garcia, J.C., Maurel, P., Bove, P. and Hirtz, J.P., 1991, "Kinetic study of metalorganic molecular beam epitaxy of GaP, InP, and GaInP", *J. Appl. Phys.*, **69**(5), 3297-3302.
- Ito, K. and Xiong, K., 2000, "New Gaussian filter for nonlinear filtering problems", *IEEE, Trans. Automatic Control*, **45**(5), 910-927.
- Kobayashi, N. and Horikoshi, Y., 1989, "Optical Investigation on the Growth Process of GaAs during Migration-Enhanced Epitaxy", *Jpn. J. Appl. Phys.*, **28**(11), L1880-L1882.
- Kobayashi, N. and Horikoshi, Y., 1990, "Spectral dependence of optical reflection during flow-rate modulation epitaxy of gallium arsenide by the surface photo-absorption method", *Jpn. J. Appl. Phys.*, **29**, L702-L705.
- Kobayashi, N., Makimoto, T., Yamauchi, Y. and Horikoshi, Y., 1991, "In-situ monitoring of gallium arsenide growth process in MOVPE by surface photo-absorption method", *J. Cryst. Growth*, **107**(1-4), 62-67.
- Larsen, C.A., Buchan, N.I. and Stringfellow, G.B., 1987, "Mass spectroscopic studies of phosphine pyrolysis and OMVPE growth of InP", *J. Crystal Growth*, **85**, 148-153.
- Li, S.H., Buchan, N.I., Larsen, C.A. and Stringfellow, G.B., 1998, "OMVPE growth mechanism for GaP using tertiarybutylphosphine and trimethylgallium", *J. Crystal Growth* **96**, 906-914.
- Li, S.H., Larsen, C.A., Buchan, N.I. and Stringfellow, G.B., 1989, "Pyrolysis of tertiarybutylphosphine", *J. of Electronic Materials*, **18**, 457-464.
- Lin, R., Gow, T.R., Backman, A.L., Cadwell, L.A., Lee, F. and Masel, R.I., 1989, "The decomposition of triethylgallium on Si(100)", *JVST*, B **7**(4), 725-728.
- McCaulley, R.J.S.J.A., and Donnelly, V.M., 1991, "Kinetics of thermal decomposition of triethylgallium, trimethylgallium, and trimethylindium adsorbed on GaAs(100)", *JVST*, A **9**(6), 2872-2886.

Murrell, A.J., Wee, A.T.S., Fairbrother, D.H., Singh, N.K., Foord, J.S., Davies, G.J. and Andrews, D.A., 1990, "Surface studies of the thermal decomposition of triethylgallium on GaAs (100)", *J. of Crystal Growth*, **105**, 199-202.

Yoshimoto, M., Hashimoto, T., Vaccaro, P. and Matsunami, H., 1994, "In-situ RHEED observation on surface reactions in laser-triggered chemical beam epitaxy of GaP", *Appl. Surf. Sci.*, **79**, 227-231.

(iii) Bibliography in alphabetic order

Banks, H.T., Alumni Distinguished Graduate Professor and Drexel Professor of Mathematics and Director, Center for Research in Scientific Computation, North Carolina State University. Ph.D. 1967, Applied Mathematics, Purdue University. Banks has published more than 275 papers in applied mathematics and engineering journals, graduated 24 Ph.D. students, directed more than 25 postdoctorals and written four books and edited several others. He served 2 terms as Managing Editor of the *SIAM J. Control and Optimization*, 2 terms as SIAM Vice President - Publications, and from 1980 to 2000 as Editor for the *Journal of Mathematical Biology*. He currently serves on the Editorial Boards of *Quarterly of Applied Mathematics*; *International J. Mathematical and Computer Modeling*; *Matematica Aplicada e Computacional*; *Applied Mathematics Letters*; *Discrete and Continuous Dynamical Systems*; *Nonlinear Analysis, Part B*; *Inverse Problems*; *J. Ill-Posed and Inverse Problems*; and *J. Intelligent Material Systems and Structures*. He is a Fellow of the IEEE, a Fellow of the Institute of Physics and in 1996 received the IEEE Control Systems Technology Award. He is currently serving on the SIAM Board of Trustees and is Editor in Chief of *SIAM Frontiers in Applied Mathematics*.

Dietz, N., Associate Professor; Department of Physics, Georgia State University. Ph.D. 1991, Solid State Physics, Technical University Berlin. Dietz has published more than 70 papers in applied physics and materials science journals. He is a member of the APS, MRS and TMS. His areas of expertise are in the optical materials- and defect characterization and the growth of materials. His current research focuses onto (i) optimization of film growth processes and real-time growth diagnostics; (ii) birefringent waveguide heterostructures, integrated optoelectronic and integrated real-time optical sensors; and (iii) linear- and nonlinear optical spectroscopy.

Ito, K., Professor, Center for Research in Scientific Computation, Department of Mathematics, North Carolina State University. Ph.D. 1981, Systems Science and Mathematics, Washington University. Ito's expertise focuses on control theory, reduced basis methods for control problems governed by PDE's, finite element methods and iterative refinement techniques for interface problems and applications, and reduced order methods for simulation and control of fluid flows.

(iv) *Author's name and affiliation*

Banks, H.T.

Center for Research in Scientific Computation and Department of Mathematics

North Carolina State University

324 Harrelson Hall, Box 8205

Raleigh, NC 27695-8205

Dietz, N.

Department of Physics and Astronomy

Georgia State University

29 Peachtree Center Avenue

Atlanta, GA 30303-3083

Ito, K.

Center for Research in Scientific Computation and

Department of Mathematics

North Carolina State University

310 Harrelson Hall, Box 8205

Raleigh, NC 27695-8205