

# Tribochemistry and Wear Life Improvement in Liquid-Lubricated H-DLC-Coated Bearings

25 July 2007

Prepared by

J. R. LINCE, H. I. KIM, and P. A. BERTRAND  
Space Materials Laboratory  
Laboratory Operations

O. L. ERYILMAZ and A. ERDEMIR  
Argonne National Laboratory  
Argonne, IL 60439

Prepared for

SPACE AND MISSILE SYSTEMS CENTER  
AIR FORCE SPACE COMMAND  
483 N. Aviation Blvd.  
El Segundo, CA 90245-2808


# 20070905207

Engineering and Technology Group

This report was submitted by The Aerospace Corporation, El Segundo, CA 90245-4691, under Contract No. FA8802-04-C-0001 with the Space and Missile Systems Center, 483 N. Aviation Blvd., El Segundo, CA 90245. It was reviewed and approved for The Aerospace Corporation by G. F. Hawkins, Principal Director, Space Materials Laboratory; and D. C. Marvin, Principal Director, Research and Program Development Office. Michael Zambrana was the project officer for the Mission-Oriented Investigation and Experimentation (MOIE) program.

This report has been reviewed by the Public Affairs Office (PAS) and is releasable to the National Technical Information Service (NTIS). At NTIS, it will be available to the general public, including foreign nationals.

This technical report has been reviewed and is approved for publication. Publication of this report does not constitute Air Force approval of the report's findings or conclusions. It is published only for the exchange and stimulation of ideas.

  
Michael Zambrana  
SMC/EA

<b>REPORT DOCUMENTATION PAGE</b>			Form Approved OMB No. 0704-0188		
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing this collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. <b>PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.</b>					
<b>1. REPORT DATE (DD-MM-YYYY)</b> 25-07-2007		<b>2. REPORT TYPE</b>		<b>3. DATES COVERED (From - To)</b>	
<b>4. TITLE AND SUBTITLE</b>  Tribochemistry and Wear Life Improvement in Liquid-Lubricated H-DLC-Coated Bearings			<b>5a. CONTRACT NUMBER</b> FA8802-04-C-0001		
			<b>5b. GRANT NUMBER</b>		
			<b>5c. PROGRAM ELEMENT NUMBER</b>		
<b>6. AUTHOR(S)</b>  J. R. Lince, H. I. Kim, P. A. Bertrand, O. L., Eryilmaz, and A. Erdemir			<b>5d. PROJECT NUMBER</b>		
			<b>5e. TASK NUMBER</b>		
			<b>5f. WORK UNIT NUMBER</b>		
<b>7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)</b>  The Aerospace Corporation Laboratory Operations El Segundo, CA 90245-4691			<b>8. PERFORMING ORGANIZATION REPORT NUMBER</b>  TR-2007(8565)-2		
<b>9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES)</b> Space and Missile Systems Center Air Force Space Command 483 N. Aviation Blvd. El Segundo, CA 90245			<b>10. SPONSOR/MONITOR'S ACRONYM(S)</b> SMC		
			<b>11. SPONSOR/MONITOR'S REPORT NUMBER(S)</b>		
<b>12. DISTRIBUTION/AVAILABILITY STATEMENT</b>  Approved for public release; distribution unlimited.					
<b>13. SUPPLEMENTARY NOTES</b>					
<b>14. ABSTRACT</b>  In contrast to typical DLC coatings, hydrogenated DLC (H-DLC) coatings exhibit extremely low friction in vacuum and dry atmospheres, suggesting their potential importance for spacecraft applications. We have conducted a study of H-DLC-coated steel thrust bearings, lubricated with a multiply-alkylated cyclopentane oil, either unformulated, or formulated with lead naphthenate or an aryl phosphate ester mixture. Data on uncoated steel thrust bearings were obtained for comparison. The surface chemistry of the additives on worn H-DLC surfaces was evaluated along with chemical analysis of the residual lubricant. In contrast with results on uncoated steel bearings, minimal additive-based tribofilm formation was detected on the surfaces of the H-DLC coatings in the wear tracks. The results indicate that additives optimized for steels may not be appropriate for H-DLC coatings. Although there were indications that H-DLC coatings increase endurance, the high roughness of the bearings contributed to statistical uncertainty. Future studies are planned with higher quality bearings.					
<b>15. SUBJECT TERMS</b> Diamond-like carbon, Spacecraft lubrication, Ball bearings, Tribochemistry, Lubricant additives, Friction and wear testing					
<b>16. SECURITY CLASSIFICATION OF:</b>			<b>17. LIMITATION OF ABSTRACT</b>	<b>18. NUMBER OF PAGES</b>  15	<b>19a. NAME OF RESPONSIBLE PERSON</b> Jeffry Lince
<b>a. REPORT</b> UNCLASSIFIED	<b>b. ABSTRACT</b> UNCLASSIFIED	<b>c. THIS PAGE</b> UNCLASSIFIED			<b>19b. TELEPHONE NUMBER (include area code)</b> (310)336-4464

# **Tribochemistry and Wear Life Improvement in Liquid-Lubricated H-DLC-Coated Bearings**

**J. R. Lince, H. I. Kim, P. A. Bertrand**

**Tribology Section**

**Space Materials Laboratory**

**The Aerospace Corporation**

**O. L. Eryilmaz and A. Erdemir**

**Argonne National Laboratory**

*F34 International Symposium on Rolling Element Bearings 2007*

*San Diego, CA, 9 May 2007*

**Space Materials Laboratory**

©2007, The Aerospace Corporation & Sandia National Laboratory. All Rights Reserved



## Acknowledgments

Thrust bearing  
Testing

Jim Kirsch

Lubricant  
Testing

Sandra Jackson

Useful  
Discussions

Buzz Carré

Funding

USAF Space and Missile Systems Center, under the Mission-Oriented Investigation and Experimentation Program, funded by the U.S. Air Force Space and Missile Systems Center under Contract No. FA8802-04-C-0001

The Aerospace Corporation's Independent Research and Development Program

U.S. Department of Energy, Office of Energy Efficiency and Renewable Energy, under Contract No. W-31-109-ENG-38

## Introduction


- The hardness and low friction of hydrogenated diamond-like carbon (H-DLC) coatings in dry atmospheres show promise for spacecraft applications
  - **Unlubricated:** Ideal for devices such as release mechanisms, latches, pointing mechanisms
    - Low temperature devices, and contamination-sensitive devices
  - **Lubricated:** Ball bearings for solar array drives, wheels/gyros
- Failure in liquid lubricated bearings is usually due to lubricant loss or degradation
  - Use of DLC precludes metal-to-metal contact, possibly reducing degradation
  - Oils and additives are optimized for steels; are they the best for DLC?
    - Alkyl phosphates: Antiwear additive reacts → Fe phosphates
    - Pbnp: Extreme pressure additive reduces → Pb, Pb-C-O tribopolymer

## Goals of this Study

- **Primary Goal:** Investigate how lubricant additive chemistry varies between steel and H-DLC in steel bearings
  - Aryl phosphate ester mixture
  - Lead Naphthenate
- **Secondary Goal:** Demonstrate improved endurance and performance of H-DLC-coated bearings compared to uncoated bearings


## Eccentric Bearing Lubricant Tester (Operated in Non-Eccentric Mode)

- Liquid lubricant, multiply-alkylated cyclopentane (MAC) synthetic hydrocarbon oil (aka Pennzane)
  - NSO 2001 oil with 2% aryl phosphate ester mixture
  - MAC with 3% Pbnp
  - NSO 2001A oil (unformulated)
- Vacuum  $1 \times 10^{-6}$  Torr
- Ball bearing raceways were 1117 steel, coated with hydrogenated DLC or uncoated (balls are 52100 steel)
- The raceway surface was high ( $R_a > 10 \mu\text{in}$ ,  $R_z \sim 50\text{-}75 \mu\text{in}$ )
  - Bearings used in space typically have much lower roughness
  - Roughness tended to drop after DLC coating




# H-DLC-Coated Thrust Bearing Testing Summary

## Tested using MAC oil (Pennzane) w/ Pbnp



- No Failure seen with either coated or uncoated bearings
  - Tests were stopped after 18-20 Mcycles

# Torque of Thrust Bearings Used with MAC oil (Pennzane) w/ Pbnp



- Torque is lower for H-DLC-coated bearings than for uncoated bearings

# Auger of Thrust Bearings Used with MAC oil w/ Pbnp – $1.7 \times 10^7$ cycle (no failure)

Uncoated Bearings





2 Mycles



18 Mycles

- Little wear after 2 Mycles
- Visible wear after 18 Mycles


NFC6-Coated Bearings





- Mild wear of coating after 2 Mycles
- Coating loss in some areas after 18 Mycles
  - Mostly near center of wear track

# Auger of Thrust Bearings


## Used with MAC oil w/ Pbnp – 18 Mcycle (no failure)



Uncoated Bearing




H-DLC-Coated Bearing



- Significantly more reacted Pb/C/O-containing tribofilm for uncoated than H-DLC-coated bearing
  - Pb concentration on worn and unworn regions of H-DLC-coated bearings similar
  - Indicates that Pbnp undergoes chemisorption, but little tribofilm formation on H-DLC

# FTIR Results on H-DLC-Coated & Uncoated Thrust Bearings



## Tested using MAC oil w/ Pbnp



- Pbnp in oil appears to break down with increasing running time
  - Regardless of tribofilm deposition (i.e., compare Auger of coated and uncoated samples)


# FTIR Difference Spectra

H-DLC-Coated & Uncoated Thrust Bearings, Tested using MAC oil w/ Pbnp



- Confirms that Pbnp in oil breaks down with increasing running time
  - Reduction of unreacted Pbnp peaks
  - Increase of breakdown product of Pbnp,  $-\text{CO}_2$

## H-DLC-Coated Thrust Bearing Testing Summary Tested using NSO2001 Oil (Pennzane w/ Phosphate Additives)



- All samples failed except one H-DLC sample (NFC6), which was stopped after 20,000,000 cycles
  - Indicates that H-DLC can provide significantly longer life with NSO2001
  - Variation likely due to high roughness of bearings




# Torque of Thrust Bearings Tested using NSO2001 Oil (Pennzane w/ Phosphate Additives)



- Torque does not appear to correlate with presence of H-DLC coating
  - Tribofilm is much thinner with phosphate esters than for Pbnp

# SEM/Auger on H-DLC-Coated (Unfailed) Thrust Bearing



Tested using NSO2001 Oil – 20 Mcycle (no failure)



- 20% Wear/delamination near center of ball track
- High carbon in delaminated areas:
  - 0.2-0.5 at% P detected in delaminated areas
  - Similar to uncoated disk: ~0.3 at% P and high C (not shown)
- P virtually undetectable in coated areas


# SEM/Auger on H-DLC-Coated (Unfailed) Thrust Bearing

Tested using NSO2001 Oil – 20 Mcycle (no failure)



- Outside of center of wear track, most of H-DLC coating is intact after successful test
- P is virtually undetectable in both areas


# FTIR Results on H-DLC-Coated Thrust Bearings Tested using NSO2001 Oil



- Degradation of aryl phosphate additives in remaining oil
  - No significant differences between oils from uncoated and H-DLC-coated samples, or between oils from failed and unfailed H-DLC-coated samples
  - Degradation of phosphate additives related only to number of cycles

# H-DLC-Coated Thrust Bearing Testing Summary

## Tested using NSO2001A Oil (Unformulated)



- H-DLC samples appeared to exhibit greater endurance, including one sample that did not fail

## Summary of H-DLC-Coated Thrust Bearing Results

- Multiply-alkylated cyclopentane (MAC) oil - Pennzane formulated with lead naphthenate (Pbnp)
  - Less deposition of Pb/C/O-containing tribofilm on H-DLC than uncoated steel
    - Agrees with Carré, Bertrand, Lince, Tribology Letters, 16(3) (2004) 207: Redox reaction of Pbnp requires metal-to-metal contact
  - Lower torque for H-DLC compared to uncoated steel. Possible reasons:
    - Lower friction of H-DLC ( $\mu < 0.01$ ) as opposed to steel ( $\mu > 0.3$ )
    - Lower roughness of coated surface
    - Less deposition of Pb-containing tribofilm (lower wear, but higher  $\mu$ ?)
  - Inconclusive results on endurance: All tests stopped at 18-20 Mcycles before failure occurred


## Summary of DLC-Coated Thrust Bearing Results

- NSO2001 - Pennzane with synthetic phosphate esters
  - Less deposition of P/C-containing tribofilm on H-DLC than uncoated steel
    - P-containing additive coatings detected only where H-DLC delaminated
  - Disappearance of aryl phosphate additives in oil in both uncoated and H-DLC-coated cases
    - Degradation of aryl phosphate additives related to cycle time, but not to presence of coating or whether failure occurred
  - Potential for increased endurance when using H-DLC coatings
- NSO2001A – Unformulated Pennzane
  - H-DLC-coated samples showed statistically greater performance than uncoated samples, possibly due to
    - Lower roughness
    - Lower lubricant degradation
  - Better performance than with aryl phosphate additives
    - Additives degrade H-DLC coating?
- Testing on bearings with lower surface roughness will begin shortly


## Part II – Effect of Environment on Friction of Hydrogenated DLC Coatings

- Hydrogenated DLC has shown very low friction and wear in vacuum use, higher friction in atmosphere
- Effect of environment critical for spacecraft applications
  - Most “inert” test environments are created by purging with  $N_2$  to minimize  $H_2O$  and  $O_2$ , but RH  $\sim 1\%$ ,  $O_2 \sim ?$
  - What level of  $H_2O$ ,  $O_2$ , and other impurities cause changes in tribology?

## Ultrahigh Vacuum Tribometer




- Ball on disk contact geometry
- Nominal sizes 3/16" ball, 0.55" disk
- UHV sample transfer to analysis chambers
  - XPS, HREELS, AES, Mass spectrum
- Controlled exposure to gases - operational pressure range  $<1 \times 10^{-9}$  Torr to ambient
- Simultaneous measurement of friction and load with orthogonal strain gages
- Possible load range 10mN to  $>10$  N
- Contact stresses from  $\sim 150$ MPa to  $>1$  GPa, material and ball size dependent
- Typical sliding speed, 1 cm/sec



# Effect of Relative Humidity on Friction


## H-DLC coated steel ball sliding on H-DLC coated steel plate



- Hydrogenated DLC coatings have extremely low friction in UHV
- The friction coefficient increases with increasing water vapor pressure in the test chamber.
- This trend is the opposite of that for non-hydrogenated DLC.



# Effect of Relative Humidity on Friction

## H-DLC coated steel ball sliding on H-DLC coated steel plate



- O<sub>2</sub> does not begin affecting friction until a pressure two orders of magnitude higher than H<sub>2</sub>O, but has similar effect
- Purified N<sub>2</sub> has negligible effect on friction


# Auger Spectroscopy of Wear Track for H-DLC sliding on H-DLC in 300 Torr O<sub>2</sub>



- No apparent difference in surface chemistry between worn and unworn regions
  - Detected oxygen due to small amounts of adsorbed O or OH from atmosphere

# The Effect of H<sub>2</sub>O on Different Carbon Coatings


## Hydrogenated vs. Non-hydrogenated



- Hydrogenated and non-hydrogenated carbon coatings have very different friction in UHV
- The converging friction properties under humid environments suggest a common lubrication mechanism by water. [Kim, Lince, Eryilmaz, Erdemir, Tribol. Lett., 21(1) (2006) 51-56.]

# Pin-on-Disk Tribometry of H-DLC

## Variation of Friction with Rotation Speed and Humidity



- Friction highly dependent on rotation speed
  - Water molecules weakly absorbed; displaced by sliding contact
  - Slower speeds allow greater water absorption between passes
- Weak effect on increasing humidity

## Conclusions

- The use of H-DLC coatings for liquid-lubricated bearings in spacecraft appears promising, although more data is needed.
  - No apparent tribofilm formation on H-DLC-coated bearing surfaces
  - Future testing will be done on bearings with lower roughness
- Tribological properties of H-DLC coatings are significantly affected by small amounts of H<sub>2</sub>O and O<sub>2</sub> impurities in “dry” N<sub>2</sub> environments.
  - Careful attention is needed for spacecraft mechanisms tested in “dry” N<sub>2</sub> for vacuum applications.

## LABORATORY OPERATIONS

The Aerospace Corporation functions as an "architect-engineer" for national security programs, specializing in advanced military space systems. The Corporation's Laboratory Operations supports the effective and timely development and operation of national security systems through scientific research and the application of advanced technology. Vital to the success of the Corporation is the technical staff's wide-ranging expertise and its ability to stay abreast of new technological developments and program support issues associated with rapidly evolving space systems. Contributing capabilities are provided by these individual organizations:

**Electronics and Photonics Laboratory:** Microelectronics, VLSI reliability, failure analysis, solid-state device physics, compound semiconductors, radiation effects, infrared and CCD detector devices, data storage and display technologies; lasers and electro-optics, solid-state laser design, micro-optics, optical communications, and fiber-optic sensors; atomic frequency standards, applied laser spectroscopy, laser chemistry, atmospheric propagation and beam control, LIDAR/LADAR remote sensing; solar cell and array testing and evaluation, battery electrochemistry, battery testing and evaluation.

**Space Materials Laboratory:** Evaluation and characterizations of new materials and processing techniques: metals, alloys, ceramics, polymers, thin films, and composites; development of advanced deposition processes; nondestructive evaluation, component failure analysis and reliability; structural mechanics, fracture mechanics, and stress corrosion; analysis and evaluation of materials at cryogenic and elevated temperatures; launch vehicle fluid mechanics, heat transfer and flight dynamics; aerothermodynamics; chemical and electric propulsion; environmental chemistry; combustion processes; space environment effects on materials, hardening and vulnerability assessment; contamination, thermal and structural control; lubrication and surface phenomena. Microelectromechanical systems (MEMS) for space applications; laser micromachining; laser-surface physical and chemical interactions; micropropulsion; micro- and nanosatellite mission analysis; intelligent microinstruments for monitoring space and launch system environments.

**Space Science Applications Laboratory:** Magnetospheric, auroral and cosmic-ray physics, wave-particle interactions, magnetospheric plasma waves; atmospheric and ionospheric physics, density and composition of the upper atmosphere, remote sensing using atmospheric radiation; solar physics, infrared astronomy, infrared signature analysis; infrared surveillance, imaging and remote sensing; multispectral and hyperspectral sensor development; data analysis and algorithm development; applications of multispectral and hyperspectral imagery to defense, civil space, commercial, and environmental missions; effects of solar activity, magnetic storms and nuclear explosions on the Earth's atmosphere, ionosphere and magnetosphere; effects of electromagnetic and particulate radiations on space systems; space instrumentation, design, fabrication and test; environmental chemistry, trace detection; atmospheric chemical reactions, atmospheric optics, light scattering, state-specific chemical reactions, and radiative signatures of missile plumes.



2350 E. El Segundo Boulevard  
El Segundo, California 90245-4691  
U.S.A.