



AFRL-ML-WP-TP-2007-490

PEPTIDE-ASSEMBLED OPTICALLY RESPONSIVE NANOPARTICLE COMPLEXES (PREPRINT)

Rajesh R. Naik and Joseph M. Slocik

Hardened Materials Branch

Survivability and Sensor Materials Division

MARCH 2007

Approved for public release; distribution unlimited.

See additional restrictions described on inside pages

STINFO COPY

**AIR FORCE RESEARCH LABORATORY
MATERIALS AND MANUFACTURING DIRECTORATE
WRIGHT-PATTERSON AIR FORCE BASE, OH 45433-7750
AIR FORCE MATERIEL COMMAND
UNITED STATES AIR FORCE**

NOTICE AND SIGNATURE PAGE

Using Government drawings, specifications, or other data included in this document for any purpose other than Government procurement does not in any way obligate the U.S. Government. The fact that the Government formulated or supplied the drawings, specifications, or other data does not license the holder or any other person or corporation; or convey any rights or permission to manufacture, use, or sell any patented invention that may relate to them.

This report was cleared for public release by the Air Force Research Laboratory Wright Site (AFRL/WS) Public Affairs Office and is available to the general public, including foreign nationals. Copies may be obtained from the Defense Technical Information Center (DTIC) (<http://www.dtic.mil>).

AFRL-ML-WP-TP-2007-490 HAS BEEN REVIEWED AND IS APPROVED FOR PUBLICATION IN ACCORDANCE WITH ASSIGNED DISTRIBUTION STATEMENT.

*//Signature//

RAJESH R. NAIK, Ph.D.
Biotechnology
Exploratory Development
Hardened Materials Branch

//Signature//

MARK S. FORTE, Acting Chief
Hardened Materials Branch
Survivability and Sensor Materials Division

//Signature//

TIM J. SCHUMACHER, Chief
Survivability and Sensor Materials Division

This report is published in the interest of scientific and technical information exchange, and its publication does not constitute the Government's approval or disapproval of its ideas or findings.

*Disseminated copies will show “//Signature//” stamped or typed above the signature blocks.

REPORT DOCUMENTATION PAGE				Form Approved OMB No. 0704-0188	
The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.					
1. REPORT DATE (DD-MM-YY) March 2007		2. REPORT TYPE Journal Article Preprint		3. DATES COVERED (From - To)	
4. TITLE AND SUBTITLE PEPTIDE-ASSEMBLED OPTICALLY RESPONSIVE NANOPARTICLE COMPLEXES (PREPRINT)				5a. CONTRACT NUMBER In-house	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER 62102F	
6. AUTHOR(S) Rajesh R. Naik and Joseph M. Slocik* (AFRL/MLPJ) Felicia Tam (Rice University, Dept. of Physics and Astronomy) Naomi J. Halas (Rice University, Dept. of Electrical and Computer Engineering)				5d. PROJECT NUMBER 4348	
				5e. TASK NUMBER RG	
				5f. WORK UNIT NUMBER M08R1000	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Hardened Materials Branch (AFRL/MLPJ) Survivability and Sensor Materials Division Materials and Manufacturing Directorate Wright-Patterson Air Force Base, OH 45433-7750 Air Force Materiel Command United States Air Force				Rice University Dept. of Physics and Astronomy Dept. of Electrical and Computer Engineering 6100 Main Street, MS-366 Houston, TX 77005-1892 ----- *NRC 500 Fifth Street, NW GR 322A Washington, DC 20001	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) Air Force Research Laboratory Materials and Manufacturing Directorate Wright-Patterson Air Force Base, OH 45433-7750 Air Force Materiel Command United States Air Force				10. SPONSORING/MONITORING AGENCY ACRONYM(S) AFRL/MLPJ	
				11. SPONSORING/MONITORING AGENCY REPORT NUMBER(S) AFRL-ML-WP-TP-2007-490	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution unlimited.					
13. SUPPLEMENTARY NOTES Journal article submitted to Nanoletters. The U.S. Government is joint author of this work and has the right to use, modify, reproduce, release, perform, display, or disclose the work. PAO Case Number: AFRL/WS 07-0559, 14 Mar 2007.					
14. ABSTRACT The design of active nanostructures whose form and properties can be modulated by remote means is an important challenge in nanoscience. Here we report two types of active nanoparticle complexes, with properties controlled by near infrared illumination, resulting from the assembly of photothermally responsive plasmonic nanoparticles with thermally labile bimolecular linkers. Au nanoshells (NS) and quantum dots (QD) are assembled using coiled-coil peptides into NS-NS and NS-QD complexes. Illumination of the NS-NS complexes results in reversible disassembly-reassembly, while illumination of NS-QD complexes results in a large, reproducible modulation of the quantum dot fluorescence without disassembly of the nanoparticle-peptide complex.					
15. SUBJECT TERMS Au Nanoshells (NS), Quantum Dots (QD), Peptide					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT: SAR	18. NUMBER OF PAGES 20	19a. NAME OF RESPONSIBLE PERSON (Monitor) Rajesh R. Naik 19b. TELEPHONE NUMBER (Include Area Code) N/A
a. REPORT Unclassified	b. ABSTRACT Unclassified	c. THIS PAGE Unclassified			

Peptide-assembled Optically Responsive Nanoparticle Complexes

*Joseph M. Slocik,^{1,4} Felicia Tam,² Naomi J. Halas,³ and Rajesh R. Naik^{*1}*

1. Materials and Manufacturing Directorate, Air Force Research Laboratory, Wright-Patterson AFB, OH
45433-7702

2. Department of Physics and Astronomy, Rice University, 6100 Main Street, MS-366, Houston, TX
77005-1892

3. Department of Electrical and Computer Engineering, Rice University, 6100 Main Street, MS-366,
Houston, TX 77005-1892

4. NRC fellow 500 Fifth Street, NW, GR 322A Washington, DC 20001

*Corresponding Author. Tel.: 937-255-9717 Email: Rajesh.Naik@wpafb.af.mil

ABSTRACT

The design of active nanostructures whose form and properties can be modulated by remote means is an important challenge in nanoscience. Here we report two types of active nanoparticle complexes, with properties controlled by near infrared illumination, resulting from the assembly of photothermally responsive plasmonic nanoparticles with thermally labile biomolecular linkers. Au nanoshells (NS) and quantum dots (QD) are assembled using coiled-coil peptides into NS-NS and NS-QD complexes. Illumination of the NS-NS complexes results in reversible disassembly-reassembly, while illumination of NS-QD complexes results in a large, reproducible modulation of the quantum dot fluorescence without disassembly of the nanoparticle-peptide complex.

The biological assembly of nanoparticles has led to advances in device fabrication, photonics, catalysis,^{1,2} electronics,³⁻⁵ and sensor development⁶⁻⁹ as a result of the precise control that biological systems offer. For example, Au nanoparticles have been assembled into discrete networks using DNA hybridization^{10,11} and various peptide motifs.¹²⁻¹⁵ Bimetallic catalytic particles have been prepared by peptide templated synthesis,^{16,17} while microorganisms⁴ and viruses³ have been used to organize gold nanoparticles into conductive networks. In addition to directing assembly, the dynamic nature of biomolecules has also been exploited to induce structural changes in nanoparticle complexes under certain controlled conditions. For example, the release of encapsulated CdS particles by the heat shock protein GroEL can be triggered by addition of ATP.¹⁸ Conformational changes to biomolecules can be stimulated by various environmental conditions, such as temperature, pH, solvent, and ionic concentration.¹⁹ In living systems, these changes are often used to signal biochemical events and pathways; in abiotic systems, they present useful mechanisms for the external triggering of structural changes in nanoparticle assemblies or networks.¹⁹ For example, pH modulation has been shown to promote the disassembly of a coiled-coil leucine zipper peptide based gold nanoparticle structure^{13, 15} and DNA functionalized gold nanoparticle assemblies.¹¹

Plasmonic nanoparticles, metal-based nanoparticles whose optical resonant properties are controlled by their geometry,^{20, 21} are highly promising components for imparting optical responsivity into nanoscale structures. This useful class of nanoparticles combines structurally tunable optical properties with facile conjugation of biomolecules to their surfaces. Optically, nanoshells can be designed to scatter and/or absorb light over a broad spectral range. Their large absorption cross section combined with their extremely weak fluorescent properties result in a very strong photothermal response upon resonant optical illumination. The large photothermal response of nanoshells has been successfully exploited in numerous

actuating applications, such as optically triggered drug delivery,^{22, 23} independently optically addressable materials,^{24, 25} microfluidic valves,²⁶ photothermal deletion of cancer cells²⁷ and photothermally induced remission of cancerous tumors.²⁸ These photothermal properties have additional potential in applications such as destruction of biological warfare agents, decontamination of pollutants, or photothermally driven devices and switches, where optical illumination may be used to toggle between a cool or heated state.

Here we report the use of a coiled-coil peptide motif to assemble two types of active nanoparticle complexes, designed to respond specifically to near infrared resonant light illumination. Extended nanoshell-nanoshell (NS-NS) and discrete nanoshell-semiconductor quantum dot (NS-QD) complexes are assembled using this peptide as a thermally labile interparticle linker. Since Au nanoshells possess a large photothermal response, when they are assembled into complexes via this thermally sensitive molecular linker, the structures and properties of the resultant nanoparticle complexes can be modulated remotely using near infrared illumination. Although the structure, properties, and active modulation response of the NS-NS and NS-QD complexes are quite different, the use of coiled-coil peptides for assembly in both cases results in optically modulated properties that are robust and reversible, capable of being optically cycled numerous times.

Au nanoshells (NS) with plasmon resonances at 805 nm were synthesized as described previously.^{29, 30} 200 μ L of nanoshells (1.1×10^{10} particles/mL) were transferred into 0.1 M phosphate buffer pH 9.0 for subsequent peptide binding. 3 μ L of one of the two matching anti-parallel coil peptides (E5) –CGGEVSALEKEVSALEKEVSALEKEVSALEKEVSALEK- or (K5) –CGGKVSALKEKVSALK EKVSALKEKVSALKEKVSALKE-³¹ (10 mg/mL, New England Peptide Inc.) were then added to the nanoshell suspensions and incubated for 2 hours. Unbound peptide was then removed through three cycles of centrifugation and dialysis in deionized water. The peptides were conjugated to the nanoshells through Au-thiol binding. FT-IR spectroscopy, obtained on a Perkin Elmer FT-IR spectrometer SPECTRUM 2000 with AutoImage system, was used to confirm the presence of NS-bound coil peptide, through the absence of S-H stretching modes and the appearance of amide I and II vibration modes.

Purified E5 and K5 peptide functionalized NS components were incubated together for 2 h, resulting in nanoshell complexes that were assembled orthogonally at a 1:1 ratio via a coiled-coil formation. The assembled NS-NS structures were characterized using a CPS disk centrifuge particle size analyzer DC240000 and using a Phillips CM200 transmission electron microscope (TEM) (Fig. 1). Free Au nanoshells possessed a diameter of 122 nm (Fig. 1B); nanoshells assembled with complementary coil peptides exhibited a size of 205 ± 60 nm, indicative of dimers (Fig. 1C). Consistent with the particle size analysis data, TEM micrographs of the assembled nanoshell complexes show the predominance of large nanoshell aggregates relative to free nanoshells.

The peptide assembled structures possessed excellent stability against external heating and chemical denaturants. This property is entirely due to the stability of the coiled-coil peptide complex to heat ($T_m > 85^\circ\text{C}$) and to guanidinium HCl, thereby making the NS-NS structures resilient to conventional biochemical methods used for protein denaturation. However, it is possible to trigger the disassembly of these nanoshell complexes by utilizing the intrinsic photothermal properties of nanoshells. Near-IR illumination was achieved with a 810 nm molded 3x LEDs (Marubeni Corp, 20mW). The NS-NS structures were irradiated for 15 minutes with 808 nm incident light, well within the linewidth of the plasmon resonance,³² to induce temperature-mediated unfolding of the coiled-coil peptide interface and therefore promote disassembly. As a result, the nanoparticle-peptide complexes were nearly completely disassembled into the individual NS components as observed by the lack of the larger aggregates by TEM (Fig. 1D). In addition, the particle size analysis of the irradiated structure revealed a size distribution centered around 122 nm, consistent with disassembled free nanoshells. The tail of the CPS plot indicates that a small number of residual dimer particles persisted. Notably, this externally triggered disassembly was found to be reversible. Five minutes after irradiation had ceased, the coil functionalized nanoshells reassembled to form the original NS-NS coiled-coil structure (Fig. 1E) due to reversible folding of the peptides upon cooling.

In the case of the peptide-assembled NS-QD heterocomplexes, discrete nanoparticle assemblies were obtained consisting of individual peptide-conjugated nanoshells linked to multiple QDs at their surfaces (Fig. 2). Similar to the NS-NS complexes, nanoshells and quantum dots were functionalized with matching anti-parallel coil peptides, E5 and K5, respectively. CdSe/ZnS Evitag-Fort Orange-Carboxyl quantum dots (QD) (Evident technologies, catalog #ET-C11-CB1-0600, conc. 0.25 mg/mL) were functionalized with coil K5 peptide by incubating 3 μ L of coil peptide K5 with 50 μ L QD-COOH that had been activated with 20 μ L of EDC/NHS for and 50 μ L of 0.1 M cysteine. TEM analysis revealed several uniform layers of quantum dots on the nanoshell surface (Fig. 2B) with characteristic lattice fringes for the QDs. EDAX mapping of the NS-QD structure confirmed the association of the Cd, Zn, and S of the quantum dot with the Au of the nanoshell (Fig. 2C). In contrast, substitution of a coil peptide with a random peptide sequence on the quantum dots resulted in no formation of NS-QD structures.

The peptide-assembled NS-QD heterostructure complexes give rise to a dramatic active response upon illumination (Fig. 3). Since metal nanoparticles significantly alter the emission of nearby fluorophores,^{33, 34} the fluorescence from the NS-QD structures was monitored during assembly using a Varian Cary Eclipse fluorimeter. Initially, as the NS-QD complexes assemble (prior to illumination), the QDs are brought into close enough proximity to the NS surface to result in a quenching of the QD fluorescence at 605 nm to 69% of the free QD emission (Fig. 3B). When the NS-QD complexes were irradiated with 808 nm light (using the fluorimeter), a dramatic increase in fluorescence to preassembly levels occurred. This behavior is reminiscent of previously reported fluorescence changes in CdTe-PEG-Au superstructures in response to bulk solution heating.^{35, 36} Following the dramatic increase in illumination-induced fluorescence, the fluorescence emission of the NS-QD complex then slowly decays back to its initial preillumination value.

Our interpretation of the active response of this heterostructure complex is based on the distance-dependent fluorescence quenching and enhancement of fluorophores by metallic nanoparticles. Because of the partial quenching of the fluorescence during initial assembly, it appears that the QDs are located

relatively close to the NS surface in equilibrium. Since the fluorescence increases upon illumination, it is likely that this corresponds to an increase in NS-QD distance, either due to a stretching/expansion of the peptide ligands, or due to dissociation of the complex. Unlike the NS-NS structures, however, particle size analysis (Fig. 3C), gel electrophoresis and TEM revealed that the NS-QD complexes do not disassemble appreciably upon near-IR illumination. The slow timescale of the observed post-illumination fluorescence decay may possibly be due to charging effects upon illumination of the complex: if the QD-ligands become charged, the resulting electrostatic repulsion would inhibit their relaxation back to the nanoshell surface.

Circular dichroism (CD) spectroscopy confirmed that the observed disassembly-reassembly of the NS-NS complexes was indeed induced by a change in the secondary structure of the coiled-coil peptides (Fig. 4A). In contrast, CD spectroscopy of the NS-QD complexes revealed no such structural change, further supporting the conclusion that the fluorescence modulation in these complexes is not due to disassembly (Fig. 4B). Using a Jasco J-720 spectropolarimeter, we monitored the change in secondary structure of the coiled-coil peptides in the NS-NS assemblies *in situ* with an array of 810 nm LED's. Upon illumination, the spectrum of NS-NS showed a 30% loss in helicity of the peptide functionalized NS's at θ_{222} and featured a decreased peak at 190 nm attributed to $\pi \rightarrow \pi^*$ transition. The change in secondary structure indicates thermal unfolding of the peptide induced by NS photothermal heating, and is consistent with the dissociation of other coil peptides.¹³ Following illumination, the disassembled coil-NS components regained ~ 90% of their original helicity upon reassembly of the NS-NS structures. In contrast, there was no difference between the CD spectra of the pre-illuminated and post-illuminated NS-QD complexes, indicating no detectable change in the structure of the peptide linkages in this case.

The difference in disassembly between the irradiated NS-NS and NS-QD structures may be due to interactions between the plasmons on adjacent NSs in the NS-NS complexes, which upon irradiation may lead to increased fields in the junction between the nanoparticles, resulting in a greater photothermal

dissociative response. In addition, it is likely that heat dissipated more quickly from the relatively isolated nanoshells in the NS-QD structures as opposed to the dense network of the NS-NS complexes.

The ability to control the nanoparticle assemblies remotely by optical illumination has highly valuable potential for ultimately manipulating material properties. We have shown that the coiled-coil peptide assembly of nanoshell-nanoshell and nanoshell-quantum dot complexes results in active nanostructures with light-inducible responses. This method affords a new means to manipulate both structural properties, such as reversible disassembly, as well as optical properties such as fluorescence quenching, without disassembly. In addition, it may be possible to tailor the optical threshold and response kinetics of such optically active nanostructure complexes by modifying the melting transition of the biomolecule interface, a property controlled by the structure of the biomolecules themselves.

ACKNOWLEDGEMENTS

This work was supported by the Air Force Office of Scientific Research Grant FA9550-06-1-0021, the National Science Foundation (NSF) Grant EEC-0304097, the Robert A. Welch Foundation C-1220, and the Multidisciplinary University Research Initiative (MURI) Grant W911NF-04-01-0203.

FIGURE LEGENDS

Figure 1. Assembly and disassembly of coiled-coil peptide functionalized nanoshell complexes. (A) Schematic illustration of the light-induced assembly/disassembly process. TEM micrographs (left panels) CPS particle size analysis (right panels) of (B) free nanoshell functionalized with E5 coil peptide, (C) assembled NS-NS complexes, (D) near-IR disassembled structures, and (E) reassembled nanoshell complexes following irradiation.

Figure 2. Assembly and characterization of NS-QD structures. (A) Schematic of the assembly process. (B) TEM image of NS-QDs. (C) EDAX maps for Au, S, Zn, and Cd on the NS-QD complexes. Scale bar, 90 nm.

Figure 3. Near-IR irradiation of NS-QD structures. (A) Schematic of the assembly process. (B) Time plot of fluorescence at 605 nm during assembly and after irradiation. Fluorescence measurements were collected and averaged every 5 sec for the assembly process; measurements were collected continuously following illumination. (C) CPS size plot showing free nanoshells, NS-QD coil assemblies, and irradiated structures.

Figure 4. Circular Dichroism measurements of (A) NS-NS and (B) NS-QD complexes before and after irradiation.

REFERENCES

1. Varpness, Z.; Peters, J. W.; Young, M.; Douglas, T. *Nano Lett.* **2005**, *5*, 2306-2309.
2. Kramer, R. M.; Sowards, L. A.; Pender, M. A.; Stone, M. O.; Naik, R. R. *Langmuir* **2005**, *21*, 8466-8470.
3. Blum, A. S.; Soto, C. M.; Wilson, C. D.; Brower, T. L.; Pollack, S. K.; Schull, T. L.; Chatterjee, A.; Lin, T.; Johnson, J. E.; Amsinck, C.; Franzon, P.; Shashidhar, R.; Ratna, B. R. *Small* **2005**, *1*, 702-706.
4. Berry, V.; Rangaswamy, S.; Saraf, R. F. *Nano Lett.* **2004**, *4*, 939-942.
5. Berry, V.; Gole, A.; Kundu, S.; Murphy, C. J.; Saraf, R. F. *J. Am. Chem. Soc.* **2005**, *127*, 17600-17601.
6. Lin, T.-J.; Huang, K.-T.; Liu, C.-Y. *Biosensors & Bioelectronics* **2006**, *22*, 513-518.
7. Cao, C.; Sim, S. J. *Biosensors & Bioelectronics* **2006**, ASAP.
8. Han, M. S.; Lytton-Jean, A. K. R.; Oh, B.-K.; Mirkin, C. A. *Angew. Chem. Int. Ed.* **2006**, *45*, 1807-1810.
9. Reynolds, A. J.; Haines, A. H.; Russell, D. A. *Langmuir* **2006**, *22*, 1156-1163.
10. Zheng, J.; Constantinou, P. E.; Micheel, C.; Alivisatos, A. P.; Kiehl, R. A.; Seeman, N. C. *Nano Lett.* **2006**, *6*, 1502-1504.
11. Sharma, J.; Chhabra, R.; Yan, H.; Liu, Y. *Chem. Commun.* **2006**, ASAP.
12. Aili, D.; Enander, K.; Rydberg, J.; Lundstrom, I.; Baltzer, L.; Liedberg, B. *J. Am. Chem. Soc.* **2006**, *128*, 2194-2195.
13. Stevens, M. M.; Flynn, N. T.; Wang, C.; Tirrell, D. A.; Langer, R. *Adv. Mater.* **2004**, *16*, 915-918.
14. Ryadnov, M. G.; Ceyhan, B.; Niemeyer, C. M.; Woolfson, D. N. *J. Am. Chem. Soc.* **2003**, *125*, 9388-9394.

15. Satyabrata, S.; Mandal, T. K. *J. Am. Chem. Soc.* **2006**, ASAP.
16. Slocik, J. M.; Naik, R. R. *Adv. Mater.* **2006**, 18, 1988-1992.
17. Banerjee, I. A.; Regan, M. R. *Mater. Lett.* **2006**, 60, 915-918.
18. Ishii, D.; Kinbara, K.; Ishida, Y.; Ishii, N.; Okochi, M.; Yohda, M.; Aida, T. *Nature* **2003**, 423, 628-632.
19. Horton, H. R.; Moran, L. A.; Ochs, R. S.; Rawn, J. D.; Scrimgeour, K. G., *Principles of Biochemistry*. 2nd ed.; Prentice-Hall: Upper Saddle River, 1996.
20. Prodan, E.; Nordlander, P.; Halas, N. J. *Nano Lett.* **2003**, 3, 1411-1415.
21. Wang, H.; Brandl, D. W.; Nordlander, P.; Halas, N. J. *Acc. Chem. Res.* **2007**, 40, (1), 53-62.
22. Hirsch, L. R.; Gobin, A. M.; Lowery, A. R.; Tam, F.; Dreze, R. A.; Halas, N. J.; West, J. L. *Annals of Biomedical Engineering* **2006**, 34, (1), 15-22.
23. Sershen, S. R.; Westcott, S. L.; Halas, N. J.; West, J. L. *Journal of Biomedical Materials Research* **2000**, 51, (3), 293-298.
24. Sershen, S. R.; Westcott, S. L.; West, J. L.; Halas, N. J. *Applied Physics B-Lasers and Optics* **2001**, 73, (4), 379-381.
25. Sershen, S. R.; Westcott, S. L.; Halas, N. J.; West, J. L. *Applied Physics Letters* **2002**, 80, (24), 4609-4611.
26. Sershen, S. R.; Mensing, G. A.; Ng, M.; Halas, N. J.; Beebe, D. J.; West, J. L. *Advanced Materials* **2005**, 17, (11), 1366-+.
27. Hirsch, L. R.; Stafford, R. J.; Bankson, J. A.; Sershen, S. R.; Rivera, B.; Price, R. E.; Hazle, J. D.; Halas, N. J.; West, J. L. *Proceedings of the National Academy of Sciences of the United States of America* **2003**, 100, (23), 13549-13554.
28. O'Neal, D. P.; Hirsch, L. R.; Halas, N. J.; Payne, J. D.; West, J. L. *Cancer Letters* **2004**, 209, (2), 171-176.
29. Oldenburg, S. J.; Averitt, R. D.; Westcott, S. L.; Halas, N. J. *Chemical Physics Letters* **1998**, 288, (2-4), 243-247.
30. Oldenburg, S. J.; Westcott, S. L.; Averitt, R. D.; Halas, N. J. *Journal of Chemical Physics* **1999**, 111, (10), 4729-4735.
31. Chao, H.; Bautista, D. L.; Litowski, J.; Irvin, R. T.; Hodges, R. S. *J. Chromat. B* **1998**, 715, 307-329; Litowski, J. R.; Hodges, R. S. *J. Biol. Chem.* **2002**, 277, 37272-37279.
32. Westcott, S. L.; Halas, N. *Physical Review B* **2002**, 66, 155431.
33. Lakowicz, J. R. *Analytical Biochemistry* **2005**, 337, (2), 171-194.
34. Tam, F.; Goodrich, G. P.; Johnson, B. R.; Halas, N. J. *Nano Letters* **2007**, in press.
35. Lee, J.; Govorov, A. O.; Kotov, N. A. *Angew. Chem. Int. Ed.* **2005**, 44, 7605-7608.
36. Govorov, A. O.; Zhang, W.; Skeini, T.; Richardson, H.; Lee, J.; Kotov, N. A. *Nanoscale Res. Lett.* **2006**, ASAP.

Figure 1.




Figure 2.




Figure 3.





Figure 4.



TOC image

