



AFRL-ML-WP-TP-2007-488

**SYNTHESIS AND NEAR-INFRARED LUMINESCENCE OF
A DEUTERATED CONJUGATED PORPHYRIN DIMER
FOR PROBING THE MECHANISM OF NON-RADIATIVE
DEACTIVATION (POSTPRINT)**

Joy E. Rogers and Paul A. Fleitz

**Hardened Materials Branch
Survivability and Sensor Materials Division**

FEBRUARY 2007

Approved for public release; distribution unlimited.

See additional restrictions described on inside pages

STINFO COPY

© 2007 The Royal Society of Chemistry

**AIR FORCE RESEARCH LABORATORY
MATERIALS AND MANUFACTURING DIRECTORATE
WRIGHT-PATTERSON AIR FORCE BASE, OH 45433-7750
AIR FORCE MATERIEL COMMAND
UNITED STATES AIR FORCE**

NOTICE AND SIGNATURE PAGE

Using Government drawings, specifications, or other data included in this document for any purpose other than Government procurement does not in any way obligate the U.S. Government. The fact that the Government formulated or supplied the drawings, specifications, or other data does not license the holder or any other person or corporation; or convey any rights or permission to manufacture, use, or sell any patented invention that may relate to them.

This report was cleared for public release by the Air Force Research Laboratory Wright Site (AFRL/WS) Public Affairs Office and is available to the general public, including foreign nationals. Copies may be obtained from the Defense Technical Information Center (DTIC) (<http://www.dtic.mil>).

AFRL-ML-WP-TP-2007-488 HAS BEEN REVIEWED AND IS APPROVED FOR PUBLICATION IN ACCORDANCE WITH ASSIGNED DISTRIBUTION STATEMENT.

**//Signature//*

PAUL A. FLEITZ, Ph.D.
Program Manager
Advanced Development
Hardened Materials Branch

//Signature//

MARK S. FORTE, Acting Chief
Hardened Materials Branch
Survivability and Sensor Materials Division

//Signature//

TIM J. SCHUMACHER, Chief
Survivability and Sensor Materials Division

This report is published in the interest of scientific and technical information exchange, and its publication does not constitute the Government's approval or disapproval of its ideas or findings.

Disseminated copies will show “//Signature//*” stamped or typed above the signature blocks.

REPORT DOCUMENTATION PAGE				Form Approved OMB No. 0704-0188	
The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.					
1. REPORT DATE (DD-MM-YY) February 2007		2. REPORT TYPE Journal Article Postprint		3. DATES COVERED (From - To)	
4. TITLE AND SUBTITLE SYNTHESIS AND NEAR-IR LUMINESCENCE OF A DEUTERATED CONJUGATED PORPHYRIN DIMER FOR PROBING THE MECHANISM OF NON-RADIATIVE DEACTIVATION (POSTPRINT)				5a. CONTRACT NUMBER In-house	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER 62102F	
6. AUTHOR(S) Joy E. Rogers and Paul A. Fleitz (AFRL/MLPJ) Michael J. Frampton and Harry L. Anderson (University of Oxford) Gianluca Accorsi and Nicola Armaroli (Istituto per la Sintesi Organica e la Fotoreattivita') Kenneth J. McEwan (Defence Science and Technology Laboratory)				5d. PROJECT NUMBER 4348	
				5e. TASK NUMBER RG	
				5f. WORK UNIT NUMBER M08R1000	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Hardened Materials Branch (AFRL/MLPJ) Survivability and Sensor Materials Division Materials and Manufacturing Directorate Wright-Patterson Air Force Base, OH 45433-7750 Air Force Materiel Command United States Air Force ----- University of Oxford, Department of Chemistry Chemistry Research Laboratory 12 Mansfield Road Oxford, UK OX1 3TA				8. PERFORMING ORGANIZATION REPORT NUMBER AFRL-ML-WP-TP-2007-488	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) Air Force Research Laboratory Materials and Manufacturing Directorate Wright-Patterson Air Force Base, OH 45433-7750 Air Force Materiel Command United States Air Force				10. SPONSORING/MONITORING AGENCY ACRONYM(S) AFRL/MLPJ	
				11. SPONSORING/MONITORING AGENCY REPORT NUMBER(S) AFRL-ML-WP-TP-2007-488	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution unlimited.					
13. SUPPLEMENTARY NOTES Journal article published in Organic & Biomolecular Chemistry. © 2007 The Royal Society of Chemistry. The U.S. Government is joint author of this work and has the right to use, modify, reproduce, release, perform, display, or disclose the work. PAO Case Number: AFRL/WS 07-0256, 06 Feb 2007. Paper contains color.					
14. ABSTRACT <i>β,meso,β</i> -Fused porphyrin oligomers have many attractive photophysical features such as strong absorption in the near-IR at wavelengths greater than 1000 nm, and high two-photon cross sections. However their ultrafast S ₁ -S ₀ deactivation ($k_d > 10^{11} \text{ s}^{-1}$) limits potential applications. We have synthesised a deuterated fused porphyrin dimer to test whether deuteration influences the rate of non-radiative deactivation. An efficient synthetic strategy was developed, starting with deuteration of dipyrromethane. Deuteration of the zinc porphyrin dimer does not affect its fluorescence quantum yield in CD ₂ Cl ₂ ($\Phi_{FD}/\Phi_{HI} = 1.00 \pm 0.05$). This implies that the ultrafast non-radiative deactivation is not simply a consequence of the small S ₁ -S ₀ energy gaps to the <i>β,meso,β</i> -fused porphyrin oligomers but with slower rates of S ₁ -S ₀ decay.					
15. SUBJECT TERMS Near-Infrared Light Emitting Diodes (DIR LEDs), Reverse-Saturable Absorption (RSA), Deuterated Conjugated Porphyrin Dimer					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT: SAR	18. NUMBER OF PAGES 12	19a. NAME OF RESPONSIBLE PERSON (Monitor) Paul A. Fleitz 19b. TELEPHONE NUMBER (Include Area Code) N/A
a. REPORT Unclassified	b. ABSTRACT Unclassified	c. THIS PAGE Unclassified			

Synthesis and near-infrared luminescence of a deuterated conjugated porphyrin dimer for probing the mechanism of non-radiative deactivation

Michael J. Frampton,^a Gianluca Accorsi,^b Nicola Armaroli,^{*b} Joy E. Rogers,^c Paul A. Fleitz,^c Kenneth J. McEwan^d and Harry L. Anderson^{*a}

Received 10th January 2007, Accepted 1st February 2007


First published as an Advance Article on the web 15th February 2007

DOI: 10.1039/b700408g

β ,*meso*, β -Fused porphyrin oligomers have many attractive photophysical features such as strong absorption in the near-IR at wavelengths greater than 1000 nm, and high two-photon cross sections. However their ultrafast S_1 - S_0 deactivation ($k_d > 10^{11} \text{ s}^{-1}$) limits potential applications. We have synthesised a deuterated fused porphyrin dimer to test whether deuteration influences the rate of non-radiative deactivation. An efficient synthetic strategy was developed, starting with deuteration of dipyrromethane. Deuteration of the zinc porphyrin dimer does not affect its fluorescence quantum yield in CD_2Cl_2 ($\Phi_D/\Phi_H = 1.00 \pm 0.05$). This implies that the ultrafast non-radiative deactivation is not simply a consequence of the small S_1 - S_0 energy gap. Comparison with other conjugated porphyrin oligomers confirms that the deactivation rate in the edge-fused oligomers is faster than would be expected from the energy gap law. This result indicates that it should be possible to create near-IR dyes with similar S_1 - S_0 energy gaps to the β ,*meso*, β -fused porphyrin oligomers but with slower rates of S_1 - S_0 decay.

Introduction

The synthesis of β ,*meso*, β -fused porphyrin dimers, such as **1a**, and longer tape-like oligomers of this type, pioneered by Osuka and coworkers,¹⁻⁵ is probably the most revolutionary development in the field of porphyrin chemistry during the last 10 years. The strong porphyrin-porphyrin π -conjugation in these oligomers shifts their absorption far into the infrared and results in strong two-photon absorption.⁶ For example dimer **1a** exhibits an absorption maximum at 1068 nm (in CHCl_3)^{1,2} and a two-photon cross-section of 14000 GM at 800 nm (in toluene);⁶ longer oligomers take this absorption to even longer wavelengths. The rate of S_1 - S_0 deactivation (k_d) is amazingly fast in these molecules, occurring in 4.5 ps in dimer **1a** (from transient absorption measurements).⁷⁻¹¹ Thus neither fluorescence nor S_1 - T_1 intersystem crossing compete with deactivation to the ground state, and fluorescence quantum yields are very low ($\Phi_f < 10^{-3}$).⁹ Accordingly, the overall rate of S_1 deactivation is dominated by the S_1 - S_0 internal conversion process ($k_d \approx k_{nr} \approx k_{ic}$, where k_{nr} and k_{ic} denote the rates of non-radiative and internal conversion processes, respectively).



The usefulness of these chromophores is limited by the negligible fluorescence quantum yield and triplet formation,⁹ precluding applications in near-infrared light emitting diodes (NIR LEDs) and fluorescence imaging or in reverse-saturable absorption (RSA).¹² The short S_1 lifetimes also preclude all applications involving photochemistry, such as photoinduced energy- and electron-transfer, photoinitiated polymerisation (e.g. for microfabrication)¹³ or photochromism (e.g. for optical data storage). We have shown that the attachment of heavy atoms to the periphery of the π -system accelerates intersystem crossing in

^aDepartment of Chemistry, Chemistry Research Laboratory, University of Oxford, 12 Mansfield Road, Oxford, UK OX1 3TA. E-mail: harry.anderson@chem.ox.ac.uk; Fax: +44 1865-28-5002; Tel: +44 1865 275744

^bMolecular Photoscience Group, Istituto per la Sintesi Organica e la Fotoreattività, Consiglio Nazionale delle Ricerche, Via Gobetti 101, 40129, Bologna, Italy. E-mail: armaroli@isof.cnr.it

^cAir Force Research Laboratory, AFRL/MLPJ, 3005 Hobson Way, Wright-Patterson Air Force Base, Dayton, Ohio, 45433-7702, USA

^dDefence Science and Technology Laboratory, St Andrews Road, Malvern, WR14 3PS, UK

1b and **1c**, bringing the triplet yield up to $\Phi_T = 0.2$ in **1c** and leading to substantial RSA in the spectral region 800–1000 nm ($\sigma_{ex}/\sigma_{gr} = 8.2$ at 870 nm).¹⁴ This work led to some promising NIR RSA materials, but there is still a strong motivation for learning to curtail the ultrafast deactivation of the lowest electronic singlet excited state (S_1) in these systems.

The ultrafast S_1 – S_0 decay in chromophores such as **1a–d** has generally been attributed^{7–10} to the energy gap law.^{15,16} In other words, it is assumed that in such rigid molecular systems the S_1 and S_0 states have very similar geometries so that their potential energy surfaces do not intersect (Fig. 1a) and that the overall deactivation rate (corresponding to k_{ic} , see above) is determined by the Frank–Condon factor, f_v , which in turn is determined by the S_1 – S_0 energy gap, ΔE , according to eqn (1) and (2):

$$k_{ic} = f_0 f_v \quad (1)$$

$$f_v = e^{-a\Delta E} \quad (2)$$

where f_0 is the maximum possible decay rate ($f_0 \approx 10^{13} \text{ s}^{-1}$ in most chromophores with C–H bonds) and a is a constant of proportionality. High frequency C–H stretch vibrations ($\nu \approx 3000 \text{ cm}^{-1}$) make a dominant contribution to the Frank–Condon factor, f_0 , so replacing C–H for C–D bonds ($\nu \approx 2200 \text{ cm}^{-1}$) generally reduces the rate of non-radiative deactivation.^{15–18} We





Fig. 1 Internal conversion (a) between matching adiabatic surfaces and (b) between intersecting surfaces.

decided to test this idea by synthesising a deuterated dimer *d*-**1a** and comparing its fluorescence quantum yield with that of **1a**. We intended only to deuterate the β -positions of **1a**, because these protons are closest to the π -system, but during the synthesis deuteration also occurred on the aryl substituents, mainly *para* to the porphyrin.

We found that deuteration has no effect on the fluorescence quantum yield, even in a deuterated solvent (CD_2Cl_2). This implies that the ultrafast internal conversion in **1a** is not simply a consequence of the energy gap law, but reflects the presence of a readily accessible intersection of the S_1 and S_0 surfaces (Fig. 1b). In the course of this work we have developed new chemistry for the synthesis of deuterated porphyrins, and to the best of our knowledge this is the first time that a deuterated porphyrin dimer has been synthesised.

Results and discussion

The deuterated fused dimer *d*-**1a** was synthesised as summarised in Scheme 1. There have been several reports of the synthesis of deuterated porphyrin derivatives,^{19–25} but no general methods have been developed for the direct perdeuteration of porphyrins. On the other hand, pyrrole is readily deuterated under acidic conditions.^{26,27} We decided to explore whether similar deuteration conditions could be applied to dipyrromethane **2**. This might appear to be a risky strategy, because dipyrromethane **2** readily undergoes decomposition and oligomerisation in acid, but we discovered that deuteration could be accomplished using a two-phase system, by stirring **2** with trifluoroacetic acid-*d* in a mixture of deuterium oxide and dichloromethane. These reaction conditions result in no detectable decomposition or oligomerisation, *d*-**2** was isolated in 73% yield and ^1H NMR analysis shows that the pyrrolic positions are deuterated to a level of >97%. No deuteration occurs at the central CH_2 . Condensation of *d*-**2** with 3,5-di-*tert*-butylbenzaldehyde in the presence of trifluoroacetic acid-*d* gave porphyrin *d*- H_2 -**3**. Deuterium enrichment of *d*- H_2 -**3** was slightly reduced to 91% on the pyrrolic positions, while enrichment to a



Scheme 1 Preparation of deuterated dimer *d*-**1a**. Ar = 3,5-di-*tert*-butylphenyl. (a) *d*-TFA, D_2O , CH_2Cl_2 , 73%; (b) i. 3,5-di-*tert*-butylbenzaldehyde, TFA, CH_2Cl_2 , ii. DDQ, 27%; (c) $\text{Ni}(\text{OAc})_2$, DMF, reflux, 94%; (d) i. 3,5-di-*tert*-butylphenyllithium, THF, 0°C to rt, D_2O , ii. DDQ, 65%; (e) i. D_2SO_4 , CH_2Cl_2 , ii. $\text{Zn}(\text{OAc})_2 \cdot 2\text{H}_2\text{O}$, MeOH, CH_2Cl_2 , 77%; (f) $\text{Sc}(\text{OTf})_3$, DDQ, PhMe, 32%.

degree of 33% was observed for the *meso*-hydrogens, suggesting scrambling of the hydrogens between these positions under the condensation conditions. Some overall reduction in the level of deuteration may have resulted from protic impurities in the dichloromethane reaction solvent, but the level of deuteration of the pyrrolic positions was sufficient for our purposes.

Metallation of *d*-H₂-3 with nickel(II) acetate yielded the nickel(II) porphyrin *d*-Ni-3. Treatment of *d*-Ni-3 with an excess of 3,5-di-*tert*-butylphenyllithium, using Senge's method,²⁸ followed by deuterium oxide work-up and oxidation gave nickel triarylporphyrin *d*-Ni-4. It is possible to perform the Senge arylation on the free base porphyrin *d*-H₂-3 instead of *d*-Ni-3, but in our hands arylation of the nickel complex was more reproducible. Demetallation was accomplished with sulfuric acid-*d*₂ and, without isolation of the free-base porphyrin, metallation to the zinc complex was achieved by neutralisation and stirring with zinc(II) acetate. Analysis of the zinc porphyrin *d*-Zn-4 by ¹H NMR indicated that further deuteration had occurred during treatment of *d*-Ni-4 with D₂SO₄. The unsubstituted porphyrinic *meso*-position was 96% deuterated, and deuteration was also evident on the 3,5-di-*tert*-butylphenyl substituents (Fig. 2). The deuteration of the aryl groups is highest *para* to the porphyrin ring and occurs without any loss or migration of the *tert*-butyl groups. Sulfuric acid-*d*₂ mediated deuterium exchange has been reported for aryl-substituents on porphyrins.²⁵ Oxidative dimerisation of *d*-Zn-4 was performed under the conditions described by Osuka,⁵ and after recrystallisation, dimer *d*-1a was isolated in 32% yield. The un-deuterated dimer **1a**, previously reported by Osuka,²⁵ was also prepared. The ¹H NMR spectra of dimers **1a** and *d*-1a, compared in Fig. 3, allow the level of deuteration in dimer *d*-1a to be quantified (Fig. 2). The β-pyrrolic positions on dimer *d*-1a were approximately 91% deuterium-enriched and the phenyl substituents were also partially deuterated. The level of




Fig. 2 Structures of *d*-2, *d*-Zn-4 and *d*-1a showing the levels of deuteration at selected positions, as determined by comparison of the ¹H NMR spectra with those of the un-deuterated analogues.




Fig. 3 ¹H NMR spectra for (a) dimer **1a** and (b) dimer *d*-1a (500 MHz in CDCl₃, containing a trace of *d*₅-pyridine). Assignment is included for the spectrum of **1a** (see Fig 2).

deuteration for dimer *d*-1, as deduced from NMR analysis, is consistent with analysis of the isotopic cluster for the molecular ion in the MALDI-TOF mass spectrum, shown in Fig 4.




Fig. 4 MALDI-TOF mass spectrum for deuterated dimer *d*-1a. The simulated spectrum is represented by the black squares, and was calculated allowing for deuteration of 93% at the β-pyrrole positions and 33% at the aryl substituents.

The absorption spectra for dimers **1a** and *d*-1a (Fig. 5) are completely superimposable, showing that, as expected, the electronic structure of the dimer is not affected by deuteration. The room temperature fluorescence spectra of dimers **1a** and *d*-1a, with excitation at 440 nm, are also shown in Fig. 5. These spectra were recorded in deuterated solvent (CD₂Cl₂) so as to exclude any effects due to solvent C–H vibrations. The emission spectra were recorded for isoabsorbing solutions of the dimers and are not normalised, so they directly show that deuteration has no effect on the fluorescence quantum yield: $\Phi_{\text{D}}/\Phi_{\text{H}} = 1.00 \pm 0.05$.

If the ultrafast S₁ decay in this system were simply a consequence of the energy gap law [eqn (2)] then one would expect the Frank-Condon factor to be dominated by C–H vibrations.^{15–17} Thus it seems likely that the ultrafast internal conversion in **1a** results from the availability of a specific deactivation pathway, such as




Fig. 5 UV-visible-nearIR absorption (solid lines) and luminescence spectra (dashed lines, isoabsorbing solutions, $\lambda_{\text{ex}} = 440$ nm) for **1a** (red) and **d-1a** (black) in CD_2Cl_2 at 298 K. The lowest energy absorption and highest energy emission peaks occur at 1185 nm and 1210 nm respectively.

an accessible intersection of the S_1 and S_0 surfaces, *via* a reaction coordinate involving the lower energy vibration of the C–C and C–N double bonds within the molecular framework (Fig. 1b).

Our conclusion that S_1 deactivation in **1a** is faster than can be accounted for by the energy gap law is supported by comparison with other related NIR chromophores. For example Therien and coworkers²⁹ have reported an alkyne-linked conjugated porphyrin pentamer exhibiting S_1 – S_0 emission at 883 nm ($\Delta E = 135$ kJ mol⁻¹) with a fluorescence quantum yield of $\Phi_f = 0.14$ and a natural radiative lifetime of $\tau_0 = 3.56$ ns, so an upper limit to the rate of non-radiative deactivation in this chromophore (assuming $k_{\text{isc}} = 0$) is $k_{\text{nr}} = (1/\Phi_f - 1)/\tau_0 = 1.7 \times 10^9$ s⁻¹. According to eqn (2), with $f_0 = 10^{13}$ s⁻¹, this implies that $\alpha = 0.064$ kJ⁻¹ mol. Dimer **1a** exhibits S_1 – S_0 emission at 1100 nm ($\Delta E = 109$ kJ mol⁻¹) so the energy gap law predicts that it should have a non-radiative rate constant $k_{\text{nr}} \approx k_{\text{isc}} = 9.3 \times 10^9$ s⁻¹, which is about 20 times less than the experimental value of $k_{\text{nr}} \approx 2.2 \times 10^{11}$ s⁻¹ (calculated from the singlet lifetime of 4.5 ps with $k_f \ll k_{\text{nr}}$ and thus negligible).

While dimers **1a–d** exhibit exceptionally short S_1 lifetimes, their T_1 lifetimes seem to be fairly normal. Although the T_1 – S_0 energy gaps must be very small (less than the S_1 – S_0 gaps) this does not result in exceptionally rapid T_1 – S_0 intersystem crossing. Previously we reported that **1b** and **1c** have triplet lifetimes of 280 ns and 52 ns respectively (in oxygen-free benzene containing 1% pyridine).¹⁴ The very low triplet yields of **1a** and **1d** make it difficult to measure their triplet lifetimes, but in the case of **1d** we were able to measure a triplet lifetime of 177 ± 25 μs (in O_2 -free benzene with 1% pyridine). We also measured the triplet lifetime of **1d** by generating the triplet by energy transfer from the triplet state of tetraphenylporphyrin, giving a lifetime of 6.8 μs for the T_1 state of **1d** (in aerated dichloromethane with 1% pyridine). The heavy atoms reduce the triplet lifetime in **1b** and **1c**, and the triplet lifetime of **1d** is sensitive to the presence of oxygen, as expected, but in general the T_1 lifetime of these systems are normal, despite the small T_1 – S_0 gap, providing another indication that the ultrafast S_1 – S_0 decay is not simply a result of the small S_1 – S_0 energy gap.

Conclusions

We have prepared a deuterated fused porphyrin dimer **d-1a** *via* deuteration of the dipyrromethane **2**. Its fluorescence quantum

yield is completely unaffected by the deuteration ($\Phi_{\text{D}}/\Phi_{\text{H}} = 1.00 \pm 0.05$), demonstrating that C–H vibrations do not contribute to radiationless deactivation (*i.e.* internal conversion). This result suggests that a specific deactivation pathway is active *via* an accessible intersection of the S_1 and S_0 surfaces. The initial motivation for this study was to synthesise a fused porphyrin dimer with retarded internal conversion, and consequently improved triplet yield, for RSA applications.¹² Although we have not achieved this objective, our results indicate that it should be possible to create near-IR dyes with similar S_1 – S_0 energy gaps to the β ,*meso*, β -fused porphyrin oligomers but with slower rates of S_1 – S_0 internal conversion, for instance by making an even more rigid molecular framework.

Experimental

NMR spectra were recorded on Bruker DPX250 or DPX400 instruments or AV500 with cryprobe. MALDI-TOF mass spectra were acquired by the EPSRC Mass Spectrometry Service, Swansea, UK from a *trans*-2-[3-(4-*tert*-butylphenyl)-2-methylprop-2-enylidene]malononitrile (DCTB) matrix. Vis-NIR absorption spectra were recorded on a Perkin-Elmer Lambda 20 or Lambda 9 spectrometer. NIR fluorescence spectra of dimers **1** and **d-1** were recorded on an Edinburgh FLS920 spectrometer equipped with a Hamamatsu R5509-72 supercooled PMT (193 K) described earlier.³⁰ Bis(1*H*-pyrrol-2-yl)methane **2** and 3,5-di-*tert*-butylbromobenzene were prepared by literature methods.^{31,32}

Preparation of **d-2**

Nitrogen was bubbled through a mixture of bis(1*H*-pyrrol-2-yl)methane **2** (2.00 g, 13.7 mmol), deuterium oxide (20 mL) and dichloromethane (200 mL). Trifluoroacetic acid-*d* (200 μL) was added and the mixture stirred vigorously at room temperature for 18 h. Anhydrous sodium carbonate was added to neutralise the aqueous layer and the organic layer was separated, dried over anhydrous magnesium sulfate and evaporated. This entire process was repeated twice, and the resultant product purified by bulb-to-bulb distillation under vacuum to give **d-2** as a white solid. Yield (1.54 g, 73%), mp 72–73 °C (lit.³¹ 75 °C for **2**) ¹H NMR (200 MHz, CDCl_3 ; Me_4Si): δ_{H} , ppm 3.97 (2 H, s, CH_2), 6.04 (2 H, s, 97.5% ²H), 6.12 (2 H, s, 98.5% ²H), 6.62 (2 H, s, 97.5% ²H), 7.64 (2 H, s, 97.5% ²H). ²H NMR (38.4 MHz, CHCl_3 ; Me_4Si) 6.14 (2 ²H, s), 6.26 (2 ²H, s), 6.68 (2 ²H, s), 6.67 (2 ²H, s, N-²H). ¹³C NMR (62.9 MHz, CDCl_3 ; Me_4Si) 26.1, 106.1 (t), 107.7 (t), 116.8 (t), 128.7. MS (FI⁺): m/z 154.1341 (calcd. for $[\text{C}_9\text{H}_2\text{D}_8\text{N}_2]^+$ 154.1346).

Preparation of **d-H₂-3**

Nitrogen gas was bubbled through a solution of **d-2** (1.25 g, 8.11 mmol) and 3,5-di-*tert*-butylbenzaldehyde (1.80 g, 8.11 mmol) in dichloromethane (1600 mL). Trifluoroacetic acid-*d* (0.19 mL, 2.4 mmol) was added and the solution stirred at room temperature for 3 h. DDQ (2.36 g, 10.4 mmol) was added and the mixture stirred for 10 min before being neutralised by the addition of sodium bicarbonate (3 g). The mixture was filtered through a plug of silica, eluting with dichloromethane, the solvent removed and the residue recrystallised from dichloromethane by layered addition of methanol to give **d-H₂-3** as purple needles. Yield 770 mg (27%), ¹H NMR (500 MHz, CDCl_3 ; Me_4Si): –2.95 (2 H, s, N-H), 1.64

(36 H, s, *t*-butyl), 7.91 (2 H, t, phenyl 4-H), 8.22 (4 H, d, phenyl 2,6-H), 9.20 (4 H, s, pyrrole-H, 91% ²H), 9.45 (4 H, s, pyrrole-H, 91% ²H), 10.36 (2 H, s, *meso*-H, 33% ²H). MS (MALDI-TOF⁺): *m/z* 694.4 (calcd. for [C₄₈H₄₆D₈N₄]⁺ 694.5).

Preparation of *d*-Ni-3

A suspension of *d*-H₂-3 (650 mg, 0.935 mol), nickel(II) acetate (2.33 g, 9.35 mmol) and *N,N*-dimethylformamide (60 mL) was heated to reflux for 2 h. The solvent was removed under vacuum and the residue passed through a plug of silica eluting with dichloromethane. Recrystallisation from dichloromethane by layered addition of methanol gave *d*-Ni-3 as burgundy needles. Yield 660 mg (94%), ¹H NMR (400 MHz, CDCl₃; Me₄Si): 1.55 (36 H, s, *t*-butyl), 7.82 (2 H, t, phenyl 4-H), 7.98 (4 H, d, phenyl 2,6-H), 9.07 (4 H, s, pyrrole-H, 91% ²H), 9.23 (4 H, s, pyrrole-H, 91% ²H), 9.93 (2 H, s, *meso*-H, 33% ²H). MS (ESI⁺): *m/z* 751.4 (calcd. for [C₄₈H₄₄D₈NiN₄ + H]⁺ 751.4).

Preparation of *d*-Ni-4

A solution of 1-bromo-3,5-di-*tert*-butylbenzene (1.18 g, 4.39 mmol) in THF (15 mL) was cooled to -78 °C and *n*-butyllithium (1.6 M in hexanes, 2.50 mL, 4.0 mmol) was added. The solution was stirred at -78 °C for 1 h, then transferred via syringe into a solution of *d*-Ni-3 (300 mg, 0.399 mmol) in THF (15 mL) at 0 °C and the solution allowed to warm to room temperature with stirring for 1 h, to give a green solution. A mixture of D₂O and THF (1 mL : 4 mL) was added and the mixture poured into a rapidly stirred solution of DDQ (362 mg, 1.60 mmol) in dichloromethane (200 mL). The mixture was filtered through a plug of silica, eluting with dichloromethane. The solvent was removed and the residue purified by column chromatography over silica, using ethyl acetate–light petroleum (bp 40–60 °C) (1 : 20) as eluent. Recrystallisation from dichloromethane by layered addition of methanol gave *d*-Ni-4 as purple needles. Yield 242 mg (65%), ¹H NMR (400 MHz, CDCl₃; Me₄Si): 1.49 (18 H, s, *t*-butyl), 1.51 (36 H, s, *t*-butyl), 7.73 (1 H, t, phenyl 4-H), 7.76 (2 H, t, phenyl 4-H), 7.90 (2 H, d, phenyl 2,6-H), 7.93 (4 H, d, phenyl 2,6-H), 8.86 (2 H, s, pyrrole-H, 91% ²H), 8.87 (2 H, s, pyrrole-H, 91% ²H), 8.96 (2 H, s, pyrrole-H, 91% ²H), 9.15 (2 H, s, pyrrole-H, 90% ²H), 9.85 (2 H, s, *meso*-H, 42% ²H). MS (ESI⁺): *m/z* 938.6 (calcd. for [C₆₂H₆₄D₈N₄Ni]⁺ 938.6).

Preparation of *d*-Zn-4

Sulfuric acid-*d*₂ (0.5 mL) was added to a solution of *d*-Ni-4 (200 mg, 0.213 mmol) in dichloromethane (25 mL) and the mixture stirred at room temperature for 5 min to give a green solution. The solution was washed with water (25 mL) and aqueous sodium hydroxide (2 M, 25 mL). A solution of zinc acetate dihydrate (195 mg, 1.06 mmol) in methanol (2 mL) was added and the mixture heated to reflux for 5 min, then filtered through a short plug of silica, eluting with dichloromethane. Recrystallisation from dichloromethane by layered addition of methanol gave *d*-Zn-4 as purple needles. Yield 156 mg (77%), ¹H NMR (400 MHz, CDCl₃; Me₄Si): 1.52 (18 H, s, *t*-butyl), 1.56 (36 H, s, *t*-butyl), 7.77 (1 H, t, phenyl 4-H, 60% ²H), 7.79 (2 H, t, phenyl 4-H, 90% ²H), 8.07 (2 H, d, phenyl 2,6-H, 10% ²H), 8.10 (4 H, d, phenyl 2,6-H, 36% ²H), 8.96 (2 H, s, pyrrole-H, 91% ²H), 8.98 (2 H, s, pyrrole-H,

91% ²H), 9.07 (2 H, s, pyrrole-H, 91% ²H), 9.33 (2 H, s, pyrrole-H, 91% ²H), 10.13 (2 H, s, *meso*-H, 96% ²H). MS (ESI⁺): *m/z* 949.6 (calcd. for [C₆₂H₅₉D₁₃N₄Zn]⁺ 949.6).

Preparation of dimer *d*-1a

A mixture of *d*-Zn-4 (50 mg, 53 μmol), scandium(III) triflate (130 mg, 264 μmol), DDQ (60.0 mg, 264 μmol) and toluene (50 mL) was stirred at 50 °C for 1 h. The colour darkened to dark purple. Once cool, the solution was washed with water (50 mL) and the organic layer separated and filtered through a plug of silica, eluting with dichloromethane–pyridine (1 : 0 to 100 : 1) and the solvent removed. The residue was purified by column chromatography over silica, eluting with light-petroleum (bp 40–60)–ethyl acetate–pyridine (10 : 1 : 1). Recrystallisation from a toluene–ethanol mixture gave dimer *d*-1a as a black solid. Yield 16 mg (32%) ¹H NMR (500 MHz, CDCl₃; Me₄Si): 1.42 (36 H, s, *t*-butyl), 1.46 (72 H, s, *t*-butyl), 7.36 (4 H, s, pyrrole-H, 91% ²H), 7.60 (2 H, t, phenyl 4-H, 61% ²H), 7.63 (4 H, t, phenyl 4-H, 93% ²H), 7.64 (4 H, s, phenyl 2,6-H, 10% ²H), 7.68 (8 H, s, phenyl 2,6-H, 30% ²H), 7.71 (4 H, s, pyrrole-H, 91% ²H), 7.76 (4 H, s, pyrrole-H, 91% ²H). MS (MALDI-TOF⁺): *m/z* 1888.2 (calcd. for [C₁₂₄H₁₂₁D₁₇N₈Zn₂]⁺ 1888.1).

Acknowledgements

We thank the EPSRC, EOARD, CNR (commessa PM-P04-ISTM-C1-ISOF-M5) and DSTL for financial support, and the EPSRC Mass Spectrometry Service (Swansea) for mass spectra.

References

- 1 A. Tsuda, A. Nakano, H. Furuta and A. Osuka, *Angew. Chem., Int. Ed.*, 2000, **39**, 2549–2552.
- 2 A. Tsuda, H. Furuta and A. Osuka, *J. Am. Chem. Soc.*, 2001, **123**, 10304–10321.
- 3 A. Tsuda and A. Osuka, *Science*, 2001, **293**, 79–82.
- 4 A. Tsuda and A. Osuka, *Adv. Mater.*, 2002, **14**, 75–79.
- 5 M. Kamo, A. Tsuda, Y. Nakamura, N. Aratani, K. Furukawa, T. Kato and A. Osuka, *Org. Lett.*, 2003, **5**, 2079–2082.
- 6 D. Y. Kim, T. K. Alm, J. H. Kwon, D. Kim, T. Ikeue, N. Aratani, A. Osuka, M. Shigeiwa and S. Maeda, *J. Phys. Chem. A*, 2005, **109**, 2996–2999.
- 7 H. S. Cho, D. H. Jeong, S. Cho, D. Kim, Y. Matsuzaki, K. Tanaka, A. Tsuda and A. Osuka, *J. Am. Chem. Soc.*, 2002, **124**, 14642–14654.
- 8 T. Miyahara, H. Nakatsuji, J. Hasegawa, A. Osuka, N. Aratani and A. Tsuda, *J. Chem. Phys.*, 2002, **117**, 11196–11207.
- 9 D. Bonifazi, M. Scholl, F. Song, L. Echegoyen, G. Accorsi, N. Armaroli and F. Diederich, *Angew. Chem., Int. Ed.*, 2003, **42**, 4966–4970.
- 10 D. Kim and A. Osuka, *J. Phys. Chem. A*, 2003, **107**, 8791–8816.
- 11 D. Bonifazi, G. Accorsi, N. Armaroli, F. Song, A. Palkar, L. Echegoyen, M. Scholl, P. Seiler, B. Jaun and F. Diederich, *Helv. Chim. Acta*, 2005, **88**, 1839–1884.
- 12 M. Calvete, G. Y. Yang and M. Hanack, *Synth. Met.*, 2004, **141**, 231–243.
- 13 K.-S. Lee, D.-Y. Yang, S. H. Park and R. H. Kim, *Polym. Adv. Technol.*, 2006, **17**, 72–82.
- 14 K. J. McEwan, P. A. Fleitz, J. E. Rogers, J. E. Slagle, G. D. McLean, H. Akdas, M. Katterle and H. L. Anderson, *Adv. Mater.*, 2004, **16**, 1933–1935.
- 15 W. Siebrand and D. F. Williams, *J. Chem. Phys.*, 1968, **49**, 1860–1871.
- 16 J. B. Birks, *Photophysics of Aromatic Molecules*, Wiley, New York, 1970.
- 17 N. J. Turo, *Modern Molecular Photochemistry*, University Science, Sausalito, 1991.
- 18 C. Dosche, M. U. Kumke, H.-G. Lömannsröben, F. Ariese, A. N. Bader, C. Gooijer, O. S. Milanic, M. Iwamoto, K. P. C. Vollhardt, R. Puchta

- and N. J. R. van Eikema Hommes, *Phys. Chem. Chem. Phys.*, 2004, **6**, 5476–5483.
- 19 K. N. Solovev, V. N. Knyukshto, M. P. Tsvirko and A. T. Gradyushko, *Opt. Spectrosc.*, 1976, **41**, 569–573.
- 20 M. J. Crossley, J. J. Gosper and M. G. Wilson, *J. Chem. Soc., Chem. Commun.*, 1985, 1798–1799.
- 21 K. M. Smith, K. C. Langry and J. S. de Roff, *J. Chem. Soc., Chem. Commun.*, 1979, 1001–1003.
- 22 K. M. Smith and K. C. Langry, *J. Chem. Soc., Perkin Trans. 1*, 1983, 439–444.
- 23 J. T. Groves, R. Quinn, T. J. McMurry, M. Nakamura, G. Lang and B. Boso, *J. Am. Chem. Soc.*, 1985, **107**, 354–360.
- 24 R. Grigg, J. Trocha-Grimshaw and L. Waring, *J. Chem. Soc., Chem. Commun.*, 1979, 557–559.
- 25 Z. Gross and L. Kaustov, *Tetrahedron Lett.*, 1995, **36**, 3735–3736.
- 26 F. A. Miller, *J. Am. Chem. Soc.*, 1942, **64**, 1543–1544.
- 27 G. R. Mitchell, F. J. Davis, R. Cywinski and W. S. Howells, *J. Phys. C: Solid State Phys.*, 1988, **21**, L411–L416.
- 28 M. O. Senge and X. Feng, *J. Chem. Soc., Perkin Trans. 1*, 2000, 3615–3621.
- 29 T. V. Duncan, K. Susumu, L. E. Sinks and M. J. Therien, *J. Am. Chem. Soc.*, 2006, **128**, 9000–9001.
- 30 N. Armadori, G. Accorsi, F. Song, A. Palkar, L. Echegoyen, D. Bonifazi and F. Diederich, *ChemPhysChem*, 2005, **6**, 732–743.
- 31 B. J. Littler, M. A. Miller, C.-H. Hung, R. W. Wagner, D. F. O'Shea, P. D. Boyle and J. S. Lindsey, *J. Org. Chem.*, 1999, **64**, 1391–1396.
- 32 C. M. D. Komen and F. Bickelhaupt, *Synth. Commun.*, 1996, **26**, 1693–1697.