

Report Documentation Page				Form Approved OMB No. 0704-0188	
Public reporting burden for the collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to a penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.					
1. REPORT DATE 17 JAN 2007		2. REPORT TYPE Technical, Success Story		3. DATES COVERED 12-08-2006 to 17-01-2007	
4. TITLE AND SUBTITLE Intelligent Machining Optimization				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S)				5d. PROJECT NUMBER 07-0147-07	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) National Center for Defense Manufacturing & Machining,1600 Technology Way,Latrobe,PA,15650				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)				10. SPONSOR/MONITOR'S ACRONYM(S)	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution unlimited					
13. SUPPLEMENTARY NOTES					
14. ABSTRACT The selection of machining parameters for cutting tool / material combinations is generally based on experience or static databases. In general, these parameters tend to cause the cutting tool and the machine tool to be grossly under utilized. The National Center for Defense Manufacturing and Machining (NCDMM), in conjunction with TechSolve Cincinnati, OH, and General Dynamics Land Systems (GDLS), Lima, OH, have worked together to optimize the machining parameters of three (3) materials chosen by GDLS. These materials are Titanium 6-4, Steel Mil-A-12560, and Aluminum 2519. The optimization database developed by TechSolve, through the efforts of this project, will potentially provide GDLS with a 3-fold increase in machining performance for the M1 tank and other related components.					
15. SUBJECT TERMS Success Stories; The National Center for Defense Manufacturing and Machining; NCDMM; TechSolve; General Dynamics Land Systems; Titanium 6-4; Steel Mil-A-12560; Aluminum 2519					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT 1	18. NUMBER OF PAGES 1	19a. NAME OF RESPONSIBLE PERSON
a. REPORT unclassified	b. ABSTRACT unclassified	c. THIS PAGE unclassified			



Intelligent Machining Optimization

NCDMM Project No. 07-0147-07

Success
Story

PROBLEM / OBJECTIVE

The selection of machining parameters for cutting tool / material combinations is generally based on experience or static databases. In general, these parameters tend to cause the cutting tool and the machine tool to be grossly under utilized. The National Center for Defense Manufacturing and Machining (NCDMM), in conjunction with TechSolve, Cincinnati, OH, and General Dynamics Land Systems (GDLS), Lima, OH, have worked together to optimize the machining parameters of three (3) materials chosen by GDLS. These materials are Titanium 6-4, Steel Mil-A-12560, and Aluminum 2519. The optimization database developed by TechSolve, through the efforts of this project, will potentially provide GDLS with a 3-fold increase in machining performance for the M1 tank and other related components. In addition, these "optimum" machining parameters will provide the best tool-life, surface finish, material removal rate (MRR), and generate minimal cutting forces. This optimization will be accomplished through a series of detailed design of experiments (DOE) developed by TechSolve and carried out by the NCDMM. The machining operations to be evaluated are face milling, end milling, and drilling utilizing specific Kennametal Inc. tooling.

ACCOMPLISHMENTS / PAYOFF

Process Improvement

To find the optimum machining parameters of the three (3) materials, the NCDMM performed sixty (60) DOE's varying multiple parameters throughout the machining trials. The parameters varied for face milling and end milling were feedrate (IPM), rotational speed (RPM), axial depth of cut (ADOC), and radial depth of cut (RDOC), and the parameters varied for drilling were feedrate (IPM) and rotational speed (RPM). Data collected while performing the non tool-life DOE's were surface finish (R_a - μ in), axial and radial cutting forces (F_x -lbf, F_y -lbf), and thrust (F_z -lbf) for face milling and end milling, and thrust (F_z -lbf) and torque (M_o -in-lbf) for drilling. In addition, tool-life testing was also performed. Tool wear (in) was measured and recorded every two (2) minutes for sixty (60) minutes, or until a tool end of life criteria of 0.020" maximum wear was reached. Utilizing the data collected while performing the aforementioned DOE's, and based on TechSolve's Machining Optimization Engine, customized machining optimization software will be developed

and implemented at GDLS. By doing so, machine operators will be achieving optimum machining performance. Figure #1 illustrates the most favorable results observed throughout the project. Figure #2 is a representation of Titanium 6-4 DOE.

Table #1							
Operation	Material	IPM*	RPM*	ADOC* (in.)	RDOC* (in.)	# Holes	Duration (Min)
Drilling	Ti 6-4	2.28	380	N/A	N/A	91	60
Face Milling	Ti 6-4	2.4	100	0.04	0.05	N/A	60
End Milling	Ti 6-4	6.0	2500	0.20	.0125	N/A	60
No Favorable Results Observed - Severe Chipping Throughout Trials							
Drilling	St 12560	19.2	1600	0.10	0.5	N/A	60
Face Milling	St 12560	12	3000	0.05	0.5	N/A	60
End Milling	St 12560						
Drilling	Al 2519	Tool-Life Testing Not Required					
Face Milling	Al 2519						
End Milling	Al 2519						

Figure #1: Tool-Life DOE Machining Trials Most Favorable Results




Figure #2: Completed Drilling DOE of Ti 6-4

Expected Benefits

By implementing the resulting data into Techsolve's Intelligent Optimization Engine, TechSolve expects GDLS to experience a 3X increase in productivity over corresponding machining data handbook cutting parameters.

TIME LINE / MILESTONE

Start Date..... August 06
End DateJanuary 07

PROJECT FUNDING

NCDMM Funding.....\$35K

PARTICIPANTS

Kennametal Inc.
TechSolve