

REPORT DOCUMENTATION PAGE			Form Approved OMB NO. 0704-0188		
The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA, 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.					
1. REPORT DATE (DD-MM-YYYY) 01-10-2008		2. REPORT TYPE Final Report		3. DATES COVERED (From - To) 1-Jun-2006 - 31-May-2008	
4. TITLE AND SUBTITLE Epitaxial Engineering of Curie Temperature in Digital Ferromagnetic Heterostructures: Final Report Extrinsic Substrate Orientation Dependence of Ferromagnetism in (Ga,Mn)As Digital Ferromagnetic Heterostructures				5a. CONTRACT NUMBER W911NF-06-1-0207	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER 7D10AB	
				5d. PROJECT NUMBER	
				5e. TASK NUMBER	
6. AUTHORS Nitin Samarth, Peter Schiffer				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAMES AND ADDRESSES Pennsylvania State University Office of Sponsored Programs The Pennsylvania State University University Park, PA 16802 -				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) U.S. Army Research Office P.O. Box 12211 Research Triangle Park, NC 27709-2211				10. SPONSOR/MONITOR'S ACRONYM(S) ARO	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S) 50960-PH-DRP.1	
12. DISTRIBUTION AVAILABILITY STATEMENT Approved for Public Release; Distribution Unlimited					
13. SUPPLEMENTARY NOTES The views, opinions and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy or decision, unless so designated by other documentation.					
14. ABSTRACT We describe the structural and magnetic properties of digital ferromagnetic heterostructures of (Ga,Mn)As grown on (001), (311), (201) and (110) GaAs surfaces. Our measurements show a systematic variation of the Curie temperature with epitaxial orientation for samples with a nominally identical structure. Control measurements of randomly alloyed (Ga,Mn)As grown on these substrates show identical trends in Curie temperature, suggesting that the substrate orientation plays a strong role in the formation of hole-compensating defects in this ferromagnetic semiconductor.					
15. SUBJECT TERMS Molecular beam epitaxy, ferromagnetic semiconductor, Curie temperature					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT SAR		15. NUMBER OF PAGES
a. REPORT U	b. ABSTRACT U	c. THIS PAGE U			
			19a. NAME OF RESPONSIBLE PERSON Nitin Samarth		19b. TELEPHONE NUMBER 814-863-0136

ABSTRACT

We describe the structural and magnetic properties of digital ferromagnetic heterostructures of (Ga,Mn)As grown on (001), (311), (201) and (110) GaAs surfaces. Our measurements show a systematic variation of the Curie temperature with epitaxial orientation for samples with a nominally identical structure. Control measurements of randomly alloyed (Ga,Mn)As grown on these substrates show identical trends in Curie temperature, suggesting that the substrate orientation plays a strong role in the formation of hole-compensating defects in this ferromagnetic semiconductor.

List of papers submitted or published that acknowledge ARO support during this reporting period. List the papers, including journal references, in the following categories:

(a) Papers published in peer-reviewed journals (N/A for none)

Number of Papers published in peer-reviewed journals: 0.00

(b) Papers published in non-peer-reviewed journals or in conference proceedings (N/A for none)

Number of Papers published in non peer-reviewed journals: 0.00

(c) Presentations

"Epitaxial engineering of ferromagnetism in (GaAs)/(Ga,Mn)As digital superlattices," M.J. WILSON, G. XIANG, B.L. SHEU, P. SCHIFFER, N. SAMARTH, March meeting of the American Physical Society, 2008.

"Controlling Spins in Semiconductor Devices," N. Samarth, 14th International Workshop on Physics of Semiconductor Devices: Plenary Talk, 12/18/2007 Indian Institute of Technology, Mumbai India.

"Substrate Orientation Dependence of Ferromagnetism in Ferromagnetic Semiconductor Superlattices," N. Samarth, DARPA Workshop on Predicting Real Optimized Materials, Tucson AZ, November 2007.

"Spin Control in Magnetic Semiconductor Heterostructures," N. Samarth, WUN International Workshop on Spintronics, Youk, United Kingdom, August 2007.

"Ferromagnetic Semiconductors: An Overview," N. Samarth, School on Spintronics & Quantum Information, SpinTech IV, Maui, Hawaii, June 2007.

Number of Presentations: 5.00

Non Peer-Reviewed Conference Proceeding publications (other than abstracts):

Number of Non Peer-Reviewed Conference Proceeding publications (other than abstracts): 0

Peer-Reviewed Conference Proceeding publications (other than abstracts):

Number of Peer-Reviewed Conference Proceeding publications (other than abstracts): 0

(d) Manuscripts

"Extrinsic Substrate Orientation Dependence of Ferromagnetism in (Ga,Mn)As Digital Ferromagnetic Heterostructures," M. J. Wilson, G.Xiang, B.L. Sheu, P. Schiffer, N. Samarth, S. May, A. Bhattacharya (submitted to Applied Physics Letters)

Number of Manuscripts: 1.00

Number of Inventions:

Graduate Students

<u>NAME</u>	<u>PERCENT SUPPORTED</u>
Mark Wilson	1.00
Ben Li Sheu	0.25
FTE Equivalent:	1.25
Total Number:	2

Names of Post Doctorates

<u>NAME</u>	<u>PERCENT SUPPORTED</u>
Gang Xiang	1.00
FTE Equivalent:	1.00
Total Number:	1

Names of Faculty Supported

<u>NAME</u>	<u>PERCENT SUPPORTED</u>	National Academy Member
Nitin Samarth	0.25	No
Peter Schiffer	0.25	No
FTE Equivalent:	0.50	
Total Number:	2	

Names of Under Graduate students supported

<u>NAME</u>	<u>PERCENT SUPPORTED</u>
FTE Equivalent:	
Total Number:	

Student Metrics

This section only applies to graduating undergraduates supported by this agreement in this reporting period

- The number of undergraduates funded by this agreement who graduated during this period: 0.00
- The number of undergraduates funded by this agreement who graduated during this period with a degree in science, mathematics, engineering, or technology fields:..... 0.00
- The number of undergraduates funded by your agreement who graduated during this period and will continue to pursue a graduate or Ph.D. degree in science, mathematics, engineering, or technology fields:..... 0.00
- Number of graduating undergraduates who achieved a 3.5 GPA to 4.0 (4.0 max scale):..... 0.00
- Number of graduating undergraduates funded by a DoD funded Center of Excellence grant for Education, Research and Engineering: 0.00
- The number of undergraduates funded by your agreement who graduated during this period and intend to work for the Department of Defense 0.00
- The number of undergraduates funded by your agreement who graduated during this period and will receive scholarships or fellowships for further studies in science, mathematics, engineering or technology fields: 0.00

Names of Personnel receiving masters degrees

<u>NAME</u>
Total Number:

Names of personnel receiving PHDs

<u>NAME</u>
Total Number:

Names of other research staff

<u>NAME</u>	<u>PERCENT SUPPORTED</u>
FTE Equivalent:	
Total Number:	

Sub Contractors (DD882)

Inventions (DD882)

Extrinsic Substrate Orientation Dependence of Ferromagnetism in (Ga,Mn)As Digital Ferromagnetic Heterostructures.

M. J. Wilson, G. Xiang, B. L. Sheu, P. Schiffer, and N. Samarth*

Dept. of Physics and Materials Research Institute,

The Pennsylvania State University, University Park PA 16802

S. May and A. Bhattacharya

Materials Science Division and Argonne National Laboratory, Argonne, Illinois 60439, USA

Abstract

We describe the structural and magnetic properties of digital ferromagnetic heterostructures of (Ga,Mn)As grown on (001), (311), (201) and (110) GaAs surfaces. Our measurements show a systematic variation of the Curie temperature with epitaxial orientation for samples with a nominally identical structure. Control measurements of randomly alloyed (Ga,Mn)As grown on these substrates show identical trends in Curie temperature, suggesting that the substrate orientation plays a strong role in the formation of hole-compensating defects in this ferromagnetic semiconductor.

PACS numbers: 75.50 Pp, 75.75.+a, 81.16.-c

The “canonical” ferromagnetic semiconductor $\text{Ga}_{1-x}\text{Mn}_x\text{As}$ has been the focal point of research in semiconductor spintronics for reasons of fundamental interest and for proof-of-concept device applications.[1] Thus far, the Curie temperature (T_C) in $\text{Ga}_{1-x}\text{Mn}_x\text{As}$ has been limited to below ~ 190 K, presumably constrained by hole-compensating defects and limits on the incorporation of substitutional Mn. Within the mean field Zener model, the path to higher values of T_C requires increasing the substitutional Mn concentration, while minimizing the defect concentration.[2] Alternative theoretical viewpoints have proposed a different route to enhancing T_C by controlling the geometrical arrangement of Mn atoms within the $\text{Ga}_{1-x}\text{Mn}_x\text{As}$ lattice. In particular, a first-principles combinatorial calculation[3] has predicted large and systematic variations in T_C for $(\text{GaAs})_m(\text{MnAs})_1$ short period superlattices – or “digital ferromagnetic heterostructures” (DFHs)[4] – grown along different epitaxy directions. In particular, this calculation predicts that DFHs grown on (201) substrates, a previously unexplored orientation, would lead to higher T_C than both random alloy samples and DFHs grown on any other substrate orientation. The predicted dependence of T_C on substrate orientation has its origins in the highly anisotropic nature of the Mn-Mn exchange interaction, as revealed by multiband tight-binding[5] and first principles calculations,[6] as well as by scanning tunneling spectroscopy.[7] The expected variation of T_C with substrate orientation provides an opportunity for unambiguous experimental tests of first principles calculations and is a strong motivation for the systematic experimental exploration of the growth of DFHs on different substrate orientations.

In this Letter, we present a comprehensive study of the structural and magnetic properties of $\text{Ga}_{1-x}\text{Mn}_x\text{As}$ DFH and random alloy samples grown on four different substrate orientations: (001), (311), (201) and (110). We find a systematic variation of T_C with substrate orientation, but the experimental results are superficially inconsistent with the theoretical predictions. By carefully examining $\text{Ga}_{1-x}\text{Mn}_x\text{As}$ random alloys grown on the same substrate orientations, we show that this discrepancy most likely has *extrinsic* origins and may be explained by the variation in As antisite defect density with substrate orientation. Our study also highlights the challenging experimental hurdles that need to be overcome in order to provide meaningful comparisons with theory.

The samples are grown by molecular beam epitaxy on semi-insulating GaAs substrates with different orientations. Substrates are mounted on indium-bonded molybdenum blocks, and the substrate temperature is carefully monitored using band-edge thermometry. We use

high purity elemental sources of Ga (5N), As (5N) and Mn (4N), evaporated from standard effusion cells. The growth is monitored using reflection high energy electron diffraction (RHEED) at 12 keV. RHEED oscillations are used to calibrate the growth rate of GaAs and MnAs on (001) GaAs. Since we have not succeeded in observing RHEED oscillations on other substrate orientations, we scale this growth rate by the respective surface densities for the other 3 substrate orientations, assuming a constant sticking coefficient. We first deposit an undoped, 180 nm thick GaAs buffer layer under standard conditions (substrate temperature of 600°C). The temperature is then reduced to 290°C for the growth of the (Ga,Mn)As layer. DFH samples are grown by alternating GaAs and MnAs growth. Random alloy samples are grown by co-depositing all three elements simultaneously.

Theoretical predictions have primarily focused on $(\text{MnAs})_1/(\text{GaAs})_m$ DFHs that contain a full monolayer (ML) of MnAs in each unit. However, as reported in the first study of DFH growth on (001) GaAs,[4] we find that it is difficult to maintain good crystallinity with more than ~ 0.5 monolayer coverage of MnAs. Thus, we restrict our DFH geometry to contain 30 repeats of units that contain a 0.5 ML coverage of MnAs, and a GaAs spacer whose thickness varies from 4.5 to 9.5 monolayers. In the absence of diffusion, such samples would ideally correspond to superlattices in which each unit consists of $(\text{Ga}_{0.5}\text{Mn}_{0.5}\text{As})_1/(\text{GaAs})_m$, where $4 \leq m \leq 9$. High resolution cross-sectional transmission electron microscopy (TEM) reveals significant interdiffusion: for instance, for growth on (001) substrates, we can clearly discern distinct layers for DFH samples with $m \geq 7$ but not for samples with shorter periods (Fig. 1(a)). We estimate a Gaussian diffusion profile of the Mn with a diffusion length of roughly 3 nm, similar to previous studies.[4] The inhomogeneous distribution of Mn atoms notwithstanding, secondary ion mass spectroscopy (SIMS) measurements of nominally identical superlattices grown on different orientations show an identical average Mn concentration. Additional structural characterization is carried out using x-ray reflectometry (Fig.1(b)). These measurements reveal a clear signature of superlattice formation in (001)-oriented samples. In addition, we observe Pendellösung thickness fringes due to the total thickness of the GaAs buffer layer and the superlattice in (001)- and (311)-oriented samples. The (201) and (110)-oriented samples were too rough to see these effects.

We carry out temperature-dependent magnetization measurements using a Quantum Design dc superconducting quantum interference device (SQUID). The samples are cooled under a 10 kOe field and measured during warming with an applied field of 50 Oe for the

DFHs and 200 Oe for the random alloys. The measuring field is applied in plane, near the anticipated easy axis for each sample. We note however that it is difficult to do this for some of the non-standard substrate orientations such as the (201) substrates. We have verified that the Curie temperature is independent of the direction of applied field. In Fig. 2(a), we show the magnetization as a function of temperature for the different DFH samples with a 7.5 ML GaAs spacer. The data indicate a clear substrate orientation dependence on T_C . This trend is robustly followed by an entire set of samples where we vary the spacer thickness (Fig. 2(b)). For a fixed spacer thickness, the (001) substrate orientation shows the highest T_C . As expected, for any given substrate orientation, T_C decreases with increasing spacer thickness. The substrate orientation dependence of T_C is clearly inconsistent with theoretical predictions.

In order to ascertain whether the experimental observations have an intrinsic origin or an extrinsic one, we carry out a set of systematic experiments. First, we explore whether the variations in T_C show any correlation with hole concentrations in the different samples. We estimate the carrier concentration by using Hall effect measurements at room temperature; in these relatively low T_C samples, contributions from the anomalous Hall effect are small and – in any case – our measurements can reveal *relative* variations in hole density. We carry out a linear fit to the Hall resistance as a function of magnetic field from 5 to 9 T and find a suggestive correlation between T_C and hole density (Fig. 2 (c)). These data indicate that extrinsic factors may be at the root of the observed orientation dependence of T_C .

To further examine the origins of the substrate-orientation dependence of T_C in the DFH samples, we explore a series of 30 nm thick random alloy $\text{Ga}_{1-x}\text{Mn}_x\text{As}$ epilayers on the four substrate orientations. We have grown sets of samples, nominally with $x = 0.05$ and $x = 0.08$. In order to eliminate possible growth condition variations, we mount all four substrates on the same molybdenum block and grow them simultaneously. Figure 3(a) shows that the random alloys exhibit the same dependence of T_C on substrate orientation as the DFH samples. These observations are consistent with the results of a recent study comparing growth of $\text{Ga}_{1-x}\text{Mn}_x\text{As}$ epilayers on (001), (311) and (110) oriented substrates. [8] We caution though that this previous study did not eliminate variations in sample to sample growth or provide a specific reason for the T_C dependence on orientation. Figure 3(b) shows that the hole concentration in our random alloy samples is also dependent on substrate orientation, and correlates roughly with the trends in T_C . Figure 3(c) shows SIMS data for

the four random alloy samples, indicating that the Mn concentration is identical among all the samples, thus ruling out variations in Mn incorporation. Our observations suggest that the substrate orientation has a strong effect on the formation of hole-compensating defects.

It is now well-established that two types of hole-compensating defects dominate the magneto-electronic properties of $\text{Ga}_{1-x}\text{Mn}_x\text{As}$: Mn interstitials and As antisites, both of which act as double donors. [2] The former can be removed to the free surface of the sample by post-growth annealing at relatively low temperatures ($T \lesssim 250^\circ\text{C}$). [9] In contrast, there is presently no evidence that As antisites are affected during such low temperature annealing. Figure 3(d) shows T_C of the random alloy samples as a function of annealing. These data indicate that – although annealing does enhance T_C in all the random alloy samples – it does not affect the relative variations in T_C between different orientations. Thus, it is unlikely that the substrate orientation affects the formation of Mn interstitials; instead, we conclude that variations in the formation of As antisites must be responsible for our observed variation of T_C and hole density for samples with different substrate orientations.

In conclusion, our extensive study has clearly established the growth conditions necessary for epitaxial growth of random and digital (Ga,Mn)As alloys on four different substrate orientations: (001), (311), (201) and (110). We have found a systematic substrate orientation dependence of T_C in both random alloy and DFH samples of $\text{Ga}_{1-x}\text{Mn}_x\text{As}$, with (001)-oriented samples giving the highest values of T_C and (110)-oriented samples giving the lowest T_C . These variations do not agree with theoretical predictions but are not intrinsic: they can be traced to different densities of hole-compensating As antisites. We conclude that meaningful experimental tests of first principles theory remain a daunting challenge for materials growth.

* Electronic address: `nsamarth@psu.edu`

- [1] A. H. Macdonald, P. Schiffer, and N. Samarth, *Nature (Materials)* **4**, 195 (2005).
- [2] T. Jungwirth, K. Y. Wang, J. Masek, K. W. Edmonds, J. Konig, J. Sinova, M. Polini, N. A. Goncharuk, A. H. MacDonald, M. Sawicki, et al., *Phys. Rev. B* **72**, 165204 (2005).
- [3] A. Franceschetti, S. V. Dudiy, S. V. Barabash, A. Zunger, J. Xu, and M. van Schilfgaarde, *Phys. Rev. Lett.* **97**, 047202 (2006).
- [4] R. K. Kawakami, E. Johnston-Halperin, L. F. Chen, M. Hanson, N. Guebels, J. S. Speck, A. C. Gossard, and D. D. Awschalom, *Appl. Phys. Lett.* **77**, 3665 (2000).
- [5] J. Tang and M. Flatte, *Phys. Rev. B* **72**, 161315 (2005).
- [6] P. Mahadevan, A. Zunger, and D. Sarma, *Phys. Rev. Lett.* **93**, 177201 (2004).
- [7] D. Kitchen, A. Richardella, J.-M. Tang, M. E. Flatte, and A. Yazdani, *Nature* **442**, 436 (2006).
- [8] U. Wurstbauer, M. Sperl, D. Schuh, G. Bayreuther, J. Sadowski, and W. Wegscheider, *J. Cryst. Growth* **301**, 260 (2007).
- [9] K. W. Edmonds, P. Boguslawski, K. Y. Wang, R. P. Campion, S. N. Novikov, N. R. S. Farley, B. L. Gallagher, C. T. Foxon, M. Sawicki, T. Dietl, et al., *Phys. Rev. Lett.* **92**, 037201 (2004).




FIG. 1: (a) High-angle annular dark-field TEM image of a (001)-oriented DFH with 0.5 ML MnAs and 7.5 ML GaAs spacer. Structure has 30 periods and the image clearly shows distinct layers. (b) X-ray reflectivity data showing a peak corresponding to the expected superlattice periodicity.




FIG. 2: (a) Magnetization vs. temperature for DFH grown on (201) substrate orientation along different measuring field directions. (b) Magnetization vs. temperature for DFH with a fixed 7.5 ML spacer and different substrate orientations. (c) T_C as a function of spacer thickness for DFH samples with different substrate orientations. (d) Variation of T_C with hole density in DFH samples with varying substrate orientation and spacer thickness.




FIG. 3: (a) Magnetization vs. temperature for random alloy samples showing similar trends as DFH samples. (b) Variation of T_C with hole density for random alloy samples of varying substrate orientation and different Mn concentration. (c) SIMS analysis of Mn concentration in random alloy samples with different substrate orientations, showing identical Mn incorporation. The increased Mn concentration near the sample surface may be the result of unintentional annealing. (d) Effect of annealing on T_C , showing that difference in Mn interstitial densities between orientations is unlikely.