



Initial Evaluation of Advanced Powder Metallurgy Magnesium Alloys for Armor Development

by Tyrone Jones and Katsuyoshi Kondoh

ARL-TR-4828

May 2009

NOTICES

Disclaimers

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Citation of manufacturer's or trade names does not constitute an official endorsement or approval of the use thereof.

Destroy this report when it is no longer needed. Do not return it to the originator.

Army Research Laboratory

Aberdeen Proving Ground, MD 21005-5066

ARL-TR-4828**May 2009**

Initial Evaluation of Advanced Powder Metallurgy Magnesium Alloys for Armor Development

Tyrone Jones

Weapons and Materials Research Directorate, ARL

Katsuyoshi Kondoh

Joining and Welding Research Institute, Japan

REPORT DOCUMENTATION PAGE				Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing the burden, to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.					
1. REPORT DATE (DD-MM-YYYY) May 2009		2. REPORT TYPE Final		3. DATES COVERED (From - To) January 2008–January 2009	
4. TITLE AND SUBTITLE Initial Evaluation of Advanced Powder Metallurgy Magnesium Alloys for Armor Development				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S) Tyrone Jones and Katsuyoshi Kondoh*				5d. PROJECT NUMBER 1L162618AH80	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) U.S. Army Research Laboratory ATTN: AMSRD-ARL-WM-TA Aberdeen Proving Ground, MD 21005-5066				8. PERFORMING ORGANIZATION REPORT NUMBER ARL-TR-4828	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)				10. SPONSOR/MONITOR'S ACRONYM(S)	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution is unlimited.					
13. SUPPLEMENTARY NOTES *Joining and Welding Research Institute, Osaka University, 11-1 Mihogaoka, Ibaraki 567-0047 Osaka, Japan					
14. ABSTRACT The U.S. Army Research Laboratory (ARL) is interested in assessing the performance of different magnesium alloys. ARL and the Joining and Welding Research Institute (JWRI) conducted an effort to develop and evaluate advanced powder metallurgy magnesium alloys AZ31B and AMX602 (Mg-6Al-0.5Mn-2Ca/mass%) sheets. JWRI performed the mechanical and metallurgical analysis, while ARL performed the ballistic analysis. The thin-gauge magnesium alloy sheets were ballistically evaluated against the 0.22-cal. fragment-simulating projectile. The magnesium alloy powders' mechanical properties and ballistic performance were compared to the conventionally processed AZ31B-H24.					
15. SUBJECT TERMS armor, powder metallurgy, magnesium alloys, AZ31B, AMX602, ballistic performance, ballistic limit					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT UU	18. NUMBER OF PAGES 46	19a. NAME OF RESPONSIBLE PERSON Tyrone Jones
a. REPORT Unclassified	b. ABSTRACT Unclassified	c. THIS PAGE Unclassified			19b. TELEPHONE NUMBER (Include area code) 410-278-6223

Contents

List of Figures	iv
List of Tables	v
Acknowledgments	vi
1. Introduction	1
2. Powder Metallurgy	1
3. Terminal Ballistic Evaluation	5
3.1 Test Setup	5
3.2 Projectile	6
3.3 Ballistic Comparison	6
3.4 Material Response	7
4. Conclusions and Future Research	10
5. References	11
Appendix A. Experimental Facility Range Setup	13
Appendix B. V_{50} Ballistic Limit Firing Data	17
Distribution List	28

List of Figures

Figure 1. AZ31B and AMX602 powder size.....	1
Figure 2. Optical microstructures of AMX602 (a–d).	2
Figure 3. X-ray diffractions of AMX602: (a) atomized powder compacts and (b) cast ingot.	3
Figure 4. SEM of AMX602 (a-1, a-2, b-1, and b-2).....	3
Figure 5. SEM-EDS of AMX602 of cast ingot extruded at 573 K (a–f).	4
Figure 6. AMX602 stress-strain curve and SEM (a–c).....	4
Figure 7. Tensile properties vs. temperature.....	5
Figure 8. The 0.22-cal. FSP dimensions.	6
Figure 9. Designation 1-1: front (a) and back (b).	8
Figure 10. Designation 2-1: front (a) and back (b).	8
Figure 11. Designation 4-1: front (a) and back (b).	8
Figure 12. Designation 5-1: front (a) and back (b).	8
Figure 13. Designation 7-1: front (a) and back (b).	9
Figure 14. Designation 8-1: front (a) and back (b).	9
Figure 15. Designation 9-1: front (a) and back (b).	9
Figure 16. Designation 10-1: front (a) and back (b).	9
Figure 17. Designation X-6: front (a) and back (b).	10
Figure 18. Designation X-7: front (a) and back (b).	10
Figure A-1. The gas gun. The distance between the gun muzzle and the target was 1.4 m.	14
Figure A-2. A sample in the test rig with a 228- × 152.4- × 0.508-mm 2024Al witness plate placed 152 mm behind and parallel to sample. The distance between the clamps was 254 mm.	15

List of Tables

Table 1. Manufacturing process.....	5
Table 2. Areal weights and ballistic limits.....	6
Table 3. Material failure analysis.....	7
Table B-1. Material sample 1-1.	18
Table B-2. Material sample 2-1.	19
Table B-3. Material sample 4-1.	20
Table B-4. Material sample 5-1.	21
Table B-5. Material sample 7-1.	22
Table B-6. Material sample 8-1.	23
Table B-7. Material sample 9-1.	24
Table B-8. Material sample 10-1.	25
Table B-9. Material sample X-6.	26
Table B-10. Material sample X-7.	27

Acknowledgments

Great appreciation is extended to U.S. Army Research Laboratory Engineer Peter Dehmer for the ballistic testing performed in the Building 4600 gas gun experimental facility.

1. Introduction

An initial ballistic evaluation of conventionally rolled AZ31B-H24 plate has been performed and serves as a baseline (1). Powder metallurgy (P/M) processing can control the microstructure by refining grains and intermetallics and producing nonequilibrium alloy compositions of metals (2). In particular, rapid solidification processing by atomization is often used to prepare raw powders with ultrafine microstructures. In this study, a water atomization process was applied to produce coarse magnesium alloy powders with fine grains and intermetallic compounds (3). Samples were consolidated by using the conventional P/M process such as cold compaction, spark plasma sintering, and hot extrusion. The alloy microstructures and mechanical properties, along with the ballistic performance of P/M wrought magnesium alloys, were evaluated. The effects of alloy elements and microstructures on the mechanical properties and ballistic performance are discussed in detail in this report.

2. Powder Metallurgy

Two kinds of magnesium alloy powder produced by water atomization process were prepared in this study—AZ31B (Mg-3Al-1Zn-0.3Mn/mass%) and AMX602 (Mg-6Al-0.5Mn-2Ca/mass%) (4) coarse powders. The powder size of each formulation was 1–4 mm, as shown in figure 1, reducing the potential of the magnesium catching fire. Samples were compacted by applying 300 MPa at room temperature. The relative density of the green compact 94-mm-diameter samples of AZ31B and AMX602 was 92% and 90%, respectively. Each powder was then supplied to the spark plasma sintering (SPS) process (5) to accelerate the metallurgical bonding between powders. In the SPS process, the raw powder filled a carbon die with a diameter of 95 mm. The temperature was controlled at 473 K in a vacuum less than 4 Pa, and a consolidation pressure of 10 MPa was applied during sintering in 1.8 ks.




Figure 1. AZ31B and AMX602 powder size.

The relative density of the SPS compact of AZ31B and AMX602 was 72% and 70%, respectively. Each compact was heated at 573, 598, and 623 K and immediately processed by hot extrusion. The extrusion ratio and speed was 40 and 50 mm/s, respectively. The final plate specimen, 40 mm wide and 5 mm thick, was obtained by hot extrusion.

Mechanical Properties

Figure 2 indicates optical microstructures of AMX602 raw materials: atomized fine (a), coarse powders (b), machined chips (c), and cast ingot (d). Fine powder (a) reveals small dendrite structures formed by rapid solidification. Due to the smaller solidification ration during atomization, coarse powder shows larger grains than those of fine powder (a). Compared to machined chips (c) and cast material (d), the powders have almost the same grain size of 60–150 μm , and some intermetallic compounds were observed at their grain boundaries.




Figure 2. Optical microstructures of AMX602 (a–d).

In particular, machined chips, shown in figure 2c, have a lot of twinning induced by machining. Figure 3 shows x-ray diffraction patterns of AMX602 wrought alloys extruded at 573 and 673 K when using atomized powder compacts (a) and cast ingot (b). Their microstructures, observed by SEM, are shown in figure 4, where (a) and (b) indicate the powder compacts and cast ingot, respectively. When employing atomized powders, the fine grains caused by dynamic recrystallization are observed. The lower extrusion temperature of 573 K is effective in forming the finer microstructures with a mean grain size of $\sim 0.45 \mu\text{m}$, which is measured by applying the image-scanning software to the scanning electron microscopy (SEM) photo. Very fine white particles are Al_2Ca compounds precipitated during heating prior to hot extrusion.




Figure 3. X-ray diffractions of AMX602: (a) atomized powder compacts and (b) cast ingot.




Figure 4. SEM of AMX602 (a-1, a-2, b-1, and b-2).

In the case of cast ingots, figure 4b-1, the mean grain size of extruded materials at 573 and 673 K is 1.96 and 3.29 μm , respectively. The higher temperature caused grain coarsening. Both wrought alloys using AMX602 cast ingots contained coarse intermetallics as well. As shown in figure 5, SEM-energy dispersive spectroscopy (EDS) analysis results on the specimen indicate the intermetallic dispersoids were mainly Al_2Ca compounds and exist at grain boundaries. The other results showed Al-Mn compounds with spherical shapes.

Both intermetallics are typical of the conventional AMX602 cast ingot. Micro Vicker's hardness of each material was as follows: powder extruded at 573 K, 113 Hv; powder extruded at 673 K, 94.3 Hv; cast ingot extruded at 573 K, 77.0 Hv; and cast ingot extruded at 673 K, 69.9 Hv. The hardness of wrought alloys using atomized powder compacts was higher than that using the cast ingot and showed a remarkable dependence on the grain size.




Figure 5. SEM-EDS of AMX602 of cast ingot extruded at 573 K (a–f).

The mechanical properties of wrought AMX602 alloys are shown in figure 6. Figure 6a shows tensile stress-strain curves in extruding the atomized powder compact and cast ingot material at 623 K. The extruded AMX602 alloy using the atomized powder compact indicates an increase of tensile strength (TS) and yield strength (YS) compared to the ingot extruded alloy, about 35% and 70%, respectively. In particular, a phenomenon suspected in yielding is detected when using the powder compact. In the fractured surface of each tensile test specimen, the powder compact extruded alloy, figure 6b, shows no fracture at primary particle boundaries and fine dimple patterns. This means the particle bonding is strong and cracks propagate inside particles, not grain boundaries. When testing the cast ingot, figure 6c, dimple patterns were observed, but some cracks occurred inside the coarse brittle intermetallics.




Figure 6. AMX602 stress-strain curve and SEM (a–c).

Figure 7 indicates a dependence of the tensile properties of wrought AMX602 alloys on the extrusion temperature. Both materials reveal the decrease of TS and YS, with increase in the extrusion temperature due to microstructure coarsening. However, the elongation increases with increasing temperature, 14.2% for the atomized powder and 17.7% for the cast ingot at 623 K. Note that the TS of 447 MPa and YS of 425 MPa is obtained in the extruded material by using the rapidly solidified AMX602 powder, which was superior to the conventional aluminum alloy 2014-T4 heat treatment.




Figure 7. Tensile properties vs. temperature.

3. Terminal Ballistic Evaluation

3.1 Test Setup

Ten magnesium plate samples were produced for ballistic evaluation. The nominal dimensions of the samples were $308 \times 38 \times 5$ mm. The test designation and the manufacturing of each sample are shown in table 1. The conventionally rolled plates were designated X-6 and X-7. The thin plates were held vertically in a test fixture by one clamp on each 308-mm edge.

Table 1. Manufacturing process.

Designation	Material
1-1	AZ31B SWAP cold compaction extrusion 300 °C
2-1	AZ31B SWAP SPS 200 °C extrusion 300 °C
4-1	AZ231B cold compaction extrusion 325 °C
5-1	AMX 602 SWAP cold compaction extrusion 325 °C
7-1	AMX 602 SWAP SPS 200 °C extrusion 325 °C
8-1	AZ31B SWAP cold compaction extrusion 350 °C
9-1	AZ31B SWAP SPS 200 °C extrusion 350 °C
10-1	AMX 602 SWAP SPS 200 °C extrusion 350 °C
X-6	AZ31B-H24 wrought plate
X-7	AZ31B-O wrought plate

Notes: SWAP = spinning water atomization process, and SPS = spark plasma sintering.

Ballistic testing of all magnesium plate samples was performed by the U.S. Army Research Laboratory (ARL) at Aberdeen Proving Ground, MD, in accordance with MIL-STD-662F (6). Ballistic results were characterized using the standard V_{50} test methodology, also documented in MIL-STD-662F. Due to the limitation of sample sizes, the V_{50} ballistic limit of samples 1-1, 2-1, and 4-1 was calculated using the average between the high partial penetration and low complete penetration. Pictures of the test setup are shown in appendix A.

3.2 Projectile

Because of the thin gauge of the samples, the 0.22-cal. fragment-simulating projectile (FSP) was selected to evaluate the magnesium alloy plates. The FSP used is produced in accordance with MIL-DTL-46593B (MR) (7) and is depicted in figure 8. This projectile design is utilized in acceptance tables for current military specifications.




Figure 8. The 0.22-cal. FSP dimensions (7).

3.3 Ballistic Comparison

V_{50} ballistic limit for each magnesium plate is shown in table 2. Each sample was weighed, and the areal density and ballistic limits were calculated. The V_{50} ballistic limit firing records are shown in appendix B.

Table 2. Areal weights and ballistic limits.

Designation	Material	Thickness (mm)	Length (mm)	Width (mm)	Weight (g)	Areal Density (kg/m ²) (lb/sf)	V_{50} (m/s) (fps)
1-1	AZ31B SWAP cold compaction extrusion 300 °C	4.877	8.938	39.7	77.0	8.54 (1.75)	277 (909)
2-1	AZ31B SWAP SPS 200 °C extrusion 300 °C	4.851	9.000	39.7	78.0	8.59 (1.76)	269 (883)
4-1	AZ231b cold compaction extrusion 325 °C	4.902	8.875	39.7	77.1	8.59 (1.76)	277 (892)
5-1	AMX 602 SWAP cold compaction extrusion 325 °C	4.877	8.938	39.7	77.7	8.64 (1.77)	270 (886)
7-1	AMX 602 SWAP SPS 200 °C extrusion 325 °C	4.851	8.938	39.7	77.1	8.54 (1.75)	268 (879)
8-1	AZ31B SWAP cold compaction extrusion 350 °C	4.877	8.938	39.7	77.1	8.54 (1.75)	277 (909)
9-1	AZ31B SWAP SPS 200 °C extrusion 350 °C	4.877	8.938	39.7	77.1	8.64 (1.75)	277 (909)
10-1	AMX 602 SWAP SPS 200 °C extrusion 350 °C	4.851	8.875	39.7	77.1	8.59 (1.76)	275 (902)
X-6	AZ31B-H24 wrought plate	4.623	8.875	63.5	117.5	8.20 (1.68)	277 (909)
X-7	AZ31B-O wrought plate	4.750	8.875	63.5	98.2	8.59 (1.76)	273 (896)

Notes: SWAP = spinning water atomization process, and SPS = spark plasma sintering.

The data did not show a statistically significant difference in ballistic performance as a result of processing. The standard deviation of the each V_{50} was within the acceptable required testing limits. Based on this data, it is recommended that any future samples have a minimum thickness of 12.7 mm.

3.4 Material Response

Initial analysis of the material responses is shown in table 3 and figures 9–18. The projectile made an initial indentation, resulting in plastic shearing and the formation of a plug. The back of the samples showed different material failures. Magnesium alloy AMX602 proved to be a brittle material under all manufacturing processes. Some of the entry holes exhibited adiabatic shearing. Large spall failure (scabbing) occurred on the back of the magnesium alloy AMX602 samples after the fragment impact. Spalling is the detachment of a layer of material in the area surrounding the location of impact, occurring on either the front or rear surfaces of a sample. This indicates the ductility of magnesium alloy AMX602 needs to be improved. The manufactured powder magnesium alloy AZ31B petalled during impact, allowing some of the energy of the projectile to be dissipated through plastic deformation. Petalling is the peeling of material into segments after impact. Conventionally rolled magnesium alloy AZ31B showed little spall compared to powder-processed magnesium alloys.

Table 3. Material failure analysis.

Designation	Material	Material Response	
		Front	Back
1-1	AZ31B SWAP cold compaction extrusion 300 °C	Initial indentation, plastic shearing then plug formation	Petalling then spall failure
2-1	AZ31B SWAP SPS 200 °C extrusion 300 °C	Initial indentation, plastic shearing then plug formation	Petalling then spall failure
4-1	AZ231B cold compaction extrusion 325 °C	Initial indentation, plastic shearing then plug formation	Petalling then spall failure
5-1	AMX 602 SWAP cold compaction extrusion 325 °C	Initial indentation, plastic shearing then plug formation, some shear cracking at hole perimeter	Large spall failure
7-1	AMX 602 SWAP SPS 200 °C extrusion 325 °C	Initial indentation, plastic shearing then plug formation, some shear cracking at hole perimeter	Large spall failure
8-1	AZ31B SWAP cold compaction extrusion 350 °C	Initial indentation, plastic shearing then plug formation	Petalling then spall failure
9-1	AZ31B SWAP SPS 200 °C extrusion 350 °C	Initial indentation, plastic shearing then plug formation	Petalling then spall failure
10-1	AMX 602 SWAP SPS 200 °C extrusion 350 °C	Initial indentation, plastic shearing then plug formation, some shear cracking at hole perimeter	Large spall failure
X-6	AZ31B-H24 wrought plate	Initial indentation, plastic shearing then plug formation	Small spall failure
X-7	AZ31B-O wrought plate	Initial indentation, plastic shearing then plug formation	Small spall failure

Notes: SWAP = spinning water atomization process, and SPS = spark plasma sintering.




Figure 9. Designation 1-1: front (a) and back (b).




Figure 10. Designation 2-1: front (a) and back (b).




Figure 11. Designation 4-1: front (a) and back (b).




Figure 12. Designation 5-1: front (a) and back (b).




Figure 13. Designation 7-1: front (a) and back (b).




Figure 14. Designation 8-1: front (a) and back (b).




Figure 15. Designation 9-1: front (a) and back (b).




Figure 16. Designation 10-1: front (a) and back (b).




Figure 17. Designation X-6: front (a) and back (b).




Figure 18. Designation X-7: front (a) and back (b).

4. Conclusions and Future Research

Ballistic performance appeared constant regardless of processing route. The magnesium plate may not be thick enough to properly show the effect of material processing differences. Therefore, it is recommended that future evaluations be conducted with magnesium plate with a minimum thickness of 12.7 mm.

These results indicated not only high TS and YS, but high elongation produced by good metallurgical bonding between primary powders. A large quantity of alloying elements in the matrix is not suitable to maintaining high elongation. The grain and intermetallics refinement was effective in improving the balance of strength and ductility of the magnesium alloys, although the thermal history in consolidating rapid, solidified magnesium alloy powder should be optimized. The effect of surface oxide (MgO) films of raw powder on the metallurgical bonding will also be investigated by microstructural analysis. Furthermore, the materials strengthening by fine dispersoids, which have a good wettability with magnesium, e.g., titanium particles, will be considered in the future work.

5. References

1. Jones, T. L.; DeLorme, R. D.; Burkins, M. S.; Gooch, W. A. A Comparison of the Ballistic Performance between Rolled Plate in AZ31B-H24 Magnesium and 5083-H131 Aluminum. *Proceedings of the 24th International Symposium on Ballistics*, New Orleans, LA, 22–26 September 2008.
2. Yoshihito, K.; Hideo, M.; Akihisa, I. *Scripta Materialia* **2000**, 43 (12), 1119–1124.
3. Otsuka, I.; Izaki, H. *Powder and Powder Metallurgy* **2001**, 48 (9), 697–702.
4. Kitahara, Y.; Shimazaki, H. *Mater. Sci. Forum* **2005**, 482, 359–362.
5. Grosdidier, T.; Ji, G.; Launois, S. *Scripta Materialia* **2007**, 57 (6), 525–528.
6. MIL-STD-662F. *V₅₀ Ballistic Test for Armor* **1997**.
7. MIL-DTL-46593B (MR). *Projectile, Calibers .22, .30, .50, and 20mm Fragment-Simulating* **2006**.

INTENTIONALLY LEFT BLANK.

Appendix A. Experimental Facility Range Setup



Figure A-1. The gas gun. The distance between the gun muzzle and the target was 1.4 m.




Figure A-2. A sample in the test rig with a 228- × 152.4- × 0.508-mm 2024Al witness plate placed 152 mm behind and parallel to sample. The distance between the clamps was 254 mm.

INTENTIONALLY LEFT BLANK.

Appendix B. V_{50} Ballistic Limit Firing Data

B.1 Material Sample 1-1

Date: 20 August 2008

Engineer: Tyrone Jones

Test facility: Bldg. 4600 - Dehmer

Target: Magnesium alloy AZ31B spinning water atomization process (SWAP) cold compaction extrusion 300 °C

Sample no.: 1-1

Sample size: 9 × 1.5 in

Sample thickness: 0.192 in

Sample weight: 77 gr

Area density: 1.75 psf

Obliquity: 0°

Projectile: 0.22-cal. fragment-simulating projectile (FSP)

Setup: Mg alloy sample – 6 in air – 0.020 in 2024Al

Table B-1. Material sample 1-1.

Shot No.	Striking Velocity (m/s)	Result (PP/CP)	Used for V ₅₀	Comments
1	314	CP	No	—
2	292	CP	No	—
3	281	CP	Yes	—
4	264	PP	No	—
5	267	PP	No	—
6	273	PP	Yes	Dent on witness
V ₅₀ calculation: 277 m/s				
High partial (HP): 273 m/s				
Low complete (LC): 281 m/s				

Notes:

- CP = complete perforation; penetrator or target material exits rear surface of the target.
- HP = highest partial perforation; V₅₀ ballistic limit is typically above this velocity.
- LC = lowest complete perforation; V₅₀ ballistic limit is typically below this velocity.
- PP = partial penetration; the penetrator is defeated by target.
- Result = result of shot; CP or PP.
- Striking velocity = velocity of the projectile just prior to impacting the target.

B.2 Material Sample 2-1

Date: 21 August 2008

Engineer: Tyrone Jones

Test facility: Bldg. 4600 - Dehmer

Target: Magnesium alloy AZ31B SWAP 200 °C extrusion 300 °C

Sample no.: 2-1

Sample size: 9 × 1.5 in

Sample thickness: 0.191 in

Sample weight: 78 gr

Area density: 1.76 psf

Obliquity: 0°

Projectile: 0.22-cal. FSP

Setup: Mg alloy sample – 6 in air – 0.020 in 2024Al

Table B-2. Material sample 2-1.

Shot No.	Striking Velocity (m/s)	Result (PP/CP)	Used for V ₅₀	Comments
1	257	PP	No	—
2	278	CP	No	—
3	274	CP	No	Pinhole in witness
4	269	CP	Yes	Pinhole in witness
5	269	PP	Yes	—
V ₅₀ calculation: 269 m/s				
High partial (HP): 269 m/s				
Low complete (LC): 269 m/s				

B.3 Material Sample 4-1

Date: 22 August 2008

Engineer: Tyrone Jones

Test Facility: Bldg. 4600 - Dehmer

Target: Magnesium alloy AZ31B cold compaction extrusion 325 °C

Sample no.: 4-1

Sample size: 8.75 × 1.5 in

Sample thickness: 0.193 in

Sample weight: 77.1 gr

Area density: 1.76 psf

Obliquity: 0°

Projectile: 0.22-cal. FSP

Setup: Mg alloy sample – 6 in air – 0.020 in 2024Al

Table B-3. Material sample 4-1.

Shot No.	Striking Velocity (m/s)	Result (PP/CP)	Used for V ₅₀	Comments
1	251	PP	No	—
2	269	CP	Yes	Dent on witness
3	268	CP	No	—
4	274	CP	Yes	—
V ₅₀ calculation: 272 m/s				
High partial (HP): 269 m/s				
Low complete (LC): 274 m/s				

B.4 Material Sample 5-1

Date: 28 August 2008

Engineer: Tyrone Jones

Test Facility: Bldg. 4600 - Dehmer

Target: Magnesium alloy AMX602 SWAP cold compaction extrusion 325 °C

Sample no.: 5-1

Sample size: 8.94 × 56 in

Sample thickness: 0.192 in

Sample weight: 77.7 gr

Area density: 1.77 psf

Obliquity: 0°

Projectile: 0.22-cal. FSP

Setup: Mg alloy sample – 6 in air – 0.020 in 2024Al

Table B-4. Material sample 5-1.

Shot No.	Striking Velocity (m/s)	Result (PP/CP)	Used for V ₅₀	Comments
1	264	PP	No	Plug ejected
2	Void	—	No	—
3	272	CP	Yes	—
4	266	PP	Yes	Plug ejected
5	271	PP	Yes	Plug ejected
6	272	CP	Yes	—
V ₅₀ calculation: 270 m/s				
High partial (HP): 271 m/s				
Low complete (LC): 266 m/s				

B.5 Material Sample 7-1

Date: 29 August 2008

Engineer: Tyrone Jones

Test facility: Bldg. 4600 - Dehmer

Target: Magnesium alloy AMX602 SWAP 200 °C extrusion 325 °C

Sample no.: 7-1

Sample size: 8.94 × 1.5 in

Sample thickness: 0.191 in

Sample weight: 77.1 gr

Area density: 1.75 psf

Obliquity: 0°

Projectile: 0.22-cal. FSP

Setup: Mg alloy sample – 6 in air – 0.020 in 2024Al

Table B-5. Material sample 7-1.

Shot No.	Striking Velocity (m/s)	Result (PP/CP)	Used for V ₅₀	Comments
1	271	PP	Yes	Plug ejected
2	270	CP	Yes	—
3	269	CP	Yes	—
4	269	CP	Yes	—
5	266	PP	Yes	Plug ejected
6	263	PP	Yes	Plug ejected
V ₅₀ calculation: 268 m/s				
High partial (HP): 271 m/s				
Low complete (LC): 269 m/s				

B.6 Material Sample 8-1

Date: 2 September 2008

Engineer: Tyrone Jones

Test facility: Bldg. 4600 - Dehmer

Target: Magnesium alloy AZZ31B cold compaction extrusion 350 °C

Sample no.: 8-1

Sample size: 8.94 × 1.56 in

Sample thickness: 0.192 in

Sample weight: 77.1 gr

Area density: 1.75 psf

Obliquity: 0°

Projectile: 0.22-cal. FSP

Setup: Mg alloy sample – 6 in air – 0.020 in 2024Al

Table B-6. Material sample 8-1.

Shot No.	Striking Velocity (m/s)	Result (PP/CP)	Used for V ₅₀	Comments
1	270	PP	No	—
2	271	PP	No	—
3	271	PP	No	—
4	271	PP	Yes	—
5	280	PP	Yes	Dent on witness
6	277	CP	Yes	—
7	278	CP	Yes	—
V ₅₀ calculation: 268 m/s				
High partial (HP): 271 m/s				
Low complete (LC): 269 m/s				

B.7 Material Sample 9-1

Date: 8 September 2008

Engineer: Tyrone Jones

Test facility: Bldg. 4600 - Dehmer

Target: Magnesium alloy AZ31B SWAP SPS 200 °C extrusion 350 °C

Sample no.: 9-1

Sample size: 8.94×1.56 in

Sample thickness: 0.192 in

Sample weight: 77.1 gr

Area density: 1.75 psf

Obliquity: 0°

Projectile: 0.22-cal. FSP

Setup: Mg alloy sample – 6 in air – 0.020 in 2024Al

Table B-7. Material sample 9-1.

Shot No.	Striking Velocity (m/s)	Result (PP/CP)	Used for V_{50}	Comments
1	247	PP	No	—
2	265	PP	No	—
3	272	PP	Yes	Dent on witness
4	273	PP	Yes	—
5	283	CP	Yes	Pinhole in witness
6	280	CP	Yes	—
V_{50} calculation: 277 m/s				
High partial (HP): 273 m/s				
Low complete (LC): 280 m/s				

B.8. Material Sample 10-1

Date: 9 September 2008

Engineer: Tyrone Jones

Test facility: Bldg. 4600 - Dehmer

Target: Magnesium alloy AZ31B SWAP SPS 200 °C extrusion 350 °C

Sample no.: 10-1

Sample size: 8.88 × 1.56 in

Sample thickness: 0.191 in

Sample weight: 77.1 gr

Area density: 1.76 psf

Obliquity: 0°

Projectile: 0.22-cal. FSP

Setup: Mg alloy sample – 6 in air – 0.020 in 2024Al

Table B-8. Material sample 10-1.

Shot No.	Striking Velocity (m/s)	Result (PP/CP)	Used for V ₅₀	Comments
1	280	CP	Yes	—
2	270	PP	Yes	Dent on witness
3	274	PP	Yes	Dent on witness
4	275	CP	Yes	—
V ₅₀ calculation: 275 m/s				
High partial (HP): 274 m/s				
Low complete (LC): 275 m/s				

B.9 Material Sample X-6

Date: 10 September 2008

Engineer: Tyrone Jones

Test facility: Bldg. 4600 - Dehmer

Target: Conventionally rolled magnesium alloy AZ31B H24

Sample no.: X-6

Sample size: 8.875×2.5 in

Sample thickness: 0.182 in

Sample weight: 117.5 gr

Area density: 1.68 psf

Obliquity: 0°

Projectile: 0.22-cal. FSP

Setup: Mg alloy sample – 6 in air – 0.020 in 2024Al

Table B-9. Material sample X-6.

Shot No.	Striking Velocity (m/s)	Result (PP/CP)	Used for V_{50}	Comments
1	269	PP	No	—
2	279	CP	Yes	Pinhole in witness
3	271	PP	No	Plug ejected
4	274	PP	Yes	—
5	276	PP	Yes	Plug ejected
6	279	CP	Yes	—
V_{50} calculation: 277 m/s				
High partial (HP): 276 m/s				
Low complete (LC): 279 m/s				

Table B.10 Material Sample X-7

Date: 10 September 2008

Engineer: Tyrone Jones

Test facility: Bldg. 4600 - Dehmer

Target: Conventionally rolled magnesium alloy AZ31B O

Sample no.: X-7

Sample size: 8.9×2 in

Sample thickness: 0.187 in

Sample weight: 98.2 gr

Area density: 1.76 psf

Obliquity: 0°

Projectile: 0.22-cal. FSP

Setup: Mg alloy sample – 6 in air – 0.020 in 2024 Al

Table B-10. Material sample X-7.

Shot No.	Striking Velocity (m/s)	Result (PP/CP)	Used for V_{50}	Comments
1	250	PP	No	—
2	269	PP	Yes	Plug ejected
3	272	CP	Yes	—
4	279	CP	Yes	—
5	273	PP	Yes	Plug ejected
V_{50} calculation: 273 m/s				
High partial (HP): 273 m/s				
Low complete (LC): 272 m/s				

NO. OF
COPIES ORGANIZATION

1 DEFENSE TECHNICAL
 (PDF INFORMATION CTR
 only) DTIC OCA
 8725 JOHN J KINGMAN RD
 STE 0944
 FORT BELVOIR VA 22060-6218

1 DIRECTOR
 US ARMY RESEARCH LAB
 IMNE ALC HRR
 2800 POWDER MILL RD
 ADELPHI MD 20783-1197

1 DIRECTOR
 US ARMY RESEARCH LAB
 AMSRD ARL CI OK TL
 2800 POWDER MILL RD
 ADELPHI MD 20783-1197

1 DIRECTOR
 US ARMY RESEARCH LAB
 AMSRD ARL CI OK PE
 2800 POWDER MILL RD
 ADELPHI MD 20783-1197

ABERDEEN PROVING GROUND

1 DIR USARL
 AMSRD ARL CI OK TP (BLDG 4600)

NO. OF
COPIES ORGANIZATION

3 CDR US ARMY TACOM
AMSTA TR S
T FURMANIAK
L FRANKS
D TEMPLETON
MS 263
WARREN MI 48397-5000

1 CDR US ARMY TACOM
AMSTA TR R
D HANSEN
WARREN MI 48397-5000

1 PM
SFAE GCSS HBCTS
J ROWE
MS 325
WARREN MI 48397-5000

2 NATL GROUND INTLLGNC CTR
J CRIDER
W GSTATENBAUER
2055 BOULDERS RD
CHARLOTTESVILLE VA 22091-5391

1 CRUSADER OPM
SFAE GCSS CR E
B ROOPCHAND
BLDG 171A
PICATINNY ARSENAL NJ 07806-5000

1 DIRECTOR
DARPA
3701 N FAIRFAX DR
ARLINGTON VA 22203-1714

1 DARPA
PRGM MGR
3701 N FAIRFAX DR
ARLINGTON VA 22203-1714

1 PM BFVS
ATTN SFAE GCSS W BV S
M KING
WARREN MI 48397-5000

1 NVL SURFC WARFARE CTR
CARDEROCK DIV
R PETERSON CODE 28
9500 MACARTHUR BLVD
WEST BETHESDA MD 20817-5700

NO. OF
COPIES ORGANIZATION

2 LAWRENCE LIVERMORE NATL LAB
RICHARD LANDINGHAM L372
JOHN REAUGH L282
PO BOX 808
LIVERMORE CA 94550

2 LOS ALAMOS NATL LAB
F ADDESSIO
M BURKETT
PO BOX 1663
LOS ALAMOS NM 87545

3 SANDIA NATL LAB
J ASAY MS 1811
L CHHABILDAS MS 1811
D CRAWFORD MS 0836 9116
PO BOX 5800
ALBUQUERQUE NM 87185-0307

1 AIR FORCE ARMAMENT LAB
AFATL DLJW
W COOK
EGLIN AFB FL 32542

4 UNIV OF TEXAS
INST FOR ADVNCD TECH
S BLESS
H FAIR
J HODGE
R SUBRAMANIAN
3925 W BRAKER LN
AUSTIN TX 78759-5316

1 UNIV OF DAYTON RSRCH INST
N BRAR KLA 14
300 COLLEGE PARK
DAYTON OH 45469-0182

3 SOUTHWEST RSCH INST
C ANDERSON
J RIEGEL
J WALKER
6220 CULEBRA RD
SAN ANTONIO TX 78238

4 US DEPT OF ENERGY
ALBANY RSCH CTR
J HANSEN (2 CPS)
P TURNER (2 CPS)
1450 QUEEN AVE SW
ALBANY OR 97321-2198

NO. OF
COPIES ORGANIZATION

1 BROWN UNIV
DIV OF ENGRG
R CLIFTON
PROVIDENCE RI 02912

2 UNIV OF CA SAN DIEGO
DEPT OF APPL MECH & ENGR
SVC RO11
S NEMAT NASSER
M MEYERS
LA JOLLA CA 92093-0411

2 AERONAUTICAL RSRCH ASSN
R CONTILIANO
J WALKER
PO BOX 2229
50 WASHINGTON RD
PRINCETON NJ 08540

1 ALLIANT TECHSYSTEMS
G JOHNSON
5050 LINCOLN DR
EDINA MN 55340-1097

1 APPLIED RSRCH ASSN INC
D GRADY
4300 SAN MATEO BLVD NE STE A
ALBUQUERQUE NM 87110

1 BRIGGS COMPANY
J BACKOFEN
2668 PETERSBOROUGH ST
HERNDON VA 20171-2443

3 CERCOM
R PALICKA
G NELSON
B CHEN
1960 WATSON WAY
VISTA CA 92083

1 CYPRESS INTERNTL
A CAPONECCHI
1201 E ABINGDON DR
ALEXANDRIA VA 22314

1 EPSTEIN AND ASSN
K EPSTEIN
2716 WEMBERLY DR
BELMONT CA 94002

NO. OF
COPIES ORGANIZATION

1 GEN RSRCH CORP
PO BOX 6770
SANTA BARBARA CA 93160-6770

1 INTERNATL RSRCH ASSN
D ORPHAL
4450 BLACK AVE
PLEASANTON CA 94566

3 GDLS
W BURKE MZ436 21 24
G CAMPBELL MZ436 30 44
D DEBUSSCHER MZ436 20 29
38500 MOUND RD
STERLING HTS MI 48310-3200

3 GDLS
J ERIDON MZ436 21 24
W HERMAN MZ435 01 24
S PENTESCU MZ436 21 24
38500 MOUND RD
STERLING HTS MI 48310-3200

1 JET PROPULSION LAB
IMPACT PHYSICS GRP
M ADAMS
4800 OAK GROVE DR
PASADENA CA 91109-8099

3 OGARA HESS & EISENHARDT
G ALLEN
D MALONE
T RUSSELL
9113 LE SAINT DR
FAIRFIELD OH 45014

2 ALLVAC OREMET FACLTY
J KOSIN
B MAHONEY
530 34TH AVE SW
PO BOX 460
ALBANY OR 97321

4 POULTER LAB
SRI INTRNTL
D CURRAN
R KLOOP
L SEAMAN
D SHOCKEY
333 RAVENSWOOD AVE
MENLO PARK CA 94025

NO. OF
COPIES ORGANIZATION

6 RMI TITANIUM CO
J BENNETT
E CHRIST
F JANOWSKI
W PALLANTE
S ROBERTSON
O YU
1000 WARREN AVE
NILES OH 44446

1 TIMET
J FANNING
PO BOX 2128
HENDERSON NV 89009

1 SIMULA INC
R WOLFFE
10016 SOUTH 51ST ST
PHOENIX AZ 85044

3 UNITED DEFNS LIMITED PARTNERS
GROUND SYS DIV
E BRADY
R JENKINS
K STRITTMATTER
PO BOX 15512
YORK PA 17405-1512

1 PENN STATE UNIV
APPLIED RSRCH LAB
ACOUSTICS PRGM
D SWANSON
504L APPLIED SCI BLDG
UNIVERSITY PK PA 16803

5 MENA
R DELORME
1001 COLLEGE ST
PO BOX 258
MADISON IL 62060

1 CENTRAL 7
R JONES
80 PALISADE AVE
WHITE PLAINS NY 10607

1 PACIFIC NORTHWEST NATL LAB
E NYBERG
MSIN P7-82
902 BATTELLE BLVD
RICHLAND WA 99352

NO. OF
COPIES ORGANIZATION

1 UNIV OF VIRGINIA
DEPT OF MTRL SCI & ENG
SCHOOL OF ENG & APPL SCI
H WADLEY
B214 THORNTON HALL
116 ENGINEERS WAY
CHARLOTTESVILLE VA 22903

1 CELLULAR MTRLS INTRNTL INC
Y MURTY
2 BOARS HEAD LN
CHARLOTTESVILLE VA 22903

1 EMBASSY OF AUSTRALIA
COUNSELLOR DEFNC SCI
1601 MASSACHUSETTS AVE NW
WASHINGTON DC 20036-2273

1 FORCE PROTECTION INDUST INC
V JOYNT
9801 HWY 78
LADSON SC 29456

2 US ARMY RSRCH DEV & ENGRG CTR
AMSRD NSC IPD B
P CUNNIFF
J WARD
KANSAS ST
NATICK MA 01760-5019

1 NVL SURFC WARFARE CTR
CARDEROCK DIV
R PETERSON CODE 28
9500 MACARTHUR BLVD
WEST BETHESDA MD 20817-5700

1 THE AIR FORCE RSRCH LAB
AFRL/MLLMP
T TURNER
BLDG 655 RM 115
2230 TENTH ST
WRIGHT-PATTERSON AFB OH
45433-7817

1 PRATT & WHITNEY ROCKETDYNE
A PANDEY
PO BOX 109600 MS 702-06
WEST PALM BEACH FL 33410-9600

1 GEN MOTORS CORP
P CREPEAU
MAIL CODE 483-730-472
823 JOSLYN RD
PONTIAC MI 48340

NO. OF
COPIES ORGANIZATION

1 CHRYSLER CORP
R BEALS
CIMS 481-01-41
800 CHRYSLER DR
AUBURN HILLS MI 48326-2757

1 BMW OF NORTH AMERICA LLC
A KHALILI
555 HAMILTON AVE STE 300
PALO ALTO CA 94301

1 MISSOURI UNIV OF SCI & TECHLGY
R MISHRA
B37 MCNUTT HALL
ROLLA MO 65409-0340

1 THIXOMAT
S LEBEAU
620 TECHNLOGY DR
ANN ARBOR MI 48108

1 US INFANTRY CTR
MTRLs LOG NCO – SCI TECHNLOGY
ADVISOR
SOLDIER DIV
S VAKERICS
6731 CONSTITUTION LOOP STE 319
FORT BENNING GA 31905

3 NATL GROUND INTLLGNC CTR
D EPPERLY
T SHAVER
T WATERBURY
2055 BOULDERS RD
CHARLOTTESVILLE VA 22911-8318

3 PROG EXECUTIVE OFC – SOLDIER
US ARMY DIR TECH MGMT
PROJ MGR - SOLDIER EQUIP
K MASTERS
C PERRITT
J ZHENG
15395 JOHN MARSHALL HWY
HAYMARKET VA 20169

1 CERADYNE INC
M NORMANDIA
3169 RED HILL AVE
COSTA MESA CA 92626

NO. OF
COPIES ORGANIZATION

2 SOUTHWEST RSRCH INST
C ANDERSON
J WALKER
6220 CULEBRA RD
PO DRAWER 28510
SAN ANTONIO TX 78228

2 FOSTER-MILLER
J REIGEL
R SYKES
195 BEAR HILL RD
WALTHAM MA 02451

2 SOUTHWEST RSRCH INST
T HOLMQUIST
G JOHNSON
5353 WAYZATA BLVD STE 607
MINNEAPOLIS MN 55416

1 US ARMY RAPID EQUIPPING FORCE
R TURNER
10236 BURBECK RD
BLDG 361T
FORT BELVOIR VA 22060-5806

1 MAGNESIUM TECH RESRCS LLC
S ERICKSON
4241 AUGUSTA CT
HOWELL MI 48843

2 LETTERKENNY ARMY DEPOT
PRODUCTION ENGRNG DIV
AMSAM LE MO E S
K HERSHEY
J FRIDAY
1 OVERCASH AVE
CHAMBERSBURG PA 17201-4150

1 TIMMINCO CORP
DIR BUS DEV
S SHOOK
3595 MOLINE ST
AURORA CO 80010

1 MINE SAFETY APPLIANCES CO
T MOYNIHAN
PO BOX 439
PITTSBURGH PA 15230-0439

1 NATL TECH SYS
S DETRUIT
3070 SW CAPTIVA CT
PALM CITY FL 34990

NO. OF
COPIES ORGANIZATION

- 1 SAINT GOBAIN
D MCELWEE
9 RENEE CT
NORTHGATE COMMONS
NEWARK DE 19711
- 1 DIR US ARMY RSRCH LAB
AMSRD ARL D
J MILLER
V WEISS
2800 POWDER MILL RD
ADELPHI MD 20783-1197
- 1 DIR US ARMY RSRCH LAB
AMSRD ARL SE SA
N SROUR
2800 POWDER MILL RD
ADELPHI MD 20783-1197
- 1 RF
R FAUCONIER
175 HIGH PLAIN RD
ANDOVER MA 01810

ABERDEEN PROVING GROUND

- 1 DIR USA EBCC
SCBRD RT
5183 BLACKHAWK RD
APG EA MD 21010-5424
- 1 CDR USA SBCCOM
AMSCB CII
5183 BLACKHAWK RD
APG EA MD 21010-5424
- 1 DIR USAMSAA
AMSRD AMS D
BLDG 392
- 1 CDR USATEC
STEAC LI LV
E SANDERSON
BLDG 400
- 1 CDR US ARMY DTC
CSTE DTC TT T
M SIMON
RYAN BLDG

NO. OF
COPIES ORGANIZATION

- 86 DIR USARL
AMSRD ARL SL
R COATES
AMSRD ARL SL B
R BOWEN
AMSRD ARL SL BE
A DIETRICH
AMSRD ARL SL BW
W BRUCHEY
L ROACH
AMSRD ARL VT UV
S WILKERSON
AMSRD ARL WM
J MCCAULEY
P PLOSTINS
J SMITH
T WRIGHT
AMSRD ARL WM B
M ZOLTOSKI
AMSRD ARL WM BC
R ANDERSON
AMSRD ARL WM BD
D LOWRY
AMSRD ARL WM M
J BEATTY
B DOWDING
S MCKNIGHT
AMSRD ARL WM MB
R CARTER
L KECSKES
S MATHAUDHU
D SNOHA
AMSRD ARL WM MC
W ROY
R SQUILLACIOTI
AMSRD ARL WM MD
E CHIN
B CHEESEMAN
J CHINELLA
K CHO
J MONTGOMERY
B SCOTT
S WALSH
AMSRD ARL WM SG
T ROSENBERGER
AMSRD ARL WM T
P BAKER
B BURNS
N GNIAZDOWSKI

NO. OF
COPIES ORGANIZATION

AMSRD ARL WM TA
 M BURKINS (5 CPS)
 W GOOCH (5 CPS)
 D HACKBARTH
 T HAVEL
 C HOPPEL
 E HORWATH
 T JONES (5 CPS)
 D KLEPONIS
 C KRAUTHAUSER
 B LEAVY
 D LITTLE
 H MEYER
 J RUNYEON
 S SCHOENFELD
 D SHOWALTER
 K STOFFEL
 AMSRD ARL WM TB
 R BANTON
 R GUPTA
 AMSRD ARL WM TC
 T FARRAND
 K KIMSEY
 L MAGNESS
 R MUDD
 D SCHEFFLER
 S SCHRAML
 S SEGLETES
 R SUMMERS
 W WALTERS
 AMSRD ARL WM TD
 S BILYK
 T BJERKE
 D CASEM
 J CLAYTON
 D DANDEKAR
 M GREENFIELD
 Y HUANG
 B LOVE
 M RAFTENBERG
 E RAPACKI
 M SCHEIDLER
 T WEERASOORIYA
 AMSRD ARL WM TE
 C HUMMER
 B RINGERS

NO. OF
COPIES ORGANIZATION

- 3 AERONAUTICAL & MARITIME
RSCH LAB
N MURMAN
S CIMPOERU
D PAUL
PO BOX 4331
MELBOURNE VIC 3001
AUSTRALIA
- 1 ARMSCOR
L DU PLESSIS
PRIVATE BAG X337
PRETORIA 0001
SOUTH AFRICA
- 1 CARLOS III UNIV OF MADRID
C NAVARRO
ESCUELA POLTEENICA SUPERIOR
C/BUTARQUE 15
28911 LEGANES MADRID
SPAIN
- 1 CELIUS MATERIAL TEKNIK
KARLSKOOGA AB
L HELLNER
S 69180 KARLSKOOGA
SWEDEN
- 3 CENTRE D'ETUDES GRAMAT
J CAGNOUX
C GALLIC
J TRANCHET
GRAMAT 46500
FRANCE
- 1 MINISTRY OF DEFENCE
DGA DSP STTC
G BRAULT
4 RUE DE LA PORTE D'ISSY
00460 ARMEES
F 75015 PARIS
FRANCE
- 1 CONDAT PROJEKT GMBH
ATTN J KIERMEIR
MAXIMILIANSTR 28
SCHEYERN 85298
GERMANY

NO. OF
COPIES ORGANIZATION

- 1 OSAKA UNIVERSITY
JOINING & WELDING RSCH INST
K KONDOH
11-1 MIHOGAOAKA IBARAKI
OSAKA 567-0047 JAPAN
- 2 DEFENCE PROCUREMENT AGCY
G LAUBE
W ODERMATT
BALLISTICS WPNS & COMBAT
VEHICLE TEST CTR
CH 3602 THUN
SWITZERLAND
- 1 TDW EADS
ATTN M HELD
PO BOX 1340
SCHROBENHAUSEN D 86523
GERMANY
- 4 DEFENSE RESEARCH AGENCY
ATTN W CARSON
ATTN T HAWKINS
ATTN B JAMES
ATTN B SHRUBSALL
PORTON DOWN
SALISBURY WTTTS SP04 OJQ
UNITED KINGDOM
- 1 DEFENCE RESEARCH AND
DEVELOPMENT-VALCARTIER
ATTN R DELAGRAVE
2459 PIE XI NORTH
VAL-BELAIR QC G3J 1X5
CANADA
- 2 DEUTSCH FRANZOSISCHES
FORSCHUNGSINSTITUT ST LOUIS
H ERNST
H LERR
CEDEX 5 RUE DU
GENERAL CASSAGNOU
F 68301 SAINT LOUIS
FRANCE
- 1 DIEHL GMBH AND CO
M SCHILDKNECHT
FISCHBACHSTRASSE 16
D 90552 ROTBENBACH AD
PEGNITZ
GERMANY

NO. OF
COPIES ORGANIZATION

- 2 ETBS DSTI
P BARNIER
M SALLES
ROUTE DE GUERAY
BOITE POSTALE 712
18015 BOURGES CEDEX
FRANCE
- 1 FEDERAL MINISTRY OF DEFENCE
DIR OF EQPT & TECH LAND
RUV 2
D HAUG
POSTFACH 1328
53003 BONN
GERMANY
- 4 FRANHOFER INSTITUT FUR
KURZZEITDYNAMIK
ERNST MACH INSTITUT
V HOHLER
E STRASSBURGER
R TRAM
K THOMA
ECKERSTRASSE4
D 79 104 FREIBURG
GERMANY
- 2 HIGH ENERGY DENSITY RSCH CTR
V FORTOV
G KANEL
IZHORSKAY STR 13/19
MOSCOW 127412
RUSSIAN REPUBLIC
- 1 INGENIEURBURO DEISENROTH
F DEISENROTH
AUF DE HARDT 33 35
D 5204 LOHMAR 1
GERMANY
- 1 INST OF CHEMICAL PHYSICS
S RAZORENOV
142432 CHERNOGOLOVKA
MOSCOW REGION
RUSSIAN REPUBLIC
- 1 INST FOR PROBLEMS
OF STRENGTH
G STEPANOV
TIMIRY AZEVSKAYA STR 2
252014 KIEV
UKRAINE

NO. OF
COPIES ORGANIZATION

- 7 INST FOR PROBLEMS IN MATLS SCI
S FIRSTOV
B GALANOV
O GRIGORIEV
V KARTUZOV
V KOVTUN
Y MILMAN
V TREFILOV
3 KRHYZHANOVSKY STR
252142 KIEV 142
UKRAINE
- 3 INST OF MECH ENGR PROBLEMS
V BULATOV
D INDEITSEV
Y MESCHERYAKOV
BOLSHOY 61 VO
ST PETERSBURG 199178
RUSSIAN REPUBLIC
- 2 IOFFE PHYSICO TECH INST
E DROBYSHEVSKI
A KOZHUSHKO
ST PETERSBURG 194021
RUSSIAN REPUBLIC
- 1 R OGORKIEWICZ
18 TEMPLE SHEEN
LONDON SW 14 7RP
UNITED KINGDOM
- 2 NATL DEFENCE HDQRTRS
PMO MRCV MAJ PACEY
PMO LAV A HODAK
OTTOWA ONTARIO KIA OK2
CANADA
- 1 OTO BRED A
M GUALCO
VIA VALDIOCCHI 15
119136 LA SPEZIA
ITALY
- 1 AMERICAN EMBASSY SINGAPORE
E STIERNA
PO BOX ODC FPO AP 96507
- 1 ROYAL NETHERLANDS ARMY
JHOENEVELD
V D BURCHLAAN 31
PO BOX 90822
2509 LS THE HAGUE
NETHERLANDS

NO. OF
COPIES ORGANIZATION

- | | |
|---|--|
| 1 | DEFENCE MATERIEL ADMIN
WEAPONS DIRECTORATE
A BERG
S 11588 STOCKHOLM
SWEDEN |
| 1 | SINGAPORE INST OF MFG TECHLGY
RSRCH SCIENTIST
FORMING TECHNLGY
M CHANDRASEKARAN
71 NANYANG DR
SINGAPORE 638075 |
| 1 | ADVNCED DEF MTRLs LTD
G ROBERSON
SIR FRANK WHITTLE BUSINESS
CENTRE
GREAT CENTRAL WAY RUGBY
WARWICKSHIRE ENGLAND
CV21 3XH |
| 1 | NATL INST FOR MTRLs SCI
MAGNETIC MTRLs CTR
NANOSTRUCTURE ANALYS GR
C MENDIS
1-2-1 SENGEN TSUKUBA
IBARAKI 305-0047 JAPAN |
| 1 | TNO SCIENCE AND INDUST
W SILLEKENS
DE RONDON 1
PO BOX 6235
5600 HE EINDHOVEN
THE NETHERLANDS |
| 1 | BISALLOYS STEELS PTY LTD
W PANG
18 RESOLUTION DR
UNANDERRA NSW 2526 AUSTRALIA |
| 1 | TNO DEFENCE SEC AND SAFETY
F T M VAN WEGEN
LANGE KLEIWEG 137
PO BOX 45
2280 AA RIJSWIJK THE NETHERLANDS |

NO. OF
COPIES ORGANIZATION

- | | |
|---|--|
| 1 | USA ITC-PAC
J P SINGH
7-23-17 ROPPONGI MINATO-KU
TOKYO JAPAN 106-0032 |
| 1 | GKSS FORSCHUNGSZENTRUM
GEESTHACHT GMBH
MAGNESIUM INNVTN CTR
N HORT
MAX PLANCK STR 1 GEB 47
D-21502 GEESTHACHT GERMANY |

INTENTIONALLY LEFT BLANK.