



AFRL-RX-WP-TP-2009-4052

SPECIMEN HETEROGENEITY ANALYSIS; A PRIMER (PREPRINT)

F. Meisenkothen and J.J. Donovan
UES, Inc.

FEBRUARY 2008

Approved for public release; distribution unlimited.

See additional restrictions described on inside pages

STINFO COPY

**AIR FORCE RESEARCH LABORATORY
MATERIALS AND MANUFACTURING DIRECTORATE
WRIGHT-PATTERSON AIR FORCE BASE, OH 45433-7750
AIR FORCE MATERIEL COMMAND
UNITED STATES AIR FORCE**

REPORT DOCUMENTATION PAGE				<i>Form Approved</i> OMB No. 0704-0188	
The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.					
1. REPORT DATE (DD-MM-YY) February 2008		2. REPORT TYPE Proceedings Preprint		3. DATES COVERED (From - To)	
4. TITLE AND SUBTITLE SPECIMEN HETEROGENEITY ANALYSIS; A PRIMER (PREPRINT)				5a. CONTRACT NUMBER F33615-03-C-5206	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER 62102F	
6. AUTHOR(S) F. Meisenkothen (UES, Inc.) J.J. Donovan (University of Oregon)				5d. PROJECT NUMBER 4347	
				5e. TASK NUMBER 13	
				5f. WORK UNIT NUMBER 43471301	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) UES, Inc. Room 066, Bldg 655 10 th and M Streets, Area B Wright-Patterson AFB, OH 45433				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) Air Force Research Laboratory Materials and Manufacturing Directorate Wright-Patterson Air Force Base, OH 45433-7750 Air Force Materiel Command United States Air Force				10. SPONSORING/MONITORING AGENCY ACRONYM(S) AFRL/RXLMP	
				11. SPONSORING/MONITORING AGENCY REPORT NUMBER(S) AFRL-RX-WP-TP-2009-4052	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution unlimited.					
13. SUPPLEMENTARY NOTES Proceedings were presented at Microscopy and Microanalysis 2008, in Albuquerque, New Mexico, on 03 Aug 2008 PAO Case Number and clearance date: WPAFB 08-0310, 11 February 2008. This work was funded in whole or in part by Department of the Air Force contract F33615-03-C-5206. The U.S. Government has for itself and others acting on its behalf an unlimited, paid-up, nonexclusive, irrevocable worldwide license to use, modify, reproduce, release, perform, display, or disclose the work by or on behalf of the U.S. Government.					
14. ABSTRACT The characterization and the quantification of specimen heterogeneity is an issue that is intimately related to the precision, or variability, of the x-ray measurements that are made on a specimen. While the precision of electron probe micro-analysis (EPMA) techniques has been studied thoroughly over the past 55 years, it is less often discussed in relation to the topic of specimen heterogeneity. For the beginning analyst, the relationship between the statistical interpretation of the data and the application of the various heterogeneity equations can be confusing. The NIST-Analysis of Variance (ANOVA) procedure provides a rigorous method for evaluating heterogeneity within research materials; however, a quick estimate of the heterogeneity range is often all that is required for a single specimen that is not intended to be used as a standard reference material [1]. For these instances, legacy equations, such as the one proposed by Goldstein, et al, have been suggested because they are quick and easy to apply [2].					
15. SUBJECT TERMS Electron probe micro-analysis, EPMA, specimen heterogeneity, ANOVA, legacy equation					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT: SAR	18. NUMBER OF PAGES 8	19a. NAME OF RESPONSIBLE PERSON (Monitor) David W. Mahaffey 19b. TELEPHONE NUMBER (Include Area Code) N/A
a. REPORT Unclassified	b. ABSTRACT Unclassified	c. THIS PAGE Unclassified			

Specimen Heterogeneity Analysis ; A Primer

F. Meisenkothen* and J. J. Donovan**

*UES, Inc., Room 066, Bldg 655, 10th and M Streets, Area B, Wright-Patterson AFB, OH 45433

**University of Oregon, Department of Geological Sciences, Eugene, OR, 97403

The characterization and the quantification of specimen heterogeneity is an issue that is intimately related to the precision, or variability, of the x-ray measurements that are made on a specimen. While the precision of electron probe micro-analysis (EPMA) techniques has been studied thoroughly over the past 55 years, it is less often discussed in relation to the topic of specimen heterogeneity. For the beginning analyst, the relationship between the statistical interpretation of the data and the application of the various heterogeneity equations can be confusing. The NIST-Analysis of Variance (ANOVA) procedure provides a rigorous method for evaluating heterogeneity within research materials; however, a quick estimate of the heterogeneity range is often all that is required for a single specimen that is not intended to be used as a standard reference material [1]. For these instances, legacy equations, such as the one proposed by Goldstein, et al, have been suggested because they are quick and easy to apply [2]. The present work takes a close look at the equation proposed by Goldstein et al, and suggests that the equation should be revised to make it better able to describe the homogeneity range found within a single specimen. The study will also include modifications to the equation for the standard deviation of the mean concentration that was proposed by Lifshin, et al [3]. Though the Lifshin, et al equation was not originally intended for use in heterogeneity studies, it can be generalized, and thus made applicable for this purpose.

Multiple EPMA-WDS heterogeneity analyses were conducted on two different titanium alloy specimens; one a nominally homogeneous alloy (Alloy 1), the other a non-homogeneous alloy (Alloy 2). Following the procedures outlined in Marinenko, et al, a full ANOVA heterogeneity study was done on both of the specimen materials [1]. The ANOVA study was used to establish benchmarks for the evaluation of two equation revisions that are proposed in this work. The large amount of data collected for the ANOVA study also made it possible to directly calculate the variation within the weight percent data set, providing a second benchmark for comparisons. Tables 1-2 (Alloy 1) and Tables 3-4 (Alloy 2) provide a summary of the calculation results of these heterogeneity studies. The homogeneity range for each alloy is given in Table 1 and Table 3, with the corresponding homogeneity levels being shown in Tables 2 and Table 4, respectively. The revised Goldstein, et al and the Lifshin, et al equations perform well in comparison with the two benchmark studies.

References

- [1] Marinenko, R. and Leigh, S., *Microscopy and Microanalysis*, 10, #4, (2004), 491.
- [2] Goldstein, J.I. et al, *Scanning Electron Microscopy and X-ray Microanalysis*, 2nd Edition, Plenum Press, NY, 1992.
- [3] Lifshin, E. et al, *Microscopy and Microanalysis*, 4, #6, (1998), 498.
- [4] The authors would like to thank the following people for many helpful discussions related to the investigation of this topic; Dale Newbury and Ryna Marinenko of N.I.S.T., Eric Lifshin of

S.U.N.Y., Albany, Paul Shade, Robert Wheeler, and Michael Uchic of the Air Force Research Laboratory, and Dan Kremser of Battelle.

TABLE 1. Alloy 1 Homogeneity Range (3-Sigma Confidence)

	<u>Al</u>	<u>Ti</u>	<u>Zr</u>	<u>Mo</u>	<u>Sn</u>	
<i>(Mean Concentration)</i>	<i>(6.1)</i>	<i>(85.9)</i>	<i>(3.9)</i>	<i>(2.02)</i>	<i>(2.02)</i>	<i>(% wt.)</i>
Weight Percent Data Set	± 0.1	± 0.6	± 0.2	± 0.04	± 0.04	(% wt.)
Marinenko - ANOVA	± 0.1	± 0.7	± 0.2	± 0.05	± 0.04	(% wt.)
Goldstein - Original	± 0.01	± 0.04	± 0.01	± 0.002	± 0.002	(% wt.)
Goldstein - Revised	± 0.1	± 0.6	± 0.2	± 0.04	± 0.03	(% wt.)
Lifshin - Generalized	± 0.1	± 0.6	± 0.2	± 0.04	± 0.04	(% wt.)

TABLE 2. Alloy 1 Homogeneity Level (3-Sigma Confidence)

	<u>Al</u>	<u>Ti</u>	<u>Zr</u>	<u>Mo</u>	<u>Sn</u>	
<i>(Mean Concentration)</i>	<i>(6.1)</i>	<i>(85.9)</i>	<i>(3.9)</i>	<i>(2.02)</i>	<i>(2.02)</i>	<i>(% wt.)</i>
Weight Percent Data Set	2%	1%	5%	2%	2%	
Marinenko - ANOVA	2%	1%	5%	2%	2%	
Goldstein - Original	0.1%	0.04%	0.3%	0.1%	0.1%	
Goldstein - Revised	2%	1%	5%	2%	2%	
Lifshin - Generalized	2%	1%	5%	2%	2%	

TABLE 3. Alloy 2 Homogeneity Range (3-Sigma Confidence)

	<u>Al</u>	<u>Ti</u>	<u>Mn</u>	<u>Nb</u>	
<i>(Mean Concentration)</i>	<i>(31)</i>	<i>(53)</i>	<i>(3)</i>	<i>(13)</i>	<i>(% wt.)</i>
Weight Percent Data Set	± 5	± 4	± 1	± 1	(% wt.)
Marinenko - ANOVA	± 6	± 4	± 1	± 1	(% wt.)
Goldstein - Original	± 0.3	± 0.3	± 0.06	± 0.07	(% wt.)
Goldstein - Revised	± 6	± 4	± 1	± 1	(% wt.)
Lifshin - Generalized	± 5	± 4	± 1	± 1	(% wt.)

TABLE 4. Alloy 2 Homogeneity Level (3-Sigma Confidence)

	<u>Al</u>	<u>Ti</u>	<u>Mn</u>	<u>Nb</u>	
<i>(Mean Concentration)</i>	<i>(31)</i>	<i>(53)</i>	<i>(3)</i>	<i>(13)</i>	<i>(% wt.)</i>
Weight Percent Data Set	17%	7%	45%	9%	
Marinenko - ANOVA	19%	8%	45%	9%	
Goldstein - Original	1%	0.5%	2%	1%	
Goldstein - Revised	18%	8%	39%	9%	
Lifshin - Generalized	17%	7%	45%	9%	