

REPORT DOCUMENTATION PAGE			Form Approved OMB NO. 0704-0188		
<p>The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA, 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.</p> <p>PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.</p>					
1. REPORT DATE (DD-MM-YYYY)		2. REPORT TYPE		3. DATES COVERED (From - To)	
		New Reprint		-	
4. TITLE AND SUBTITLE Nonlinear optical transmission of lead phthalocyaninedopednematic liquid crystal composites for multiscale nonlinearswitching from nanosecond to continuous wave			5a. CONTRACT NUMBER		
			W911NF-06-1-0283		
			5b. GRANT NUMBER		
6. AUTHORS ChuanXiang Sheng, Robert A. Norwood, Jiafu Wang, Jayan Thomas			5c. PROGRAM ELEMENT NUMBER		
			611103		
			5d. PROJECT NUMBER		
7. PERFORMING ORGANIZATION NAMES AND ADDRESSES University of Central Florida Office of Research University of Central Florida Orlando, FL 32826 -0150			5e. TASK NUMBER		
			5f. WORK UNIT NUMBER		
			8. PERFORMING ORGANIZATION REPORT NUMBER		
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) U.S. Army Research Office P.O. Box 12211 Research Triangle Park, NC 27709-2211			10. SPONSOR/MONITOR'S ACRONYM(S) ARO		
			11. SPONSOR/MONITOR'S REPORT NUMBER(S) 50372-CH-MUR.115		
12. DISTRIBUTION AVAILABILITY STATEMENT Approved for public release; distribution is unlimited.					
13. SUPPLEMENTARY NOTES The views, opinions and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy or decision, unless so designated by other documentation.					
14. ABSTRACT We have formulated composites of lead (II) tetrakis (4-cumylphenoxy) phthalocyanine (PbTCPC) doped into nematic liquid crystal (LC), 40-pentyl-4-biphenylcarbonitrile (5-CB), that has received a 90° twisted alignment and investigated the nonlinear transmission properties using both pulsed (Nd:YLF 524nm, 5 ns) and cw (532 nm) lasers. In the nanosecond regime, this compound is a reverse saturable absorber performing					
15. SUBJECT TERMS nonlinear optics, liquid crystals, organic dye, nonlinear switching					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT	15. NUMBER OF PAGES	19a. NAME OF RESPONSIBLE PERSON
a. REPORT	b. ABSTRACT	c. THIS PAGE			Eric Van Stryland
UU	UU	UU	UU		19b. TELEPHONE NUMBER
					407-823-6835

## **Report Title**

Nonlinear optical transmission of lead phthalocyaninedopednematic liquid crystal composites for multiscale nonlinearswitching from nanosecond to continuous wave

### **ABSTRACT**

We have formulated composites of lead (II) tetrakis (4-cumylphenoxy) phthalocyanine (PbTCPc) doped into nematic liquid crystal (LC), 40-pentyl-4-biphenylcarbonitrile (5-CB), that has received a 90° twisted alignment and investigated the nonlinear transmission properties using both pulsed (Nd:YLF 524nm, 5 ns) and cw (532 nm) lasers. In the nanosecond regime, this compound is a reverse saturable absorber performing

---

**REPORT DOCUMENTATION PAGE (SF298)**  
**(Continuation Sheet)**

---

Continuation for Block 13

ARO Report Number 50372.115-CH-MUR  
Nonlinear optical transmission of lead phthalocyanine ...

Block 13: Supplementary Note

© 2009 . Published in Applied Optics, Vol. Ed. 0 48, (14) (2009), ( 14). DoD Components reserve a royalty-free, nonexclusive and irrevocable right to reproduce, publish, or otherwise use the work for Federal purposes, and to authorize others to do so (DODGARS §32.36). The views, opinions and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy or decision, unless so designated by other documentation.

Approved for public release; distribution is unlimited.

# Nonlinear optical transmission of lead phthalocyanine-doped nematic liquid crystal composites for multiscale nonlinear switching from nanosecond to continuous wave

ChuanXiang Sheng,<sup>1,\*</sup> Robert A. Norwood,<sup>1</sup> Jiafu Wang,<sup>1</sup> Jayan Thomas,<sup>1</sup>  
Diane Steeves,<sup>2</sup> Brian Kimball,<sup>2</sup> and N. Peyghambarian<sup>1</sup>

<sup>1</sup>College of Optical Sciences, University of Arizona, Tucson, Arizona 85721, USA

<sup>2</sup>AMSRD-NSC-WS-N, Kansas Street, Natick, Massachusetts 01760-5020, USA

\*Corresponding author: cxsheng@yahoo.com

Received 24 February 2009; accepted 16 March 2009;  
posted 20 April 2009 (Doc. ID 107950); published 6 May 2009

We have formulated composites of lead (II) tetrakis (4-cumylphenoxy) phthalocyanine (PbTCPc) doped into nematic liquid crystal (LC), 4'-pentyl-4-biphenylcarbonitrile (5-CB), that has received a 90° twisted alignment and investigated the nonlinear transmission properties using both pulsed (Nd:YLF 524 nm, 5 ns) and cw (532 nm) lasers. In the nanosecond regime, this compound is a reverse saturable absorber performing similarly to low-concentration solutions of PbTCPc. Under cw conditions, we observe optically self-activated polarization switching with low threshold input energy. Our results suggest the potential for an all-optical switch working from the nanosecond time scale to cw. © 2009 Optical Society of America

OCIS codes: 190.5940, 160.4330.

Nonlinear transmission can be used to protect optical sensors or human eyes from the damage caused by high intensity lasers. Many nonlinear optical processes, such as thermal diffraction [1], molecular reorientation [2,3], multiphoton absorption [4], and reverse saturable absorption (RSA) [5,6], and corresponding materials have been studied. In recent years, organic macromolecules, such as phthalocyanines (Pc) and their metal complexes have been widely studied because their strong RSA effect is promising for nonlinear optical applications in the nanosecond (ns) regime, especially when heavy metal atoms are substituted at the center [7–11], as this increases the population of molecules in the triplet ground state. One major challenge for applications is presented by the multiple time scales of laser

sources: materials that work at one time scale are often useless at others. For example, Pc macromolecules work mainly in the ns regime because this is the relevant time scale for intersystem crossing from the singlet to the triplet state. On the other hand, laser-induced polarization switching has been studied in dye-doped nematic liquid crystals (LCs) for passive all-optical switching at the microsecond time scale and above [2,12].

In this work, we have combined these two materials into a composite that takes advantage of each of their beneficial properties in one system. The lead (II) tetrakis (4-cumylphenoxy) phthalocyanine (PbTCPc) was dissolved in a twisted alignment nematic LC, 4'-pentyl-4-biphenylcarbonitrile (5CB). We established this to be an effective process for making an easily fabricated, phase-stable PbTCPc/LC compound nonlinear optical switch. With an appropriate concentration of dye, the devices provided performance comparable to that of dilute solutions of

## Report Documentation Page

*Form Approved*  
*OMB No. 0704-0188*

Public reporting burden for the collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to a penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.

1. REPORT DATE <b>2009</b>	2. REPORT TYPE	3. DATES COVERED <b>00-00-2009 to 00-00-2009</b>			
4. TITLE AND SUBTITLE <b>Nonlinear optical transmission of lead phthalocyanine doped nematic liquid crystal composites for multiscale nonlinear switching from nanosecond to continuous wave</b>		5a. CONTRACT NUMBER <b>W911NF-06-1-0283</b>			
		5b. GRANT NUMBER			
		5c. PROGRAM ELEMENT NUMBER			
6. AUTHOR(S)		5d. PROJECT NUMBER			
		5e. TASK NUMBER			
		5f. WORK UNIT NUMBER			
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) <b>College of Optical Sciences, University of Arizona, Tucson, AZ, 85721</b>		8. PERFORMING ORGANIZATION REPORT NUMBER <b>; 50372-Ch-MUR.16</b>			
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) <b>U.S. Army Research Office, P.O. Box 12211, Research Triangle Park, NC, 27709-2211</b>		10. SPONSOR/MONITOR'S ACRONYM(S)			
		11. SPONSOR/MONITOR'S REPORT NUMBER(S) <b>50372-Ch-MUR.16</b>			
12. DISTRIBUTION/AVAILABILITY STATEMENT <b>Approved for public release; distribution unlimited</b>					
13. SUPPLEMENTARY NOTES					
14. ABSTRACT					
15. SUBJECT TERMS					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT <b>Same as Report (SAR)</b>	18. NUMBER OF PAGES <b>4</b>	19a. NAME OF RESPONSIBLE PERSON
a. REPORT <b>unclassified</b>	b. ABSTRACT <b>unclassified</b>	c. THIS PAGE <b>unclassified</b>			

PbTCPc in the ns regime [8]. Conversely, the same device exhibited optically activated polarization switching with low threshold energy, suitable for continuous-wave (cw) optical switching.

The nonlinear absorption dye used was lead tetrakis (4-cumylphenoxy) phthalocyanine (PbTCPc, 90%, Aldrich). Roughly 3% by weight PbTCPc was doped into the nematic LC, 4'-pentyl-4-biphenylcarbonitrile (5-CB, 98% pure, Aldrich). The glass window surface was coated with 300 nm of polyvinyl alcohol (PVA, Sigma), and the PVA film was subsequently rubbed unidirectionally to create planar alignment. The cells were prepared using two glass substrates with their alignment layers orthogonal to each other, separated by a 140  $\mu\text{m}$  spacer and a 70  $\mu\text{m}$  spacer for Samples 1 and 2, respectively. When filled with the dye/LC mixture and sealed with epoxy, a 90° twisted alignment PbTCPc-doped nematic LC cell is thus fabricated. Figure 1 shows pictures of Sample 1 and Sample 2, each of which had been stored in air for more than two weeks; the pictures were taken after all the measurements had been done. The lower part of Fig. 1 depicts the 90° twisted alignment of the nematic LC cell.

The nonlinear transmission experiments were performed with a frequency doubled Nd:YLF laser (524 nm), which provides 5 ns width pulses with a repetition rate of 1 Hz. We used two polarizers in series to act as an attenuator for adjusting the incident laser energy; then the input laser was split into two beams, one being employed as a reference and the other focused onto the sample using a 10 cm focal length lens. The reference and transmitted laser energies were collected with a lens and measured simultaneously by two identical photodiodes. The response of the system over the fluence dynamic range of this work has been checked using a glass substrate as a linear reference sample. The linear transmittance was determined by dividing the signal magnitude on the detector photodiode with the sample in the beam and without the sample in the beam at low fluence, which were 0.37 and 0.62 at 524 nm




Fig. 1. (Color online) Images of two samples and schematic view of the twist of LC between planar glass windows with orthogonally oriented PVA alignment layers.

for Sample 1 and Sample 2, respectively, as expected considering the thicknesses of the two samples.

The cw laser measurement setup was similar to the pulsed laser one, except that the sample was placed between two crossed polarizers and the laser was unfocused. The polarization direction of the input laser beam was parallel to the rubbed direction of the incident glass substrate. The transmitted light will be ordinarily rotated 90° by the LC cell, according to the Mauguin theorem. Therefore, the transmission through the analyzer is expected to be at a maximum.

Figure 2 shows the normalized transmittance as a function of input fluence for Sample 1 and Sample 2 for ns pulse measurements. We define the threshold for nonlinear transmission to be the incident fluence for which the transmittance of the film is 50% of the linear transmittance. Thus, the threshold fluence is 40 and 75  $\text{mJ}/\text{cm}^2$  for Sample 1 and Sample 2, respectively, which is comparable to the threshold of  $\sim 70 \text{ mJ}/\text{cm}^2$  observed in PbTCPc solution with 62% linear transmittance when measured by a similar ns 532 nm Nd:YAG laser [8].

It has been discussed that the mechanism of nonlinear transmission for heavy-atom-substituted Pcs in the ns regime can be attributed to the RSA effect from both singlet excited states and triplet states [7–11]. Nonlinear absorption processes for metallo-phthalocyanines (MPcs) have been studied in detail using five-level models, depicted schematically in Fig. 3 [13]. An electron in the ground state absorbs one photon and is excited to first singlet state  $S_1$  with cross section  $\sigma_g$ . The excited electron may directly absorb another photon and be promoted to a higher singlet excited state  $S_2$  with a cross section  $\sigma_s$ , or can undergo an intersystem crossing transition to the triplet state  $T_1$ , before relaxing back to ground state. Subsequently, the electron in the  $T_1$  state may also absorb another photon, thereby occupying a higher




Fig. 2. (Color online) Normalized nonlinear transmission of PbTCPc-doped LC cells, as well as PbTCPc dilute solution (inset), with respective fitting results.




Fig. 3. Schematic diagram of the five-level model and equivalent quasi-three-level model.

triplet state with a cross section  $\sigma_t$ , or decay back to ground state as well. If the weak absorption from the ground states results in a substantial electron population in any of the lowest excited states ( $S_1$  or  $T_1$ ), and those excited states have larger absorption cross sections than  $\sigma_g$ , an overall decrease in transmittance upon excitation is expected. Consequently, the nonlinear transmission properties are a function of the input fluence as well as pulse duration. For example, if the lifetime for electrons' transition from the  $S_1$  states to  $T_1$  states, i.e.,  $1/K_{isc}$ , is much longer than pulse width, the contributions of the triplet states to nonlinear absorption can be neglected. If only total pulse fluence is of interest, the quasi-three-level system shown in Fig. 3, which consists of ground state absorption and an equivalent excited state absorption process [13], can be used to describe the nonlinear absorption. The equivalent excited absorption,  $\sigma_{ex}$ , can range from  $\sigma_s$  to  $\sigma_t$  and is finally determined by the lifetimes of the energy levels, the intersystem crossing rate  $K_{isc}$ , and the laser pulse width. Although  $\sigma_{ex}$  has no direct physical meaning, it is a convenient parameter for comparing the performance among materials for a given laser system.

Within the three-level approximation, the total pulse fluence  $F$  changes with  $z$  according to Ref. [13]:

$$\frac{\partial F}{\partial z} = -(\sigma_{ex}N_0 - (\sigma_g - \sigma_{ex}) \times [\exp(-F/F_s) - 1]N_0F_s/F)F; \quad (1)$$

$\sigma_g$  is the ground state absorption cross section, which has been determined by linear transmittance measurements of dilute solutions to be  $2.0 \times 10^{-18} \text{ cm}^2$ .  $F_s = h\nu/\sigma_g$  is the saturation fluence. Therefore, only one unknown parameter,  $\sigma_{ex}$ , must be determined to fit the measurements shown in Fig. 2. For reference, a dilute PbTCPc solution sample with a concentration of 0.43 mg/ml was prepared in a 1 mm cell with a linear transmittance of 62% and limiting threshold of  $75 \text{ mJ/cm}^2$ . The nonlinear transmission versus input fluence of the solution was fitted using Eq. (1) as well (Fig. 2 inset). All the data are well fitted by  $\sigma_{ex} = 33 \times 10^{-18} \text{ cm}^2$ , which is close to  $\sigma_t$  of  $\sim 33 \times 10^{-18} \text{ cm}^2$  and  $\sigma_s$  of  $40 \times 10^{-18} \text{ cm}^2$  of lead Pc dilute solutions [14]. Therefore, we conclude that

MPc-doped LC cells can be as effective a nonlinear absorber as MPc dilute solution.

Figure 4 shows the transmitted power as the function of the input power in the cw measurements. The laser is unfocused with a beam diameter of 4 mm, and the sample is illuminated for 10 s for each data point. The threshold power, defined as the input power at which the output power begins to decrease, is 110 and 250 mW for Sample 1 and Sample 2, respectively; for completeness, a pure twisted LC cell of  $70 \mu\text{m}$  thickness has been tested, and there is no polarization switching effect observed using the same experimental procedure. For smaller beam size, the power threshold is reduced correspondingly. For example, using the same measurement procedure, the threshold for Sample 1 with another unfocused 532 nm laser with a beam diameter of 1.5 mm is about 30 mW. The underlying mechanism could be laser-induced LC molecular axis reorientation (assisted by dye) and/or order parameter modifications, from whence the LC cell stops rotating the polarization direction of the light, showing that the crossed polarizer pair can switch off light effectively as shown in Fig. 4 [10]. This polarization switching process can operate at microsecond speeds for higher input intensities [11].

To further investigate the cw configuration, we made another composite, using the dye EUT-57, at roughly 0.76% weight ratio in 5-CB and placed it in a  $70 \mu\text{m}$  LC cell with alignment layers and orientation as described above. The threshold power in this case is 25 mW as shown in Fig. 5; a picture of the fabricated cell is shown in the inset. With a smaller beam size, the power threshold is reduced. For example, with a focused beam (diameter of  $80 \mu\text{m}$ ), the power threshold was reduced to about 1.5 mW, indicating that very low power operation is possible with further optimization.

In conclusion, we have presented RSA and polarization switching effects in one sample of a nonlinear absorber dye (PbTCPc) doped in nematic liquid




Fig. 4. (Color online) Transmitted power as a function of the input laser power for an unfocused laser.




Fig. 5. (Color online) Transmitted power as a function of the input laser power for an unfocused laser for the EUT-57/5-CB composite; the inset shows a photograph of the sample.

crystals and have further investigated cw operation in another composite of EUT-57 and LC. The PbTCPc device works for both nanosecond pulses as well as cw and provides a promising approach to fabricating passive all-optical switches for multiple-time-scale lasers.

We acknowledge support from the U.S. Army through the Natick Soldier Center, Nanomaterial Science Team. This paper is also based on work supported in part by the U.S. Army Research Office (ARO) under contract/grant number 50372-CH-MUR.

## References

1. X. Yang, S. Qi, K. Chen, C. Zhang, J. Tian, and Q. Wu, "Optical limiting characteristics of mercury dithizonate in polymer film," *Opt. Mater.* **27**, 1358–1362 (2005).
2. I. C. Khoo, J.-H. Park, and J. Liou, "All-optical switching of continuous wave, microsecond lasers with a dye-doped nematic liquid crystal," *Appl. Phys. Lett.* **90**, 151107 (2007).
3. C.-X. Sheng, R. A. Norwood, J. Wang, J. Thomas, Y. Wu, Z. Zheng, N. Tabirian, D. M. Steeves, B. R. Kimball, and N. Peyghambarian, "Time-resolved studies of photoinduced birefringence in azobenzene dye-doped polymer films," *Appl. Opt.* **47**, 5074–5077 (2008).
4. N. Venkatram, D. N. Rao, and M. A. Akundi, "Nonlinear absorption, scattering and optical limiting studies of CdS nanoparticles," *Opt. Express* **13**, 867–872 (2005).
5. Y.-P. Sun and J. E. Riggs, "Organic and inorganic optical limiting materials. From fullerenes to nanoparticles," *Int. Rev. Phys. Chem.* **18**, 43–90 (1999).
6. D. T. Nguyen, C.-X. Sheng, J. Thomas, R. Norwood, B. Kimball, D. M. Steeves, and N. Peyghambarian, "Observation of nonlinear transmission enhancement in cavities filled with nonlinear organic materials," *Appl. Opt.* **47**, 5777–5783 (2008).
7. C. C. Byeon, M. M. McKerns, W. Sun, T. M. Nordlund, and C. M. Lawson, "Excited state lifetime and intersystem crossing rate of asymmetric pentaazadentate porphyrin-like metal complexes," *Appl. Phys. Lett.* **84**, 5174–5176 (2004).
8. J. S. Shirk, R. G. S. Pong, F. J. Bartoli, and A. W. Snow, "Optical limiter using a lead phthalocyanine," *Appl. Phys. Lett.* **63**, 1880–1882 (1993).
9. A. Santhi, V. V. Namboodiri, P. Radhakrishnan, and V. P. N. Nampoore, "Spectral dependence of third order nonlinear optical susceptibility of zinc phthalocyanine," *J. Appl. Phys.* **100**, 053109 (2006).
10. J. W. Perry, K. Mansour, S. R. Marder, K. J. Perry, S. Alvarez, Jr., and I. Choong, "Enhanced reverse saturable absorption and optical limiting in heavy-atom-substituted phthalocyanines," *Opt. Lett.* **19**, 625–627 (1994).
11. J. W. Perry, K. Mansour, J. Y. S. Lee, X. L. Xu, P. V. Bedworth, C. T. Chen, D. Ng, S. R. Marder, P. Miles, T. Wada, M. Tian, and H. Sasabe, "Organic optical limiter with a strong nonlinear absorptive response," *Science* **273**, 1533–1536 (1996).
12. I. C. Khoo, J. H. Park, and J. Liou, "Theory and experimental studies of all-optical transmission switching in a twist-alignment dye-doped nematic liquid crystal," *J. Opt. Soc. Am. B* **25**, 1931–1937 (2008).
13. T. Xia, D. J. Hagan, A. Dogariu, A. A. Said, and E. W. Van Stryland, "Optimization of optical limiting devices based on excited-state absorption," *Appl. Opt.* **36**, 4110–4122 (1997).
14. P. A. Miles, "Bottleneck optical limiters: the optimal use of excited-state absorbers," *Appl. Opt.* **33**, 6965–6979 (1994).