

REPORT DOCUMENTATION PAGE					<i>Form Approved</i> <i>OMB No. 0704-0188</i>	
The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing the burden, to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.						
1. REPORT DATE (DD-MM-YYYY) 04-22-2010		2. REPORT TYPE Final			3. DATES COVERED (From - To) 09-01-07 to 05-31-08	
4. TITLE AND SUBTITLE The Birth, Life and Death of the CNT: Imaging Carbon Nanotube Growth				5a. CONTRACT NUMBER W911NF-07-0550		
				5b. GRANT NUMBER NA		
				5c. PROGRAM ELEMENT NUMBER NA		
6. AUTHOR(S) Eric A. Stach				5d. PROJECT NUMBER 52909MS1107122		
				5e. TASK NUMBER		
				5f. WORK UNIT NUMBER		
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Purdue University Birck Nanotechnology Center 1205 W. State St., West Lafayette, IN 47907					8. PERFORMING ORGANIZATION REPORT NUMBER RNON	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) Dr. David M. Stepp U.S. Army Research Office AMSRD-ARL-RO-EM (Materials Science Division) P.O. Box 12211 Research Triangle Park, NC 27709-2211					10. SPONSOR/MONITOR'S ACRONYM(S) ARO	
					11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution unlimited.						
13. SUPPLEMENTARY NOTES						
14. ABSTRACT Carbon nanotubes have received extraordinary attention, in part because of their unique mechanical and electronic properties. Despite an enormous number of studies concerning their properties and potential applications, relatively little is known regarding the mechanisms by which they nucleate and grow. This is presently the predominant reason that their application is not widespread: we cannot make them either efficiently enough to yield high volume / low cost materials or with sufficient control for applications in electronics.						
15. SUBJECT TERMS						
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT UU	18. NUMBER OF PAGES	19a. NAME OF RESPONSIBLE PERSON	
a. REPORT U	b. ABSTRACT U	c. THIS PAGE U			19b. TELEPHONE NUMBER (Include area code)	

Reset

INSTRUCTIONS FOR COMPLETING SF 298

1. REPORT DATE. Full publication date, including day, month, if available. Must cite at least the year and be Year 2000 compliant, e.g. 30-06-1998; xx-06-1998; xx-xx-1998.

2. REPORT TYPE. State the type of report, such as final, technical, interim, memorandum, master's thesis, progress, quarterly, research, special, group study, etc.

3. DATES COVERED. Indicate the time during which the work was performed and the report was written, e.g., Jun 1997 - Jun 1998; 1-10 Jun 1996; May - Nov 1998; Nov 1998.

4. TITLE. Enter title and subtitle with volume number and part number, if applicable. On classified documents, enter the title classification in parentheses.

5a. CONTRACT NUMBER. Enter all contract numbers as they appear in the report, e.g. F33615-86-C-5169.

5b. GRANT NUMBER. Enter all grant numbers as they appear in the report, e.g. AFOSR-82-1234.

5c. PROGRAM ELEMENT NUMBER. Enter all program element numbers as they appear in the report, e.g. 61101A.

5d. PROJECT NUMBER. Enter all project numbers as they appear in the report, e.g. 1F665702D1257; ILIR.

5e. TASK NUMBER. Enter all task numbers as they appear in the report, e.g. 05; RF0330201; T4112.

5f. WORK UNIT NUMBER. Enter all work unit numbers as they appear in the report, e.g. 001; AFAPL30480105.

6. AUTHOR(S). Enter name(s) of person(s) responsible for writing the report, performing the research, or credited with the content of the report. The form of entry is the last name, first name, middle initial, and additional qualifiers separated by commas, e.g. Smith, Richard, J, Jr.

7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES). Self-explanatory.

8. PERFORMING ORGANIZATION REPORT NUMBER. Enter all unique alphanumeric report numbers assigned by the performing organization, e.g. BRL-1234; AFWL-TR-85-4017-Vol-21-PT-2.

9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES). Enter the name and address of the organization(s) financially responsible for and monitoring the work.

10. SPONSOR/MONITOR'S ACRONYM(S). Enter, if available, e.g. BRL, ARDEC, NADC.

11. SPONSOR/MONITOR'S REPORT NUMBER(S). Enter report number as assigned by the sponsoring/monitoring agency, if available, e.g. BRL-TR-829; -215.

12. DISTRIBUTION/AVAILABILITY STATEMENT. Use agency-mandated availability statements to indicate the public availability or distribution limitations of the report. If additional limitations/ restrictions or special markings are indicated, follow agency authorization procedures, e.g. RD/FRD, PROPIN, ITAR, etc. Include copyright information.

13. SUPPLEMENTARY NOTES. Enter information not included elsewhere such as: prepared in cooperation with; translation of; report supersedes; old edition number, etc.

14. ABSTRACT. A brief (approximately 200 words) factual summary of the most significant information.

15. SUBJECT TERMS. Key words or phrases identifying major concepts in the report.

16. SECURITY CLASSIFICATION. Enter security classification in accordance with security classification regulations, e.g. U, C, S, etc. If this form contains classified information, stamp classification level on the top and bottom of this page.

17. LIMITATION OF ABSTRACT. This block must be completed to assign a distribution limitation to the abstract. Enter UU (Unclassified Unlimited) or SAR (Same as Report). An entry in this block is necessary if the abstract is to be limited.

The Birth, Life and Death of the CNT: Imaging Carbon Nanotube Growth


PI: Eric A. Stach, Purdue University

Carbon nanotubes have received extraordinary attention, in part because of their unique mechanical and electronic properties. Despite an enormous number of studies concerning their properties and potential applications, relatively little is known regarding the mechanisms by which they nucleate and grow. This is presently the predominant reason that their application is not widespread: we cannot make them either efficiently enough to yield high volume / low cost materials or with sufficient control for applications in electronics.

The primary reason that we lack this understanding is because of the difficulties of finding appropriate characterization methods to quantify how these processes occur. The best technique to characterize individual nanotubes is transmission electron microscopy (TEM). However, TEM is generally a static imaging technique. During this STTR grant period we have optimized a unique new environmental-cell transmission electron microscope (E-TEM) at Purdue's Birck Nanotechnology Center to observe nanotube growth processes directly, at elevated temperature and pressure and with atomic level resolution. This development has included creation of appropriate sample geometries that mimic the catalyst substrate systems used for the growth of high-quality and high-density nanotube 'carpet' arrays and the reworking of the TEM vacuum and gas manifold systems to yield conditions for controlled nanotube synthesis. At the end of the grant period, we were in a position where nanotube nucleation and growth visualization is a routine accomplishment.

We have utilized these observations to understand a number of phenomena associated with nanotube growth. Perhaps most importantly, during the course of early, unsuccessful experimentation we noticed that the catalysts responsible for nanotube nucleation exhibited a strong tendency to coarsen via the Ostwald ripening mechanism. In this mechanism, larger particles grow at the expense of smaller ones, as the large ones have a lower chemical potential due to their smaller surface free energy.

Working with the Hauge group at Rice and Dr. Benji Maruyama at WP-AFRL, we have systematically demonstrated that Ostwald ripening was a mechanism by which nanotube growth terminates, and that catalyst conditioning via both atomic hydrogen exposure and controlled water vapor incorporation during growth leads to substantially longer nanotube growths. These systematic observations were correlated with in-situ observations (such as those shown here) of catalyst coarsening at the termination of growth. These results have important ramifications on creation of high yield nanotube carpet arrays: systems of interest for applications such as field emission and for interconnecting polymer composite laminates.




Real time images of nanotube growth and termination, acquired at 650°C in 2.5 mTorr C₂H₂ and 7.5 mTorr H₂.

The catalyst that is circled coarsens via the Ostwald ripening process.

Observing nanotube nucleation & growth





- Understanding nanostructure synthesis requires real time observations of nucleation, growth and growth termination.
- We utilize a unique new transmission electron microscope to watch growth processes as they happen, at temperature, pressure and atomic resolution.
- During the grant period we optimized the system (microscope, gas manifolds, sample preparation) to yield routine in-situ nanotube growth



Plan view TEM image of nanotube nucleation and growth. Rapid extension of the tube between images C & D is correlated with catalyst liquefaction, as reflected in poorer image conditions.

Understanding nanotube growth termination

- Carbon nanotubes have great promise as reinforcing elements in advanced composites.
- However, it is difficult to create tubes greater than a couple of millimeters in length.
- Using real time imaging of nanotube growth, we have shown that growth termination is caused by catalyst coarsening via the Ostwald ripening mechanism.
- These results are correlated with careful growth studies at Rice and the WP-AFRL that clarify the role of water on inhibiting catalyst coarsening.





Real time images of nanotube growth and termination, acquired at 650°C in 2.5 mTorr C₂H₂ and 7.5 mTorr H₂.

The catalyst that is circled coarsens via the Ostwald ripening process.

P.B. Amama, et al., Role of Water in Super Growth of Single-Walled Carbon Nanotube Carpets. Nano Lett., **9**(1) 44-49, 2009.

Scalable synthesis of BN nanotubes

- Boron nitride nanotubes have invariant electronic properties and high oxidation resistance.
- Synthesis using borazine, ammonia and a floating nickelocene catalyst performed at Sneddon Lab at U Penn and WP-AFRL
- Transmission electron microscopy images reveal creation of high quality double-walled tubes.
- Electron energy loss spectroscopy confirms that the tubes are free of carbon.
- The synthesis method is scalable, dramatically increasing the number of applications and utility of these structures.



M. J. Kim, et al., Δουβλε-ωαλλεδ βορον νιτριδε νανοτυβεσ γρωων βψ φλοατινγ χημιχαλ παπορ δεποσιτιον, Nano Letters, 8(10), 3298-3302,