

Synthesis and Characterization of YB₄ Ceramics

J. A. Zaykoski,^{†,*} M. M. Opeka,^{†,*} L. H. Smith,[§] and I. G. Talmy^{†,*}

[†]Naval Surface Warfare Center Carderock Division (NSWCCD), West Bethesda, Maryland, 20817 5700

[§]Northwestern University, Chicago, IL, 60208

Yttrium tetraboride was synthesized by reactions of Y₂O₃ with B₄C or with a B₄C/C mixture. Fully dense YB₄ ceramics were prepared by hot-pressing at 1800°C and 20 MPa in He. The flexural strength and microhardness of the YB₄ were about 300 MPa and 27 GPa, respectively. Pure YB₄ showed considerable oxidation above 1200°C. The effect of SiC, AlN, and AlN/SiC on the properties of YB₄ ceramics was characterized. No chemical interactions were identified in the YB₄ SiC and YB₄ AlN pseudo binaries. The addition of SiC improved the oxidation resistance below 1200°C. At higher temperatures, the low viscosity of a surface melt caused its continuous runoff and the loss of the oxidation-protection capability of the scale. The addition of AlN/SiC improved the oxidation resistance compared to the ceramics containing only SiC, which was attributed to the presence of Al₂O₃ in the Y₂O₃ SiO₂ B₂O₃ glass leading to an increase in its viscosity and preventing glass runoff. A significant improvement in the oxidation resistance of the YB₄ ceramics and extension of their oxidation stability to 1400°C was accomplished by the introduction of AlN only.

I. Introduction

NEW materials are required for a variety of high temperature applications including hypersonic vehicle leading edges, thermal protection systems, and rocket propulsion components. Such materials typically must have a use capability at temperatures above 2000°C¹ with adequate mechanical properties and oxidation resistance.

Refractory metal borides based on HfB₂ and ZrB₂ have been the primary focus for these applications.^{2,3} The oxidation resistance of these materials was significantly improved by the addition of SiC, which resulted in the formation of a protective multi oxide layer composed of refractory crystal line oxides and borosilicate glass.^{1–3} A further increase in the oxidation resistance was accomplished by the addition of the Group IV VI transition metal borides, which was the result of phase separation in surface borosilicate glass induced by the corresponding metal oxides.⁴

There has been very little research into the potential of rare earth metal borides for use as materials for ultra high temperature (UHT) applications. However, for instance, yttrium tetraboride, YB₄, appears promising as an UHT material since it melts congruently at 2800°C⁵ and the possible oxidation product, Y₂O₃, also has a high melting point of 2415°C. The YB₄ compound has been the subject of few previous investigations mostly limited in scope to its crystal structure and

characterization of emissive, electrical, and magnetic properties, and neutron absorption characteristics.^{6–13}

Yttrium tetraboride is not commercially available, and synthesis methods have not been widely explored. Reaction between the elements^{9,12} and borothermal reduction of Y₂O₃^{6,7,10–13} have been documented. Other methods^{11,12} for synthesis of metal borides (carbothermal, aluminothermal, boron carbide, and combined boron carbide/carbothermal) have not been used for the preparation of YB₄.


There is very limited information on the preparation of YB₄ ceramics. Hoyt¹³ prepared fully dense rare earth borides by hot pressing at 1700°–2200°C at 15–25 MPa for 5–40 min to characterize their neutron absorption properties for nuclear applications. Kadintseva *et al.*¹⁰ prepared samples for characterization of emissive properties by hot pressing at 2000°C and 30 MPa for 20 min. Meerson *et al.*⁶ synthesized YB₄ powder by borothermal reduction and pressureless sintered samples at about 2200°C in vacuum.

Table I lists the reported¹² properties of the YB₄ including crystal structure, microhardness, and flexural strength. The low value of strength (29 MPa) was a result of the high porosity of the samples (22%–26%). Available data on rare earth borides indicate that they are much less resistant to oxidation than transition metal borides and oxidize rapidly in air above 1000°C.^{13–15}

The objective of the present study was to synthesize YB₄, to develop a processing procedure for preparation of dense YB₄ ceramics, and to characterize mechanical properties and oxidation resistance. The additives (SiC, AlN, and AlN/SiC) were also introduced into YB₄ ceramics to identify the potential improvement of oxidation resistance by the modification of the composition and structure of the oxidation products. The effect of these additives on the mechanical properties of YB₄ ceramics was also explored.

II. Experimental Procedure

The YB₄ ceramics were synthesized using a reaction with B₄C (boron carbide reduction method) and a reaction with B₄C/C mixture (combined boron carbide/carbothermal reduction method) according to:



The starting materials B₄C (1.7 μm, 99.4% purity) and Y₂O₃ (<10 μm, 99.99% purity) were purchased from Alfa Aesar (Ward Hill, MA), and carbon black (Monarch 120, 60 nm, 96% purity) from Cabot (Alpharetta, GA). The reactant powders were mixed with a corundum mortar and pestle in acetone. The mixing procedure was repeated three times with intermediate drying. The mixtures were cold pressed into briquettes, which were pressureless heated at 1700° and 1800°C for 2 h to allow chemical reaction to occur. In these experiments, samples were packed in BN and heated in a He atmosphere. The briquettes were ground to a particle size below 45 μm, and then hot pressed (Model 912G, Thermal

R. Naslain—contributing editor

Manuscript No. 28682. Received September 28, 2010; approved May 04, 2011.
 This work was supported by the Office of Naval Research (Dr. S. Fishman and Dr. D. Shiffler).

*Member, American Ceramic Society

[†]Author to whom correspondence should be addressed. e-mail: james.zaykoski@navy.mil

Report Documentation Page				Form Approved OMB No. 0704-0188	
Public reporting burden for the collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to a penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.					
1. REPORT DATE 24 JUN 2011		2. REPORT TYPE		3. DATES COVERED 00-00-2011 to 00-00-2011	
4. TITLE AND SUBTITLE Synthesis And Characterization Of YB4 Ceramics				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S)				5d. PROJECT NUMBER	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Naval Surface Warfare Center Carderock Division (NSWCCD), West Bethesda, MD, 20817				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)				10. SPONSOR/MONITOR'S ACRONYM(S)	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution unlimited					
13. SUPPLEMENTARY NOTES Journal of the American Ceramic Society					
14. ABSTRACT Yttrium tetraboride was synthesized by reactions of Y2O3 with B4C or with a B4C/C mixture. Fully dense YB4 ceramics were prepared by hot-pressing at 1800°C and 20 MPa in He. The flexural strength and microhardness of the YB4 were about 300 MPa and 27 GPa, respectively. Pure YB4 showed considerable oxidation above 1200°C. The effect of SiC, AlN, and AlN/SiC on the properties of YB4 ceramics was characterized. No chemical interactions were identified in the YB4?SiC and YB4?AlN pseudo binaries. The addition of SiC improved the oxidation resistance below 1200°C. At higher temperatures, the low viscosity of a surface melt caused its continuous runoff and the loss of the oxidation-protection capability of the scale. The addition of AlN/SiC improved the oxidation resistance compared to the ceramics containing only SiC, which was attributed to the presence of Al2O3 in the Y2O3?SiO2?B2O3 glass leading to an increase in its viscosity and preventing glass runoff. A significant improvement in the oxidation resistance of the YB4 ceramics and extension of their oxidation stability to 1400°C was accomplished by the introduction of AlN only.					
15. SUBJECT TERMS					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT Same as Report (SAR)	18. NUMBER OF PAGES 8	19a. NAME OF RESPONSIBLE PERSON
a. REPORT unclassified	b. ABSTRACT unclassified	c. THIS PAGE unclassified			

Table I. Previously Reported Properties of YB₄^{6,12}

Crystal structure	Tetragonal, space group <i>P4/mbm</i>
Lattice parameters (Å)	
<i>a</i>	7.107
<i>c</i>	4.018
<i>c/a</i>	0.565
Density (g/cm ³)	4.36
Melting temperature (°C)	2800
Microhardness (Vickers, GPa)	28.5 ± 1.0
Flexural strength (MPa)	29 [†]
Coefficient of thermal expansion (10 ⁻⁶ /°C)	
<i>a</i>	7.6
<i>c</i>	6.4

[†]Porosity of the samples was 22%–26%.

Technology Inc., Santa Rosa, CA) in a graphite mold at 1700°C and 1800°C with 20 MPa pressure for 30–45 min in a He atmosphere. The SiC (2 µm, 99.8% purity) and AlN (200 mesh, 99.8% purity) additives, both purchased from Cerac Inc. (Milwaukee, WI), were introduced into the ground briquette powders.

The phase composition of hot pressed samples was analyzed using X-ray diffractometry (Siemens Theta/Theta, Model D 500; Bruker AXS, Madison, WI), and their microstructure was evaluated using scanning electron microscopy (SEM, Model ISI ABT SR 50A, Withington, Manchester, U.K.). Energy dispersive spectroscopy (EDS; Noran Instruments, Waltham, MA) was also used to characterize the composition of samples.

Flexural strength (3 point, sample size 25 mm × 2 mm × 3 mm, span 20 mm) and Young's modulus were measured using an Instron 8562 universal testing machine (Instron, Norwood, MA). The tensile surfaces of the specimens were polished with diamond paste to 6 µm finish and the edges were beveled to minimize edge defects. Vickers hardness (1 kg load) was measured (Micromet II; Buehler Ltd., Lake Bluff, IL) on an average of 10 polished samples for each composition.

The oxidation behavior of the ceramics was characterized by furnace heating in air at 1000°–1400°C for 2 h. Bars of about 1.0 cm² surface area were supported by their ends on alumina semi-rings for maximum contact with the atmosphere. The samples were inserted in the furnace heated to a test temperature. Air quenching of the samples after heating was conducted to retain the high temperature condition of the surface layer for room temperature X-ray and microscopic evaluations. The mass changes normalized by surface area, and oxidation layer thickness (measured by SEM analysis) were used to quantify the oxidation behavior. The composition of the oxidized surface of the samples was determined by XRD.

III. Results and Discussion

(1) Synthesis and Characterization of YB₄

Yttrium tetraboride was successfully synthesized by both the boron carbide and the combined boron carbide/carbothermal methods. The XRD analyses of briquettes from both synthesis methods fired at 1700°C for 2 h indicated that the reactions were not completed. After firing at 1800°C for 2 h the materials prepared using both methods yielded nearly pure YB₄ with small amounts of YBO₃ and YB₂C₂.

Fully dense YB₄ ceramics (open porosity of 0.11%) were prepared by hot pressing of the reground briquette powders at 1800°C for 30 min. Hot pressing at 1700°C resulted in ceramics with open porosity of 4.00%.

The SEM micrograph of the YB₄ ceramics (Fig. 1) showed a very dense structure with a grain size below 10 µm. The flexural strength of dense YB₄ ceramics (Table II) was




Fig. 1. SEM micrograph of YB₄ ceramics hot pressed at 1800°C and 20 MPa for 30 min.

Table II. Mechanical Properties of YB₄ Ceramics With and Without Additives



Sample composition	Microhardness, Vickers (GPa)	Flexural strength (MPa)
YB ₄	27.40 ± 1.06	268 ± 51 [†] 317 ± 3 [‡]
YB ₄ + 20 vol% SiC	17.07 ± 1.44	250 ± 34
YB ₄ + 20 vol% AlN	14.81 ± 1.77	148 ± 11
YB ₄ + 10 vol% SiC + 10 vol% AlN	13.56 ± 1.48	202 ± 12

[†]YB₄ synthesized using the boron carbide-based method.

[‡]YB₄ synthesized using the combined boron carbide/carbothermal method.

268 (±51) and 317 (±3) MPa for the ceramics prepared by boron carbide based and combined methods, respectively, which was an order of magnitude greater than the only available literature value (29 MPa)¹² for the material with high porosity of 22%–26%. The higher strength of the ceramics produced by the combined boron carbide/carbothermal method could be the result of the elimination of oxides from grain boundaries with carbon. The microhardness of the ceramics (synthesized by boron carbide method) under a 1 kg load was 27.40 (±1.06) GPa, which was close to the previously reported 28.50 GPa value.

The oxidation chemistry of YB₄ ceramics can be presented by a two step process assuming the formation of Y₂O₃ and B₂O₃ by reaction (2) as a first step and their interaction to form YBO₃ and B₂O₃ by reaction (3) as a second step.



The YBO₃–B₂O₃ part of the Y₂O₃–B₂O₃ phase diagram¹⁶ (Fig. 2) shows that the melting temperature of YBO₃ is about 1650°C, and a liquidus temperature up to about 97 mol% B₂O₃ is 1373°C. According to (3), the calculated content of B₂O₃ in the YB₄ oxidation products is 60 mol% (63.7 vol%).

The phase diagram suggested that during oxidation below 1373°C the surface scale would consist of an YBO₃ solid skeleton penetrated with liquid B₂O₃, while during oxidation above this temperature the surface scale would be all liquid. The XRD (Fig. 3) patterns showed the presence of only YBO₃ after oxidation at all the test temperatures (1000°–1300°C). Thus, the reaction between Y₂O₃ and B₂O₃




Fig. 2. Modified YBO_3 - B_2O_3 phase diagram¹⁶ (X indicates the calculated composition of oxidation products of YB_4 .)




Fig. 3. XRD of the surface of pure YB_4 ceramics oxidized at 1000°C 1300°C for 2 h.

occurred below 1000°C. Boria was not identified because of its amorphous nature.

Figure 4 shows the normalized mass gain and thickness of oxidation layer as a function of temperature. The mass gain changed from about 22–31 g/m^2 with increasing temperature from 1000°C to 1200°C. The thickness of the oxidation layer in the same temperature range increased from 10 to 65 μm . The relatively small mass gain change compared to a considerable increase in the thickness of the oxidation layer could be due to the competing rates of mass loss via boria evaporation and mass gain from oxide formation. A significant increase in both mass gain and scale thickness occurred at 1300°C reaching 115 g/m^2 and 215 μm , respectively.

Figure 5 showed the SEM micrographs of the cross section and surface of the sample after oxidation at 1300°C. As was expected from the YBO_3 - B_2O_3 phase diagram the oxide scale was solid at this temperature. The surface layer consisted of rounded YBO_3 grains with sizes that ranged from submicron to 2–3 μm with some signs of sintering. The presence of boria on the surface was not observed. The poor protective capability of dense YBO_3 layer above




Fig. 4. Mass changes and thickness of an oxidized scale of YB_4 ceramics after oxidation for 2 h as a function of temperature.




Fig. 5. SEM of the cross section (a) and surface (b) of YB_4 ceramics oxidized at 1300°C for 2 h.

1200°C is difficult to interpret. It could be related to high oxygen diffusivity through YBO_3 at these temperatures. However, no literature data confirming this hypothesis were found.

Heating at 1400°C resulted in complete oxidation of the YB_4 sample (dimensions about 2 mm $\times$ 3 mm $\times$ 6 mm) after 1 h exposure and melting of the oxidation products in agreement with the phase diagram. It was concluded from the obtained data that pure YB_4 ceramics cannot be used in an oxidizing environment at temperatures exceeding 1300°C.

(2) Synthesis and Characterization of YB_4 Ceramics with Additives

As was mentioned in the introduction, the additives (SiC, AlN, and AlN/SiC) were introduced into YB_4 ceramics in

attempts to improve the oxidation resistance by the compositional and structural modifications of a protective oxidation layer. The introduction of SiC, with SiO_2 as an oxidation product, aimed to form borosilicate glass, which is known to increase the oxidation resistance of Group IV–VI transition metal diborides.^{1–4} Alumina, the product of AlN oxidation, was expected to react with B_2O_3 forming aluminum borates, or react with Y_2O_3 forming high melting temperature yttrium aluminates.¹⁷ Finally, the addition of an AlN/SiC complex additive was expected to form increased viscosity aluminoborosilicate glass,^{18–20} compared to that of borosilicate glass. The additives were introduced in the amounts of 20 vol%. The complex additive was introduced as 10 vol% SiC and 10 vol% AlN. The compositions of oxidation scales of the studied ceramics would belong to the ternary Y_2O_3 – SiO_2 – B_2O_3 and Y_2O_3 – Al_2O_3 – B_2O_3 systems, respectively, for SiC and AlN additions, and to the quaternary Y_2O_3 – SiO_2 – Al_2O_3 – B_2O_3 system for the ceramics with the AlN/SiC additive. It has to be noted that these phase diagrams have not been studied.

The X-ray diffraction analysis (not shown) of hot pressed YB_4 ceramics containing the additives did not show any evidence of new compounds formed by chemical reaction between the starting materials. Therefore, it is assumed that the amount of the additives in the fully processed ceramics remained the same as in the initial mixtures at 20 vol%. The samples were dense (open porosities below 1%) after hot pressing. The microstructure of the additive containing YB_4 ceramics is shown in Fig. 6. The YB_4 /SiC ceramics demonstrated a very uniform microstructure with a decrease in average grain size of YB_4 (light phase) to about $5\text{ }\mu\text{m}$ as compared to pure YB_4 . The grain size of SiC (dark phase) was about $2\text{--}3\text{ }\mu\text{m}$. The microstructure of the AlN modified ceramics was also uniform, but the grain size was larger compared to the SiC containing ceramics. Both materials exhibited a transgranular fracture pattern. Ceramics containing both SiC and AlN exhibited a uniform fine grained microstructure with grain size below $2\text{ }\mu\text{m}$.

The presence of the additives resulted in a decreased microhardness and flexural strength of the YB_4 ceramics (Table II). The YB_4 /SiC samples exhibited the highest hardness and strength (17.07 GPa and 250 MPa, respectively) after those of pure YB_4 . The strength value of the YB_4 /AlN/SiC samples (202 MPa), was unexpectedly low considering the fine grained microstructure of the material.

The results of the oxidation studies for the modified YB_4 ceramics, showing mass changes and scale thickness data, are summarized in Fig. 7 and 8, respectively. The YB_4 /SiC ceramics showed very low and even slightly negative mass change at 1200°C (not shown). The thickness of the scale after oxidation at 1200°C was $35\text{ }\mu\text{m}$ compared to $65\text{ }\mu\text{m}$ for pure YB_4 . The smaller thickness of the SiC containing material could be an indication of an increase in the oxidation resistance of YB_4 in the presence of SiC by analogy with transition metal borides.^{2–4} However, it should be mentioned that the sample supporting semi ring looked glazed after the 1200°C test that, obviously, was the sign of the runoff of some glass formed on the surface. Only a thin layer of the residual surface glass was observed on the SEM surface images (not shown). Thus, a low mass change shown by the SiC containing ceramics during oxidation at 1200°C was a result of the competing mass gain from oxide formation and mass loss via boron evaporation and glass runoff from the surface. XRD identified (Fig. 9) predominantly YBO_3 on the surface of samples after oxidation at $1000^\circ\text{--}1200^\circ\text{C}$. Some $\text{Y}_2\text{Si}_2\text{O}_7$ was also identified. Its content became significant after oxidation at 1200°C . The complete oxidation of the sample ($6\text{ mm} \times 5\text{ mm} \times 2\text{ mm}$) and melting of the oxidation products were observed after exposure to 1300°C for 2 h. Thus, the addition of SiC improved the oxidation resistance of the YB_4 ceramics only at temperatures below 1200°C . It could be assumed that the composition in the Y_2O_3 – SiO_2 –




Fig. 6. SEM Micrographs of YB_4 ceramics with additions of SiC, AlN, and SiC + AlN.

B_2O_3 system containing 16.7 mol% Y_2O_3 , 66.7 mol% B_2O_3 , and 16.7 mol% SiO_2 had a melting temperature close to 1200°C and, what is more important is, a low viscosity of the melt. Both low melting temperature and low viscosity caused continuous melting and runoff of the surface layer and the loss of its oxidation protection capability at temperatures above 1200°C . The low viscosity of the yttrium borosilicate glass observed in the present study supported literature data^{21–24} reporting an effective decrease in the viscosity of aluminosilicate or borosilicate glasses as a result of the introduction of Y_2O_3 or La_2O_3 .

The addition of AlN/SiC resulted in a substantial improvement of their oxidation resistance compared to the ceramics containing only SiC in the temperature range from 1200° to 1300°C . While the SiC containing ceramics were completely oxidized and molten at 1300°C , the ceramics containing the AlN/SiC additive had an adherent glass layer on the surface at this temperature and showed a scale thickness of only $135\text{ }\mu\text{m}$. It could be assumed on the basis of literature data^{18–20} that the presence of Al_2O_3 in the Y_2O_3 – SiO_2 – B_2O_3 glass led to an increase in its viscosity preventing glass




Fig. 7. Mass changes of YB_4 based ceramics after oxidation for 2 h as a function of composition and temperature.




Fig. 8. Thickness of oxidized layer of YB_4 based ceramics as a function of composition and temperature.

runoff from the surface. This increase in viscosity extended the protective capability of the scale to 1300°C.

An increase in the temperature to 1400°C resulted in total oxidation, likely due to a significant viscosity decrease with increasing temperature. The oxidation products consisted mostly of YBO_3 . Only small amounts of Y_2SiO_5 and $Y_3Al_5O_{12}$ were identified on the surface after oxidation at 1300°C. The formation of Y_2SiO_5 is confirmed by the presence of bar like morphology crystals typical for Y_2SiO_5 [Fig. 10(b)]²⁵ in the surface glass.

The introduction of AlN/SiC complex additive improved the oxidation resistance of the pure YB_4 ceramics that is demonstrated by the significant decrease in the thickness of an oxidized scale from 215 μm for YB_4 to 135 μm for AlN/SiC containing material after two hours hold at 1300°C.

A significant improvement in the oxidation resistance of the YB_4 ceramics was accomplished by the introduction of AlN . Of all studied compositions (Figs. 7 and 8), this material was the only one that formed a relatively protective oxide scale (180 μm thick) during two hours of oxidation at 1400°C. After 1300°C test, the thickness of the scale was 80 μm for the YB_4 ceramics containing AlN compared to 135 and 215 μm for the ceramics with the AlN/SiC additive and pure YB_4 , respectively.




Fig. 9. XRD of the surface of YB_4 ceramics with AlN/SiC additive after oxidation at 1000°C and 1200°C for 2 h.




Fig. 10. SEM of the cross section (a) and surface (b) of $YB_4/SiC/AlN$ ceramics oxidized at 1300°C for 2 h.

The oxidation scale of AlN modified ceramics was dense and exhibited evidence of sintering with an increasing grain size with test temperature. The phase composition of the surface is shown in Fig. 11. After oxidation at 1200°C the




Fig. 11. XRD of the surface of 20 vol% AlN modified YB_4 ceramics after oxidation at 1200° 1400°C for 1 or 2 h.

composition was represented by predominantly YBO_3 with small amounts of Al_5BO_9 and $\text{Y}_3\text{Al}_5\text{O}_{12}$. After oxidation at higher temperatures, the surface still contained YBO_3 as a predominant phase, but the $\text{Y}_3\text{Al}_5\text{O}_{12}$ content became significant. This change in the composition of the surface layer with a substantial decrease in YBO_3 content could be attributed to the evaporation of B_2O_3 at temperatures above 1200°C. It should be noted that the YB_4/AlN samples were completely oxidized and molten after heating at 1500°C. As was mentioned above, the phase equilibrium in the $\text{Y}_2\text{O}_3\text{-Al}_2\text{O}_3\text{-B}_2\text{O}_3$ system was not reported in the literature. However, the existence of a low melting eutectic (about 1500°C) in the $\text{YBO}_3\text{-Y}_3\text{Al}_5\text{O}_{12}$ pseudo binary system (melting points of the end members of 1650° and 1900°C, respectively) could be expected.

It would be insightful to compare the oxidation behavior of YB_4 and ZrB_2 , which was the focus of numerous previous studies.^{1–3,26,27} In the case of ZrB_2 , the oxidation products are ZrO_2 and liquid B_2O_3 (about 56 vol%). The oxides do not react to form low melting zirconium borates. In the initial stages of oxidation, boron fills the porosity in the fine grained zirconia preventing the gaseous diffusion of oxygen to the ZrB_2 surface and provides oxidation protection. Since B_2O_3 evaporates readily at temperatures above 1100°C, the porous ZrO_2 layer with a decreasing amount of B_2O_3 remains. Above ~1400°C, the oxide layer is not protective and rapid oxidation has been observed. With SiC additions to ZrB_2 the formation of binary $\text{SiO}_2\text{-B}_2\text{O}_3$ glass provides much more effective oxidation protection due to higher viscosity, higher melting temperature, lower oxygen diffusivity, and lower vapor pressure compared to B_2O_3 . As oxidation progresses, the evaporation of B_2O_3 from the molten glass and increase in SiO_2 content leads to the continuing increase in its melting temperature and viscosity. The SiC containing ZrB_2 does not oxidize significantly even at 1500°C.

As described above, in the case of YB_4 , the oxidation products were YBO_3 (not Y_2O_3) and B_2O_3 which form a eutectic at 1373°C. Below this temperature the oxide scale consisted of solid YBO_3 and liquid B_2O_3 , and thus, is similar to solid ZrO_2 and liquid B_2O_3 in the oxidation of ZrB_2 . The scale thickness after oxidation at 1200°C for 2 h was

65 μm for YB_4 compared to 102 μm for ZrB_2 ceramics²⁷ indicating better oxidation performance of YB_4 at this temperature. However, at higher temperature the oxidation rate of YB_4 significantly increased, and after oxidation at 1300°C, the thickness of the scale was 215 μm compared to 160 μm for ZrB_2 . It is believed that this oxidation behavior reversal could be due to a significant change in the properties of the YB_4 oxidation products near the eutectic temperature such that the oxidation mechanism may be fundamentally different.

In contrast to the role of SiC in the ZrB_2 ceramics, the addition of SiC to YB_4 resulted in the formation of a low viscosity ternary $\text{Y}_2\text{O}_3\text{-SiO}_2\text{-B}_2\text{O}_3$ glass, which ran off the sample surface at temperatures above 1200°C causing the total loss of the oxidation protection capability of the scale.

The oxidation data for YB_4 ceramics relative to the ZrB_2 ceramics confirmed that the oxidation behavior of non oxide ceramics depends on the significantly different chemical composition and properties of the oxidation products.

IV. Summary

Yttrium tetraboride was successfully synthesized by reactions of Y_2O_3 with B_4C or with a $\text{B}_4\text{C}/\text{C}$ mixture. Fully dense YB_4 ceramics were prepared using hot pressing at 1800°C with 20 MPa pressure for 30–45 min in a He. The flexural strength and microhardness of the YB_4 ceramics were about 300 MPa and 27 GPa, respectively. Pure YB_4 showed considerable oxidation above 1200°C, and very rapid oxidation and melting at higher temperatures due to the low melting $\text{YBO}_3\text{-B}_2\text{O}_3$ eutectic at 1373°C. The effect of additives (SiC, AlN, and AlN/SiC) on the mechanical properties and oxidation resistance of YB_4 ceramics was explored. Chemical compatibility was identified in the $\text{YB}_4\text{-SiC}$ and $\text{YB}_4\text{-AlN}$ pseudo binaries, which has not been previously reported.

The introduction of additives resulted in a decreased microhardness and flexural strength of the YB_4 ceramics. The addition of SiC improved the oxidation resistance only at temperatures below 1200°C. At higher temperatures, the low viscosity of a surface melt caused its continuous runoff of the surface and the loss of the oxidation protection capability of the scale. The addition of AlN/SiC resulted in a substantial improvement of the oxidation resistance compared to the ceramics containing only SiC and extended their oxidation stability to 1300°C. This was attributed to the presence of Al_2O_3 in the $\text{Y}_2\text{O}_3\text{-SiO}_2\text{-B}_2\text{O}_3$ glass leading to an increase in its viscosity and preventing glass runoff from the surface. A significant improvement in the oxidation resistance of the YB_4 ceramics and further extension of their oxidation stability to 1400°C was accomplished by the introduction of AlN only.

References

- M. M. Opeka, I. G. Talmy, and J. A. Zaykoski, "Oxidation-Based Materials Selection for 2000°C + Hypersonic Aerosurfaces: Theoretical Considerations and Historical Experience," *J. Mater. Sci.*, **39** [19] 5887–904 (2004).
- W. G. Fahrenholtz, G. E. Hilmas, I. G. Talmy, and J. A. Zaykoski, "Refractory Diborides of Zirconium and Hafnium," *J. Am. Ceram. Soc.*, **90** [5] 1347–64 (2007).
- A. Bellosi and F. Monteverde, "Fabrication and Properties of Zirconium Diboride-based Ceramics for UHT Applications"; pp. 65–71 in *Hot Structures and Thermal Protection Systems for Space Vehicles*. Proceedings of the 4th European Workshop, November 26–29, 2002, Palermo, Italy, European Space Agency, Paris, 2003.
- I. G. Talmy, J. A. Zaykoski, M. M. Opeka, and S. Dallek, "Oxidation of ZrB_2 Ceramics Modified with SiC and Group IV–VI Transition Metal Borides"; pp. 144–53. in *High Temperature Corrosion and Materials Chemistry III*. Edited by M. McNallan and E. Opila. The Electrochemical Society, Pennington, NJ, 2001.
- P. K. Liao and K. E. Spear, "The B–Y (boron–yttrium) system," *J. Phys. Equil. and Diff.*, **16** [6] 521–4 (1995).
- G. A. Meerson, N. N. Zhyravlev, R. M. Manelis, A. D. Runov, A. A. Stepanova, L. P. Grishina, and N. V. Gramm, "Some Properties of Yttrium Borides (*Nekotorye Svoistva Boridov Itriya*)," *News Acad. Sci. USSR Inorg.*

Mater. (Izvestiya Akademii Nauk SSSR: Neorganicheskiye Materialy), **2** [4] 608 16 (1966).

⁷B. Jäger, S. Paluch, W. Wolf, P. Herzig, O. J. Šoga, N. Shitsevalova, and Y. Paderno, "Characterization of the Electronic Properties of YB₄ and YB₆ using ¹¹B NMR and First-Principles Calculations," *J. Alloys Compd.*, **383** [1 2] 232 8 (2004).

⁸J. Günster, T. Tanaka, and R. Souda, "Surface reorganization observed on YB₄ (001)," *Phys. Rev. B: Condens. Matter*, **56** [24] 15962 6 (1997).

⁹J. Bauer and H. Nowotny, "The Ternary System Yttrium-Boron-Carbon (Der Dreistoff Yttrium-Bor-Kohlenstoff)," *Chemical Monthly (Monatshefte für Chemie)*, **102**, 1129 45 (1971).

¹⁰G. A. Kudintseva, G. M. Kuznetsova, V. P. Bondarenko, N. F. Selivanova, and V. Ya. Shlyuko, "Preparation and Emissive Properties of Some Yttrium and Gadolinium Borides," *Powder Metall. Met. Ceram.*, **7** [2] 115 20 (1968).

¹¹N. N. Greenwood, R. B. Parish, and P. Thornton, "Metal Borides," *Q. Rev. Chem. Soc.*, **20**, 441 64 (1966).

¹²G. V. Samsonov, T. I. Serebryakova, and V. A. Neronov, Borides. p. 163 7, Atomizdat, Moscow, 1975.

¹³E. W. Hoyt, "Rare-Earth Borides for Nuclear Applications"; pp. 287 99 in Proceedings of the Second Conference on Rare Earth Research, Edited by J. F. Nachman and L. E. Lundin. Gordon and Breach Science Publishers, New York, 1962.

¹⁴G. V. Samsonov, L. Ya. Markovsky, A. F. Zhigach, and M. G. Valyashko, "Boron, Its Compounds and Alloys," *Akademia Nauk Ukrainskoi SSR, Kiev*, 422 511 (1960) (in Russian)

¹⁵J. F. Lynch, Engineering Properties of Selected Ceramic Materials. *American Ceramic Society*, Columbus, OH, 1966.

¹⁶E. M. Levin and H. F. McMurdie, Phase Diagrams for Ceramists, 1975 Supplement, Fig. 4390, The American Ceramic Society, Columbus, OH, 1975.

¹⁷E. M. Levin and H. F. McMurdie, "Phase Diagrams for Ceramists 1975 Supplement," Edited by M.K. Reser, Fig. 4370, p. 132, The American Ceramic Society, Columbus, Ohio (1975) from T. Noguchi and M. Mizuno, *Kogyo Kagaku Zasshi*, **70** [6] 834 9 (1967).

¹⁸J. Kraxner, R. Klement, and M. Liška, "High-Temperature Viscosity and Density of Alumino-Borosilicate Glasses as a Model System for Commercial E-glass," *Ceramics-Silikáty*, **52** [3] 148 54 (2008).

¹⁹P. Hrma, B. M. Arrighi, and M. J. Schweiger, "Viscosity of Many-Component Glasses," *J. Non-Cryst. Solids*, **355** [14 15] 891 902 (2009).

²⁰S. Song, Z. Wen, Y. Liu, Q. Zhang, X. Wu, J. Zhang, and J. Han, "Influence of Dopants on the Crystallization of Borosilicate Glass," *Ceram. Int.*, **35** [8] 3037 42 (2009).

²¹T. S. Schaller and J. F. Stebbins, "The Structural Role of Lanthanum and Yttrium in Aluminosilicate Glasses: A ²⁷Al and ¹⁷O MAS NMR Study," *J. Phys. Chem. B*, **102**, 10690 7 (1998).

²²W. Zheng, J. Cheng, L. Tang, J. Quan, and X. Cao, "Effect of Y₂O₃ Addition on Viscosity and Crystallization of the Lithium Aluminosilicate Glasses," *Thermochimica Acta*, **456** [1] 69 74 (2007).

²³J. She, P. Mechnich, M. Schmucker, and H. Schneider, "Reaction-Bonding Behavior of Mullite Ceramics with Y₂O₃ Addition," *J. European Ceram. Soc.*, **22** [3] 323 8 (2002).

²⁴X. Miao, "Modification of Porous Alumina Ceramics with Bioinert and Bioactive Glass Coatings," *Adv. Mater. Res.*, **32**, 211 4 (2008).

²⁵I. G. Talmy and J. A. Zaykoski, "Oxidation Resistance of Si₃N₄ Ceramics Modified with Boron and Transition Metal Diborides"; pp. 361 76 in High Temperature Corrosion and Materials Chemistry IV, Edited by E. Opila, P. Hou, T. Maruyama, B. Pieraggi, D. Shifler, and E. Wuchina, The Electrochemical Society, Pennington, NJ, 2003.

²⁶A. Bellosi, S. Guicciardi, V. Medri, F. Monteverde, D. Sciti, and L. Silvestroni, "Processing And Properties of Ultra-Refractory Composites Based on Zr- and Hf-Borides: State of the Art and Perspectives"; pp. 147 60 in Boron Rich Solids, Sensors, Ultra High Temperature Ceramics, Thermoelectrics, Armor, Edited by N. Orlovskaya and M. Lugovy, NATO Science for Peace and Security Series B: Physics and Biophysics, Springer Science and Business Media B.V., Dordrecht, Netherlands, 2011.

²⁷I. G. Talmy, J. A. Zaykoski, and M. M. Opeka, "High-Temperature Chemistry and Oxidation of ZrB₂ Ceramics Containing SiC, TaSi₂, Ta₅Si₃, and Si₃N₄," *J. Am. Ceram. Soc.*, **91** [7] 2250 7 (2008). □