



Yttria Nanoparticle Reinforced Commercially Pure (CP) Titanium

by Sesh Tamirisa

ARL-CR-0680

September 2011

Prepared by

**FMW Composite Systems, Inc.
1200 W. Benedum Industrial Drive
Bridgeport, WV 26330**

Under Contract

W911NF-11-2-0003

ERRATA SHEET

re: **ARL-CR-0680, *Yttria Nanoparticle Reinforced Commercially Pure (CP) Titanium*,
March 2012, by Sesh Tamirisa**

This is an errata sheet for ARL-CR-0680. Please replace the old version of the report with the new version, and destroy the old version.

Page	Should Read
The tensile data were switched for the CP Ti and CP Ti + 0.3 Y₂O₃ samples in table 1. These changes in the data set have affected the text of the report in the following sections.	
ii	Adjusted abstract.
1	Adjusted summary.
6	Adjusted paragraph.
7	Corrected table 1.
7	Corrected table 1.
8	Corrected figure 4.
8	Corrected figure 5.
10	Corrected figure 7.
11	Corrected figure 8.
11	Corrected figure 9.
12	Adjusted conclusion.
12	Adjusted future work.



Vincent H. Hammond

U.S. Army Research Laboratory
Weapons and Material Research Directorate
ATTN: RDRL-WMM-F
Aberdeen Proving Ground, MD 21005

NOTICES

Disclaimers

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Citation of manufacturer's or trade names does not constitute an official endorsement or approval of the use thereof.

Destroy this report when it is no longer needed. Do not return it to the originator.

Army Research Laboratory

Aberdeen Proving Ground, MD 21005

ARL-CR-0680**September 2011**

Yttria Nanoparticle Reinforced Commercially Pure (CP) Titanium

**Sesh Tamirisa
FMW Composite Systems, Inc.
1200 W. Benedum Industrial Dr
Bridgeport, WV 26330**

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188		
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing the burden, to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.					
1. REPORT DATE (DD-MM-YYYY) September 2012		2. REPORT TYPE Final		3. DATES COVERED (From – To) October 2010 to July 2011	
4. TITLE AND SUBTITLE Yttria Nanoparticle Reinforced Commercially Pure (CP) Titanium			5a. CONTRACT NUMBER W911NF-11-2-0003		
			5b. GRANT NUMBER		
			5c. PROGRAM ELEMENT NUMBER		
6. AUTHOR(S) Sesh Tamirisa			5d. PROJECT NUMBER		
			5e. TASK NUMBER		
			5f. WORK UNIT NUMBER		
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) FMW Composite Systems, Inc. 1200 W. Benedum Industrial Dr Bridgeport WV 26330			8. PERFORMING ORGANIZATION REPORT NUMBER ARL-CR-0680		
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) U.S. Army Research Laboratory ATTN: RDRL-WMM-F Aberdeen Proving Ground MD 21005			10. SPONSOR/MONITOR'S ACRONYM(S)		
			11. SPONSOR/MONITOR'S REPORT NUMBER(S)		
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution unlimited.					
13. SUPPLEMENTARY NOTES					
14. ABSTRACT Previous literature reports have indicated as much as an approximately twofold increase in tensile properties in commercially pure (CP) titanium (Ti) following the introduction of yttria (Y₂O₃) nanoparticles. However, these initial studies used laboratory-scale samples produced via an arc-melting process. In order to evaluate the potential for scale-up, CP Ti powders containing both yttria nanoparticles as well as titanium boride (TiB) reinforcements were produced through gas atomization. After consolidation and extrusion, room temperature tensile tests were conducted to determine the influence of reinforcements on strength and ductility. Three alloy powders—CP Ti, CP Ti + 0.3% Y₂O₃, and CP Ti + 0.3% Y₂O₃ + 0.5 B—were fabricated using a conventional Ti powder metallurgy route. Powder compacts were fabricated via hot isostatic pressing and billets were extruded to produce 12.7-mm-diameter bars. Room temperature testing indicated that the addition of 0.3% Y₂O₃ reduced the tensile strength by approximately 20%. The addition of both 0.5% B and 0.3% Y₂O₃ increased the tensile yield strength by 33% relative to CP Ti. The addition of 0.5% B increased the tensile modulus of CP Ti by 20%.					
15. SUBJECT TERMS Titanium, yttria, TiB, nanoreinforcements, tensile					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT UU	18. NUMBER OF PAGES 20	19a. NAME OF RESPONSIBLE PERSON Vincent H. Hammond
a. REPORT Unclassified	b. ABSTRACT Unclassified	c. THIS PAGE Unclassified			19b. TELEPHONE NUMBER (Include area code) (410) 306-0855

Contents

List of Figures	iv
List of Tables	iv
Summary	1
1. Fabrication of Yttria Nano-particle Reinforced CP Titanium	3
2. Tensile Properties of Yttria Nano-particle Reinforced CP Titanium	5
3. Conclusions	12
4. Future Work	12
List of Symbols, Abbreviations, and Acronyms	13
Distribution List	14

List of Figures

Figure 1. Chemical analysis and sieve analysis of yttria nanoparticle reinforced CP Ti powders.	4
Figure 2. Fabrication process flow of yttria nanoparticle reinforced CP Ti extruded bars.	5
Figure 3. Tensile specimen drawing used for evaluating CP Ti extruded bars.	6
Figure 4. Tensile stress-strain curves at room temperature on CP Ti extruded bar.	8
Figure 5. Tensile stress-strain curves at room temperature on CP Ti + 0.3 yttria extruded bar.	8
Figure 6. Tensile stress-strain curves at room temperature on CP Ti + 0.3 yttria + 0.5 B extruded bar.	9
Figure 7. Comparison of tensile strengths (average values) of nano-yttria particle reinforced CP Ti extrusions.	10
Figure 8. Comparison of tensile modulus (average values) of nano-yttria particle reinforced CP Ti extrusions.	11
Figure 9. Comparison of tensile elongation (average values) of nano-yttria particle reinforced CP Ti extrusions.	11

List of Tables

Table 1. Room temperature tensile test data on yttria nanoparticle reinforced CP Ti bars.	7
--	---

Summary

A previous report in the literature¹ asserted that the doubling of tensile properties is achievable via nano-sized yttria (Y_2O_3) dispersion in titanium (Ti). These initial studies reported proof of concept using small laboratory-scale samples produced via an arc-melting process, but follow-on studies to establish the technology and applications have been lacking. The objective of this work is to study the scale-up feasibility of yttria dispersed Ti and investigate the influence of yttria nanoparticles on the tensile properties of Ti. The focus of this effort is to perform initial experiments to determine if this strengthening effect occurs in metal powder produced through gas atomization. In addition, a higher strength version of the material was sought through the addition of boron (B). This project is designed to explore the efficiency of nano-sized yttria at improving tensile properties of commercially pure (CP) Ti for U.S. Army applications. This phase of the project is focused on evaluating the tensile properties of a limited number of samples with specified compositions.

CP Ti and inert gas atomization were selected as material and process in this study. Scale-up feasibility of nano-yttria dispersed CP Ti was successfully demonstrated by producing large quantities of CP Ti alloys via conventional titanium powder metallurgy route. Three alloys—CP Ti, CP Ti + 0.3% Y_2O_3 , and CP Ti + 0.3% Y_2O_3 + 0.5 B—were made. Powder compacts were fabricated via hot isostatic pressing and billets were extruded to produce 0.5 in (12.7 mm) diameter bars. Room temperature tensile testing was performed on multiple specimens machined from bars. Addition of 0.3% Y_2O_3 reduced the tensile strength of CP Ti by approximately 20%. The tensile yield strength of the CP Ti + 0.3% Y_2O_3 + 0.5% B alloy was 33% higher relative to CP Ti and 66% relative to the CP Ti + 0.3% Y_2O_3 alloy. The addition of 0.5% B increased the tensile modulus of CP Ti by 20% in addition to significantly increasing strength while maintaining adequate ductility. Yttria addition, on the other hand, resulted in only a modest increase in total elongation.

The feasibility of producing yttria-dispersed Ti and the resultant tensile properties were successfully demonstrated. In contrast to the previous literature report, the yttria-reinforced alloy actually demonstrated reduced tensile strengths. In contrast, the boron-containing alloy demonstrated significant improvements in tensile strengths relative to CP Ti and the CP Ti/ytria alloy. The use of TiB reinforcements represents one method for producing higher strength CP Ti alloys with the potential for significant weight reduction benefits for U.S. Army applications.

¹ de Castro, V.; Leguey, T.; Munoz, A.; Monge, M. A.; Pareja, R. Microstructure and tensile properties of Y_2O_3 -dispersed titanium produced by arc melting. *Materials Science and Engineering A* **April 2006**, A422 (1–2), 189–197.

INTENTIONALLY LEFT BLANK.

1. Fabrication of Yttria Nano-particle Reinforced CP Titanium

Pre-alloyed powders of commercial purity (CP) titanium (Ti), CP Ti + 0.3% yttria (Y_2O_3), and CP Ti + 0.3% yttria + 0.5% boron (B) were produced via inert gas atomization technique. As-atomized powders were sieved to obtain –35 mesh (500- μm -mesh opening size) fractions. Chemical analysis (wt.%) and sieve analysis of all three powder compositions are given in figure 1. In comparison to typical CP Ti Grade 2 chemistry (0.3% max iron [Fe] and 0.25% max oxygen [O]), the Fe and O contents were lower in the powder materials produced in this study. However, these levels were similar in the baseline CP Ti and yttria-modified CP Ti, which allows accurate comparison of properties.



6515 Steubenville Pike
Pittsburgh, PA 15205-1005
(412) 923-2955; FAX (412) 788-4665

Page 1 of 1

Date: February 25, 2011

CERTIFICATE OF TEST

CR Order: T802

Customer: FMW Composite Systems	Purchase Order No: 11462	Purchase Order Date: December 7, 2010
------------------------------------	-----------------------------	--

Specification:

Item No.:	Weight:	Product Description:
1	15.0 lbs	CP Ti Grade 2 Powder, -35 Mesh, Heat 4255
2	65.0 lbs	CP Ti Grade 2 + 0.45Y ₂ O ₃ Powder, -35 Mesh, Blend B630
3	65.0 lbs	CP Ti Grade 2 + 0.45Y ₂ O ₃ + 0.5B Powder, -35 Mesh, Blend B631

Chemical Analysis (Wt%):

Lot	Fe	Y	B	C	O	N	H	Ti
4255	0.038	0.005	----	0.051	0.088	0.006	0.003	Bal.
B630	0.044	0.30	----	0.035	0.107	0.003	0.003	Bal.
B631	0.053	0.32	0.53	0.041	0.101	0.005	0.004	Bal.

Powder Sieve Analysis (% Under):

Lot	-35	-45	-60	-80	-100	-140	-200	-230	-270	-325	Tap Density (g/cc)	Flow Rate (sec)
4255	100.0	91.1	72.4	51.6	41.0	19.1	7.1	3.8	2.4	1.5	2.53	38
B630	100.0	88.4	65.5	46.0	38.2	21.4	11.2	7.2	5.0	3.3	2.91	33
B631	100.0	87.9	65.9	46.3	37.9	20.2	10.3	6.3	4.6	3.0	2.84	31

Note: The recording of false, fictitious, or fraudulent statements or entries on this document may be punishable as a felony under Federal Statutes. This test report shall not be reproduced except in full without the written approval of ATI Powder Metals.

Certified by:

Joseph F. Muha
Joseph F. Muha

2/25/11
Date

CR Form 4-003 Rev. 5 10/26/09

Figure 1. Chemical analysis and sieve analysis of yttria nanoparticle reinforced CP Ti powders.

2. Tensile Properties of Ytria Nano-particle Reinforced CP Titanium

Powders of about 10 lb from each composition were packed in mild steel cans, hot offgassed at 500 °F for 2 h, and vacuum sealed. Sealed cans were subjected to hot isostatic pressing (HIP) at 1750 °F and 15 ksi for 3 h, and fully dense powder compacts were produced. Compacts were decanned and machined into billets of 2.95 inches in diameter and 7 inches in height. Billets were extruded into 0.75-in-diameter bars using conditions of 1650 °F billet temperature with 1 h soak time, 12:1 extrusion ratio, 100 in/min ram speed, and air cooling after extrusion. Pictures of powder cans, machined billets, and extruded bars are shown in figure 2.




Figure 2. Fabrication process flow of yttria nanoparticle reinforced CP Ti extruded bars.

Blanks of 3-in length were cut from extrusions and tensile specimens of 0.25-in gauge diameter and 1-in gauge length were machined. Six samples from each alloy were machined to tensile specimen drawing shown in figure 3. Tensile testing of specimens was performed at room temperature per the American Society for Testing and Materials (ASTM) standard E8 using an initial ram speed of 0.005 in/in/min (0.00212 mm/mm/s). Digital elongation data were recorded using an extensometer of 1-in length attached to the gauge portion of the specimen.




Figure 3. Tensile specimen drawing used for evaluating CP Ti extruded bars.

Tensile data generated on all three alloys are presented in table 1. Tensile stress-strain curves of all tested samples are presented in figures 4–6 (the data on CP Ti and CP Ti + 0.3% Y_2O_3 samples were truncated as the number of data points exceeded the Excel plotting limit). Tensile strengths (0.2% yield and ultimate) of three alloys are compared in figure 7. The addition of 0.3% Y_2O_3 reduced the tensile strength of CP Ti by 20% (–50 MPa in tensile yield strength [TYS] and –80 MPa in ultimate tensile strength [UTS]) while the tensile elongation value remained unchanged. For both alloys, it was noted that tensile strengths were significantly lower and the tensile elongations were higher compared to typical CP Ti Grade 2 (275 MPa guaranteed minimum TYS and 20% tensile elongation). These results are consistent with the lower Fe and O contents in powder materials. The addition of 0.5% B increased the tensile strength (22–33%, +80 MPa in TYS and +90 MPa in UTS) compared to the baseline CP Ti. The addition of B also increased the tensile modulus by 20% (+20 GPa) compared to the baseline CP Ti and yttria-modified CP Ti, as shown in figure 8. In the B-modified CP Ti, a reduction in total tensile elongation to 28% occurred compared to the baseline alloy (figure 9). However, the tensile elongation is well above the desired value of 10–15% for a majority of applications.

Table 1. Room temperature tensile test data on yttria nanoparticle reinforced CP Ti bars.

Alloy	ID	Dia., mm	TYS		UTS		TE	TM	
			MPa	ksi	MPa	ksi	%	GPa	Msi
CP Ti	#1-1	6.345	240.9	35	407.4	59.1	43.0	103.8	15.1
	#1-2	6.317	245	36	409.7	59.4	43.5	105.7	15.3
	#1-3	6.325	247.9	36	410.5	59.5	44.0	109.2	15.8
	#1-4	6.322	248	36	409.7	59.4	49.6	103.8	15.1
	#1-5	6.317	249	36	408.3	59.2	44.3	112.8	16.4
	#1-6	6.314	251	36	412.9	59.9	46.8	106.6	15.5
		Avg	247	36	410	59	45	107.0	15.5
		Std Dev	3.6	0.5	1.9	0.3	2.5	3.5	0.5
CP Ti + 0.3 Y ₂ O ₃	#2-1	6.320	210.0	31	326.2	47.3	54.4	111.8	16.2
	#2-2	6.322	198	29	323.9	47.0	47.8	103.2	15.0
	#2-3	6.327	197.1	29	329.8	47.8	49.2	105.8	15.3
	#2-4	6.335	193	28	331.6	48.1	47.4	106.8	15.5
	#2-5	6.340	192	28	333.0	48.3	44.5	111.4	16.2
	#2-6	6.325	184	27	334.3	48.5	53.1	97.5	14.1
		Avg	196	28	330	48	49	106.1	15.4
		Std Dev	8.6	1.2	4.0	0.6	3.7	5.4	0.8
CP Ti + 0.3 Y ₂ O ₃ + 0.5 B	#3-1	6.335	316	46	488.0	70.8	28.7	125.4	18.2
	#3-2	6.320	332	48	495.7	71.9	27.0	128.5	18.6
	#3-3	6.345	331	48	503.0	73.0	27.9	137.7	20.0
	#3-4	6.335	328	48	505.2	73.3	28.0	114.5	16.6
	#3-5	6.342	324	47	502.2	72.8	29.4	121.5	17.6
	#3-6	6.330	328	48	503.1	73.0	27.3	134.5	19.5
		Avg	327	47	500	72	28	127.0	18.4
		Std Dev	5.9	0.8	6.5	0.9	0.9	8.5	1.2




Figure 4. Tensile stress-strain curves at room temperature on CP Ti extruded bar.




Figure 5. Tensile stress-strain curves at room temperature on CP Ti + 0.3 yttria extruded bar.




Figure 6. Tensile stress-strain curves at room temperature on CP Ti + 0.3 yttria + 0.5 B extruded bar.





Figure 7. Comparison of tensile strengths (average values) of nano-yttria particle reinforced CP Ti extrusions.




Figure 8. Comparison of tensile modulus (average values) of nano-yttria particle reinforced CP Ti extrusions.




Figure 9. Comparison of tensile elongation (average values) of nano-yttria particle reinforced CP Ti extrusions.

3. Conclusions

The following is a summary of the results of this study:

- The scale-up feasibility of nano-yttria dispersed CP Ti was successfully demonstrated by producing large quantities of modified alloys using conventional Ti powder metallurgy production processes.
 - The addition of 0.3% Y_2O_3 reduced the tensile strength of CP Ti by approximately 20%.
 - The TYS of the CP Ti + 0.3% Y_2O_3 + 0.5% B alloy was 33% higher than the CP Ti alloy, while the UTS was increased by 22%. In comparison to the CP Ti + 0.3% Y_2O_3 alloy, the yield and ultimate strengths were increased 66% and 51%, respectively.
 - Addition of 0.5% B increased the tensile modulus of CP Ti by 20% in addition to significantly increasing strength while maintaining adequate tensile elongation. Yttria addition, on the other hand, provided only an increase in total elongation to CP Ti.
-

4. Future Work

The following future work needs to be conducted to further this effort:

- We need to determine the reason for the reduction in tensile strengths observed for the CP Ti + 0.3% Y_2O_3 alloy.
- Optimization of the alloy chemistry to match the Fe and O contents to those in typical CP Ti Grade 2 could provide further improvements in tensile strength.
- Optimization of the B content is necessary to obtain optimal property combinations in CP Ti.
- Microstructural evaluations need to be conducted to understand the structure-property relationships and guide microstructural engineering.

List of Symbols, Abbreviations, and Acronyms

ASTM	American Society for Testing and Materials
B	boron
CP	commercially pure
FE	iron
O	oxygen
Ti	titanium
TiB	titanium boride
TYS	tensile yield strength
UTS	ultimate tensile strength
wt%	weight percent
Y ₂ O ₃	yttria

NO. OF
COPIES ORGANIZATION

1 (PDF only)	DEFENSE TECHNICAL INFORMATION CTR DTIC OCA 8725 JOHN J KINGMAN RD STE 0944 FORT BELVOIR VA 22060-6218
1	DIRECTOR US ARMY RESEARCH LAB IMNE ALC HRR 2800 POWDER MILL RD ADELPHI MD 20783-1197
1	DIRECTOR US ARMY RESEARCH LAB RDRL CIO LL 2800 POWDER MILL RD ADELPHI MD 20783-1197
1	DIRECTOR US ARMY RESEARCH LAB RDRL CIO MT 2800 POWDER MILL RD ADELPHI MD 20783-1197
1 + PDF	DIRECTOR US ARMY RESEARCH LAB ATTN: RDRL WMM F V HAMMOND 2800 POWDER MILL RD APG MD 21005
1	FMW COMPOSITE SYSTEMS, INC. ATTN SESH TAMIRISA 1200 W BENEDUM INDUSTRIAL DR BRIDGEPORT WV 26330

TOTAL: 7 (2 ELEC, 5 HCS)