

REPORT DOCUMENTATION PAGE				Form Approved OMB No. 0704-0188	
The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing the burden, to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.					
1. REPORT DATE (DD-MM-YYYY)		2. REPORT TYPE		3. DATES COVERED (From - To)	
30-12-2011		Performance/Technical Report (Monthly)		12/1/2011 - 12/30/2011	
4. TITLE AND SUBTITLE Polyfibroblast: A Self-Healing and Galvanic Protection Additive				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER N00014-09-1-0383	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S) Benkoski, Jason J.				5d. PROJECT NUMBER	
				5e. TASK NUMBER FGY25	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) The Johns Hopkins University Applied Physics Laboratory 11100 Johns Hopkins Rd Laurel, MD 20723				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) Office of Naval Research 875 North Randolph Street Arlington, VA 22203-1995				10. SPONSOR/MONITOR'S ACRONYM(S) ONR	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for Public Release: distribution is Unlimited.					
13. SUPPLEMENTARY NOTES					
14. ABSTRACT The goal of this project is to develop a primer additive that mimics the self-healing ability of skin by forming a polymer scar across scratches. Designed to work with existing military grade primers, Polyfibroblast consists of microscopic, hollow zinc tubes filled with a moisture-cured polyurethane-urea (MCPU). When scratched, the foaming action of a propellant ejects the resin from the broken tubes and completely fills the crack. No catalysts or curing agents are needed since the polymerization is driven by ambient humidity.					
15. SUBJECT TERMS corrosion protection, self-healing, coatings, polymers					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT UU	18. NUMBER OF PAGES 4	19a. NAME OF RESPONSIBLE PERSON
a. REPORT	b. ABSTRACT	c. THIS PAGE			Jason J Benkoski
U	U	U			19b. TELEPHONE NUMBER (Include area code) 240-228-5140

POLYFIBROBLAST: A SELF-HEALING AND GALVANIC PROTECTION ADDITIVE

Progress Report #1

Prepared for:

Cody M. Reese
Logistics S&T Thrust Manager
Office of Naval Research
Code 30, Room 1149
875 North Randolph Street
Arlington, VA 22203-1995

Prepared by:

Jason J. Benkoski, Ph.D., Senior Research Scientist
The Johns Hopkins University Applied Physics Laboratory
The Milton S. Eisenhower Research Center
11100 Johns Hopkins Rd, MS 9-110
Laurel, MD 20723
Tel. (240) 228-5140

Reporting Period: December 1 2011 through December 30, 2011
Date of Report: December 30, 2011

20120109031

TABLE OF CONTENTS

1	SUMMARY	3
2	PROJECT GOALS AND OBJECTIVES	3
3	KEY ACCOMPLISHMENTS	3
3.1	PRE-KICKOFF MEETING	3
3.2	DRYING	3
3.3	INTERFACIAL POLYMERIZATION	4
4	NEXT STEPS	4
4.1	SYNTHESIS IMPROVEMENTS	4

1 Summary

Our initial goal is to solve two major processing hurdles discovered during FY11: shorten the microcapsule polymerization time from several days to several hours, and dry the samples without resorting to freeze-drying. The former has been shortened to overnight, and the latter appears to have been solved by using anti-caking additives during filtration.

2 Project Goals and Objectives

While we await additional funding and the establishment of a subcontract agreement, we will use our first \$30k allocation to improve the speed, cost, and scalability of our sample preparation protocol.

3 Key Accomplishments

3.1 Pre-Kickoff Meeting

A formal kickoff meeting including APL, PPG, and ONR will be scheduled as soon as the remaining funding arrives. In the interim, we held an informal kickoff meeting at APL to outline our plan for the first \$30k allocation. The first month will focus solely on manufacturability. By developing an improved processing protocol up front, we can benefit from improved sample making efficiency throughout the year. In addition, sample preparation methods will remain static and will not cause unexpected variations in coating performance.

At the meeting we reviewed the formulations that were tested in FY11, identified the most promising samples, and made plans to repeat those experiments. We also outlined a series of new formulations that will be tested in FY12 to further optimize performance. The experiments were then scheduled to align with the milestones outlined in the FY12 technical proposal.

3.2 Drying

If the microcapsules are filtered and dried on the benchtop, they suffer irreversible clumping. To date, we have addressed this problem by freeze-drying. Freeze-drying results in free-flowing powders that mix readily with primer resin to form the Polyfibroblast primer. Unfortunately, freeze-drying is a slow and costly process that does not translate well to mass production.

Previous attempts to improve drying have mostly involved transfer of the microcapsules from water to a solvent with a lower boiling point and/or surface tension. This approach did not completely solve the caking problem, and solvents such as methanol and acetone frequently damaged the microcapsules in the process.

Preliminary experiments indicate that anti-caking agents may allow us to air dry the microcapsules after filtration. So far, sodium dodecylsulfate and Brij 30 surfactant have resulted in free-flowing powders after only one hour of drying on the benchtop.

3.3 Interfacial Polymerization

Another manufacturing issue identified in FY11 was the slow cure time for the polymer skin layer. It currently takes three days to fully form the outer polymer shell of the microcapsules. Most attempts to speed this reaction result in unwanted internal polymerization and through curing. Preliminary experiments have shown that toluene diisocyanate and ethylene diamine may react more quickly at the interface than previously thought. With a functionality of two, these monomers can only form a linear polymer. Our previous experience actually showed that such chemicals were actually *more* prone to internal curing. The difference here may be that the formulation now includes a high volume fraction (75%) of silane coupling agent. Since the silanes do not polymerize, they may help to limit the precipitation of polyurea within the microcapsule interior.

4 Next Steps

4.1 Synthesis Improvements

Further experiments will be performed to verify that surfactants prevent caking and further optimize the process. We will also test to make sure that the surfactant residue does not adversely affect the subsequent primer performance.

We will continue to investigate ways to increase the microcapsule formation for 75% octadecyltrimethoxy silane (OTS) microcapsules. Lessons learned for the 75% OTS microcapsules will then be applied to our more typical formulations.