



AFRL-RZ-WP-TP-2012-0093

EVALUATING SUPERCONDUCTING YBCO FILM PROPERTIES USING X-RAY PHOTOELECTRON SPECTROSCOPY (POSTPRINT)

Paul N. Barnes, Justin C. Tolliver, and Timothy J. Haugan

**Mechanical Energy Conversion Branch
Energy/Power/Thermal Division**

Sharmila M. Mukhopadhyay

Wright State University

John T. Grant

University of Dayton

FEBRUARY 2012

Approved for public release; distribution unlimited.

See additional restrictions described on inside pages

STINFO COPY

© 2004 The American Ceramic Society

**AIR FORCE RESEARCH LABORATORY
PROPULSION DIRECTORATE
WRIGHT-PATTERSON AIR FORCE BASE, OH 45433-7251
AIR FORCE MATERIEL COMMAND
UNITED STATES AIR FORCE**

REPORT DOCUMENTATION PAGE				Form Approved OMB No. 0704-0188	
The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.					
1. REPORT DATE (DD-MM-YY) February 2012		2. REPORT TYPE Conference Paper Postprint		3. DATES COVERED (From - To) 01 January 2002 – 01 January 2004	
4. TITLE AND SUBTITLE EVALUATING SUPERCONDUCTING YBCO FILM PROPERTIES USING X-RAY PHOTOELECTRON SPECTROSCOPY (POSTPRINT)				5a. CONTRACT NUMBER In-house	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER 62203F	
6. AUTHOR(S) Paul N. Barnes, Justin C. Tolliver, and Timothy J. Haugan (AFRL/RZPG) Sharmila M. Mukhopadhyay (Wright State University) John T. Grant (University of Dayton)				5d. PROJECT NUMBER 3145	
				5e. TASK NUMBER 32	
				5f. WORK UNIT NUMBER 314532Z9	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Mechanical Energy Conversion Branch (AFRL/RZPG) Energy/Power/Thermal Division Air Force Research Laboratory Propulsion Directorate Wright-Patterson Air Force Base, OH 45433-7251 Air Force Materiel Command, United States Air Force				8. PERFORMING ORGANIZATION REPORT NUMBER AFRL-RZ-WP-TP-2012-0093	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) Air Force Research Laboratory Propulsion Directorate Wright-Patterson Air Force Base, OH 45433-7251 Air Force Materiel Command United States Air Force				10. SPONSORING/MONITORING AGENCY ACRONYM(S) AFRL/RZPG	
				11. SPONSORING/MONITORING AGENCY REPORT NUMBER(S) AFRL-RZ-WP-TP-2012-0093	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution unlimited.					
13. SUPPLEMENTARY NOTES Conference paper published in the proceedings of the <i>Fabrication of Long-Length and Bulk High-Temperature Superconductors</i> . The conference was the 105th annual meeting of The American Ceramic Society, held April 27-30, 2003, in Nashville, TN. © 2004 The American Ceramic Society. The U.S. Government is joint author of the work and has the right to use, modify, reproduce, release, perform, display, or disclose the work. Work on this effort was completed in 2004. PA Case Number: ASC-03-2986; Clearance Date: 06 Dec 2004.					
14. ABSTRACT Initial results have been recently reported that suggest a potential correlation exists between the full-width-half-maximum (FWHM) of the Y(3d) peak obtained by x-ray photoelectron spectroscopy (XPS) and the critical current density a YBa ₂ Cu ₃ O _{7-x} film can carry. In particular, the Y(3d _{5/2}) demonstrated a stronger correlation. Transport currents were determined by the 4-point contact method using the 1μV/cm criterion. An apparent correlation was also suggested between the Y(3d) FWHM and ac loss data points were acquired to further test the usefulness of the correlations. Samples were created by pulsed laser deposition of YBa ₂ Cu ₃ O _{7-x} on LaAlO ₃ substrates.					
15. SUBJECT TERMS x-ray, transport currents, ac loss, data points, samples, pulsed laser deposition, substrates					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT: SAR	18. NUMBER OF PAGES 16	19a. NAME OF RESPONSIBLE PERSON (Monitor) Timothy J. Haugan 19b. TELEPHONE NUMBER (Include Area Code) N/A
a. REPORT Unclassified	b. ABSTRACT Unclassified	c. THIS PAGE Unclassified			

EVALUATING SUPERCONDUCTING YBCO FILM PROPERTIES USING X-RAY PHOTOELECTRON SPECTROSCOPY

Paul N. Barnes, Justin C. Tolliver, and Timothy J. Haugan
Air Force Research Laboratory
AFRL/PRPG, Building 450
Wright-Patterson AFB, OH 45433

Sharmila M. Mukhopadhyay
Wright State University
Russ Engineering Center
Dayton, OH 45435

John T. Grant
University of Dayton
300 College Park
Dayton, OH 45469

ABSTRACT

Initial results have been recently reported that suggest a potential correlation exists between the full-width-half-maximum (FWHM) of the Y(3d) peak obtained by x-ray photoelectron spectroscopy (XPS) and the critical current density a $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$ film can carry. In particular, the Y(3d_{5/2}) demonstrated a stronger correlation. Transport currents were determined by the 4-point contact method using the 1 $\mu\text{V}/\text{cm}$ criterion. An apparent correlation was also suggested between the Y(3d) FWHM and ac loss data from magnetic susceptibility measurements. In this report, a few additional data points were acquired to further test the usefulness of the correlations. Samples were created by pulsed laser deposition of $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$ on LaAlO_3 substrates.

INTRODUCTION

Significant progress has been made in the development of the high temperature superconducting (HTS) $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$ (YBCO) coated conductors.¹⁻⁴ These achievements have been accomplished by using a variety of techniques investigating multiple aspects of the conductor architecture and growth.⁵⁻⁶ Successful long length development of the YBCO coated conductor will result in its availability for use in a variety of commercial applications such as power transmission cables, high field magnets, transformers, high power generators and motors, etc.

To the extent authorized under the laws of the United States of America, all copyright interests in this publication are the property of The American Ceramic Society. Any duplication, reproduction, or republication of this publication or any part thereof, without the express written consent of The American Ceramic Society or fee paid to the Copyright Clearance Center, is prohibited.

However, many improvements can still be made in the properties of the coated conductor as well as production of longer lengths.⁷⁻⁹ Continuing development of the coated conductor necessitates not only a detailed study of deposition techniques, source materials, deposition conditions, and substrates employed, but also characterization of the final deposited films. A technique used in this paper is x-ray photoelectron spectroscopy (XPS), especially of the YBCO layer. XPS was used to investigate the chemical and microstructural profiles of YBCO coated conductor samples.¹⁰⁻¹¹ Use of the technique can give consideration to interfacial issues and determine composition and chemistry at different depths in the conductor architecture.

BACKGROUND

Comparison of the XPS spectra for the various constituents of YBCO coated conductor samples revealed that the Y(3d) photoelectron peak shape observed from the YBCO layer differed among various samples investigated.¹⁰⁻¹¹ This difference in XPS peak shape may indicate that there could be some difference in the atomic co-ordination between the samples. The observed difference, when compared to the particular film's properties, may also indicate the possibility of a correlation with the particular quality of the film.

In a previous study by Beyer et al.,¹² a difference in samples was also noted that depended on the particular substrate used. In this study, two series of samples were prepared by hollow cathode sputtering of the YBCO film, between 100 nm to 300 nm thick. One series was grown on (100) MgO and the other on (001) YSZ buffered r-plane sapphire. The T_c s were typically between 80-91 K, a wide variance by recent deposition standards. During the various treatments, the Y emission remained fairly stable, but the Ba ($3d_{5/2}$) structure showed distinct differences in its lineshape in the YBCO deposited on the two different substrates. Beyer et al. noted that the differences were not caused by surface impurities but were characteristic of the samples. A structural deviation was assumed to be responsible for the difference. Even so, this does not rule out that the differences might correlate to the film's current transport properties since some substrates indeed provide better subsequent films than others.

Another possible correlation cited in the previous work is the relationship of the Y(3d) peak FWHM and the samples ac loss data from magnetic susceptibility measurements. It has been previously observed that with widening of the temperature-dependent ac susceptibility curves with increasing applied magnetic field the quality of the YBCO film generally decreases.¹³ However, a documented study of this correlation to current transport properties using the loss component of ac susceptibility data has not been published, making it unclear how effective this correlation is.¹⁴ Even so, the relationship between the Y(3d) peak FWHM and the ΔT of the magnetic field lines reinforces the possibility. In this case, ΔT of the magnetic field lines refers to either the difference between the temperatures at which the maxima in the ac loss occurs for the 0.025 and 2.2 Oe applied magnetic

fields (peak to peak of χ'') or to the FWHM of the 2.2 Oe (in particular) magnetic field data χ'' vs. T

EXPERIMENTAL

In this study, samples were created by pulsed laser deposition of YBCO on single crystal LaAlO_3 . Previously, most samples were made in the same manner although other samples are included such as YBCO on buffered metallic tape and buffered single crystals.¹⁰ The laser ablation was accomplished using a Lambda Physik LPX 305i excimer laser at the KrF transition, $\lambda = 248$ nm with a 25 ns pulse width. Mounting of the substrates in the deposition chamber was accomplished using silver paste. Specific details of the deposition conditions were given previously.¹⁰ The YBCO layers of the newly created samples were between 0.25 to 0.40 micrometers thick.

Since the previous study contained data representing a limited number of low quality samples, i.e. $J_c < 10^6$ A/cm², the three samples used here were particularly chosen for this study due to their poor film quality. One sample was unintentionally made with low quality and the other two were intentionally made so by specifically reducing the deposition temperature in the PLD chamber by ~ 100 °C. The critical transition temperature (T_c) of YBCO was measured by ac magnetic susceptibility and the critical current density (J_c) by four-contact transport current measurement.

The composition and chemistry of each sample was measured by X-ray photoelectron spectroscopy (XPS) using a Kratos AXIS Ultra. The monochromatic Al K_α x-ray line was used for enhanced spectral resolution. The analysis spot size was approximately 110 μm^2 . An electron flood charge neutralizer was used during analysis to avoid charge build-up differences between different surfaces (if any). Ion beam sputtering was performed using a mini-beam ion gun. Ar^+ ions were used at an energy of 3 keV. In the raster setting used, the sputtered area was approximately a 1 mm x 0.5 mm elliptical region, several times larger than the spot size analyzed by XPS. Spectroscopic analysis was performed on as received surfaces and after subsequent sputtering to avoid the influence of surface contamination or any chemical reactivity with air.

RESULTS AND DISCUSSION

The J_c s of the samples were 1.5×10^5 A/cm² for the unintentionally made poor sample, 2×10^5 A/cm² for the one low deposition temperature sample and $< 10^4$ A/cm² for the other low deposition temperature sample. All three YBCO samples in this study had a reduced T_c . Refer to Figure 1 for the low temperature deposition sample with the higher critical current density. The T_c for the sample made with the normal deposition temperature had a T_c of ~ 86.1 K. Since samples were exposed to air the top surface was removed by sputtering. The before and after sputtering values obtained by XPS are largely uncorrelated as evidenced by




Fig. 1. The ac susceptibility data for sample CT23 made with the low deposition temperature but had a nominal J_c of 2×10^5 A/cm². The different curves result from the different applied fields listed in the legend—the field increases from right to left.




Fig. 2. Comparison of XPS data taken before and after sputtering of the surface for contaminate removal.

the scatter of the data given in Figure 2 which shows values for all samples included in the previous study, although not reported there.

In Figure 3, the relative peak intensity ratios of all samples for both studies are shown. The two stray points depicted were the two that were intentionally made poor by lowering the deposition temperature. Since all other samples had similar peak intensity ratios, it is likely that the difference caused by the low deposition temperature is due to inclusions and alternate phases incorporated during




Fig. 3. Comparison of the relative XPS peak intensities of the various samples. The two compositionally stray points were made with the low deposition temperature.




Fig. 4. Comparison of the Y(3d_{5/2}) peak FWHM and transport J_c.

deposition. As such, these compositionally stray points will be excluded from the correlation charts as being invalid for comparison.

In Figure 4 the correlation of the FWHM for the $Y(3d_{5/2})$ peak and the critical transport current density (four point resistive) is given. The new point provided by the additional sample is located at 1.35 eV FWHM $Y(3d_{5/2})$ with 0.15 MA/cm^2 . For the given plot, this data resulted in a stray point from the other points which indicate a correlation. The point located at 1.8 eV is not stray since it fits the pattern of low J_c correlated to a larger $Y(3d_{5/2})$ FWHM. It is not clear if the lower transport current was a result of cracks in the film which can cause a lower transport current and yet not affect the XPS spectra. However, it is interesting to note that this sample also resulted in a stray point to a greater degree on the following figure, Figure 5, which gives the relationship between the FWHM for the $Y(3d_{5/2})$ peak and the FWHM of the critical transition temperature by susceptibility measurement.

Figure 5 depicts the relationship between the FWHM for the $Y(3d_{5/2})$ peak and the FWHM of the 2.2 Oe magnetic field line at the critical transition temperature by ac susceptibility measurement. As previously mentioned, the new data point on this plot (5 K for ΔT) also strayed from the others based on the expected relationship. Exactly why there is a corroborative stray form the original data in both graphs is not clear, but a correlation between the points apparently still exists. This clearly indicates the need for additional data to determine the effectiveness of the correlations as well as determining the exact relationship of the two plots presented here. Figure 6 shows the χ'' susceptibility data for sample CT23, from Figure 1, from which the FWHM for the $Y(3d_{5/2})$ peak was derived. The FWHM of the 2.2 Oe magnetic field data was used, although this does not imply that this is the predominant usage.¹³⁻¹⁴




Fig. 5. Comparison of the XPS $Y(3d_{5/2})$ FWHM and the T_c FWHM determined by ac susceptibility measurement (2.2 Oe).




Fig. 6. χ'' versus temperature plot of the ac susceptibility data. 0.025 to 2.2 Oe magnetic field used. The different curves result from the different applied fields listed in the legend—the field increases from right to left.

CONCLUSION

It is seen that the FWHM of certain XPS peaks as well as XPS cationic peak ratios averaged over the analysis area can vary between YBCO samples. A possible correlation of the FWHM of the Y(3d_{5/2}) XPS peak of YBCO to the thin film quality, specifically the critical transport current density (J_c) may exist but is not clear. This relationship is dependent upon the appropriately phased YBCO for a proper comparison and YBCO samples whose nonstoichiometric composition will lead to an alternate XPS spectra. Broadening of the FWHM of the Y(3d_{5/2}) XPS peak can indicate alternate undesirable bonding in the YBCO. More data is necessary to fully verify these relationships.

ACKNOWLEDGMENT

The authors gratefully acknowledge the assistance of Lyle Brunke, Julianna Evans, and Timothy Campbell of the Air Force Research Laboratory for their assistance in film preparation, x-ray diagnostics, and making the critical current transport measurements.

REFERENCES

- ¹V. Selvamanickam, H.G. Lee, Y. Li, X. Xiong, Y. Qiao, J. Reeves, Y. Xie, A. Knoll, and K. Lenseth, "Fabrication of 100 A class, 1 m long coated conductor tapes by metal organic chemical vapor deposition and pulsed laser deposition," *Physica C*, **392-396** [2], pp. 859-862 (2003).
- ²D.T. Verebelyi, U. Schoop, C. Thieme, X. Li, W. Zhang, T. Kodenkandath, A.P. Malozemoff, N. Nguyen, E. Siegal, D. Buczek, J. Lynch, J. Scudiere, M. Rupich, A. Goyal, E.D. Specht, P. Martin, and M. Paranthaman, "Uniform performance of continuously processed MOD-YBCO-coated conductors using a textured Ni-W substrate," *Superconductivity Science & Technology*, **16**, pp. L19-L22 (2003).
- ³J.R. Groves, P.N. Arendt, S.R. Foltyn, Q. Jia, T.G. Holesinger, H. Kung, R.F. DePaula, P.C. Dowden, E.J. Peterson, L. Stan, and L.A. Emmert, "Recent progress in continuously processed IBAD MgO template meters for HTS applications," *Physica C*, **382** [1], pp. 43-47 (2002).
- ⁴A. Goyal, D.F. Lee, F.A. List, E.D. Specht, R. Feenstra, M. Paranthaman, X. Cui, S.W. Lu, P.M. Martin, D.M. Kroeger, D.K. Christen, B.W. Kang, D.P. Norton, C. Park, D.T. Verebelyi, J.R. Thompson, R.K. Williams, T. Aytug, and C. Cantoni, "Recent progress in the fabrication of high- J_c tapes by epitaxial deposition of YBCO on RABiTS," *Physica C*, **357-360** [2], pp. 903-913 (2001).
- ⁵Air Force Office of Scientific Research High Temperature Superconducting Coated Conductor Review, St. Petersburg, Florida, January 22-24, 2003.
- ⁶Department of Energy Superconductivity for Electric Systems Annual Peer Review, Washington, DC, July 23-25, 2003.
- ⁷C.B. Cobb, P.N. Barnes, T.J. Haugan, J. Tolliver, E. Lee, M. Sumption, E. Collings, C.E. Oberly, "Hysteresis loss reduction in striated YBCO," *Physica C*, **382**, pp. 52-56 (2002).
- ⁸T.J. Haugan, P.N. Barnes, I. Maartense, E.J. Lee, M. Sumption, and C.B. Cobb, "Island growth of Y_2BaCuO_5 nanoparticles in $(211\sim 1.5nm/123\sim 10nm)_xN$ composite multilayer structures to enhance flux pinning of $YBa_2Cu_3O_{7-d}$ films," *J. Mater. Res.*, **18**, pp.2618-2623 (2003).
- ⁹T.J. Haugan, M.E. Fowler, J.C. Tolliver, P.N. Barnes, W. Wong-Ng, and L.P. Cook, "Flux Pinning and Properties of Solid-Solution $(Y,Nd)_{1+x}Ba_{2-x}Cu_3O_{7-d}$ Superconductors," *Ceramic Trans.*, **140**, pp. 299-325 (2003).
- ¹⁰P.N. Barnes, S. M. Mukhopadhyay, S. Krishnaswami, T.J. Haugan, J.C. Tolliver, and I. Maartense, "Correlation between the XPS peak shapes of $Y_1Ba_2Cu_3O_{7-x}$ and film quality," *IEEE Trans. on Appl. Superconductivity*, **13**, pp. 3643-3646 (2003).
- ¹¹P.N. Barnes, S. Mukhopadhyay, R. Nekkanti, T. Haugan, R. Biggers, and I. Maartense, "XPS depth profiling studies of YBCO layer on buffered substrates," *Advances in Cryogenic Engineering*, **48B**, pp. 614-618 (2002).

¹²J. Beyer, Th. Schurig, S. Menkel, Z. Quan, and H. Koch, "XPS investigation of the surface composition of sputtered YBCO thin films," *Physica C*, **246**, pp.156-162 (1995).

¹³I. Maartense and A. K. Sarkar, "Annealing of pressure-induced structural damage in superconducting Bi-Pb-Sr-Ca-Cu-O ceramic," *J. Mater. Res.*, **8**, pp. 2177 (1993).

¹⁴P. N. Barnes, T.J. Haugan, S. Sathiraju, I. Maartense, A.L. Westerfield, R.M. Nekkanti, L.B. Brunke, T.L. Peterson, J.M. Evans, and J.C. Tolliver, "Correlation of AC Loss Data from Magnetic Susceptibility Measurements with YBCO Film Quality," to be presented at MRS Fall Meeting, Boston, MA, December 1-5, 2003.