

REPORT DOCUMENTATION PAGE

Form Approved
OMB No. 0704-0188

The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing the burden, to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.

PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.

1. REPORT DATE (DD-MM-YYYY) 26-12-2012		2. REPORT TYPE Performance/Technical Report (Monthly)		3. DATES COVERED (From - To) 11/26/12 - 12/26/12	
4. TITLE AND SUBTITLE Polyfibroblast: A Self-Healing and Galvanic Protection Additive				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER N00014-09-1-0383	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S) Benkoski, Jason J.				5d. PROJECT NUMBER	
				5e. TASK NUMBER FGY25	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) The Johns Hopkins University Applied Physics Laboratory 11100 Johns Hopkins Rd Laurel, MD 20723				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) Office of Naval Research 875 North Randolph Street Arlington, VA 22203-1995				10. SPONSOR/MONITOR'S ACRONYM(S) ONR	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for Public Release: distribution is Unlimited.					
13. SUPPLEMENTARY NOTES					
14. ABSTRACT The goal of this project is to develop a primer additive that mimics the self-healing ability of skin by forming a polymer scar across scratches. Designed to work with existing military grade primers, Polyfibroblast consists of microscopic, hollow zinc tubes filled with a moisture-cured polyurethane-urea (MCPU). When scratched, the foaming action of a propellant ejects the resin from the broken tubes and completely fills the crack. No catalysts or curing agents are needed since the polymerization is driven by ambient humidity.					
15. SUBJECT TERMS corrosion protection, self-healing, coatings, polymers					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT UU	18. NUMBER OF PAGES 4	19a. NAME OF RESPONSIBLE PERSON Jason J Benkoski
a. REPORT U	b. ABSTRACT U	c. THIS PAGE U			19b. TELEPHONE NUMBER (Include area code) 240-228-5140

REDD-2013-012

POLYFIBROBLAST: A SELF-HEALING AND GALVANIC PROTECTION ADDITIVE

Progress Report #13

Prepared for:

Cody M. Reese
Logistics S&T Thrust Manager
Office of Naval Research
Code 30, Room 1149
875 North Randolph Street
Arlington, VA 22203-1995

Prepared by:

Jason J. Benkoski, Ph.D., Senior Research Scientist
The Johns Hopkins University Applied Physics Laboratory
The Milton S. Eisenhower Research Center
11100 Johns Hopkins Rd, MS 21-N109
Laurel, MD 20723
Tel. (240) 228-5140

Reporting Period: November 26, 2012 through December 26, 2012
Date of Report: December 26, 2012

20130111015

TABLE OF CONTENTS

1	SUMMARY	3
2	PROJECT GOALS AND OBJECTIVES	3
3	KEY ACCOMPLISHMENTS	3
3.1	FIELD TEST PLANS FINALIZED	3
3.2	FINAL BATCH INSPECTION	3
4	NEXT STEPS	4
4.1	FIELD TEST	4

1 Summary

Planning and preparation for the MTRV field test is underway. The test dates have been set as the week of January 14th. The USMC Corrosion Control team has requested 10 gallons of paint for the test rather than the originally planned 5. PPG is on track to deliver. In initial tests of the 10-gallon batch, PPG has demonstrated a particle size cutoff below 100 μm in the primer, acceptable sprayout, and acceptable adhesion for the Polyfibroblast coating stack.

2 Project Goals and Objectives

PPG will deliver 10 gallons of self-healing paint for the January 14th field test in Camp Lejeune, NC.

3 Key Accomplishments

3.1 Field Test Plans Finalized

PPG and APL conducted a teleconference with Andrew Sheetz and Jay Ong from the USMC corrosion control team. The test will be conducted during the week of January 14th. It will be performed at the Corrosion Repair Facility (CRF) at Camp Lejeune, NC. Representatives from both APL and PPG will be in attendance, and observers from ONR are also welcome to attend.

The current plan is to drop ship all items to Camp Lejeune, including 10 gallons of paint, MSDSs, thinner, spray guns, pans, cups, drop cloths, filters, rags, gloves, and respirators. All attendees must be equipped with steel-toe shoes and overalls. The painter from the CRF will perform the painting. They will paint one half of the truck bed of an MTRV with the self-healing primer, and the other half with Niles zinc-rich primer. On top of the primer will be applied a second layer of CARC primer, followed by the CARC topcoat. All will be applied according to the appropriate military specifications.

PPG will ship the self-healing paint as a two-component mixture. Although APL has proven that the pot life of the primer can be as long as three months, PPG has experienced mixed results, with some primers gelling only hours after adding the microcapsules. To ensure a successful test, the microcapsules and zinc rich primer will be shipped in separate containers and mixed onsite.

With the extra, unused paint, the USMC Corrosion Control Team will also paint a large series of witness panels to undergo accelerated weathering tests along with a large number of other coatings that they are evaluating.

3.2 Final Batch Inspection

PPG has begun testing small aliquots of the 10-gallon batch to qualify them prior to the field test. According to standard protocol, PPG crushed the microcapsules under a microscope to

verify that they possessed hard polymer shells that cracked when broken. PPG also inspected the dispersion of the microcapsules in the MIL-P-26915 primer using a Hegman gauge. The Hegman gauge reported a particle size cutoff below 100 μm , indicating minimal agglomeration. Finally, the self-healing paint aliquots were spray painted on several test panels and tested for adhesion. Spray out showed no obvious issues, and the tape strip adhesion measurements passed specification. Unless new technical issues arise, PPG will complete processing of the roughly 4 kg of microcapsules that are required for 10 gallons of paint.

4 Next Steps

4.1 Field Test

PPG will organize the items necessary for the field test and ship them to the CRF in Camp Lejeune. At least one representative from APL and PPG will make travel plans and attend.

