

REPORT DOCUMENTATION PAGE			Form Approved OMB NO. 0704-0188	
The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA, 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number. PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.				
1. REPORT DATE (DD-MM-YYYY)		2. REPORT TYPE Technical Report		3. DATES COVERED (From - To) -
4. TITLE AND SUBTITLE Fabrication and Test of MC/BZY Proton Conductor		5a. CONTRACT NUMBER W911NF-13-1-0158		
		5b. GRANT NUMBER		
		5c. PROGRAM ELEMENT NUMBER 206022		
6. AUTHORS Kevin Huang		5d. PROJECT NUMBER		
		5e. TASK NUMBER		
		5f. WORK UNIT NUMBER		
7. PERFORMING ORGANIZATION NAMES AND ADDRESSES Benedict College Office of Research 1600 Harden St. Columbia, SC 29204 -1058			8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS (ES) U.S. Army Research Office P.O. Box 12211 Research Triangle Park, NC 27709-2211			10. SPONSOR/MONITOR'S ACRONYM(S) ARO	
			11. SPONSOR/MONITOR'S REPORT NUMBER(S) 62940-CH-REP.9	
12. DISTRIBUTION AVAILABILITY STATEMENT Approved for public release; distribution is unlimited.				
13. SUPPLEMENTARY NOTES The views, opinions and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy or decision, unless so designated by other documentation.				
14. ABSTRACT Technical report of 2013-2014 (experimental part)				
15. SUBJECT TERMS BZY, Proton conductor, SOFC, Molten Carbonate				
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT UU	15. NUMBER OF PAGES
a. REPORT UU	b. ABSTRACT UU	c. THIS PAGE UU		
				19a. NAME OF RESPONSIBLE PERSON Changyong Qin
				19b. TELEPHONE NUMBER 803-705-4582

Report Title

Fabrication and Test of MC/BZY Proton Conductor

ABSTRACT

Technical report of 2013-2014 (experimental part)

Novel MC/BZY Proton Conductor: Materials Development, Device Evaluation, and Theoretical Exploration using CI and DFT Methods

Changyong Qin, Benedict College, Columbia, SC 29204 (PI)

Kevin Huang, University of South Carolina, Columbia, SC 29208 (Co-PI)

(Experimental Part)

I. Experimental procedures

1. Infiltration of molten carbonates into porous BZY pellets

1.1 Fabrication of Porous BZY Pellets

BZY ($\text{BaZr}_{0.8}\text{Y}_{0.2}\text{O}_{2.9}$) electrolyte was made by classical solid state reaction. The starting precursors for BZY are BaCO_3 (99.8%, Alfa Aesar), ZrO_2 (99.7%, Alfa Aesar) and Y_2O_3 (99.9%, Alfa Aesar). After weighing and mixing, calcinations were first carried out at 1100°C for five hours. The calcined samples were then broken up into powders and calcined at 1300°C for another five hours, followed by grinding down to fine powders. Proportional carbon black, as pore former, was added into the as-prepared BZY powder before dry pressing. Additional burn-out processing was carried out at 400°C for 2 hours and 600°C for 2 hours, respectively. Finally, BZY pellets were sintered at 1500°C for 5 hours and ready for molten carbonate infiltration.

1.2 Synthesis of Molten Carbonate and Infiltration

Li/K and Li/Na carbonate were prepared by melting lithium carbonate (99%, Alfa Aesar) and potassium carbonate (99%, Alfa Aesar) in 62:38 (mol%), lithium carbonate (99%, Alfa Aesar) and sodium carbonate (99%, Alfa Aesar) in 52:48 (mol%) at 650°C for 2 hours. The as-prepared BZY pellets were loaded into a silver basket and immersed into the molten carbonate for 2 hours, and then pulled out of the melts before they were cooled down to room temperature. Thus fabricated MC/BZY composites were then slightly polished on the surfaces to remove the residual melt. All the pellets were ready for electrochemical impedance measurement.

2 Characterization of MC/BZY

The sintered BZY powders were examined by X-ray diffraction (XRD) patterns to confirm the formation of BZY, while the microstructures of BZY pellets as well the MC/BZY composites were observed by a field emission scanning electron microscopy (SEM).

Ionic conductivity of MC/BZY composites were measured by electrochemical impedance spectroscopy. Before measurement, MC/BZY pellets were made to be a symmetrical cell configuration with Ag as the electrode. To study ionic conductivity of MC/BZY composites, air contained 3% H_2O , and 5% hydrogen in nitrogen containing 3% H_2O , represented as the atmosphere of cathode and anode, respectively, were used in the temperature range of 400 to 650°C . For the study of the effect of H_2O partial pressure on ionic conductivity, gas was passed through a water saturator at fixed temperature. A humidity sensor (Vaisala model 332) was used to measure the real steam content in the gas.

II. Results and Discussion

1 XRD Examinations and Microstructural Features

The XRD pattern shown in Fig.1 indicates a single cubic perovskite structure for BZY after calcining at 1300°C for 5 h.




Fig.1 XRD pattern of BZY

The microstructures of porous BZY and MC/BZY composite are shown in Fig.2 (a) and (b). Before infiltration, BZY pellets appear to be non-uniform in grain size and poorly connected. In contrast, Fig.2 (c) and (d) show that the MC/BZY composite is dense and crack free after infiltration with carbonate well dispersed within BZY grains.




Fig.2 SEM image of (a) surface and (b) fracture of BZY sintered at 1500°C; (c) and (d) fracture surface of Li-Na carbonate/BZY composite fired at 650°C

2 The Effects on Conductivity

It is found that higher MC loading leads to a higher conductivity. Different amount of carbon black were added to BZY powder to create different porosities, which has resulted in an obvious difference in $\text{Li}_2\text{CO}_3\text{-K}_2\text{CO}_3$ (62:38 mol%) loading as shown in Fig.3. The conductivity of samples with higher MC loading is higher below 490°C when carbonate is in solid state, while the difference is less apparent above 490°C.




Fig.3 Plots of conductivity as a function of temperature in 3% H_2O -air of MC/BZY composites with different MC loading

Different alkaline composition of MC also affected specimen's conductivity. For a BZY sample with the same porosity infiltrated with $\text{Li}_2\text{CO}_3\text{-K}_2\text{CO}_3$ (62:38 mol%) and $\text{Li}_2\text{CO}_3\text{-Na}_2\text{CO}_3$ (52:48 mol%), the results shown in Fig. indicate that the sample infiltrated with $\text{Li}_2\text{CO}_3\text{-Na}_2\text{CO}_3$ (52:48 mol%) has a higher conductivity at $> 500^\circ\text{C}$. This observation is consistent with that Li-Na carbonate has a higher conductivity than Li-K carbonate.




Fig.4 Plots of conductivity as a function of temperature in 3% H_2O -air of BZY pellets with the same porosity and infiltrated by Li/K and Li/Na carbonates

It is also found that the conductivity is higher in wet hydrogen than in wet air. BZY pellets with the highest porosity were infiltrated by $\text{Li}_2\text{CO}_3\text{-Na}_2\text{CO}_3$ (52:48 mol%), resulting in a MC loading as of 57 vol%. As indicated in Fig.5, the conductivity in 3% $\text{H}_2\text{O-H}_2$ is higher than that in 3% $\text{H}_2\text{O-air}$ over the whole temperature range, but difference was larger below 490°C. As a reference, the conductivity of pure $\text{Li}_2\text{CO}_3\text{-Na}_2\text{CO}_3$ (52:48 mol%) was presented, which indicated the highest conductivity possible. A set of reference conductivity for the MC/BZY composite at 600°C is 1.11 S/cm for 3% $\text{H}_2\text{O-H}_2$ and 0.65 S/cm for 3% $\text{H}_2\text{O-air}$.




Fig. 5 Plots of conductivity as a function of temperature in 3% $\text{H}_2\text{O-air}$ and in 3% $\text{H}_2\text{O-H}_2$ of Li-Na carbonate/BZY composite sample

The conductivity is found to increase with humidity in H_2 . The isothermal conductivity of a MC/BZY composite with the highest $\text{Li}_2\text{CO}_3\text{-Na}_2\text{CO}_3$ (52:48 mol%) loading was measured as a function of partial pressure of H_2O ($P_{\text{H}_2\text{O}}$) at 600°C, as shown in Fig.6. Compared to those measured in air, the conductivity measured in hydrogen was almost twice higher and it appeared to linearly increase with $P_{\text{H}_2\text{O}}$ in both atmospheres.




Fig. 6 Plots of conductivity as a function of $P_{\text{H}_2\text{O}}$ of Li-Na carbonate/BZY composite

III. Conclusion and next step

In summary, the BZY/MC composite ionic conductor has been characterized microstructurally and electrochemically. It was found that the original porous BZY pellets become dense after being filled with molten carbonates. The conductivity shows a sharp increase at the solid-liquid phase transformation temperature. The conductivity of BZY/MC composite ionic conductor increases with lower partial pressure of oxygen and higher humidity.

During the next reporting period, we will focus on study of developing compatible electrode materials for MC/BZY and electrochemical testing of MC/BZY based SOFCs and SOECs.