

REFERENCE ONLY

TM No. 841072



NAVAL UNDERWATER SYSTEMS CENTER
NEW LONDON LABORATORY
NEW LONDON, CONNECTICUT 06320

TECHNICAL MEMORANDUM

DIELECTRIC PROPERTIES OF PIEZOELECTRIC
POLYVINYLIDENE FLUORIDE (PVDF)

Date: April 16, 1984

Prepared by:

Mark B. Moffett

MARK B. MOFFETT
Target Physics
Sensor Technology Branch

REFERENCE ONLY

James M. Powers

JAMES M. POWERS
Electroacoustic
Transduction Branch

Approved for public release; distribution unlimited

Report Documentation Page			Form Approved OMB No. 0704-0188		
Public reporting burden for the collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to a penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.					
1. REPORT DATE 16 APR 1984		2. REPORT TYPE Technical Memo		3. DATES COVERED 16-04-1984 to 16-04-1984	
4. TITLE AND SUBTITLE Dielectric Properties of Piezoelectric Polyvinylidene Fluoride (PVDF)			5a. CONTRACT NUMBER		
			5b. GRANT NUMBER		
			5c. PROGRAM ELEMENT NUMBER		
6. AUTHOR(S) Mark Moffett; James Powers			5d. PROJECT NUMBER A61404		
			5e. TASK NUMBER		
			5f. WORK UNIT NUMBER		
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Naval Underwater Systems Center, New London, CT, 06320			8. PERFORMING ORGANIZATION REPORT NUMBER TM 841072		
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) NAVMAT			10. SPONSOR/MONITOR'S ACRONYM(S) NAVMAT 05B		
			11. SPONSOR/MONITOR'S REPORT NUMBER(S)		
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution unlimited					
13. SUPPLEMENTARY NOTES NUWC2015					
14. ABSTRACT Measurements were made of the free dielectric constant and the dielectric loss tangent of piezoelectric polyvinylidene fluoride (PVDF) at frequencies between 1 kHz and 5 MHz and temperatures between -28??C and +51??C. Samples of nonvoided and voided PVDF were tested. The dielectric constant increases with increasing temperature and/or decreasing frequency, ranging from about 3 to 11 for the voided material and from about 4 to 14 for the nonvoided material. The dielectric loss tangent (dissipation factor) ranged from about 0.02 at low frequencies and high temperatures to about 0.3 at high frequencies and high temperatures. The voided material was not as lossy as the nonvoided material with maximum values - 0.2 for the voided material and 0.3 for the nonvoided material. A slight temperature aging effect was observed; an increase of a few percent in dielectric constant resulted from cycling the samples to 51??C.					
15. SUBJECT TERMS piezoelectricity; polyvinylidene fluoride; PVDF					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT Same as Report (SAR)	18. NUMBER OF PAGES 21	19a. NAME OF RESPONSIBLE PERSON
a. REPORT unclassified	b. ABSTRACT unclassified	c. THIS PAGE unclassified			

cy001

NAVAL UNDERWATER SYSTEMS CENTER
NEW LONDON LABORATORY
NEW LONDON, CONNECTICUT 06320

TECHNICAL MEMORANDUM

DIELECTRIC PROPERTIES OF PIEZOELECTRIC
POLYVINYLIDENE FLUORIDE (PVDF)

Date: April 16, 1984

Prepared by:

Mark B. Moffett

MARK B. MOFFETT
Target Physics
Sensor Technology Branch

James M. Powers

JAMES M. POWERS
Electroacoustic
Transduction Branch

Approved for public release; distribution unlimited

ABSTRACT

Measurements were made of the free dielectric constant and the dielectric loss tangent of piezoelectric polyvinylidene fluoride (PVDF) at frequencies between 1 kHz and 5 MHz and temperatures between -28°C and $+51^{\circ}\text{C}$. Samples of nonvoided and voided PVDF were tested. The dielectric constant increases with increasing temperature and/or decreasing frequency, ranging from about 3 to 11 for the voided material and from about 4 to 14 for the nonvoided material. The dielectric loss tangent (dissipation factor) ranged from about 0.02 at low frequencies and high temperatures to about 0.3 at high frequencies and high temperatures. The voided material was not as lossy as the nonvoided material, with maximum values ~ 0.2 for the voided material and 0.3 for the nonvoided material. A slight temperature aging effect was observed; an increase of a few percent in dielectric constant resulted from cycling the samples to 51°C .

ADMINISTRATIVE INFORMATION

This memorandum was prepared under Job Order No. A61404, "Broadband Hydrophone for Transient Measurements," Principal Investigator: Dr. M. B. Moffett, Code 3321, Associate Investigator: J. M. Powers, Code 3234, Sponsoring Activity: NAVMAT 05B (CAPT Z. L. Newcomb), NUSC IED Program, Program Manager: Dr. K. M. Lima, Code 101. The authors are located at the Naval Underwater Systems Center, New London, CT 06320.

I. INTRODUCTION

Piezoelectric polyvinylidene fluoride (PVDF) is a useful hydrophone-element material because of its shock resistance, low density, and low mechanical impedance.^{1,2} However, the capacitance is about 100 times less than that of piezoelectric ceramics, so that capacitive coupling loss is more likely to be a problem with PVDF hydrophone designs than with conventional lead zirconate-titanate (PZT) hydrophones. Furthermore, PVDF is a much lossier material than PZT,³⁻⁵ a fact which appears to preclude its use in underwater projectors.⁶ The dielectric constant and dissipation factor of PVDF have been measured at room temperature by Pennwalt workers⁷ to about 400 kHz. Callera, Tancrell and Wilson,³ interested in medical ultrasonic applications, extended the frequency range to 20 MHz. Further extension to 100 MHz was provided by Leung and Yung⁴ and by Chen.⁵ All of these measurements were made on nonvoided material at room temperature. Because of the importance of the temperature dependence, we decided to measure the dielectric constant and dissipation factor as a function of temperature as well as frequency. The advent of thick-film, voided PVDF⁸ made it desirable to perform the same measurements on the newer material as well.

II. EXPERIMENT

Two samples of PVDF were tested: 1) a nonvoided 2.5 cm x 2.5 cm x 0.11 mm, nickel-aluminum electroded Kynar® element manufactured by Pennwalt Corporation,⁷ and 2) a voided 6.3 cm x 6.3 cm x 0.64 mm element, serial number AC 47/3, manufactured by Thorn EMI, Limited.⁸ The voided element had electroplated copper electrodes. The sample under test was held by a specially-made alligator clip making separate electrical contact with each electrode. A 3-ft length of RG-58C/U cable passing through a cloth insulator served as the electrical feedthrough into the temperature-controlled environment. The latter was provided by a Tenney Junior oven/refrigerator unit. All impedance measurements were made with a Hewlett-Packard 4192A low-frequency impedance analyzer with a 16095A probe fixture operated in a single-ended mode.

The impedance of the connecting cable was accounted for after measurement of the impedances, Z_{sc} and Z_{oc} , with the alligator clip contacts short-circuited and open-circuited, respectively. If the cable is assumed to behave as a uniform transmission line, the element impedance, Z , can be calculated from the measured impedance, Z_{in} (with element and cable in place), as follows:

$$Z = Z_{oc} (Z_{in} - Z_{sc}) / (Z_{oc} - Z_{in}) \quad (1)$$

The element capacitance is then

$$C = \text{Im}(Z^{-1}) / 2\pi f, \quad (2)$$

where f is the frequency. The dissipation factor is

$$D = \text{Re}(Z^{-1}) / \text{Im}(Z^{-1}) = -\text{Re}(Z) / \text{Im}(Z). \quad (3)$$

The (free) dielectric constant, $\epsilon_{33}^T/\epsilon_0$ was determined from the capacitance, C, as

$$\epsilon_{33}^T/\epsilon_0 = C/C_0 = Ct/\epsilon_0 A \quad (4)$$

where C_0 is the capacitance of an air gap dimensionally equal to the element size, ϵ_0 is the permittivity of free space, 8.85pF/m, t is the element thickness and A the element area. C_0 was 50.3pF for the nonvoided element and 54.9pF for the voided one.

The samples were subjected to the temperature history depicted in Figure 1. The material was considered to be "virgin" during the first 22°C to 31°C to -27°C cycle, but a rise in capacitance of several percent was noted after cycling (and holding for about 2 hrs) to 51°C and so data obtained after that point are for "aged" material.

III. RESULTS

The element capacitances are given in Table I. After division by C_0 (see Eq. 4), the dielectric constants of Table II and Figures 2-5 were obtained. It can be seen that the dielectric constant decreases monotonically with increasing frequency and with decreasing temperature. In fact, over the range of frequencies and temperatures in this study, the dielectric constant changed by a factor of more than three. The dielectric constant of the nonvoided material was generally higher than that of the voided material.

The dielectric loss tangents are given in Table III and Figures 6-9. There is a broad maximum in the loss tangent which shifts upward in frequency as the temperature is raised. At low temperatures, the voided material exhibited a sharp peak in loss factor at about 1 MHz. (It should be noted that since most of the measurements were made in a 1-2-5 frequency sequence, there is a possibility that other sharp peaks of this type existed but escaped unnoticed between the large frequency steps.) A similar "resonance" has been observed by workers at Thorn EMI.⁹

IV. DISCUSSION

The dielectric constant and dissipation factor curves of Figures 2-9 have the general shape of a dielectric relaxation process. However, each of these curves changes too slowly with frequency to be described by a single relaxation time, i.e., a multiplicity of relaxation times must be involved. Another way of seeing this result is that since the relaxation time, τ , of a conductive dielectric is given by $\tau = \epsilon/\sigma$, where σ is the electrical conductivity, and since we can express the conductivity, σ , as $2\pi f\epsilon D$, then the relaxation time, τ , would be given by $(2\pi f D)^{-1}$. In other words, to be describable by a single (constant) relaxation time, τ , the dissipation factor, D, would have to be inversely proportional to frequency. This is clearly not the case, as can be seen in Figures 6-9.

V. CONCLUSIONS

The free dielectric constant of nonvoided PVDF ranges from about 4 to 14 over the -28°C to 51°C temperature range and 1 kHz to 5 MHz frequency range, with a value of approximately 12 at 1 kHz and room temperature. (This compares reasonably well with literature values.^{7,11}) The voided material has a lower dielectric constant, ranging from about 3 to 11 over the temperature and frequency ranges considered here.

The voided material is not as lossy as the nonvoided material. The maximum dissipation factor was about 0.2 for the voided material and 0.3 for the nonvoided sample. At room temperature and 1 kHz, the dissipation factor was about 0.012 for each material.

After cycling to 51°C , the dielectric constant was elevated a few percent, but the dissipation factor was essentially unchanged.

VI. ACKNOWLEDGMENTS

The authors wish to thank W. L. Clay for the use of the oven/refrigerator unit, G. R. Giordano and J. F. Lindberg for the use of the impedance analyzer and accessories, and A. P. Sullivan for the use of the sample holder.

$f(\text{kHz})$	1	2	5	10	20	50	100	200	500	1000	2000	5000	
$T(^{\circ}\text{C})$													
31	616.7	613.7	609.6	605.0	591.4	575.6	566.6	546.9	509.4	468.8	420.1	350.8	virgin nonvoided element $C_0 = 50.3$ pF
22	602.7	599.7	592.6	586.0	580.4	549.6	532.6	504.0	454.7	408.9	362.5	304.7	
11	576.7	571.7	562.6	551.0	537.4	495.6	471.6	435.0	383.0	342.8	306.2	265.5	
2	552.7	543.7	526.6	507.0	481.4	433.6	402.6	365.1	321.2	290.4	264.9	236.7	
-8	501.7	482.7	451.6	423.0	392.4	348.6	320.6	294.1	265.3	246.8	230.2	212.5	
-17	418.7	395.7	362.6	337.0	313.4	283.6	265.7	249.1	230.4	219.1	208.9	196.2	
-27	318.7	302.7	281.6	266.0	252.4	237.6	225.7	216.1	205.4	199.2	192.5	183.9	
51	681.7	676.7	670.6	665.0	663.4	634.6	630.6	620.9	600.9	577.5	543.5	474.2	aged nonvoided element $C_0 = 50.3$ pF
41	656.7	653.7	647.6	643.0	644.4	617.6	604.6	594.9	569.1	537.5	493.0	412.0	
31	639.7	635.7	629.6	624.0	617.4	593.6	579.6	562.9	525.3	485.5	435.1	361.3	
22	619.7	614.7	607.6	600.0	591.4	562.6	543.6	517.0	467.6	421.7	372.0	311.3	
11	587.7	582.7	572.6	560.0	543.4	505.6	477.6	440.0	385.9	343.8	306.2	263.6	
2	559.7	549.7	531.6	512.0	486.4	436.6	404.6	367.1	321.2	290.4	264.0	235.3	
-9	504.7	486.7	454.6	425.0	394.4	349.6	321.6	294.1	264.3	245.8	229.2	211.0	
-17	421.7	398.7	363.6	338.0	313.4	283.6	264.7	248.1	229.4	218.1	207.0	195.4	
-28	317.7	300.7	279.6	265.0	251.4	235.6	224.7	215.1	204.4	197.3	190.5	182.3	
31	516.7	514.7	511.6	506.0	496.4	488.6	478.6	463.0	435.7	401.9	367.8	316.6	virgin voided element $C_0 = 54.9$ pF
22	505.7	502.7	497.6	491.0	478.4	466.6	449.6	428.0	391.9	355.6	322.3	279.6	
11	481.7	472.7	470.6	463.0	444.4	424.6	402.6	375.1	338.1	305.2	280.2	248.4	
2	460.7	453.7	440.6	426.0	402.4	374.6	349.6	323.1	291.2	265.6	247.5	224.4	
-8	418.7	404.7	381.6	361.0	336.4	309.6	289.6	270.1	248.3	230.0	219.5	204.2	
-17	359.7	342.7	319.6	301.0	282.4	261.6	248.7	236.1	221.4	207.2	202.1	191.2	
-27	286.7	274.7	259.6	248.0	238.4	224.6	216.7	209.2	200.5	193.3	187.6	179.7	
51	581.7	578.7	574.6	570.0	558.4	552.6	545.6	535.9	523.3	499.1	473.6	422.5	aged voided element $C_0 = 54.9$ pF
41	553.7	550.7	546.6	541.0	531.4	525.6	518.6	508.0	489.4	461.8	430.8	374.2	
31	542.7	539.7	534.6	531.0	519.4	510.6	499.6	484.0	456.6	421.6	385.8	330.9	
22	524.7	521.7	516.6	509.0	496.4	483.6	468.6	446.0	409.8	371.4	335.6	290.6	
11	498.7	493.7	485.6	476.0	459.4	437.6	413.6	386.1	345.1	311.2	284.1	250.9	
2	474.7	466.7	452.6	437.0	414.4	383.6	357.6	329.1	295.2	268.6	249.5	226.1	
-9	429.7	415.7	391.6	370.0	343.4	314.6	292.6	272.1	249.3	230.0	219.5	204.3	
-17	366.7	348.7	323.6	305.0	284.4	263.6	249.7	236.1	221.4	207.2	201.2	190.4	
-28	288.7	276.7	260.6	248.0	237.4	224.6	216.7	208.2	199.5	192.3	186.6	178.9	

Table I. Capacitance, C , of PVDF elements (picofarads).

$f(\text{kHz})$ $T(^{\circ}\text{C})$	1	2	5	10	20	50	100	200	500	1000	2000	5000	
31	12.3	12.2	12.1	12.0	11.8	11.4	11.3	10.9	10.1	9.3	8.4	7.0	virgin nonvoided element
22	12.0	11.9	11.8	11.6	11.5	10.9	10.6	10.0	9.0	8.1	7.2	6.1	
11	11.5	11.4	11.2	11.0	10.7	9.9	9.4	8.6	7.6	6.8	6.1	5.3	
2	11.0	10.8	10.5	10.1	9.6	8.6	8.0	7.3	6.4	5.8	5.3	4.7	
-8	10.0	9.6	9.0	8.4	7.8	6.9	6.4	5.8	5.3	4.9	4.6	4.2	
-17	8.3	7.9	7.2	6.7	6.2	5.6	5.3	5.0	4.6	4.4	4.2	3.9	
-27	6.3	6.0	5.6	5.3	5.0	4.7	4.5	4.3	4.1	4.0	3.8	3.7	
51	13.6	13.5	13.3	13.2	13.2	12.6	12.5	12.3	11.9	11.5	10.8	9.4	aged nonvoided element
41	13.1	13.0	12.9	12.8	12.8	12.3	12.0	11.8	11.3	10.7	9.8	8.2	
31	12.7	12.6	12.5	12.4	12.3	11.8	11.5	11.2	10.4	9.7	8.6	7.2	
22	12.3	12.2	12.1	11.9	11.8	11.2	10.8	10.3	9.3	8.4	7.4	6.2	
11	11.7	11.6	11.4	11.1	10.8	10.0	9.5	8.7	7.7	6.8	6.1	5.2	
2	11.1	10.9	10.6	10.2	9.7	8.7	8.0	7.3	6.4	5.8	5.2	4.7	
-9	10.0	9.7	9.0	8.4	7.8	6.9	6.4	5.8	5.3	4.9	4.6	4.2	
-17	8.4	7.9	7.2	6.7	6.2	5.6	5.3	4.9	4.6	4.3	4.1	3.9	virgin voided element
-28	6.3	6.0	5.6	5.3	5.0	4.7	4.5	4.3	4.1	3.9	3.8	3.6	
31	9.4	9.4	9.3	9.2	9.0	8.9	8.7	8.4	7.9	7.3	6.7	5.8	
22	9.2	9.2	9.1	8.9	8.7	8.5	8.2	7.8	7.1	6.5	5.9	5.1	
11	8.8	8.7	8.6	8.4	8.1	7.7	7.3	6.8	6.2	5.6	5.1	4.5	
2	8.4	8.3	8.0	7.8	7.3	6.8	6.4	5.9	5.3	4.8	4.5	4.1	
-8	7.6	7.4	6.9	6.6	6.1	5.6	5.3	4.9	4.5	4.2	4.0	3.7	
-17	6.6	6.2	5.8	5.5	5.1	4.8	4.5	4.3	4.0	3.8	3.7	3.5	aged voided element
-27	5.2	5.0	4.7	4.5	4.3	4.1	3.9	3.8	3.7	3.5	3.4	3.3	
51	10.6	10.5	10.5	10.4	10.2	10.1	9.9	9.8	9.5	9.1	8.6	7.7	
41	10.1	10.0	10.0	9.9	9.7	9.6	9.4	9.3	8.9	8.4	7.8	6.8	
31	9.9	9.8	9.7	9.7	9.5	9.3	9.1	8.8	8.3	7.7	7.0	6.0	
22	9.6	9.5	9.4	9.3	9.0	8.8	8.5	8.1	7.5	6.8	6.1	5.3	
11	9.1	9.0	8.8	8.7	8.4	8.0	7.5	7.0	6.3	5.7	5.2	4.6	
2	8.6	8.5	8.2	8.0	7.5	7.0	6.5	6.0	5.4	4.9	4.5	4.1	
-9	7.8	7.6	7.1	6.7	6.3	5.7	5.3	5.0	4.5	4.2	4.0	3.7	
-17	6.7	6.4	5.9	5.6	5.2	4.8	4.5	4.3	4.0	3.8	3.7	3.5	
-28	5.3	5.0	4.7	4.5	4.3	4.1	3.9	3.8	3.6	3.5	3.4	3.3	

Table II. Dielectric constant, $\epsilon_{33}^T/\epsilon_0$ of PVDF elements.

$f(\text{kHz})$	1	2	5	10	20	50	100	200	500	1000	2000	5000	
$T(^{\circ}\text{C})$													
31	.011	.015	.019	.025	.039	.055	.075	.101	.151	.199	.248	.305	virgin nonvoided element
22	.012	.019	.026	.035	.055	.079	.109	.139	.192	.229	.258	.282	
11	.020	.028	.043	.059	.080	.126	.152	.185	.220	.236	.243	.241	
2	.035	.050	.074	.098	.127	.171	.188	.206	.214	.212	.204	.193	
-8	.074	.096	.126	.148	.168	.195	.187	.184	.174	.162	.152	.143	
-17	.117	.134	.150	.156	.160	.168	.148	.140	.128	.117	.111	.107	
-27	.118	.123	.123	.119	.116	.112	.099	.095	.086	.082	.080	.085	aged nonvoided element
51	.016	.018	.019	.023	.030	.043	.045	.058	.086	.122	.174	.274	
41	.014	.016	.019	.023	.040	.042	.055	.073	.113	.161	.225	.333	
31	.014	.018	.023	.028	.040	.055	.073	.099	.149	.197	.249	.312	
22	.016	.021	.029	.039	.054	.080	.106	.138	.192	.234	.269	.301	
11	.022	.031	.046	.062	.086	.125	.155	.190	.226	.244	.253	.261	
2	.037	.052	.076	.100	.130	.175	.192	.210	.219	.218	.211	.204	virgin voided element
-9	.075	.098	.128	.151	.171	.199	.191	.188	.178	.167	.158	.154	
-17	.118	.135	.151	.159	.162	.175	.151	.143	.131	.120	.114	.113	
-28	.118	.123	.123	.120	.116	.116	.099	.095	.087	.082	.080	.085	
31	.010	.015	.020	.026	.033	.049	.066	.092	.133	.168	.200	.231	
22	.012	.018	.025	.034	.046	.068	.092	.123	.164	.191	.206	.218	
11	.019	.028	.042	.058	.077	.105	.130	.157	.131	.194	.194	.188	aged voided element
2	.033	.047	.069	.090	.111	.139	.154	.168	.174	.175	.163	.151	
-8	.066	.085	.110	.126	.142	.148	.150	.149	.141	.140	.123	.112	
-17	.097	.110	.121	.127	.136	.126	.121	.115	.107	.119	.092	.084	
-27	.092	.097	.099	.098	.097	.090	.083	.078	.074	.111	.063	.061	
51	.015	.017	.020	.022	.024	.030	.039	.051	.079	.104	.142	.206	aged voided element
41	.013	.015	.018	.023	.026	.034	.046	.064	.098	.131	.173	.231	
31	.014	.018	.023	.028	.034	.049	.065	.090	.132	.169	.205	.245	
22	.015	.021	.029	.037	.048	.070	.093	.123	.166	.197	.217	.235	
11	.022	.030	.044	.059	.077	.107	.133	.161	.190	.203	.202	.200	
2	.034	.048	.071	.092	.113	.143	.160	.176	.183	.183	.171	.163	
-9	.069	.087	.113	.130	.146	.156	.156	.156	.149	.146	.129	.120	
-17	.101	.114	.127	.133	.140	.134	.125	.121	.110	.120	.095	.091	
-28	.096	.101	.104	.101	.102	.093	.086	.082	.075	.110	.065	.065	

Table III. Dissipation factor, D , of PVDF elements.




Figure 1. Temperature history of PVDF samples.

Virgin nonvoided PVDF




Figure 2. Dielectric constant, virgin nonvoided PVDF.

Aged nonvoided PVDF




Figure 3. Dielectric constant, nonvoided PVDF after exposure to 51°C .

Virgin voided PVDF




Figure 4. Dielectric constant, virgin voided PVDF.

Aged voided PVDF




Figure 5. Dielectric constant, voided PVDF after exposure to 51°C .

Virgin nonvoided PVDF




Figure 6. Dissipation factor, virgin nonvoided PVDF.

Aged nonvoided PVDF




Figure 7. Dissipation factor, nonvoided PVDF after exposure to 51°C.

Virgin voided PVDF




Figure 8. Dissipation factor, virgin voided PVDF.

Aged voided PVDF




Figure 9. Dissipation factor, voided PVDF after exposure to 51°C.

VII. REFERENCES

1. B. Woodward, "The Suitability of Polyvinylidene Fluoride as an Underwater Transducer Material, "Acustica 38, 264-268 (1977).
2. Steven W. Meeks and Robert Y. Ting, "The evaluation of PVF₂ for underwater shock-wave sensor application," J. Acoust. Soc. Am. 75, 1010-1012 (1984).
3. J. Callerame, R. H. Tancrell, and D. T. Wilson, "Comparison of Ceramic and Polymer Transducers for Medical Imaging," IEEE Ultrasonics Symposium Proceedings, 117-121 (1978).
3. W. P. Leung and K. K. Yung, "Internal losses in polyvinylidene fluoride (PVF₂) ultrasonic transducers," J. Appl. Phys. 50, 8031-8033 (1979).
5. Wen-Hsien Chen, "Analysis of the High-Field Losses of Polyvinylidene Fluoride Transducers, IEEE Transactions on Sonics and Ultrasonics SU-30, 238-249 (1983).
6. J. Callerame, R. H. Tancrell, and D. T. Wilson, "Transmitters and Receivers for Medical Ultrasonics," IEEE Ultrasonics Symposium Proceedings, 407-411 (1979).
7. "Kynar® Piezo Film," Pennwalt Corporation, 900 First Avenue, P.O. Box C, King of Prussia, PA 19406-0018.
8. John C. McGrath, Lyn Holt, Derek M. Jones, and Ian M. Ward, "Recent Measurements on Improved Thick Film Piezoelectric PVDF Polymer Materials for Hydrophone Applications," Ferroelectrics 50, 13-20 (1983).
9. John C. McGrath, private communication to the authors.
10. Wolfgang K. H. Panofsky and Melba Phillips, Classical Electricity and Magnetism (Addison - Wesley, 1962), pp. 122-123.
11. Donald Ricketts, "Model for a piezoelectric polymer flexural plate hydrophone," J. Acoust Soc. Am. 70, 929-935 (1981).

DIELECTRIC PROPERTIES OF PIEZOELECTRIC
POLYVINYLDENE FLUORIDE (PVDF)
Mark B. Moffett
Target Physics Sensor Technology Branch
James M. Powers
Electroacoustic Transduction Branch
TM No. 841072
16 April 1984
UNCLASSIFIED

DISTRIBUTION LIST

External

NAVSEA Code 63D
63R-12 (C. C. Walker)
63X (B. E. McTaggart)

NOSC Code 712B (D. Carson, C. Hicks, J. Lockwood)

NRL/USRD (T. A. Henriquez, R. Y. Ting, A. L. Van Buren)

ONR Code 220B (T. Warfield)
431 (R. C. Pohanka)

Natl. Bur. of Standards (M. G. Broadhurst)

Univ. of Leeds, England (I. M. Ward)

Pennsylvania State Univ. (L. E. Cross)

Pennwalt Corp. (P. Bloomfield)

Raychem Corp. (G. Bischak, P. Soni)

Raytheon Corp. Research Div. (R. Tancrell)
Sub. Signal Div. (D. Ricketts)

Thorn EMI, Ltd. (D. M. Jones, J. C. McGrath)

TM No. 841072

DIELECTRIC PROPERTIES OF PIEZOELECTRIC
POLYVINYLIDENE FLUORIDE (PVDF)

Mark B. Moffett

Target Physics Sensor Technology Branch

James M. Powers

Electroacoustic Transduction Branch

TM No. 841072

16 April 1984

UNCLASSIFIED

DISTRIBUTION LIST

Internal

Code 02111

021311 (3 copies)

10

101 (R. Elswick, K. Lima, F. Weigle)

323

3232

3232 (H. Bakewell, R. Hauptmann)

3233

3234

3234 (G. Battista, R. Crooks, A. Corcella, J. Dantly, C. LeBlanc,
J. Lindberg, T. Mapes, H. Miller, T. Meyers, A. Palmer,
J. Powers (15 copies), A. Sullivan)

3292

33A

33A2

332

3321

3321 (L. Carlton, M. Moffett (4 copies))

3631 (C. Ledoux)

38

External Copies 21

Internal Copies 52

Total 73