

UNCLASSIFIED

AD NUMBER	
ADA800405	
CLASSIFICATION CHANGES	
TO:	unclassified
FROM:	restricted
LIMITATION CHANGES	
TO: Approved for public release; distribution is unlimited.	
FROM: Distribution authorized to DoD only; Administrative/Operational Use; 24 NOV 1951. Other requests shall be referred to Naval Sea Systems Command, Washington, DC 20362. Pre-dates formal DoD distribution statements. Treat as DoD only.	
AUTHORITY	
E.O. 10501 dtd 5 Nov 1953; NAVSEA ltr dtd 4 Dec 1968	

THIS PAGE IS UNCLASSIFIED

ATI

CLASSIFICATION CHANGED

FROM RESTRICTED TO UNCLASSIFIED
Insert Class Insert Class

158360

ON 4 FEB 1956 By authority of
Month Day Year

Classification cancelled in accordance with
Executive Order 10501 issued 5 November 1953

Document Service Center
Armed Services Tech. Info Agcy

This action was rendered by

Arthur E. Creech OSA
Name in full Date

Document Service Center, ASTIA

RESTRICTED

AT1 158 360

(Copies obtainable from ASTIA-DSC)

Bausch and Lomb Optical Co., Rochester, N.Y.

Interim Research Report for Radiophotoluminescent and Tenebrescent
Glasses - 24 Oct to 24 Nov 1951

Kreidl, N.J. 24 Nov '51 18pp. graphs

USN Contr. No. NObsr-57016

Glass - Optical properties
Luminescence
Crystals - Growth
Gamma rays

Materials, Non-Metallic (8)
Ceramics (1)

RESTRICTED

SECURITY INFORMATION

RESTRICTED

Report Number _____ Date 24 Oct. 1951 to 24 Nov. 1951

1STIA FILE COPY

ATTN No. 158360

Subject INTERIM RESEARCH REPORT

FOR

RADIOPHOTOLUMINESCENT AND TENEBRESCENT GLASSES

NAVY DEPARTMENT BUREAU OF SHIPS ELECTRONICS DIVISIONS

NObsr-57016 NE-051551

By N. J. Kreidl

Chemical Research Director

Bausch & Lomb Optical Co.

Rochester 2, New York

RESTRICTED

FOR RESEARCHER EXTENSION
BY _____

RESTRICTED

INTERIM RESEARCH REPORT
FOR
RADIOPHOTOLUMINESCENT AND TENEBRESCENT GLASSES

This report covers the period 24 October, 1951 to 24 November, 1951

BAUSCH AND LOMB OPTICAL CO.
ROCHESTER 2, NEW YORK

NAVY DEPARTMENT BUREAU OF SHIPS ELECTRONIC DIVISIONS

NObsr-57046 NE-051551

"WARNING: This document contains information affecting the national defense of the United States within the meaning of the Espionage Laws, Title 18, U.S.C., Sections 793 and 794. The transmission or the revelation of its contents in any manner to an unauthorized person is prohibited by law. Reproduction of this document in any form by other than activities of the Department of Defense and the Atomic Energy Commission is not authorized unless specifically approved by the Secretary of the Navy or the Chief of Naval Operations."

Copy No. 15

RESTRICTED

SECURITY INFORMATION

RESTRICTED

CONTENTS

	Page
Distribution List	1
Abstract	4
Part I Present Status	
1.1 Purpose	5
1.2 General Factual Data	6
1.3 Detail Factual Data	8
1.4 Conclusions	14
Part II Program for Next Interval	
2.1 Theory	16
2.2 Experiment	16
Figure 1	17
Figure 2	18

RESTRICTED

SECURITY INFORMATION

RESTRICTED

Distribution List

Copy No. 1	Office of the Chief of Naval Operations (Op-36) Department of the Navy Washington 25, D. C.
Copy No. 2	Chief, Bureau of Aeronautics (Code AE-54) Department of the Navy Washington 25, D. C.
Copy No. 3	Chief, Bureau of Medicine and Surgery (Atomic Defense Division) Department of the Navy Washington 25, D. C.
Copy No. 4	Office of Naval Research (Nuclear Physics Section) Department of the Navy Washington 25, D. C.
Copy No. 5	Commanding Officer Naval Medical Research Institute (Maynard Eicher) Building 17, Bethesda, Maryland
Copy No. 6	Commanding Officer (Code 996) U. S. Naval Radiological Defense Laboratory San Francisco 24, California
Copies No. 7 - 8	Commanding Officer U. S. Naval Radiological Defense Laboratory Nucleonics Division (Dr. Guthrie) San Francisco 24, California
Copy No. 9	Commanding Officer and Director U. S. Navy Electronics Laboratory San Diego 52, California
Copy No. 10	Commander, New York Naval Shipyard (Material Laboratory) Naval Base Brooklyn 1, New York
Copy No. 11	Director, Naval Research Laboratory Technical Information Division Washington 20, D. C.

RESTRICTED

RESTRICTED

Copy No. 12	Director, Naval Research Laboratory (Mr. Egli, Metallurgy Division) Washington 20, D. C.
Copy No. 13	Director, Evans Signal Laboratory (Technical Reports Section) Belmar, New Jersey
Copy No. 14	Director, Evans Signal Laboratory (Nucleonics Section, General) Engineering Branch Belmar, New Jersey
Copy No. 15	Commanding General Air Research and Development Command Wright-Patterson Air Force Base Dayton, Ohio
Copy No. 16	Department of the Air Force, Headquarters United States Air Force Washington 25, D. C. Attention: AFDRD-EQ-1
Copy No. 17	Office of the Chief Signal Officer Engineering and Technical Division Washington 25, D. C. Attention: SIGGG-P
Copy No. 18	Chairman, Radiation Instruments Branch (Technical Coordination Section) U. S. Atomic Energy Commission Division of Biology and Medicine Washington 25, D. C.
Copies No. 19 - 28	Secretary, Panel on Radiological Instruments Armed Forces Special Weapons Project Post Office Box 2610 Washington 25, D. C.
Copy No. 29	The President Army Field Forces Board No. 1 Fort Bragg, North Carolina
Copies No. 30 - 33	Navy Department Bureau of Ships, Chief Attention: Code 816 Washington 25, D. C.

RESTRICTED

RESTRICTED

Copy No. 34	Inspector of Naval Material Navy Department 495 Summer Street Boston, Massachusetts
Copies No. 35 - 40	Navy Department Bureau of Ships, Chief Attention: Code 854 Washington 25, D. C.
Copy No. 41	Dr. W. A. Weyl School of Mineral Industries Pennsylvania State College State College, Pennsylvania
Copy No. 42	Dr. G. Monk Senior Physicist Remote Control Engineering Division Argonne National Laboratories P. O. Box 5207 Chicago 80, Illinois
Copy No. 43	V. Young
Copy No. 44	M. Scott
Copy No. 45	N. Kreidl
Copy No. 46	K. Reynolds
Copy No. 47	C. Cala
Copy No. 48	A. Anderson
Copy No. 49	T. Pett
Copy No. 50	C. Bausch
Copy No. 51	H. Coleman

Copies 43 - 51 are
Bausch and Lomb Copies

RESTRICTED

RESTRICTED

ABSTRACT

Contractual Matters

All necessary equipment and consultation approvals have been applied for and delivery dates scheduled. Authority required for purchase of radioactive material has been received from the Atomic Energy Commission.

Tenebrescence

K_2O was found as one of the fundamental factors in the sensitivity of tenebrescent glasses, as one of the results of a study of the systems $K_2O-Al_2O_3-P_2O_5$ and $BaO-Al_2O_3-P_2O_5$.

A theoretical study on tenebrescence was initiated and a program of experiments derived from preliminary results.

Calibration Glasses for Radiophotoluminescence

Glasses containing Mn^{++} have been found which essentially duplicate the photoluminescence of the radiophotoluminescent glass.

Radiophotoluminescence

The addition of small amounts of certain modifiers did not improve the working properties of the existing radiophotoluminescent glass.

RESTRICTED

RESTRICTED

1.

PART I

PRESENT STATUS

1.1

PURPOSE

The purpose of this investigation is to determine, in glasses, the causes of optical changes produced by X - or gamma radiation, to select and develop these compositions which combine optimum indication and integration of X or gamma radiation with desirable technological properties affecting their eventual manufacture, and to develop a glass which without radiation by X or gamma rays will fluoresce in a manner similar to the existing dosimeter glass.

RESTRICTED

RESTRICTED

1.2 GENERAL FACTUAL DATA

1.2.1 Personnel

Since the report of 24 October, 1951 the project has lost the services of G. Sherwood Smith (indicated in a special report) who was ordered to active duty on 2 November, 1951 as a 2nd Lieutenant, CE, U.S.A.R.

The Iowa Military District, Building 92, Gruber Street, Des Moines, Iowa turned down the request for deferment submitted by this company to the New York Military District on 30 October, 1951.

This company will appeal the decision on the basis that four years training in Ceramics is a scarce commodity. Coupled with Mr. Smith's work on this project, it represents a more extensive and more critical investment than his ROTC training.

In order to prevent delay in the project, Mr. G. Brewster was shifted from a purely advisory capacity to carrying on the melting operations.

This company's projects have been put on an overtime basis to allow this project to operate during normal working hours. This was reported to Bureau of Ships, via Naval Inspector of Ordnance in a letter dated 23 November, 1951.

Authority to utilize the services of Dr. K. H. Sun, Pittsburgh, Pennsylvania, to cooperate with Dr. Kreidl, of this project, in writing a survey of the scientific background as a basis for the investigations

RESTRICTED

RESTRICTED

of this contract was requested by letter dated 10 October, 1951 to the Contracting Officer, Bureau of Ships. This has not yet been authorized.

1.2.2. Equipment and Facilities

Authority to purchase the necessary source of gamma radiation, equipment for its safe handling, and the monitoring equipment required by the Atomic Energy Commission was requested on 18 October, 1951. This authorization has not been received. Our authority from the Atomic Energy Commission to purchase radiocobalt expires 31 December, 1951. Delivery dates on our equipment orders have been quoted by our supplier, on some items involved, as 90 days.

Authority to erect 13 feet of wall to separate the radiocobalt source from the rest of the laboratory in compliance with general requirements of the Atomic Energy Commission, was requested 12 November, 1951. This request has not been authorized.

The gradient furnace, mentioned later, is one which this laboratory constructed from ideas gained from the paper "An Improved Apparatus for the Determination of Liquidus Temperature and Rates of Crystal Growth" by O. H. Grauer and E. H. Hamilton of the National Bureau of Standards (Journal of National Bureau of Standards 44 (1950) R.P. 2096).

RESTRICTED

RESTRICTED

1.3 DETAIL FACTUAL DATA

1.3.1 Topic I - Radiophotoluminescent Glasses

(Note: Topic I has been generalized from title used in first report)

(Note: Topic I is temporarily emphasized as it does not in its initial phase require testing equipment not yet available.)

1.3.1.1 Devitrification

1.3.1.1.1 Purpose

The purpose of this phase of the work was to find modifications of composition which had less tendency to devitrify (grow crystals) when made in larger crucibles than are used in the laboratory, and which had a longer working range (rate of change of viscosity with temperature is less).

1.3.1.1.2 Experimental Approach

The approach to this problem was to modify the r-glass by small amounts of MgO , Al_2O_3 , ZnO , or SiO_2 .

The following compositions were melted:

<u>Melt No.</u>	<u>$Al(PO_3)_3$</u>	<u>KPO_3</u>	<u>$Ba(PO_3)_2$</u>	<u>$Mg(PO_3)_2$</u>	<u>$Zn(PO_3)_2$</u>	<u>Al_2O_3</u>	<u>SiO_2</u>
1A-3707	50.0	25.0	20.0	2.00	2.00	1.00	-
1A-3708	50.0	25.0	19.0	2.00	2.00	1.00	1.00

All compositions are weight percent.

These glasses were compared with r-glass in the gradient furnace, to determine devitrification tendencies.

RESTRICTED

RESTRICTED

1.3.1.1.3 Results

All glasses were completely devitrified at all temperatures investigated, 500° to 900° C.

1.3.1.1.4 Conclusions

The composition variations showed no improvement in properties. Work will be resumed after making exploratory experiments on other approaches.

1.3.1.2 Phosphate Base1.3.1.2.1 Purpose

The purpose of this phase of the work was to investigate suitability for radiophotoluminescence of bases chemically related to present base of r-glass but known to have better working properties.

1.3.1.2.2 Experimental Approach

The following composition was melted:

<u>Melt No.</u>	<u>SiO₂</u>	<u>Na₂O</u>	<u>Al₂O₃</u>	<u>B₂O₃</u>	<u>P₂O₅</u>
1A-3709	20.0	20.0	30.0	10.0	20.0

Composition Wt. %

1.3.1.2.3 Results

The melting properties were not good under the conditions tested. Other melting conditions will be studied. The silver solubility of this glass has not been tested.

RESTRICTED

RESTRICTED

1.3.2 Topic 2 - Standard Glasses

(Note: Topic 2 is also emphasized because special equipment is not required.)

1.3.2.1 Purpose

The purpose of this work was to develop a glass having the same fluorescence as r-glass without previous irradiation by gamma rays.

1.3.2.2 Background

1.3.2.2.1 A glass, E-9272 having the composition SiO_2 -34.1%, Na_2O -23.3%, B_2O_3 -33.0%, MnO_2 -2.50%, Sb_2O_3 -5.65, and As_2O_3 -1.50%, developed by this company prior to this study, had been found to fluoresce similarly but much brighter than r-glass.

1.3.2.2.2 The variation of the activator system $\text{MnO-Sb}_2\text{O}_3$ to obtain a desired intensity was considered possible, but complicated because of the opposing influences of quenching, oxidation, and color. The quenching phenomena is the reducing of the amount of fluorescence by too much Mn^{++} , the oxidation phenomena is the effect of the ratio of Mn^{++} to Mn^{++} and Mn^{+++} in determining fluorescence, and the color phenomena is the increase in color due the increase of Mn^{+++} which produces an intense purple color causing fluorescence to be affected by thickness. It was considered promising to cut down on the fluorescence of the Mn^{++} by adding a small amount of iron.

RESTRICTED

RESTRICTED

1.3.2.3 Experimental Approach

To a glass of the composition of E-9272 substitutions of Fe_2O_3 were made for SiO_2 . These are shown below together with a visual estimate of their fluorescence.

<u>Melt No.</u>	<u>Fe_2O_3 Added</u>	<u>Visual Estimate of Fluorescence</u>
E-9530	0.315 Wt. %	Too Dark
E-9541	0.160	Correct
E-9535	0.080	Nearly Correct- but bright

These glasses will be tested by Dr. Schulman at the Naval Research Laboratory. All three glasses have slight brown color.

1.3.3 Topic 3 - Tenebrescent Glasses

1.3.3.1 System Al_2O_3 - K_2O - P_2O_5

1.3.3.1.1. Purpose

The Naval Research Laboratory has discovered that r-glass from which silver phosphate is omitted (in the following called r-base) represents one of the best tenebrescent compositions to date. The r-base is a composition in the quaternary system Al_2O_3 - K_2O - P_2O_5 - BaO . In order to better understand this fact simpler binary and ternary compositions were considered. The theoretical work of N. Kreidl and K. Sun, that will be presented in the next report, suggests attention to the role of K_2O .

RESTRICTED

RESTRICTED

1.3.3.1.2 Experimental Approach

Melts were made of various compositions in 2 inch zircon crucibles.

1.3.3.1.3 Results

1.3.3.1.3.1 The approximate glass formation area in this system is indicated by the solid line in the composition field of figure 1. Glasses to the right of the dashed line were not investigated. Such glasses, containing more P_2O_5 than the metaphosphates, are usually soluble in water, difficult to prepare, and unreliable in composition due to the volatilization of P_2O_5 . However, glass formation is expected to exist in most of this area. Glasses produced near the $K_2O-P_2O_5$ binary side of the field are hygroscopic resulting in poor samples. However, these are of sufficient interest to warrant further attempts to prepare better samples, preserving them in a desiccator.

1.3.3.1.3.2 Since no radiation source was available here, selected samples were prepared and submitted to Dr. Schulman, Navy Research Laboratory, for exploratory examination. Ratings so obtained are inscribed in figure 1. The rating most refers, according to Dr. Schulman, to tenebrescence comparable with the r-base. These results are also shown with the compositions:

RESTRICTED

RESTRICTED

<u>Glass</u>	<u>K₂O</u>	<u>Al₂O₃</u>	<u>P₂O₅</u>	<u>Sensitivity</u>
F-0008-1	55	20	25	Slightly less sensitive than 2 and 3
F-0008-2	45	10	45	One of most sensitive
F-0008-3	45	20	35	One of most sensitive
F-0008-4	15	20	65	Slightly more sensitive than 5
F-0008-5	5	30	65	Least sensitive
F-0008-6	35	30	35	Slightly less sensitive than 2 and 3

Compositions are mol %

r-base sensitivity about same as F-0008-2 and 3.

Additional melts as shown have been submitted to Dr. Schulman.

These have the following compositions:

<u>Glass</u>	<u>K₂O</u>	<u>Al₂O₃</u>	<u>P₂O₅</u>
F-0008-7	42.5	4.0	53.5
F-0008-8	57.5	2.5	40.0
F-0008-9	37.0	16.0	47.0

Compositions are mol %

The first two glasses were prepared to investigate the field in the absence of alumina, the last glass was a composition between the compositions of F-0008-2 and F-0008-3, the two best of the previous study.

1.3.3.1.4

Conclusions

The results indicate a strong sensitizing influence of K₂O.

RESTRICTED

RESTRICTED

1.3.3.2 System Al_2O_3 -BaO- P_2O_5

1.3.3.2.1 Purpose

The purpose of this work was to separate the influence of BaO on the sensitivity from the quaternary system (Al_2O_3 -BaO-K₂O- P_2O_5) r-base.

1.3.3.2.2 Experimental Approach

Melts were made in the same manner as in 1.3.3.1.2. Samples have been submitted to Dr. Schulman for irradiation.

1.3.3.2.3 Results

1.3.3.2.3.1 Glass formation is indicated as sub A in figure 2.

1.3.3.2.3.2 Radiation results are not yet available.

1.4 CONCLUSIONS

1.4.1 Topic I

1.4.1.1 Devitrification of r-glass cannot be sufficiently prevented with the addition of $\text{Zn}(\text{PO}_3)_2$, $\text{Mg}(\text{PO}_3)_2$, Al_2O_3 and SiO_2 for $\text{Ba}(\text{PO}_3)_2$.

1.4.1.2 Other Base Glasses

No conclusions can be drawn.

1.4.2 Topic 2

The fluorescence of a Mn^{++} glass can be controlled to make it match that of r-glass by adding Fe_2O_3 .

RESTRICTED

RESTRICTED

1.4.3 Topic 3

1.4.3.1 The K_2O in the r-base is believed to be one of the dominating components in this glass. The domain of usable glasses has been determined for the system $K_2O-Al_2O_3-P_2O_5$.

1.4.3.2 The domain of usable glasses has been determined for the system $BaO-Al_2O_3-P_2O_5$.

RESTRICTED

RESTRICTED

2.

PART II

PROGRAM FOR NEXT INTERVAL

2.1 THEORY

The theoretical study by N. Kreidl and K. Sun will be continued in the hope that it can be submitted in the next interim report.

2.2 EXPERIMENTAL

2.2.1 Topic I

Silver solubility and devitrification will be studied in various phosphate glasses.

2.2.2 Topic 2

Additional work will depend on test results obtained on standards containing small amounts of iron in conjunction with manganese activators.


2.2.3 Topic 3

Planned work, as derived from completed theoretical studies, comprises:

- a) Simple phosphate systems (current).
- b) Comparison of K_2O-SiO_2 and $K_2O-B_2O_3$ system with $K_2O-P_2O_5$ system.
- c) Compositions of aluminates particularly potassium.
- d) The addition of F, Cl, I, and S to $K_2O-P_2O_5-X$ systems.
- e) Investigation of fluoride glasses.

RESTRICTED

RESTRICTED



RESTRICTED
SECURITY INFORMATION

