

UNCLASSIFIED

Defense Technical Information Center
Compilation Part Notice

ADP012834

TITLE: Raman Study of Optical Vibrations in InAs/GaAs Self-Assembled Quantum Dots

DISTRIBUTION: Approved for public release, distribution unlimited
Availability: Hard copy only.

This paper is part of the following report:

TITLE: Nanostructures: Physics and Technology International Symposium [6th] held in St. Petersburg, Russia on June 22-26, 1998 Proceedings

To order the complete compilation report, use: ADA406591

The component part is provided here to allow users access to individually authored sections of proceedings, annals, symposia, etc. However, the component should be considered within the context of the overall compilation report and not as a stand-alone technical report.

The following component part numbers comprise the compilation report:

ADP012712 thru ADP012852

UNCLASSIFIED

Raman study of optical vibrations in InAs/GaAs self-assembled quantum dots

Yu. A. Pusep[†], *G. Zanelatto*[†], *J. C. Galzerani*[†], *S. W. da Silva*[‡],
P. P. Gonzalez-Borrero[¶], *P. Basmaji*[¶] and *A. I. Toropov*[§]

[†] Universidade Federal de São Carlos, 13565-905 São Carlos, SP, Brasil

[‡] Universidade de Brasília, 70910-900, Brasília, DF, Brasil

[¶] Instituto de Física de São Carlos, Universidade de São Paulo, 13560-970 São Carlos, SP, Brasil

[§] Institute of Semiconductor Physics, 630090 Novosibirsk, Russia

The optical vibrational modes were studied in the strained InAs/GaAs heterostructures containing self-assembled quantum dots. The both, optical phonons in the InAs dots and in the GaAs barrier were detected by the resonance Raman scattering at the $E_0 + D_0$ gaps of InAs and GaAs correspondingly.

The LO and TO phonons in the InAs dots revealed strong shifts due to the strain. The observed strain induced frequency shifts were found in good agreement with the values calculated for the pyramidal InAs dots embedded in GaAs [1].

A number of Raman lines were observed in the frequency range of the GaAs optical phonons; the intensities of these lines significantly increased with increase of the density of the InAs dots measured by atomic force microscope. The theoretical analysis based on the calculation of the energy spectrum of the interface modes localised at sharp tips [2] and on the strain calculated for the pyramidal InAs/GaAs dots showed that the observed modes can be assigned to the GaAs-like interface modes localised at the apexes of the InAs pyramids, which are subjected to the strain. The Raman scattering measured with different excitation energies revealed the dispersion of these interface modes caused by both the spatial distribution of the strain in the InAs/GaAs heterostructure and the spatial dependence of the electrostatic potential of the interface modes.

References

- [1] M. Grundmann, O. Stier, D. Bimberg, *Phys. Rev. B* **52**, 11969 (1995).
- [2] P. A. Knipp, T. L. Reinecke, *Phys. Rev. B* **46**, 10310 (1992).