

UNCLASSIFIED

Defense Technical Information Center
Compilation Part Notice

ADP013002

TITLE: Collective Behavior of the Interwell Excitons in Biased
GaAs/AlGaAs Double Quantum Wells

DISTRIBUTION: Approved for public release, distribution unlimited
Availability: Hard copy only.

This paper is part of the following report:

TITLE: Nanostructures: Physics and Technology International Symposium
[8th] Held in St. Petersburg, Russia on June 19-23, 2000 Proceedings

To order the complete compilation report, use: ADA407315

The component part is provided here to allow users access to individually authored sections of proceedings, annals, symposia, etc. However, the component should be considered within the context of the overall compilation report and not as a stand-alone technical report.

The following component part numbers comprise the compilation report:
ADP013002 thru ADP013146

UNCLASSIFIED

Collective behaviour of the interwell excitons in biased GaAs/AlGaAs double quantum wells

V. B. Timofeev[†], *A. V. Larionov*[†], *J. M. Hvam*[‡] and *C. B. Soerensen*[‡]

[†] Institute of Solid State Physics, 142432 Chernogolovka, Russia

[‡] Microelectronics Center, DK 2800 Lyngby, Denmark

Photoluminescence (PL) and photoluminescence excitation spectra of the interwell excitons of GaAs/AlGaAs double quantum wells (n-i-n structures) with a thin AlAs barrier (four monolayers) have been investigated under applied electrical bias. In the limit of a rather weak excitation power and low enough temperatures interwell excitons are strongly localized on the random potential fluctuations and exhibit in photoluminescence spectra an inhomogeneously broaden line (FWHM of 3–4 meV) related with a laterally fluctuating potential relief. Under resonant photoexcitation of 1s HH-intrawell excitons by circularly polarized light we have observed a significant narrowing of PL interwell exciton line (down to 1 meV) on excitation power. Simultaneously we have found a superlinear growth of PL intensity and a sharp increase of the circular polarization degree of the corresponding interwell exciton line. Besides of optical orientation of interwell exciton by resonant circularly polarized resonant excitation we have found a sharp increase of the optical dipole moment alignment of the interwell excitons by linearly polarized resonant photoexcitation. All above described phenomena are very sensitive to the temperature and are observed only at $T < 5$ K.

Same behavior of the interwell radiative recombination, — narrowing of the interwell exciton line, its critical behavior on temperature and significant increase of the corresponding radiative decay rate, — we have observed under picosecond laser photoexcitation and by consequent analysis of the time evolution of PL spectra.

Described phenomena are associated with the creation of a collective excitonic phase. Dielectric excitonic nature of this new phase is confirmed by its diamagnetic behavior and by Zeeman splittings in magnetic field parallel to the structure growth direction (Faraday geometry). Space coherence of collective excitonic phase is investigated and discussed.