

UNCLASSIFIED

Defense Technical Information Center
Compilation Part Notice

ADP015097

TITLE: InP/InGaAs Heterojunction Bipolar Transistors Grown on Ge/P
Co-implanted InP Substrates by Metal-Organic Molecular Beam Epitaxy

DISTRIBUTION: Approved for public release, distribution unlimited

This paper is part of the following report:

TITLE: Proceedings IEEE Lester Eastman Conference on High
Performance Devices at University of Delaware, Newark, Delaware,
August 6, 7, and 8. 2002

To order the complete compilation report, use: ADA423729

The component part is provided here to allow users access to individually authored sections of proceedings, annals, symposia, etc. However, the component should be considered within the context of the overall compilation report and not as a stand-alone technical report.

The following component part numbers comprise the compilation report:
ADP015065 thru ADP015131

UNCLASSIFIED

InP/InGaAs Heterojunction Bipolar Transistors Grown on Ge/P Co-implanted InP Substrates by Metal-Organic Molecular Beam Epitaxy

W.J. Sung, R.F. Kopf, D.J. Werder, C.T. Liu, Y.K. Chen,
J. Chen*, E.J. Zhu* and M.F. Chang*

Bell Laboratories, Lucent Technologies, Murray Hill, NJ 07974;

* University of California, Los Angeles, CA 90095

Abstract

InP/InGaAs Heterojunction Bipolar Transistors (HBTs) have demonstrated excellent high-frequency performance [1-4] and are widely used for optical fiber transmission [5-7]. However, the current mesa HBT structure utilizes a very thick, highly doped n^+ InGaAs layer for the subcollector contact. This added mesa height makes multi-level interconnection processes more difficult, which impedes the capability of fabricating compact integrated circuits. In addition, InP has a much higher thermal conductivity than InGaAs, so heat dissipation may be a problem for densely packed circuits with the above structure. This paper reports on InP/InGaAs HBTs grown on Ge/P co-implanted substrates by Metal-Organic Molecular Beam Epitaxy (MOMBE). This embedded subcollector HBT structure offers several advantages for the fabrication of large-scale integrated circuits on InP substrates.

I. Ion-Implantation Conditions





Various elements have been reported for n-type implantation species into InP [8-10]. However, presently there is no obvious evidence to judge which species is better. In this paper, an embedded subcollector layer was formed by co-implanted Ge/P into Fe-doped InP substrates. Multi-energy and multi-dose implantation has been used to optimize the doping profile of both the bulk and surface doping densities. The latter is extremely important to form a good ohmic contact. The conditions are shown in Table I. After ion implantation, the substrates were annealed at 750°C by rapid thermal annealing (RTA). Hall measurements showed low sheet resistance of 54 $\Omega/\square$, and a very good X-ray diffraction spectrum with a FWHM of 15 arc-secs. This was almost the same as InP substrates without implantation.

Table I. The Ge/P ion-implantation energy and dose for forming embedded subcollector layers.

	Energy (keV)	Dose ($10^{14}/\text{cm}^2$)
Ge	100	0.2
	275	0.5
	550	1.3
P	50	0.2
	120	0.5
	250	1.3

II. Device Performance

Figure 1 shows the cross section of the InP/ InGaAs HBT with an embedded, ion-implanted subcollector layer. A 3500Å undoped InGaAs collector layer, followed by 500Å C-doped InGaAs base layer, 850Å n-type InP emitter layer and 1150 Å emitter contact layer were grown on ion-implanted and annealed InP substrates by MOMBE. Figures 2, 3 and 4 illustrate the dc performance of the HBT, including common-emitter dc characteristics, Gummel plots, and beta gain versus V_{BE} , respectively. A low turn on voltage of $<0.25V$, high breakdown voltage BV_{CEO} of $>3V$, and high beta current gain of >60 are achieved. These results are very similar to a reference InP/InGaAs HBT grown directly on a regular Fe-doped InP substrate with an n^+ InGaAs layer for the subcollector contact. In summary, this experiment demonstrates that InP/InGaAs HBTs can be successfully grown on implanted InP substrates with excellent dc characteristics.



References

- [1] S. Lee et al., "Transferred-Substrate InP/InGaAs/InP DHBT's with $f_{\max}=425\text{GHz}$," IEEE GaAs IC Symp. Tech. Dig., 2001, pp. 185-187.
- [2] A. Fujihara et al., "High-Speed InP/InGaAs DHBTs with ballistic collector launcher structure," IEDM Tech. Dig., 2001.
- [3] M. Ida et al., "InP/InGaAs DHBTs with 341-GHz f_T at high current density of over 800 kA/cm^2 ," IEDM Tech. Dig., 2001.
- [4] C.T. Liu et al., "High-Performance and High-Uniformity InP/InGaAs/InP DHBT Technology For High-Speed Optical Communication Systems" (to be published).
- [5] G. Raghaven et al., "InP ICs unleash the high-frequency spectrum," IEEE Spectrum, October 2000.
- [6] Y. Baeyens et al., "InP D-HBT IC's for 40Gb/s and higher bit-rate lightwave traneivers," IEEE GaAs IC Symp. Tech. Dig., 2001, pp. 125-128.
- [7] Y.K. Chen et al., "Semiconductor Technologies for High-Speed Optical Networking," IEDM Tech. Dig., 2001; and OFC Tech. Dig., 2002.
- [8] A. Dodabalapur et al., "Growth of InAlAs/InGaAs and InGaAlAs/InGaAs heterojunction bipolar transistors on Si-implanted InP substrates by molecular beam epitaxy," J. Appl. Phys., Vol. 71, pp. 2449-2451, 1992.
- [9] J. Vellanki et al., "MeV Energy Sufur Implantation in GaAs and InP," J. Electron. Mater., Vol. 22, pp. 559-566, 1993.
- [10] M.C. Ridgway et al., "Ion implantation of group IV or VI elements for n-type doping of InP," Nucl. Instr. And Meth. In Phys. Res. B, Vol. 96, pp.311-314, 1995.